

Supporting information:

Salting out in Organic Solvent: A New Route to Carbon Nanotube Bundle

Engineering

Maxim V. Fedorov^{*1}, Raz N. Arif², Andrey I. Frolov¹, Martin Kolar^{2,3}, Anastasia O. Romanova¹,
Aleksy G. Rozhin^{*2}

¹Max Planck Institute for Mathematics in the Sciences, D 04103 Leipzig, Germany

²School of Engineering & Applied Science, Aston University, Aston Triangle, Birmingham, B4 7ET, UK

³Faculty of Mechanical Engineering, Brno University of Technology, 616 69 Brno, Czech Republic




Figure S1. Samples of the CNT-NMP dispersions with addition of different amounts of salt (NaI) and aging for 1 hour. The left sample (0) is the control CNT-NMP dispersion with no salt. There are visible aggregates in the samples 1-3 formed by self-assembly of CNTs stimulated by addition of the salt. The size of the aggregates increases with the increase of salt concentration.

^{*}Corresponding authors: fedorov@mis.mpg.de (MVF), a.rozhin@aston.ac.uk (AGR)




Figure S2. Samples of the CNT-NMP dispersions with addition of different amounts of salt (NaI) and aging for 24 hours. We performed the centrifugation of all samples to extract bundles.