

Thermally activated processes in an organic long-persistent luminescent system

Kazuya Jinnai,^{a,b} Naohiro Nishimura,^{a,b} Chihaya Adachi^{*a,b,c} and Ryota Kabe^{*b,d}

^a Center for Organic Photonics and Electronics Research (OPERA), Kyushu University, 744 Motooka, Nishi-ku, Fukuoka 819-0395, Japan

^b JST, ERATO Adachi Molecular Exciton Engineering Project, 744 Motooka, Nishi-ku, Fukuoka 819-0395, Japan.

^c International Institute for Carbon Neutral Energy Research (WPI-I2CNER), Kyushu University, 744 Motooka, Nishi-ku, Fukuoka 819-0395, Japan.

^d Organic Optoelectronics Unit, Okinawa Institute of Science and Technology Graduate University, 1919-1 Tancha, Onna-son, Kunigami-gun Okinawa, Japan 904-0495

Table S1. Emission lifetime of the m-MTDATA/PPT film.

	τ_1 (μs)	τ_2 (μs)
300 K	0.350	21.5
200 K	0.356	23.1
100 K	0.441	19.5
50 K	0.581	-




Figure S1. (a) Fluorescence (solid lines) and phosphorescence (dashed lines) spectra of m-MTADATA or PPT in toluene solution (330 nm excitation) and the steady-state PL spectrum of the m-MTADATA/PPT film (340±5 nm excitation). (b) Fluorescence (solid lines) and phosphorescence (dashed lines) spectra of the melt-casted PPT film.




Figure S2. (a) Representation of Figure 4(b) without normalization (b) Representation of Figure 4(c) without normalization

[ここに入力]