

MoO₂ nanoparticles embedded in N-doped hydrangea-like carbon as sulfur host for high-performance lithium sulfur batteries

Yasai Wang^a, Guilin Feng^b, Yang Wang^a, Zhenguo Wu^a, Yanxiao Chen^{a*}, Xiaodong Guo^a, Benhe Zhong^a

^a School of Chemical Engineering, Sichuan University, Chengdu 610065, P. R. China.

^b RIES, Hokkaido University, N20W10, Kita-Ward, Sapporo 001-0020, Japan

Corresponding Authors:

Tel: +86-28-85406702; Fax: +86-28-85406702

E-mail address:

yxchen888@163.com




Fig.S1 XPS of MHC-2 composite




Fig.S2 specific capacity of MHC at 1 A g^{-1} for 300 cycles




Fig.S3 CV curves of AB/S electrode from 0.1 to 0.5 mV S^{-1}

Table S1 slope of the fitted line for the peak current at different scan rates

Slope(mA/V s^{-1}) ^{0.5}	Peak a	Peak c ₁	Peak c ₂
MHC/S-2	182.43	105.33	148.34
AB/S	111.14	53.05	93.16

Table S2 The chemical performance comparison of MHC with other matrixs repeorted in the literatures

matrix	Rate behavior	cycle performance (initial-final)	S content
α -MoO ₃ ^[1]	1151 mA h g ⁻¹ 0.1C	684-649 mA h g ⁻¹ 350 cycles 2C	85%
TiO ₂ @TiN ^[2]	931 mA h g ⁻¹ 0.1C	823-525 mA h g ⁻¹ 200 cycles 2C	60%
Mo ₂ C@C ^[3]	1099 mA h g ⁻¹ 0.1C	800-650 mA h g ⁻¹ 300cycles 1C	80%
RuO ₂ @NMCs ^[4]	1103 mA h g ⁻¹ 0.2C	1065-934 mA h g ⁻¹ 500 cycles 0.5C	70%
MnO/MPC ^[5]	900 mA h g ⁻¹ 0.1A g ⁻¹	723-515mAh g ⁻¹ 150cycles 0.2 A g ⁻¹	75%
NiFeO ₄ /C ^[6]	1041mA h g ⁻¹ 0.2A g ⁻¹	-700 mA h g ⁻¹ 500 cycles 0.5 A g ⁻¹	70%
MoO ₂ /NC ^{this work}	1057mA h g ⁻¹ 0.2A g ⁻¹	797-680mA h g ⁻¹ 300cycles 1.0A g ⁻¹	75%

- [1] P. Ji, B. Shang, Q. Peng, X. Hu, J. Wei, α -MoO₃ spheres as effective polysulfides adsorbent for high sulfur content cathode in lithium-sulfur batteries, *Journal of Power Sources*, 2018, 400,572-579.
- [2] W. Xu, H.M. Pang, H.L. Zhou, Z.X. Jian, R.M. Hu, Y.L. Xing, S.C. Zhang, Lychee-like TiO₂@TiN dual-function composite material for lithium-sulfur batteries, *Rsc Advances*, 2020,10, 2670-2676.
- [3] Z. Wang, X. Xu, Z. Liu, S. Ji, S.O. Ahmed Idris, J. Liu, Hollow spheres of Mo₂C@C as synergistically confining sulfur host for superior Li-S battery cathode, *Electrochimica Acta*, 2020, 332, 135482.
- [4] R. Wang, K. Wang, S. Gao, M. Jiang, J. Han, M. Zhou, S. Cheng, K. Jiang, Electrocatalysis of polysulfide conversion by conductive RuO₂ nano dots for lithium-sulfur batteries, *Nanoscale*, 2018, 10, 16730-16737.
- [5] Y. Liu, G. Feng, X. Guo, Z. Wu, Y. Chen, W. Xiang, J. Li, B. Zhong, Employing MnO as multifunctional polysulfide reservoirs for enhanced-performance Li-S batteries, *Journal of Alloys and Compounds*, 2018, 748, 100-110.
- [6] H. Wang, N. Zhang, Y. Li, P. Zhang, Z. Chen, C. Zhang, X. Qiao, Y. Dai, Q. Wang, S. Liu, Unique Flexible NiFe₂O₄@S/rGO-CNT Electrode via the Synergistic Adsorption/Electrocatalysis Effect toward High-Performance Lithium-Sulfur Batteries, *The journal of physical chemistry letters*, 2019,10, 6518-6524.