Electronic Supplementary Information

Small Functionalized Iron Oxide Nanoparticles for Dual Brain Magnetic

Resonance Imaging and Fluorescence Imaging

Ruixue Wei,*a Yang Liu,a Jinhao Gao, V. Wee Yong, and Mengzhou Xue*a

^aDepartment of Cerebrovascular Diseases, The Second Affiliated Hospital of Zhengzhou University,

Zhengzhou 450052, Henan, China

^bState Key Laboratory of Physical Chemistry of Solid Surfaces, The MOE Laboratory of Spectrochemical Analysis & Instrumentation, and The Key Laboratory for Chemical Biology of Fujian Province, College of Chemistry and Chemical Engineering, Xiamen University, Xiamen 361005, China.

^eHotchkiss Brain Institute and Department of Clinical Neurosciences, University of Calgary, Calgary, Alberta, Canada

*Author for correspondence:

Mengzhou Xue, MD, PhD, 2 Jingba Road, Zhengzhou, Henan, China, 450001

E-mail: xuemengzhou@zzu.edu.cn





Figure S1 (a) Hydrodynamic diameter of SIONs@NH₂ and SIONs@ANG/Ce6/PEG. Zeta potential in PBS (1×, pH 7.4) of (b) SIONs@NH₂ and (c) SIONs@ANG/Ce6/PEG.






Figure S3 UV-vis spectra of SIONs@ANG/Ce6/PEG, Ce6, and SIONs@NH₂.




Figure S4 (a) UV-Vis spectra of Ce6 at different concentrations. (b) Calibration curve of Ce6 based on (a).




Figure S5 Fluorescence spectrum of SIONs and SIONs@ANG/Ce6/PEG with excitation at 590 nm.




Figure S6 Fourier transform infrared (FT-IR) spectra of OA coated SIONs, SIONs@NH₂, and SIONs@ANG/Ce6/PEG.




Figure S7 Hemolysis test of SIONs. The diluted red blood cells were exposed to SIONs at a concentration gradient and no significant hemolysis effect were obseaverd at even 3.6 mM [Fe] till 4 h incubation.




Figure S8 Biodistribution of SIONs and SIONs@ANG/Ce6/PEG in mice organs at 2 h after intravenous injection (20 mg Fe /kg body weight, n = 3/group). The iron contents were measured by ICP-MS and the background was subtracted.