

Supporting Information

High Mass Loading Flower-like MnO₂ on NiCo₂O₄ Deposited Graphene/Nickel Foam as High-performance Electrodes for Asymmetric Supercapacitors

Jing Jin^{a,b}, Jie Ding^{a,b}, Xing Wang^c, Congcong Hong^c, Huaping Wu^{a,b}, Min Sun^{a,b}, Xiehong Cao^d, Congda Lu^{*a,b}, and Aiping Liu^{*c}

Voltage (V)	1.0	1.1	1.2	1.3	1.4	1.5
Leakage current (μA cm ⁻²)	0.007	0.012	0.016	0.022	0.026	2.556
Voltage (V)	1.6	1.7	1.8	1.9	2.0	2.1
Leakage current (μA cm ⁻²)	7.298	23.260	34.560	54.180	91.480	128.900

Table S1 The values of leakage currents at different voltages after 2-h test.

Fig. S3 Self-discharge curves of the supercapacitor.

