Electronic Supplementary Information for

Synthesis of Porous Microplatelets of α Form Anhydrous Guanine in DMSO/Water Mixed Solvents

Fenghua Chen, a,b,c Yurong Ma, $^{a\,*}$ and Limin Qi b

^aSchool of Chemistry and Chemical Engineering, Beijing Institute of Technology, 5 South

Zhongguancun Street, Haidian District, Beijing 100081, China

^bBeijing National Laboratory for Molecular Sciences, College of Chemistry, Peking University,

No.5 Yiheyuan Road, Haidian District, Beijing 100871, China

°School of Resources and Chemical Engineering, Sanming University, No. 25 Jingdong Road,

Sanming 365004, Fujian, China

Corresponding Author *(Y. M.) E-mail: yurong.ma@bit.edu.cn



Figure S1. The effects of molecular weight of PVP on guanine microplatelets. SEM images of microplatelets with PVP of different molecular weight. (a) $Mw \sim 240,000, 1.7 \text{ mg} \cdot \text{ml}^{-1}$, (b) $Mw \sim 360,000, 8 \text{ mg} \cdot \text{ml}^{-1}$. The reaction time was overnight.



Figure S2. The effects of PVP K30 concentrations on guanine samples. SEM images of guanine samples with (a) 0.0008, (b) 0.008, (c) 0.08, (d) 0.8, (e) 8 mg • ml⁻¹ PVP K30, (f) the ratios of length and width with different PVP K30 concentrations measured from SEM images. The reaction time was overnight.