Electronic Supplementary Material (ESI) for Materials Advances. This journal is © The Royal Society of Chemistry 2021

## $\label{eq:Supplementary Information for} In formation for $$ The chemodynamic antibacterial effect of $MnO_X$ nanosheets$


## decorated silicon nanowire arrays

Mingkang Li,† Guize Li,† Hongwei Wang\* and Lin Yuan\*

State and Local Joint Engineering Laboratory for Novel Functional Polymeric Materials, College of Chemistry, Chemical Engineering and Materials Science, Soochow University, 199 Ren'ai Road, Suzhou 215123, P. R. China.

† These authors contributed equally to this work.

<sup>\*</sup> Corresponding authors. E-mail: wanghw@suda.edu.cn, yuanl@suda.edu.cn



**Fig. S1** SN@MnO<sub>X</sub>, Si@PDA@MnO<sub>X</sub> and SN@PDA@MnO<sub>X</sub> surface Mn content. Data were expressed as mean  $\pm$  SD, n=3.

 $SN@PDA@MnO_X$  was put into a small amount of ultrapure water and was peeled off from the substrate under the action of ultrasound. About 10 ml of aqua regia was used to fully dissolve  $SN@PDA@MnO_X$  in the solution, and then, the aqua regia with  $SN@PDA@MnO_X$  dissolved in it was boiled until about 1 ml remained. The solution was diluted to 10 ml with ultrapure water and subjected to ICP-MS test.