

Electronic Supplementary Information

Fabrication of the narrow size nano curcuminoids emulsion by combining phase inversion temperature and ultrasonication: preparation and bioactivity

Quang- Hieu Tran^{a*}, Thi Thanh- Ho Thuy^b, Thanh-Tu Nguyen^b

Fig S1. MS spectra of curcuminoids extracted from turmeric, Curcumin: (Cur), $m/z = 367.11$, $C_{21}H_{20}O_6$, Demethoxycurcumin (DMC): $C_{20}H_{18}O_5$, $m/z = 339.22$ and Bisdemethoxycurcumin (BDMC): $C_{19}H_{16}O_4$, $m/z = 308.25$.

Fig S2. Size distribution of NCE-03

Fig S3. Size distribution of NCE-03 after 30 days of storage

Fig S4. Size distribution of NCE-03 after 60 days of storage

Fig S5. Size distribution of NCE-01

Fig S6. Size distribution of NCE-01 after 60 days of storage

Fig S7. Size distribution of NCE-04 after 60 days of storage

Fig S8. Size distribution of NCE-08

Fig S9. Size distribution of NCE-08 after 60 days of storage

Fig S10. Size distribution of NCE-05

Fig S11. Size distribution of NCE-05 after 60 days of storage

Fig S12. Zeta Potential of NCE-1

Fig S13. Zeta Potential of NCE-3

Fig S14. Preparation of Intestinal absorption test.


Rawdata_20180905112334 #41 RT: 0.34 AV: 1 NL: 7.29E4
T: - p EST Q1MS [100.000-600.000]

Fig S1. MS spectra of curcuminoids extracted from turmeric, Curcumin: (Cur), $m/z = 367.11$, $C_{21}H_{20}O_6$, Demethoxycurcumin (DMC): $C_{20}H_{18}O_5$, $m/z = 339.22$ and Bisdemethoxycurcumin (BDMC): $C_{19}H_{16}O_4$, $m/z = 308.25$.




Fig S2. Size distribution of NCE-03




Fig S3. Size distribution of NCE-03 after 30 days of storage




Fig S4. Size distribution of NCE-03 after 60 days of storage




Fig S5. Size distribution of NCE-01




Fig S6. Size distribution of NCE-01 after 60 days of storage




Fig S7. Size distribution of NCE-04 after 60 days of storage




Fig S8. Size distribution of NCE-08




Fig S9. Size distribution of NCE-08 after 60 days of storage




Fig S10. Size distribution of NCE-05




Fig S11. Size distribution of NCE-05 after 60 days of storage

SZ-100

Measurement Results

110-Zeta.nzt Measurement Results

Date : Thursday, May 9, 2019 7:22:08 AM
Measurement Type : Zeta Potential
Sample Name : 110
Temperature of the Holder : 25.0 °C
Dispersion Medium Viscosity : 0.896 mPa·s
Conductivity : 0.076 mS/cm
Electrode Voltage : 3.8 V

Calculation Results

Peak No.	Zeta Potential	Electrophoretic Mobility
1	-11.2 mV	-0.000087 cm ² /Vs
2	--- mV	--- cm ² /Vs
3	--- mV	--- cm ² /Vs

Zeta Potential (Mean) : -11.2 mV
Electrophoretic Mobility Mean : -0.000087 cm²/Vs




Fig S12. Zeta Potential of NCE-1

SZ-100

Measurement Results

711-Zeta.nzt


Measurement Results

Date : Monday, September 30, 2019 10:40:59 AM
Measurement Type : Zeta Potential
Sample Name : 711
Temperature of the Holder : 24.9 °C
Dispersion Medium Viscosity : 0.897 mPa·s
Conductivity : 0.297 mS/cm
Electrode Voltage : 3.3 V

Calculation Results

Peak No.	Zeta Potential	Electrophoretic Mobility
1	-11.3 mV	-0.000088 cm ² /Vs
2	--- mV	--- cm ² /Vs
3	--- mV	--- cm ² /Vs

Zeta Potential (Mean) : -11.3 mV
Electrophoretic Mobility Mean : -0.000088 cm²/Vs



Explore the future

Automotive Test Systems | Process & Environmental | Medical | Semiconductor | Scientific

HORIBA

1/1

Fig S13. Zeta Potential of NCE-3




Fig S14. Preparation of Intestinal absorption test.
