Electronic Supplementary Material (ESI) for Biomaterials Science. This journal is © The Royal Society of Chemistry 2023

Titanium dioxide nanoparticles affect osteoblasts derived exosomes cargo and impairs osteogenic differentiation of human mesenchymal stem cells

Wanderson de Souza^{a,b}, Sara G. Piperni^{b,c}, Liliana Grenho^{d,i}, Luís. A. Rocha^{e,f}, José M. Granjeiro^{a,b,c,g}, Sonia A. Melo^h, Maria. H. Fernandes^{d, i†}, Ana R. Ribeiro^{b,j†*}

Supplementary Information

^a Directory of Metrology Applied to Life Sciences, National Institute of Metrology Quality and Technology, Rio de Janeiro, Brazil.

^b Postgraduate Program in Biotechnology, National Institute of Metrology Quality and Technology, Rio de Janeiro, Brazil.

^c Postgraduate Program in Translational Biomedicine, University Grande Rio, Duque de Caxias, Brazil.

^d Faculty of Dental Medicine, University of Porto, Porto, Portugal.

^e Physics Department, Paulista State University, São Paulo, Brazil.

^f IBTN/Br – Brazilian Branch of the Institute of Biomaterials, Tribocorrosion and Nanomedicine, São Paulo State University, Bauru, São Paulo, Brazil.

g Dental School, Fluminense Federal University, Niterói, Brazil.

hi3S-Institute for Research and Innovation in Health, University of Porto, Portugal, Porto, Portugal.

ⁱLAQV/REQUIMTE, University of Porto, Porto, Portugal.

^j NanoSafety group, International Iberian Nanotechnology Laboratory, Braga, Portugal.

[†]Both authors contributed equally to this investigation.

			\mathbf{A}
Titanium dioxide nanoparticles (TiO ₂ NPs)			
Sample	Average size	Polydispersity index (PDI)	1
TiO ₂ 0 Hours	247,50 ± 13,3 nm	0,77 ± 0,06	7
TiO ₂ 24 Hours	113,03 ± 1,1 nm	0.18 ± 0.01	
TiO ₂ αMEM 10% FBS	143,43 ± 2,2 nm	0.24 ± 0.01	






Figure of Complementary Information. 1: TiO_2 NPs and definition of Exos markers suitable for osteoblast cell lines: Table with the average size and polydispersity index of TiO_2 NPs in water and culture medium that was evaluated by dynamic light scattering (A). Fluorescence micrographs of MG63 and SAOS-2 cells were marked in green for CD9, CD81, and CD82 (B), F-actin in red, and nucleus in blue (scale bar: $100 \mu m$). The experiment was performed with a n = 3.



Complementary Information Figure. 2: Nanoparticle Tracking Analysis (NTA) for identifying TiO₂ NPs in Exos: NTA showing the refractive index of TiO₂ NPs diluted in water (100 μ g/mL); Exos obtained from Immature osteoblasts (ExosMG63) and osteoblasts (ExosSAOS2) without interaction with TiO₂ NPs (control); Exos obtained from immature osteoblasts (ExosNPs (MG63)) and osteoblasts (ExosNPs (SAOS-2)) after interaction with TiO₂ NPs for 72 hours. The experiment was performed with a n = 3.



Complementary Information Figure. 3 TiO2 nanoparticles alter the charge of exosomes derived from MG63 and

SAOS-2: (A) Heat map of identified proteins from three replicated samples of Exos derived from MG63 and SAOS-2 exposed or not to TiO_2 NPs by LC-MS/MS (Abundance = amount of peptides). The samples were analyzed in the Uniprot database for taxonomic selection for Homo sapiens. Data are presented as mean \pm sd. Statistical significance was calculated by one-way ANOVA and the unpaired Student's *t*-test (*P < 0.01, significant difference between control (Exos) and treatment (ExosNPs), n = 3)).