

Supporting Information

Efficient FeCo nanoalloy catalysts derived from F127-assisted metal-organic frameworks for oxygen reduction reaction

Jianbo Zhao,^{1,*} Wanzhen Bing,¹ Haifeng Yuan,¹ Weichuang Yang,¹ Xiaomeng Li,¹ Meng Zhang,¹ Lifeng Han,² Xiaodong Jia^{1,*}, Shanyong Chen^{3,*}

¹ School of Material and Chemical Engineering, Zhengzhou University of Light Industry, No. 136 of Science Road, Zhengzhou 450001, P. R. China

² Henan Provincial Key Laboratory of Surface and Interface Science, Zhengzhou University of Light Industry, No. 136 of Science Road, Zhengzhou 450001, P. R. China

³ State Key Laboratory of Powder Metallurgy, School of Physical and Electronics, Central South University, No.932 South Lushan Road, Changsha Hunan 410083, P.R. China




Fig.S1 XRD pattern of ZIF-67 and ZIF-67-F
127




Fig.S2 SEM images of (A) ZIF-67 and (B) ZIF-67-F
127




Fig.S3 SEM images: (A1-A2) Fe_{0.3}Co@NC-F127 and (B1-B2) Fe_{0.7}Co@NC-F127




Fig.S4 Comparative CV curves of samples at 1600 rpm in O₂-saturated 0.1 M KOH




Fig.S5 LSV curves of $\text{Fe}_{0.5}\text{Co@NC-F127}$ catalysts (A) prepared at different temperatures of the first pyrolysis when the second pyrolysis temperature was fixed at 500 °C; (B) prepared at different temperatures of the second pyrolysis when the first pyrolysis temperature was fixed at 900°C.

Table 1S Relative percentages of atoms of samples based on the XPS results

Sample	Fe	Co	N	C	O	Cl
$\text{Fe}_{0.5}\text{Co@NC-F127}$	5.15	9.25	3.78	48.63	24.39	8.80
Co@NC-F127	---	3.71	9.39	72.96	13.94	---
Fe@NC-F127	14.48	---	7.25	42.72	33.59	1.96

Table S2 The ORR performance values of previously reported non-precious catalysts

Samples	Onset potential(V)	Half-wave potential (V)	Limiting current Density(mAcm ⁻²)	Ref.
MnFn ₂ O ₄ /NiCo ₂ O ₄	0.88	0.76	5.01	Appl.Catal. B. 2018, 236, 413-419
Fe ₃ /Co ₁ -NC	0.87	0.82	5.50	Inorg.Chem.Front 2021, 8, 109-121
Fe _{1.2} Co@NC/NCNTs	0.84	0.82	5.60	ACS.Sustainable Chem.Eng. 2019, 7, 8530-8541.
Co ₄ N@NC	0.90	0.82	4.36	Appli. Catal. B Environm 2020, 275, 119104
FeCo-NC-850	0.99	0.86	5.80	Appli.Surf.Sci.2019, 487, 496-502.
Co-Fe BMOF		0.89	5.40	J. Am. Chem. Soc 2019, 141, 10744-10750.
CoFe/NH-C NS		0.84	4.60	ACS Sustainable Chem.Eng 2019, 7, 15278-15288.
Fe _{0.5} Co@NC-F127	0.91	0.84	4.95	This work




Fig.S6 SEM of Fe_{0.5}Co@NC-F127 after recycling for ORR.