

Support information

Preparation of High-performance Supercapacitors from Waste Polyurethane-based Hierarchical Porous Carbon

Weining Li^a, Kunyin Wang^a, Zhuo Li^b, Chengyu Sun^a, Shuyang Zhao^a, Dequan
Zhang^a, Kun Chen^{*a}, Aijun Guo^{*a}

^a *State Key Laboratory of Heavy Oil Processing, College of Chemical Engineering, China
University of Petroleum (East China), 66 Changjiang West Road, Huangdao District, Qingdao,
Shandong 266580, China.*

^b *Key Laboratory of Bioinorganic and Synthetic Chemistry of Ministry of Education, School of
Chemistry, SunYat-Sen University, Guangzhou 510275, China.*

*Corresponding author:

Tel: 086-0532-8698-3050, e-mail address: chenkun@upc.edu.cn (K. Chen)

Tel: 086-0532-8698-0607, e-mail address: ajguo@upc.edu.cn (Aj. Guo)




Fig. S1 The Raman fitting result of sample




Fig. S2 Cycling stability of PUHPC-700 at 20 A g⁻¹

Table S1 The detailed Raman fitting result of sample.

Peak	Peak area		Ratio ((D ₁ +D ₂ +D ₃)/G)
	D ₁ +D ₂ +D ₃	G	
PUHPC-600	738838	300014	2.46
PUHPC-800	871845	335056	2.60
PUHPC-700	1874507	730023	2.57
KOH-free	1142676	480112	2.38
MgO-free	1174900	430052	2.49