

Supplementary Information

**Bilayer dressing based on aerogel/electrospun mats with self-catalytic hydrogen sulfide
generation and enhanced antioxidant ability**

Xiao Han¹, Lijuan Wang¹, Yushang Shang¹, Xu Liu¹, Inn-kyu Kang³, Jian Shen^{*,1,2}, Jiang Yuan^{*,1}

¹National and Local Joint Engineering Research Center of Biomedical Functional Materials,
School of Chemistry and Materials Science, Nanjing Normal University, Nanjing 210023, P. R.
China

²Jiangsu Engineering Research Center of Interfacial Chemistry, Nanjing University, Nanjing
210023, P. R. China

³Department of Polymer Science and Engineering, Kyungpook National University, Daegu 702-
701, Republic of Korea

*Corresponding authors: bioalchem@yahoo.com(J. Yuan), jshen@njnu.edu.cn(J. Shen)

1. UV-Vis spectra of keratin and KTC




Fig.S1 UV-Vis spectra of keratin and KTC

2. H-NMR of keratin and KTC




Fig.S2 H-NMR of keratin(lower) and KTC(upper)

3. H-NMR spectrum of GelMA




Fig.S3 The H-NMR spectra of GelMA

4. Water vapor transmission

Table S1 Water vapor transmission profile for control and PU/GSH layer.

Samples	Water Vapor Transmission Rate (mL/m ² /day)
Control	1369.4 ± 94.2
PU/GSH layer	1264.3 ± 80.3

5. H&E staining




Fig.S4 The newborn hair follicles (A) and the newborn sebaceous glands (B) in the ulcer bed as treated with PU/GSH//GelMA/KTC bilayer dressing for 15 days (blue arrows indicated hair follicles and green arrows indicated sebaceous glands, respectively).