

An efficient blue-excitible broadband
 $\text{Y}_3\text{ScAl}_4\text{O}_{12}:\text{Ce}^{3+}$ garnet phosphor for WLEDs

Hanwei Zhao,^{a,c} Dashuai Sun,^{*a,d} Zeyu Lyu,^a Sida Shen,^a Lixuan Wang,^a Luhui Zhou,^a Zheng Lu,^a Jianhui Wang,^a Jinhua He,^{*b} and Hongpeng You^{*a,c}

^aKey Laboratory of Rare Earths, Chinese Academy of Sciences; Ganjiang Innovation Academy, Chinese Academy of Sciences, Ganzhou 341000, China.

E-mail: hpyou@ciac.ac.cn, dssun@gia.cas.cn

^bJiangsu Bree Optronics Company Limited, Nanjing 210000, China.

E-mail: hejinhua_2001@aliyun.com

^cSchool of Rare Earths, University of Science and Technology of China, Hefei 230026, P. R. China.




Figure S1. XRD patterns of the YSAO:0.03Eu³⁺, YAG:0.03Eu³⁺ and YAG:0.08Ce³⁺.

Table S1. Bond lengths in YAG:0.08Ce³⁺ and YSAO:0.08Ce³⁺.

Sampls	Y-O1 (Å)	Y-O2 (Å)	(Sc/Al1)-O (Å)	Al2-O (Å)
YAG:0.08Ce ³⁺	2.43	2.30	1.91	1.77
YSAO:0.08Ce ³⁺	2.46	2.36	2.06	1.67




Figure S2. Configuration coordinate chart.