Supplementary Information

Flexible Electrode of Fe-doped NiSe₂@Porous Graphene as binder-free anode for Lithium-Ion Batteries

Caiyun Guo^a, Bo Zhang^b, Mengru Xiao^a, Mingming Hao^a, Liting Zhao^a, Xiaoting Zhang*a, Hongyan Zhang*a and Rui Wang*a

^aBeijing Key Laboratory of Clothing Materials R & D and Assessment, Beijing Engineering Research Center of Textile Nanofiber, School of Materials Design & Engineering, Beijing Institute of Fashion Technology, Beijing 100029, China.

^bHeavy Oil Processing Department, PetroChina Petrochemical Research Institute, Beijing, 102206, China

* Corresponding author. E-mail: zhangxt@bift.edu.cn, zhyzz@bift.edu.cn, clywangrui@bift.edu.cn




Fig. S1 XRD patterns of Ni@PG.




Fig. S2 XRD patterns of FeNi@PG.

 $\begin{tabular}{lll} \textbf{Table S1} & The & electrolyte & resistance, & SEI & film & resistance, & and & charge-transfer & resistance & of & NiSe_2@PG & and & Fe-NiSe_2@PG. & & PG. & PG.$

| | NiSe ₂ @PG | Fe-NiSe ₂ @PG |
|--------------------------------|-----------------------|--------------------------|
| The electrolyte resistance | 1.5 | 1.562 |
| The SEI film resistance | 16.33 | 9.504 |
| The charge-transfer resistance | 106 | 44.64 |