

Table S1. Effect of ultrasonic conditions with different amounts of water and time on particle sizes of ZnO NPs (— means there is precipitation).

Time Water	3 min	5 min	10 min
1000 mL	—	420.3/0.373	559.83/0.317
2000 mL	589.13/0.383	537.06/0.247	—
3000 mL	633.5/0.339	752.2/0.426	—