

Effect of molar mass and alkyl chain length on the surface properties and biocompatibility of poly(alkylene terephthalate)s for potential cardiovascular applications

Lenny Van Daele^{a,°}, Babs Van de Voorde^{a,°}, Robin Colenbier^{a,b}, Lobke De Vos^a, Laurens Parmentier^a, Louis Van der Meeren^c, André Skirtach^c, Ruslan I. Dmitriev^b, Peter Dubruel^{a,*}, Sandra Van Vlierberghe^{a,*}

^a Polymer Chemistry and Biomaterials Group (PBM), Centre of Macromolecular Chemistry (CMaC), Department of Organic and Macromolecular Chemistry, Ghent University, Krijgslaan 281 S4, 9000 Ghent, Belgium

^b Tissue engineering and Biomaterials Group, Department of Human structure and repair, Faculty of Medicine and Health Sciences, Ghent University, C. Heymanslaan 10, 6B3, UZP123, 9000 Ghent, Belgium

^c Department of Biotechnology, Ghent University, Proeftuinstraat 86, 9000 Ghent, Belgium

[°] Both authors contributed equally to the manuscript

* Sandra.VanVlierberghe@UGent.be, Peter.Dubruel@UGent.be

Table S1: Weight-average molar mass and polydispersity index of all used polymers.

| Polymer | M _w (kg/mol) | PDI |
|-------------------------|-------------------------|-----|
| PAT _(n = 8) | 131 | 1.5 |
| PAT _(n = 9) | 28 | 1.1 |
| PAT _(n = 9) | 62 | 1.5 |
| PAT _(n = 9) | 116 | 1.6 |
| PAT _(n = 9) | 168 | 1.5 |
| PAT _(n = 9) | 206 | 1.5 |
| PAT _(n = 10) | 119 | 1.5 |
| PAT _(n = 11) | 162 | 1.8 |
| PAT _(n = 12) | 119 | 1.8 |