

## Supporting Information

### Three-Dimensional Carbon Coated and High Mass-Loaded NiO@Ni foam Anode with High Specific Capacity for Lithium Ion Battery

Nurbolat Issatayev,<sup>a</sup> Diana Abdumutaliyeva,<sup>b</sup> Yerbolat Tashenov,<sup>b</sup> Dossym Yeskozha,<sup>a</sup> Adilkhan Seipiyev,<sup>a</sup> Zhumabay Bakenov<sup>\*a, c, d</sup> and Arailym Nurpeissova<sup>\*a, c</sup>

<sup>a</sup> Institute of Batteries, 53 Kabanbay Batyr Ave., Astana 010000, Kazakhstan

<sup>b</sup> Department of Chemistry, L.N. Gumilyov Eurasian National University, 2 Satpayev St., Astana, 010008 Kazakhstan

<sup>c</sup> National Laboratory Astana, Nazarbayev University, 53 Kabanbay Batyr Ave., Astana, 010000, Kazakhstan

<sup>d</sup> Department of Chemical and Materials Engineering, Nazarbayev University, 53 Kabanbay Batyr Ave., Astana, 010000, Kazakhstan

\* Corresponding Author: [arailym.nurpeissova@nu.edu.kz](mailto:arailym.nurpeissova@nu.edu.kz); [zbakenov@nu.edu.kz](mailto:zbakenov@nu.edu.kz)




Figure S1. Cycle performance of C@NiO@Ni foam/2, C@NiO@Ni foam/4, and C@NiO@Ni foam/6 at a current density of 1C.




Figure S2. Nyquist plots of the NiO@Ni foam and C@NiO@Ni foam measured after 5<sup>th</sup> cycle.

Table S1. Fitting results of the Nyquist plots of the NiO@Ni foam and C@NiO@Ni foam.

	<i>5<sup>th</sup> cycle</i>		
	$R_s, \Omega$	$R_f, \Omega$	$R_{ct}, \Omega$
<i>NiO@Ni foam</i>	2.74	4.23	14.98
<i>C@NiO@Ni foam</i>	2.16	4.09	11.12