

Supplementary Information

for

Bacterial Imprinted Polymer-based Detection of *Escherichia coli* Using Polydopamine on Gold Nanodendrite/Graphene Oxide Modified Electrodes

Yilei Xue^{*a,b}, Jessica Chen^{*a}, Meissam Noroozifar^a, Ruby M. A. Sullan^{a,b} and Kagan Kerman^{†a,b}

^a Department of Physical and Environmental Sciences, University of Toronto Scarborough, 265 Military Trail, Toronto, Ontario, M1C 1A4, Canada

^b Department of Chemistry, University of Toronto, 80 St. George Street, Toronto, Ontario, M5S 3H6, Canada

[†]Corresponding author: kagan.kerman@utoronto.ca




Figure S1. SEM images with different magnification for modified GCE with (a-b) GO, (c-d) GO/AuNDs, (e-f) GO/AuNDs/PDA-bacteria, (g-h) MIP, and (i-j) NIP.




Figure S2. XPS stack plot of in the regions of the (a) N, (b) C, (c) O. XPS (d) N 1 s, (e) C 1s, and (f) O 1s spectra of GO/AuNDs/PDA-w/o bacteria (without bacteria after the washing processes) with fitting. XPS (g) N 1 s, (h) C 1s, and (i) O 1s spectra of GO/AuNDs/PDA-bacteria with fitting. XPS (j) C 1s, and (k) O 1s spectra of GO/AuNDs. XPS (l) C 1s, and (m) O 1s spectra of GO.




Figure S3. Images of the liquid culture of mCherry *E. coli* suspended in 1X PBS under (a) visible light and (b) fluorescence. Images of mCherry *E. coli* washed off from modified electrodes using HNO₃/SDS solution under (c) visible light and (d) fluorescence.




Figure S4. AFM images of GO/AuNDs/PDA/HOPG before and after washing with a 0.01 equiv. M HNO₃/SDS solution for 20 min sonication.




Figure S5. (a) Electropolymerization of DA with 20, 15, and 10 cycles of CV from -0.5 to +0.5 V in the presence of 5 mM DA and 1.0×10^8 CFU/mL bacteria solution. Nyquist plots of GO/AuNDs/PDA GCE prepared with (b) 20 cycles of CV and (d) 15 cycles of CV measured in 5 mM $[\text{Fe}(\text{CN})_6]^{3-/4-}$ containing 0.1 M KNO_3 from 100 kHz to 0.01 Hz. The plot of ΔR_{ct} vs. log concentration of *E. coli* for (c) 20 cycles and (e) 15 cycles of CV ($n = 3$). The ΔR_{ct} was calculated using the baseline subtraction.

Table S1. R_{ct} and χ^2 obtained from the EIS measurements fitting of the calibration study using GO/AuNDs/PDA/GCE for *E. coli* quantification.

	blank	10 ¹ CFU/mL	10 ² CFU/mL	10 ³ CFU/mL	10 ⁴ CFU/mL	10 ⁵ CFU/mL	10 ⁶ CFU/mL	10 ⁷ CFU/mL
R_{ct} (kΩ ± s.d.)	13.3±0.4	19.3±0.6	26.1±0.1	32.6±1.1	37.4±0.3	38.3±0.2	37.5±0.4	37.7±0.7
$\chi^2 \pm \text{s.d.}$	0.13±0.03	0.07±0.01	0.05±0.02	0.06±0.01	0.08±0.02	0.07±0.02	0.05±0.01	0.04±0.01




Figure S6. Plot of *E. coli* concentration as a function of ΔR_{ct} using the GO/AuNDs/PDA/GCE with Langmuir-Freundlich isotherm fit line (red).




Figure S7. (a) Nyquist plots of GO/AuNDs/PDA SPE after incubation in different concentrations of *E. coli*, measured in 5 mM $[\text{Fe}(\text{CN})_6]^{3-/4-}$ in 0.1 M KNO_3 from 100 kHz to 0.01 Hz ($n = 3$), and measurements were fitted with the modified Randles equivalent circuit (inset) and (b) the calibration plot of ΔR_{ct} vs. \log concentration of *E. coli*. The ΔR_{ct} was calculated using the baseline subtraction.




Figure S8. Nyquist plots of GO/AuNDs/PDA GCE measurements in the presence and absence of 1000 CFU/mL of *E. coli* at Day 0 and Day 45 in 5 mM $[\text{Fe}(\text{CN})_6]^{3-/4-}$ in 0.1 M KNO_3 from 100 kHz to 0.01 Hz ($n = 3$).