

# A Facilitated Method to Grow Crystals of Cobalt Tellurite Multiferroic Material $\text{Co}_3\text{TeO}_6$

Chaoqun Zhou<sup>1</sup>, Luyao Wang<sup>1</sup>, Xiuyun Lei<sup>1</sup>, Congling Yin<sup>1</sup>, Lajun Liu<sup>1</sup>, Wenbin Guo<sup>1\*</sup>

*1. MOE Key Laboratory of New Processing Technology for Nonferrous Metal and Materials, Guangxi Key Laboratory of Optical and Electronic Materials and Devices, Collaborative Innovation Center for Exploration of Nonferrous Metal Deposits and Efficient Utilization of Resources, College of Materials Science and Engineering, Guilin University of Technology, Guilin 541004, P. R. China*

*2. State Key Laboratory of Structural Chemistry, Fujian Institute of Research on the Structure of Matter, Chinese Academy of Sciences, Fuzhou, Fujian 350002, P. R. China*

E-mail: [guo0281@163.com](mailto:guo0281@163.com) (W. G.),

Fig. S1 The Rietveld refinement of polymorphs $\text{Na}_2\text{Co}_2\text{TeO}_6$ .	S-3
Fig. S2 The EDS of (a) monoclinic polymorph and (b) hexagonal polymorph.	S-3
Fig. S3 The EDS results of $\text{Co}_3\text{TeO}_6$ crystals using (a) monoclinic $\text{Na}_2\text{Co}_2\text{TeO}_6$ as precursor, (b) the X-ray diffraction patterns of $\text{Co}_3\text{TeO}_6$ crystals and (c) EDS result using single crystals. Zone 1, zone 2 and zone 3 in Fig S3c represent the phases of $\text{Co}_3\text{TeO}_6$ , $\text{Na}_2\text{MoO}_4$ and $\text{Na}_2\text{TeO}_4$ , respectively.	S-4
Fig. S4 The differential magnetic susceptibilities with respect to temperature ( $T$ ) under various magnetic fields from 0.5 to 5 T along $a$ , $b$ and $c$ axis.	S-4
Fig. S5 The magnetic susceptibilities with external field from 1 T to 5 T parallel to Archimedean lattice.	T11 S-5
Table S1 The refined crystallographic parameters of polymorphs $\text{Na}_2\text{Co}_2\text{TeO}_6$ .	S-6
Table S2 The Structural refinement parameters of $\text{Co}_3\text{TeO}_6$ .	S-7
Table S3 Summary of exemplary crystal growth of tellurides.	S-8
References	S-9




Fig. S1 The Rietveld refinement of polymorphs  $\text{Na}_2\text{Co}_2\text{TeO}_6$ , yielding the unit-cell parameters (a)  $a = 5.3521(1) \text{ \AA}$ ,  $b = 9.2380(1) \text{ \AA}$ ,  $c = 5.7898(1) \text{ \AA}$  and  $\beta = 108.899(1)^\circ$  for monoclinic polymorph and (b)  $a = b = 5.2732(1) \text{ \AA}$ ,  $c = 11.2421(1) \text{ \AA}$  and  $\gamma = 120^\circ$  for hexagonal one, respectively.




Fig. S2 The EDS of (a) monoclinic polymorph and (b) hexagonal polymorph of  $\text{Na}_2\text{Co}_2\text{TeO}_6$ , respectively.

Fig. S3 The EDS results of  $\text{Co}_3\text{TeO}_6$  crystals using (a) monoclinic  $\text{Na}_2\text{Co}_2\text{TeO}_6$  as precursor, (b) the X-ray diffraction patterns of  $\text{Co}_3\text{TeO}_6$  crystals and (c) EDS result using single crystals. Zone 1, zone 2 and zone 3 in Fig S3c represent the phases of  $\text{Co}_3\text{TeO}_6$ ,  $\text{Na}_2\text{MoO}_4$  and  $\text{Na}_2\text{TeO}_4$ , respectively.




Fig. S4 The magnetic susceptibilities and its differential under various magnetic fields from 0.5 to 5 T along  $a$  (a,d),  $b$  (b,e) and  $c$  (c,f) axis.




Fig. S5 The magnetic susceptibilities with external field from 1 T to 5 T parallel to Archimedean T11 lattice.

Table S1 The refined crystallographic parameters of polymorphs  $\text{Na}_2\text{Co}_2\text{TeO}_6$ .

Materials	Na <sub>2</sub> Co <sub>2</sub> TeO <sub>6</sub>	Na <sub>2</sub> Co <sub>2</sub> TeO <sub>6</sub>
	Monoclinic	Hexagonal
Space group	<i>C</i> 2/m	<i>P</i> 6 <sub>3</sub> 22
<i>a</i> (Å),	5.3521(1),	5.2732(1),
<i>b</i> (Å),	9.2380(1),	5.2732(1),
<i>c</i> (Å)	5.7898(1)	11.2421(1)
$\alpha, \beta, \gamma$ (°)	90, 108.899(1), 90	90, 90, 120
Na1-4 <i>h</i> , ( <i>x</i> , <i>y</i> , <i>z</i> )	(0.5, 0.3243(10), 0.5)	Na1-12 <i>i</i> , ( <i>x</i> , <i>y</i> , <i>z</i> ) (0.2465, 0.65, -0.026)
Na2-2 <i>d</i> , ( <i>x</i> , <i>y</i> , <i>z</i> )	(0, 0.5, 0.5)	Na2-2 <i>a</i> , ( <i>x</i> , <i>y</i> , <i>z</i> ) (0, 0, 0)
Co1-4 <i>g</i> , ( <i>x</i> , <i>y</i> , <i>z</i> )	(0, 0.6657(3), 0)	Na3-12 <i>i</i> , ( <i>x</i> , <i>y</i> , <i>z</i> ) (0.7181(29), 0.0677(29), 0.0060(24))
Te1-2 <i>a</i> , ( <i>x</i> , <i>y</i> , <i>z</i> )	(0, 0, 0)	Co1-2 <i>b</i> , ( <i>x</i> , <i>y</i> , <i>z</i> ) (0, 0, 0.25)
O1-8 <i>j</i> , ( <i>x</i> , <i>y</i> , <i>z</i> )	(0.2806(8), 0.3456(9), 0.8030(3))	Co2-2 <i>d</i> , ( <i>x</i> , <i>y</i> , <i>z</i> ) (2/3, 1/3, 0.25)
O2-4 <i>i</i> , ( <i>x</i> , <i>y</i> , <i>z</i> )	(0.2647, 0.5, 0.1923)	Te1-2 <i>c</i> , ( <i>x</i> , <i>y</i> , <i>z</i> ) (1/3, 2/3, 0.25)
$\chi^2, R_{wp}$ (%), $R_p$ (%)	1.63, 2.54, 1.85	O1-12 <i>i</i> , ( <i>x</i> , <i>y</i> , <i>z</i> ) (0.6432, -0.0252, 0.3452)
		$\chi^2, R_{wp}$ (%), $R_p$ (%) 1.78, 2.91, 1.88

Table S2 The Structural refinement parameters of single-crystal Co<sub>3</sub>TeO<sub>6</sub>.

Empirical formula	Co <sub>3</sub> TeO <sub>6</sub>
Formula weight / g/mol	400.39
Temperature / K	100.00(10)
Crystal system	Monoclinic
Space group	<i>C2/c</i>
<i>a</i> / Å	14.7610(11)
<i>b</i> / Å	8.8319(6)
<i>c</i> / Å	10.3387(8)
$\beta$ / °	95.102(7)
Volume / Å <sup>3</sup>	1342.49(17)
$\rho_{\text{calc}}$ / g/cm <sup>3</sup>	5.943
$\mu$ / mm <sup>-1</sup>	17.328
<i>F</i> (000)	2172.0
Crystal size / mm <sup>3</sup>	0.96 × 0.73 × 0.58
Radiation MoK $\alpha$	Mo K $\alpha$ ( $\lambda$ = 0.71073 Å)
2 $\theta$ range for data collection / °	5.380 to 61.642
Index ranges	-19 ≤ <i>h</i> ≤ 21, -11 ≤ <i>k</i> ≤ 11, -14 ≤ <i>l</i> ≤ 14
Reflections collected	4934
Independent reflections	1787
Goodness-of-fit on <i>F</i> <sup>2</sup>	1.073
Final <i>R</i> indexes [ <i>I</i> ≥ 2 $\sigma$ ( <i>I</i> )]	<i>R</i> <sub>1</sub> = 0.0600,
Final <i>R</i> indexes [all data]	<i>R</i> <sub>1</sub> = 0.0635,
$R_1 = \sum   F_o  -  F_c   / \sum  F_o , wR_2 = \{ \sum w[(F_o)^2 - (F_c)^2]^2 / \sum w[(F_o)^2]^2 \}^{1/2}$	

Table S3 Summary of exemplary crystal growth of tellurides.

Compound	Raw materials	Method	Magnetism	Space group	Reference
CoTe <sub>6</sub> O <sub>13</sub>	BaCO <sub>3</sub> , TeO <sub>2</sub> , CoCl <sub>2</sub> ·6H <sub>2</sub> O	Hydrothermal synthesis	$T_N = 21$ K, AFM	$R\bar{3}$	1
MnTe <sub>6</sub> O <sub>13</sub>	MnCl <sub>2</sub> ·4H <sub>2</sub> O, TeO <sub>2</sub>	Hydrothermal synthesis	$T_N = 13$ K, AFM	$R\bar{3}$	1
Na <sub>2</sub> Co <sub>2</sub> Te <sub>6</sub>	Na <sub>2</sub> O, Co <sub>3</sub> O <sub>4</sub> , TeO <sub>2</sub>	Flux Method	$T_N = 9.6$ K, AFM	$P6_322$	2
CoTeMoO <sub>6</sub>	CoTeMoO <sub>6</sub> , TeO <sub>2</sub> , MoO <sub>3</sub>	Flux Method	$T_N = 23.44$ K, AFM	$P2_12_12$	3
Cu <sub>3</sub> TeO <sub>6</sub>	CuO, TeO <sub>2</sub> , PbCl <sub>2</sub>	Flux Method	$T_N = 60$ K, AFM	$Ia\bar{3}$	4
Ni <sub>3</sub> TeO <sub>6</sub>	NiO, CuO, TeO <sub>2</sub> , NiCl <sub>2</sub>	Chemical vapor transport	$T_N = 52$ K, AFM	$R3$	5
CoTeO <sub>4</sub>	CoTeO <sub>4</sub> , H <sub>6</sub> TeO <sub>6</sub> , Co(NO <sub>3</sub> ) <sub>2</sub> (H <sub>2</sub> O) <sub>6</sub>	Chemical vapor transport	$T_N = 50$ K, AFM	$P21/n$	6
Pb <sub>2</sub> CoTeO <sub>6</sub>	PbO, CoO, TeO <sub>2</sub>	Flux Method	$T_N = 16$ K, AFM	$R\bar{3}$	7
CaCo <sub>4</sub> (TeO <sub>3</sub> ) <sub>4</sub> Cl <sub>2</sub>	CaO, CoCl <sub>2</sub> , CoO, TeO <sub>2</sub>	Flux Method	$T_N = 11.5$ K, AFM	$C2/c$	8
Mn <sub>3</sub> TeO <sub>6</sub>	MnO, TeO <sub>3</sub> , PtCl <sub>2</sub>	Chemical vapor transport	$T_N = 23$ K, AFM	$R\bar{3}$	9
Na <sub>2</sub> Ni <sub>2</sub> TeO <sub>6</sub>	Na <sub>2</sub> Ni <sub>2</sub> TeO <sub>6</sub> , Na <sub>2</sub> O, TeO <sub>2</sub>	Flux method	$T_N = 25$ K, AFM	$P6_322$	10
Co <sub>3</sub> TeO <sub>6</sub>	Co <sub>3</sub> TeO <sub>6</sub> , PbCl <sub>2</sub>	Flux method	$T_N = 26$ K, AFM	$C2/c$	11
Co <sub>3</sub> TeO <sub>6</sub>	Co <sub>3</sub> TeO <sub>6</sub> , PtCl <sub>2</sub> or HCl	Chemical vapor transport	$T_N = 26$ K, AFM	$C2/c$	12,13
Co <sub>3</sub> TeO <sub>6</sub>	Na <sub>2</sub> Co <sub>2</sub> TeO <sub>6</sub> , MoO <sub>3</sub>	Flux method	$T_N = 26$ K, AFM	$C2/c$	this work

## Reference

- 1 J. T. S. Irvine, M. G. Johnston and W. T. A. Harrison, *Dalton Trans.*, 2003, **13**, 2641-2645.
- 2 G. Xiao, Z. Xia, W. Zhang, X. Yue, S. Huang, X. Zhang, F. Yang, Y. Song, M. Wei, H. Deng and D. Jiang, *Cryst. Growth Des.*, 2019, **19**, 2658–2662.
- 3 M. Mączka, K. Hermanowicz, A. Majchrowski, Ł. Kroenke, A. Pietraszko and M. Ptak, *J. Solid State Chem.*, 2014, **220**, 142–148.
- 4 K. Y. Choi, P. Lemmens, E. S. Choi and H. Berger, *J. Phys.: Condens. Matter.*, 2008, **20**, 505214.
- 5 I. Živković, K. Prša, O. Zaharko and H. Berger, *J. Phys.: Condens. Matter.*, 2010, **22**, 056002.
- 6 P. P. Pramanik, F. Eder, M. Weil, S. A. Ivanov, P. Maltoni, R. Miletich, T. Edvinsson and R. Mathieu, *Phys. Rev. B.*, 2024, **110**, 054104.
- 7 C. Artner and M. Weil, *J. Solid State Chem.*, 2019, **276**, 75–86.
- 8 K. Stolze, T. Kong, F. O. Von Rohr and R. J. Cava, *J. Solid State Chem.*, 2018, **263**, 141–147.
- 9 S. A. Ivanov, P. Nordblad, R. Mathieu, R. Tellgren, C. Ritter, N. V. Golubko, E. D. Politova and M. Weil, *Mater. Res. Bull.*, 2011, **46**, 1870–1877.
- 10 R. Sankar, I. Panneer Muthuselvam, G. J. Shu, W. T. Chen, S. K. Karna, R. Jayavel and F. C. Chou, *CrystEngComm.*, 2014, **16**, 10791–10796.
- 11 C. B. Liu, C. C. Ma, T. Li, H. W. Wang, R. Chen, M. Y. Cui, J. B. Cheng, J. B. He, S. J. Jin, Y. S. Luo and J. F. Wang, *Phys. Rev. B.*, 2024, **109**, 214408.
- 12 M. Hudl, R. Mathieu, S. A. Ivanov, M. Weil, V. Carolus, Th. Lottermoser, M. Fiebig, Y. Tokunaga, Y. Taguchi, Y. Tokura and P. Nordblad, *Phys. Rev. B.*, 2011, **84**, 180404.
- 13 R. Becker, M. Johnsson and H. Berger, *Acta Crystallogr C Cryst Struct Commun.*, 2006, **62**, i67–i69.