

# Supporting Information for: Investigating PVC Polymer-Plasticizer Interactions with Atomistic MD Simulations and Potential of Mean Force Calculations

Sai Athmeeya G Shet,<sup>†</sup> Jan-Michael Y. Carrillo,<sup>\*,‡</sup> Jacek Jakowski,<sup>¶</sup> S S R Kumar  
Challa,<sup>§</sup> and V N Ravi Kishore Vutukuri<sup>\*,†</sup>

<sup>†</sup>*Department of Chemistry, Sri Sathya Sai Institute of Higher Learning, Puttaparthi,  
Andhra Pradesh - 515134, India*






<sup>‡</sup>*Center for Nanophase Materials Sciences, Oak Ridge National Laboratory, Oak Ridge,  
Tennessee 37831, United States*








<sup>¶</sup>*Computational Sciences and Engineering Division, Oak Ridge National Laboratory, Oak  
Ridge, Tennessee 37831, United States*



<sup>§</sup>*Xheme Inc., 100 Carlson Ave, Newton, Massachusetts 02459, United States*

E-mail: carrillojy@ornl.gov; vnrkishorevutukuri@sssihl.edu.in

**Table S1: List of all plasticizers used in this study along with their acronyms.**

Plasticizer	Structure	Molar Mass (g/mol)	Category
<b>DEHA</b> Bis(2-ethylhexyl) Adipate		370.6	Aliphatic dicarboxylate (Adipate)
<b>DOA</b> Diocetyl Adipate		370.6	Aliphatic dicarboxylate (Adipate)
<b>ATBC</b> Acetyl Tributyl Citrate Citroflex A-4 (CA-4)		402.5	Citrate
<b>BTHC</b> Butyryl Trihexyl Citrate Citroflex B-6		514.7	Citrate
<b>ATHC</b> Acetyl Trihexyl Citrate Citroflex A-6 (CA-6)		486.6	Citrate

<b>DEHP</b> Bis(2-ethylhexyl) Phthalate		390.6	Orthophthalate
<b>DINP</b> Diisononyl Phthalate		418.6	Orthophthalate
<b>DPHP</b> Di(2-propylheptyl) Phthalate		446.7	Orthophthalate
<b>DIDP</b> Diisodecyl Phthalate		446.7	Orthophthalate
<b>DIBP</b> Diisobutyl Phthalate		278.3	Orthophthalate
<b>DIOP</b> Diisooctyl Phthalate		390.6	Orthophthalate
<b>DITP</b> Diisotridecyl Phthalate		530.8	Orthophthalate

<b>DEHT</b>		390.6	Terephthalate
Bis(2-ethylhexyl) Terephthalate (DOTP/DEHT)			
<b>TOTM</b>		546.8	Trimellitate
Tris(2-ethylhexyl) Trimellitate (TEHTM)			

**Table S2: Statistical analysis of the variation in slope and  $y$ -intercept values of pairs of plasticizers for investigation of the structure-property relationships of plasticizers interacting with PVC polymers of varying chain lengths (6-20 repeating units) derived from linear fits of N-PMF vs. molar mass of PVC polymer for different plasticizers**

Plasticizer 1	Plasticizer 2	Slope		$y$ -Intercept	
		t-Test value	Significance ( $P < 0.05$ )	t-Test value	Significance ( $P < 0.05$ )
DEHT	DIOP	5.582	Yes	-9.665	Yes
DEHP	DIOP	2.2043	Yes	-1.241	No
DEHP	DEHT	-3.153	Yes	9.0337	Yes
DEHT	TOTM	-2.527	Yes	-8.249	Yes
DEHP	TOTM	-4.579	Yes	1.4978	No
DEHA	DOA	-0.852	No	3.2033	Yes
DIDP	DPHP	-0.419	No	-2.266	Yes




Figure S1: Flowchart illustrating the methodology and parameters used in all simulations.




Figure S2: Correlation of PMF values for a system consisting of PVC20 and DEHP with GAFF2 and OPLS-AA force fields. For the PMF calculations using OPLS-AA force field, the parameter files were generated using libpargen<sup>1-3</sup> and polypargen<sup>4</sup> online web servers. The simulation settings for the OPLS-AA included a non-bonded cutoff set to 12 Å, and all remaining settings were identical to those used for the GAFF2 force field.




Figure S3: Histogram of configurations obtained from uniformly spaced windows generated by pulling the polymer along the reaction coordinate.




Figure S4: A typical PMF plot showing the interaction between polymer PVC20 and TOTM.




Figure S5: Plot of slope values from the N-PMF plots of orthophthalates plotted against the molar mass of PVC polymer with 6-20 monomer units. The red line is a visual guide and is drawn to show the trend.




Figure S6: Plot of  $y$ -intercept values from the N-PMF plots of orthophthalates plotted against the molar mass of PVC polymer with 6-20 monomer units and a  $1/r$  fit using the equation  $y = c/x$ , where  $c = 3.51 \pm 0.33$ , with a regression coefficient of 0.85.




Figure S7: N-PMF versus molar mass of citrate plasticizer along with the linear fit for PVC polymers of different lengths.




Figure S8: Plot of *y*-intercept values derived from N-PMF plot of citrates (red circles) and orthophthalates (black squares) plotted against the molar mass of PVC polymer.




Figure S9: Plot of slope values derived from N-PMF plot of citrates (red circles) and orthophthalates (black squares) plotted against the molar mass of PVC polymer.




Figure S10: N-PMF plot of plasticizer ATBC with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $7.09 \times 10^{-8}$  and a  $y$ -intercept of  $5.13 \times 10^{-3}$




Figure S11: N-PMF plot of plasticizer ATHC with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $2.25 \times 10^{-6}$  and a  $y$ -intercept of  $3.99 \times 10^{-3}$ .




Figure S12: N-PMF plot of plasticizer BTHC with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $2.02 \times 10^{-6}$  and a  $y$ -intercept of  $4.41 \times 10^{-3}$ .




Figure S13: N-PMF plot of plasticizer DEHA with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $2.33 \times 10^{-6}$  and a  $y$ -intercept of  $1.77 \times 10^{-3}$ .




Figure S14: N-PMF plot of plasticizer DEHP with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $3.54 \times 10^{-6}$  and a  $y$ -intercept of  $3.23 \times 10^{-3}$ .




Figure S15: N-PMF plot of plasticizer DEHT with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $4.20 \times 10^{-6}$  and a  $y$ -intercept of  $2.10 \times 10^{-3}$ .




Figure S16: N-PMF plot of plasticizer DIBP with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $-7.83 \times 10^{-7}$  and a  $y$ -intercept of  $6.10 \times 10^{-3}$ .




Figure S17: N-PMF plot of plasticizer DIDP with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $3.02 \times 10^{-6}$  and a  $y$ -intercept of  $2.98 \times 10^{-3}$ .




Figure S18: N-PMF plot of plasticizer DINP with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $3.22 \times 10^{-6}$  and a  $y$ -intercept of  $2.91 \times 10^{-3}$ .




Figure S19: N-PMF plot of plasticizer DIOP with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $2.91 \times 10^{-6}$  and a  $y$ -intercept of  $3.44 \times 10^{-3}$ .




Figure S20: N-PMF plot of plasticizer DITP with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $3.48 \times 10^{-6}$  and a  $y$ -intercept of  $2.52 \times 10^{-3}$ .




Figure S21: N-PMF plot of plasticizer DOA with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $2.43 \times 10^{-6}$  and a  $y$ -intercept of  $1.51 \times 10^{-3}$ .




Figure S22: N-PMF plot of plasticizer DPHP with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $3.18 \times 10^{-6}$  and a  $y$ -intercept of  $3.55 \times 10^{-3}$ .




Figure S23: N-PMF plot of plasticizer TOTM with molar mass of PVC polymer of different lengths (6-20 repeating units). The linear fit of the data is also shown in the figure. Linear regression analysis of the data gave a slope of  $4.61 \times 10^{-6}$  and a y-intercept of  $3.01 \times 10^{-3}$ .




Figure S24: Histogram plot of all the backbone dihedral angles of PVC10 polymer in DITP - PVC10 system. Dihedral angles from total interaction studies are shown in Black (both LJ and Coulombic interactions included) and angles from only LJ studies, i.e., electrostatic interactions being turned off, are shown in red.




Figure S25: Radius of gyration ( $R_g$ ) values of DIBP plasticizer and PVC polymer of 20 repeating units from DIBP-PVC20 potential of mean force (PMF) calculations along the reaction coordinate. The  $R_g$  values are plotted for both cases, one with only van der Waals interactions (Blue triangles-PVC; Green triangles-DIBP) and the other considering all interactions *i.e.*, both van der Waals and electrostatic interactions (Black squares-PVC20; Red circles-DIBP) between PVC polymer and plasticizer.




Figure S26: Radius of gyration ( $R_g$ ) values of DITP plasticizer and PVC polymer of 20 repeating units from DITP-PVC20 potential of mean force (PMF) calculations along the reaction coordinate. The  $R_g$  values are plotted for both cases, one with only van der Waals interactions (Blue triangles-PVC; Green triangles-DITP) and the other considering all interactions *i.e.*, both van der Waals and electrostatic interactions (Black squares-PVC20; Red circles-DITP) between PVC polymer and plasticizer.




Figure S27: Plot of PMF vs temperature of DITP - PVC10 system. PMF data points arising from total interactions (both LJ and Coulombic) are shown in Blue and the PMF data from LJ only studies are shown in orange. The linear fits of the data shown by dashed lines resulted in a slope ( $m$ ) of  $-0.030 \pm 0.003$ ; intercept ( $b_1$ ) of  $14.87 \pm 0.90$ ; intercept ( $b_2$ ) =  $12.79 \pm 0.88$ ; and Global weighted  $R^2 = 0.95$ .




Figure S28: Average CHELPG atomic charges (squares) and corresponding RMS fluctuations (error bars) are shown as a function of the reaction coordinate (RC) from  $\omega$ B97X-D3 single-point DFT calculations for PVC-20 in contact with (a) BTHC, (b) DEHP, and (c) TOTM. For each RC value (0.0–20.0 Å), the reported charges are averaged over an ensemble of 11 MD snapshots. Four charge descriptors are reported (from left to right) for each system: (i) the charge on the PVC carbon atom adjacent to Cl ( $C_{adj}$ , red), (ii) the total charge of the  $-CCl$  group ( $C_{adj}+Cl$ , black), (iii) the charge on the plasticizer ester carbon atom ( $C_{ester}$ , blue), and (iv) the total charge of the ester group (sum of CHELPG charges over atoms in the ester group, green).




Figure S29: N-PMF values obtained from interaction studies between a PVC polymer with 14, 10, and 6 repeating units, respectively, and various plasticizers




Figure S30: Correlation between the N-PMF values obtained for interaction between PVC20 and five orthophthalates and the heat of mixing calculated in ref.<sup>5</sup>

## References

- (1) Jorgensen, W. L.; Tirado-Rives, J. Potential energy functions for atomic-level simulations of water and organic and biomolecular systems. *Proceedings of the National Academy of Sciences* **2005**, *102*, 6665–6670.
- (2) Dodda, L. S.; Vilseck, J. Z.; Tirado-Rives, J.; Jorgensen, W. L. 1.14\* CM1A-LBCC: localized bond-charge corrected CM1A charges for condensed-phase simulations. *The Journal of Physical Chemistry B* **2017**, *121*, 3864–3870.
- (3) Dodda, L. S.; Cabeza de Vaca, I.; Tirado-Rives, J.; Jorgensen, W. L. LigParGen web server: an automatic OPLS-AA parameter generator for organic ligands. *Nucleic acids research* **2017**, *45*, W331–W336.
- (4) YABE, M.; MORI, K.; UEDA, K.; TAKEDA, M. Development of PolyParGen software to facilitate the determination of molecular dynamics simulation parameters for polymers. *Journal of Computer Chemistry, Japan-International Edition* **2019**, *5*, 2018–0034.
- (5) Li, D.; Panchal, K.; Mafi, R.; Xi, L. An atomistic evaluation of the compatibility and plasticization efficacy of phthalates in poly (vinyl chloride). *Macromolecules* **2018**, *51*, 6997–7012.