

Stability Trends of Near- and Equiatomic ($n \simeq m$)

Co_nMo_m and Mo_nCo_m ($n + m = 2 - 15$)

Subnanoalloys From DFT and *K*-Means

Clustering[†]

Olga Gabriela Santos de Araújo, Amanda Souza Alves, Maíra dos Santos
Costa, and Karla Furtado Andriani*

*Department of Exact Sciences, State University of Santa Cruz, P.O. Box 45662-900, Ilhéus, BA,
Brazil*

E-mail: kfandriani@uesc.br

Contents

1	Mathematical Background	SI-2
1.1	Relative Total Energy	SI-2
1.2	Second Order Energy	SI-2
1.3	Binding Energy	SI-3
1.4	Excess Energy	SI-3
1.5	Stabilization Energy	SI-3
1.6	Structural Parameters	SI-4
1.7	average chemical order parameter and Number of Chemical Bonds	SI-5
1.8	Self-Consistency Computational Parameters	SI-5
2	Gas-phase Co_n Clusters	SI-6

3 Gas-phase Mo_n Clusters	SI-22
4 Gas-phase Co_nMo_m Subnanoalloys	SI-40
5 Gas-phase Mo_nCo_m Subnanoalloys	SI-64
6 Data Availability	SI-87
References	SI-87

1 Mathematical Background

1.1 Relative Total Energy

A crucial aspect of our investigation involves the use of several energetic properties; however, their mathematical definitions are not explicitly outlined in the main manuscript. Therefore, we provide these definitions here to ensure clarity and completeness. We define the relative total energy (ΔE_{tot}^i) as follows:

$$\Delta E_{\text{tot}}^i = E_{\text{tot}}^i - E_{\text{tot}}^{\text{lowest}}, \quad (1)$$

where E_{tot}^i denotes the total energy of configuration i under consideration, and $E_{\text{tot}}^{\text{lowest}}$ denotes the total energy of the lowest-energy configuration. Accordingly, ΔE_{tot}^i quantifies the relative stability of each configuration and provides a normalized metric that facilitates direct comparison among different isomers.

1.2 Second Order Energy

To evaluate the relative stability of the clusters as a function of size, we calculate the second-order difference in total energy, $\Delta^2 E$, which we define as:

$$\Delta^2 E(N) = E_{\text{tot}}(N-1) + E_{\text{tot}}(N+1) - 2E_{\text{tot}}(N), \quad (2)$$

where $E_{\text{tot}}(N)$ represents the total energy of the lowest-energy isomer of size N . In this

analysis, positive values (peaks) in $\Delta^2 E$ indicate cluster sizes that exhibit enhanced stability relative to their neighbors ($N - 1$ and $N + 1$).

1.3 Binding Energy

To obtain the binding energy, E_b , we employed the following equation:

$$E_b = \frac{1}{(n+m)} (E_{tot}^{Mo_nCo_m} - nE_{tot}^{Mo,free-atom} - mE_{tot}^{Co,free-atom}), \quad (3)$$

where $E_{tot}^{Mo_nCo_m}$ is the total energy of the Mo_nCo_m cluster, while $E_{tot}^{Mo,free-atom}$ and $E_{tot}^{Co,free-atom}$ are the total energies of the free-atoms Mo and Co , respectively.

1.4 Excess Energy

The excess energy, E_{exc} , is one of the most important parameters to evaluate the relative energetic stability of a given specific binary composition with respect to their parent unary clusters. The E_{exc} is defined as follows,

$$E_{exc} = \frac{1}{(n+m)} (E_{tot}^{Mo_nCo_m} - \frac{n}{(n+m)} E_{tot}^{Mo_{(n+m)}} - \frac{m}{(n+m)} E_{tot}^{Co_{(m+n)}}), \quad (4)$$

where $E_{tot}^{Mo_nCo_m}$ is the total energy of the binary Mo_nCo_m cluster. $E_{tot}^{Mo_{(n+m)}}$ and $E_{tot}^{Co_{(m+n)}}$ are the total energies of the $Mo_{(n+m)}$ and $Co_{(m+n)}$ unary clusters, respectively, in their lowest energy configuration. From its definition, $E_{exc} = 0$ meV for $Mo_{(n+m)}$ and $Co_{(m+n)}$ clusters, where a negative value of E_{exc} indicates a favorable energetic mixing, whereas positive values imply that the binary clusters are less stable than their parent unary ones.

1.5 Stabilization Energy

The stabilization energy, E_{stab} , quantifies the tendency to form a specific binary composition relative to its corresponding gas-phase unary clusters.

$$E_{stab} = \frac{1}{(n+m)} (E_{tot}^{MonCom} - E_{tot}^{Mon} - E_{tot}^{Com}), \quad (5)$$

where E_{tot}^{MonCom} denotes the total energy of the binary *MonCom* cluster. E_{tot}^{Mon} and E_{tot}^{Com} denote the total energies of the *Mon* and *Com* unary clusters, respectively, in their lowest-energy configurations.

1.6 Structural Parameters

Following the approach adopted in several previous studies^{1,2}, we evaluated the most relevant structural properties using the effective coordination concept^{3,4}. As a result, we obtained the weighted bond length (d_{av}) and the effective coordination number (ECN^{*i*}) for each atom *i* within the cluster. In this framework, the weighted quantities are calculated using an exponential function to determine the d_{av}^i values, as described below:

$$d_{av}^{i,new} = \frac{\sum_j d_{ij} \exp \left[1 - \left(\frac{d_{ij}}{d_{av}^{i,old}} \right)^6 \right]}{\sum_j \exp \left[1 - \left(\frac{d_{ij}}{d_{av}^{i,old}} \right)^6 \right]}, \quad (6)$$

where d_{av}^i is determined using a self-consistent procedure.

In our implementation, the initial value of $d_{av}^{i,old}$ is set equal to the shortest distance between atoms *i* and *j*. Convergence is achieved when the condition $|d_{av}^{i,new} - d_{av}^{i,old}| < 10^{-4}$ Å is satisfied for every atom *i* in the molecular system. Convergence typically occurs in fewer than 10 iterations for complex systems with reduced symmetry. Furthermore, once the d_{av}^i values are determined, the ECN^{*i*} values are obtained using the following equation:

$$\text{ECN}^i = \sum_j \exp \left[1 - \left(\frac{d_{ij}}{d_{av}^i} \right)^6 \right]. \quad (7)$$

Thus, the average values of ECN^{*i*} and d_{av}^i , hereafter denoted as ECNav and *dav*, respectively, are obtained as follows:

$$\text{ECNav} = \frac{1}{N} \sum i \text{ECN}^i, \quad (8)$$

and

$$d_{av} = \frac{1}{N} \sum_i d_{av}^i, \quad (9)$$

where N denotes the total number of atoms in the system.

1.7 average chemical order parameter and Number of Chemical Bonds

To characterize the formation of bonds among the A and B atoms, we calculated the average chemical order parameter, σ_{av} , as follows:

$$\sigma_{av} = \frac{N_{Mo-Mo} + N_{Co-Co} - N_{Mo-Co}}{N_{Mo-Mo} + N_{Co-Co} + N_{Mo-Co}}, \quad (10)$$

where N_{Mo-Mo} , N_{Co-Co} , N_{Mo-Co} are the numbers of $Mo-Mo$, $Co-Co$ and $Mo-Co$ bonds, respectively. Therefore, from its definition σ can assume values ranging from -1 to 1 . A value of $\sigma \approx -1$ indicates a homogeneous distribution of Mo and Co (mixing), whereas $\sigma \approx 1$ implies the complete segregation of Mo and Co , leading to the formation of homogeneous regions within the Mo_nCo_m alloys.

1.8 Self-Consistency Computational Parameters

Table SI1: Self-consistency computational parameters employed to control the self-consistency process, namely `sc_accuracy_etot` (total energy), `sc_accuracy_rho` (electron density), `sc_accuracy_eev` (sum of the eigenvalues), `sc_accuracy_forces` (atomic forces) and `relax_geometry trm` (geometric optimization).

Flags	Values
<code>sc_accuracy_etot</code>	$1.0 \times 10^{-6} \text{ eV}$
<code>sc_accuracy_force</code>	$1.0 \times 10^{-4} \text{ eV \AA}^{-1}$
<code>sc_accuracy_rho</code>	$1.0 \times 10^{-5} e$
<code>sc_accuracy_eev</code>	$1.0 \times 10^{-3} \text{ eV}$
<code>relax_geometry trm</code>	$1.0 \times 10^{-3} \text{ eV \AA}^{-1}$

2 Gas-phase Co_n Clusters

Table SI2: Structural, energetic and electronic properties for Co_n clusters with $n = 2 - 5$, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

Co_n	i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
Co_2	1	0	-1.27	4	-3.75	-3.09	0.66	1	1.96	1	1.00	0.98
Co_3	2	0	-1.68	7	-3.65	-3.53	0.11	1	2.11	3	1.00	1.30
Co_3	1	0	-1.68	7	-3.65	-3.53	0.12	1	2.11	3	1.00	1.30
Co_4	1	68	-2.15	10	-4.19	-3.83	0.35	2	2.15	5	1.00	1.67
Co_4	3	68	-2.15	10	-4.19	-3.83	0.35	2	2.15	5	1.00	1.67
Co_4	4	68	-2.15	10	-4.19	-3.83	0.35	2	2.15	5	1.00	1.67
Co_4	2	0	-2.17	10	-4.16	-3.65	0.51	2	2.14	6	1.00	1.40
Co_5	1	1399	-2.19	11	-3.77	-3.54	0.22	1	2.12	5	1.00	1.91
Co_5	3	687	-2.33	11	-3.98	-3.53	0.45	2	2.22	7	1.00	2.23
Co_5	8	687	-2.33	11	-3.98	-3.53	0.45	2	2.22	7	1.00	2.23
Co_5	7	524	-2.36	11	-3.86	-3.32	0.53	2	2.21	8	1.00	2.06
Co_5	5	152	-2.44	13	-4.04	-3.90	0.14	3	2.24	8	1.00	1.55
Co_5	6	152	-2.44	13	-4.04	-3.90	0.14	3	2.24	8	1.00	1.55
Co_5	2	152	-2.44	13	-4.04	-3.90	0.14	3	2.24	8	1.00	1.55
Co_5	4	0	-2.47	13	-4.20	-3.71	0.49	2	2.22	9	1.00	1.56

Table SI3: Structural, energetic and electronic properties for Co_6 cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
4	3223	-2.28	14	-4.07	-3.77	0.30	2	2.21	8	1.00	3.01
5	2218	-2.45	12	-3.93	-3.61	0.32	2	2.22	9	1.00	2.40
1	1783	-2.52	14	-3.72	-3.63	0.08	2	2.21	10	1.00	1.90
6	1626	-2.55	12	-3.48	-3.15	0.33	3	2.23	10	1.00	1.95
2	1102	-2.64	14	-3.95	-3.58	0.36	2	2.21	9	1.00	1.72
0	1045	-2.65	14	-3.81	-3.57	0.23	3	2.24	11	1.00	1.89
9	1	-2.82	14	-3.98	-3.45	0.53	4	2.27	12	1.00	1.60
7	0	-2.82	14	-3.98	-3.45	0.53	4	2.27	12	1.00	1.60
3	0	-2.82	14	-3.98	-3.45	0.53	4	2.27	12	1.00	1.60

Table SI4: Structural, energetic and electronic properties for Co₇ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
5	2620	-2.50	15	-3.88	-3.73	0.15	3	2.23	11	1.00	2.98
11	1103	-2.72	15	-3.86	-3.58	0.27	3	2.24	12	1.00	2.31
7	891	-2.75	15	-3.75	-3.42	0.33	3	2.27	14	1.00	2.30
3	890	-2.75	15	-3.75	-3.42	0.33	3	2.27	14	1.00	2.30
14	890	-2.75	15	-3.75	-3.42	0.33	3	2.27	14	1.00	2.30
2	800	-2.76	15	-3.66	-3.39	0.27	3	2.24	13	1.00	2.09
8	659	-2.78	15	-3.67	-3.47	0.19	4	2.30	15	1.00	2.29
10	461	-2.81	15	-3.64	-3.64	0.00	4	2.29	15	1.00	2.01
9	377	-2.82	15	-3.64	-3.33	0.30	3	2.24	13	1.00	1.93
12	327	-2.83	15	-3.61	-3.41	0.19	3	2.23	13	1.00	1.78
1	238	-2.84	15	-3.62	-3.39	0.23	3	2.25	13	1.00	1.95
13	224	-2.84	15	-3.73	-3.49	0.24	4	2.30	16	1.00	1.95
4	184	-2.85	15	-3.61	-3.37	0.23	3	2.27	15	1.00	2.06
16	184	-2.85	15	-3.61	-3.37	0.23	3	2.27	15	1.00	2.06
6	145	-2.85	15	-3.59	-3.40	0.18	4	2.29	16	1.00	1.89
15	0	-2.88	15	-3.72	-3.38	0.33	4	2.29	15	1.00	2.21

Table SI5: Structural, energetic and electronic properties for Co₈ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
15	3018	-2.61	16	-3.86	-3.65	0.20	3	2.22	13	1.00	2.88
3	1404	-2.81	16	-3.70	-3.40	0.29	3	2.27	16	1.00	2.51
11	1401	-2.81	16	-3.70	-3.40	0.29	3	2.27	16	1.00	2.52
2	956	-2.86	16	-3.53	-3.31	0.21	4	2.30	18	1.00	2.41
5	894	-2.87	16	-3.53	-3.28	0.25	3	2.22	14	1.00	2.17
4	868	-2.87	16	-3.61	-3.20	0.41	3	2.20	18	1.00	1.98
14	759	-2.89	16	-3.68	-3.39	0.29	4	2.28	19	1.00	2.36
6	681	-2.90	18	-3.88	-3.67	0.20	4	2.32	18	1.00	2.81
18	672	-2.90	16	-3.68	-3.37	0.31	4	2.30	18	1.00	2.41
8	670	-2.90	16	-3.68	-3.37	0.31	4	2.30	18	1.00	2.41
19	452	-2.93	16	-3.56	-3.35	0.20	4	2.30	18	1.00	2.43
17	423	-2.93	16	-3.57	-3.34	0.23	4	2.32	19	1.00	2.39
16	370	-2.94	16	-3.66	-3.48	0.17	4	2.29	18	1.00	2.12
13	335	-2.94	16	-3.60	-3.30	0.29	4	2.30	18	1.00	2.17
10	156	-2.96	16	-3.62	-3.23	0.39	4	2.30	19	1.00	2.17
1	100	-2.97	16	-3.56	-3.19	0.36	4	2.28	17	1.00	2.12
9	100	-2.97	16	-3.56	-3.19	0.36	4	2.28	17	1.00	2.12
7	0	-2.98	16	-3.56	-3.25	0.30	4	2.30	20	1.00	2.10
12	0	-2.98	16	-3.56	-3.26	0.30	4	2.30	20	1.00	2.10

Table SI6: Structural, energetic and electronic properties for Co₉ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
16	3179	-2.70	19	-3.90	-3.59	0.31	3	2.25	16	1.00	3.03
13	1281	-2.91	19	-3.79	-3.54	0.24	4	2.31	21	1.00	3.01
2	1208	-2.92	19	-3.73	-3.48	0.24	4	2.29	21	1.00	3.03
7	1057	-2.94	17	-3.42	-3.20	0.22	4	2.30	21	1.00	2.52
6	687	-2.98	19	-3.76	-3.54	0.22	4	2.32	22	1.00	2.93
20	652	-2.98	19	-3.80	-3.53	0.26	4	2.32	22	1.00	2.86
21	651	-2.98	19	-3.80	-3.53	0.26	4	2.32	22	1.00	2.86
10	626	-2.99	17	-3.42	-3.24	0.18	4	2.32	22	1.00	2.44
4	610	-2.99	19	-3.78	-3.54	0.23	4	2.32	22	1.00	2.92
15	586	-2.99	17	-3.58	-3.35	0.22	4	2.30	21	1.00	2.47
5	520	-3.00	17	-3.42	-3.23	0.18	4	2.29	20	1.00	2.37
14	506	-3.00	17	-3.55	-3.30	0.25	4	2.32	22	1.00	2.47
17	445	-3.01	17	-3.47	-3.20	0.26	4	2.30	21	1.00	2.26
9	435	-3.01	17	-3.42	-3.20	0.22	5	2.33	23	1.00	2.32
11	430	-3.01	19	-3.71	-3.46	0.24	4	2.31	22	1.00	2.78
8	395	-3.01	19	-3.74	-3.53	0.20	4	2.31	23	1.00	2.87
19	342	-3.02	17	-3.66	-3.39	0.26	4	2.31	22	1.00	2.40
1	301	-3.02	17	-3.45	-3.24	0.20	4	2.30	23	1.00	2.38
12	299	-3.02	17	-3.45	-3.24	0.20	4	2.30	23	1.00	2.38
3	0	-3.06	17	-3.48	-3.31	0.17	4	2.30	21	1.00	2.21
18	0	-3.06	17	-3.48	-3.31	0.17	4	2.30	21	1.00	2.21

Table SI7: Structural, energetic and electronic properties for Co₁₀ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
14	784	-3.04	18	-3.41	-3.20	0.20	5	2.33	26	1.00	2.51
20	757	-3.05	20	-3.66	-3.44	0.22	4	2.32	25	1.00	2.84
17	755	-3.05	20	-3.66	-3.43	0.23	4	2.31	24	1.00	3.14
25	734	-3.05	18	-3.59	-3.33	0.25	4	2.31	24	1.00	2.57
10	723	-3.05	20	-3.64	-3.42	0.21	4	2.32	26	1.00	3.12
16	721	-3.05	20	-3.64	-3.42	0.21	4	2.32	26	1.00	3.11
15	721	-3.05	20	-3.65	-3.45	0.20	4	2.32	26	1.00	2.82
26	668	-3.06	20	-3.49	-3.41	0.08	4	2.31	26	1.00	2.42
18	587	-3.06	20	-3.60	-3.44	0.15	5	2.33	26	1.00	2.98
21	553	-3.07	18	-3.41	-3.19	0.22	5	2.34	27	1.00	2.37
22	546	-3.07	20	-3.70	-3.50	0.19	5	2.33	26	1.00	2.90
24	545	-3.07	20	-3.70	-3.50	0.19	5	2.33	26	1.00	2.90
11	544	-3.07	20	-3.63	-3.46	0.16	4	2.31	26	1.00	2.96
2	542	-3.07	20	-3.49	-3.41	0.07	4	2.32	25	1.00	2.41
19	517	-3.07	22	-3.90	-3.72	0.17	4	2.31	25	1.00	2.76
5	485	-3.07	18	-3.42	-3.26	0.15	4	2.31	27	1.00	2.43
03	458	-3.08	18	-3.45	-3.16	0.29	5	2.33	26	1.00	2.48
9	415	-3.08	18	-3.46	-3.23	0.23	4	2.31	25	1.00	2.34
12	414	-3.08	20	-3.65	-3.50	0.14	4	2.31	24	1.00	2.79
1	380	-3.09	20	-3.57	-3.44	0.13	4	2.32	26	1.00	2.69
6	379	-3.09	20	-3.62	-3.49	0.13	4	2.31	24	1.00	2.74
23	287	-3.09	20	-3.72	-3.40	0.31	4	2.31	24	1.00	2.87
8	243	-3.10	20	-3.73	-3.45	0.28	5	2.33	26	1.00	2.82
7	238	-3.10	18	-3.44	-3.23	0.21	4	2.31	24	1.00	2.40
4	0	-3.12	20	-3.67	-3.46	0.20	4	2.31	25	1.00	2.63

Table SI8: Structural, energetic and electronic properties for Co₁₁ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
25	949	-3.07	23	-3.84	-3.63	0.20	4	2.32	28	1.00	3.18
19	899	-3.08	23	-3.77	-3.58	0.19	4	2.32	28	1.00	3.04
22	870	-3.08	21	-3.51	-3.36	0.14	5	2.33	29	1.00	2.54
16	867	-3.08	21	-3.51	-3.36	0.15	5	2.33	29	1.00	2.54
12	747	-3.09	21	-3.64	-3.41	0.23	4	2.31	28	1.00	3.34
13	552	-3.11	23	-3.85	-3.68	0.17	4	2.32	29	1.00	3.21
20	467	-3.12	23	-3.74	-3.63	0.10	5	2.33	29	1.00	2.89
14	463	-3.12	21	-3.63	-3.49	0.13	4	2.32	28	1.00	2.81
21	431	-3.12	23	-3.67	-3.55	0.12	5	2.36	31	1.00	2.49
6	395	-3.12	21	-3.61	-3.38	0.23	5	2.32	28	1.00	2.97
17	387	-3.12	19	-3.31	-3.08	0.22	5	2.34	30	1.00	2.45
30	368	-3.12	21	-3.58	-3.41	0.17	4	2.31	27	1.00	2.88
36	367	-3.12	21	-3.70	-3.48	0.21	4	2.31	29	1.00	2.90
4	353	-3.13	23	-3.80	-3.60	0.19	4	2.33	30	1.00	3.08
34	349	-3.13	21	-3.60	-3.46	0.13	5	2.32	29	1.00	3.07
10	334	-3.13	23	-3.81	-3.68	0.13	4	2.32	27	1.00	2.89
24	331	-3.13	19	-3.42	-3.21	0.21	4	2.31	31	1.00	2.40
9	322	-3.13	21	-3.61	-3.45	0.16	4	2.32	27	1.00	3.12
31	318	-3.13	21	-3.61	-3.45	0.16	4	2.32	27	1.00	3.12
3	317	-3.13	23	-3.74	-3.52	0.22	4	2.32	27	1.00	3.18
2	282	-3.13	23	-3.78	-3.55	0.23	4	2.32	27	1.00	3.02
33	270	-3.13	21	-3.57	-3.44	0.13	5	2.34	30	1.00	2.92
35	248	-3.14	21	-3.62	-3.39	0.22	5	2.34	30	1.00	3.03
23	246	-3.14	21	-3.62	-3.39	0.22	5	2.34	30	1.00	3.03
32	190	-3.14	23	-3.91	-3.64	0.27	4	2.32	30	1.00	2.86
1	190	-3.14	23	-3.70	-3.59	0.11	5	2.33	30	1.00	2.74
27	190	-3.14	23	-3.71	-3.59	0.11	5	2.33	30	1.00	2.74
15	190	-3.14	23	-3.70	-3.59	0.11	5	2.33	31	1.00	2.74
11	158	-3.14	21	-3.61	-3.47	0.14	5	2.32	28	1.00	2.73
18	143	-3.15	23	-3.83	-3.61	0.21	5	2.35	30	1.00	2.94
5	131	-3.15	21	-3.61	-3.38	0.22	5	2.33	30	1.00	2.76
7	72	-3.15	23	-3.82	-3.65	0.17	5	2.33	28	1.00	2.93
28	26	-3.16	23	-3.66	-3.56	0.09	5	2.32	29	1.00	2.70
8	22	-3.16	19	-3.43	-3.21	0.21	5	2.32	29	1.00	2.45
29	16	-3.16	23	-3.89	-3.66	0.22	5	2.33	30	1.00	3.02
26	0	-3.16	23	-3.81	-3.58	0.22	5	2.33	29	1.00	3.06

Table SI9: Structural, energetic and electronic properties for Co₁₂ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
11	1424	-3.11	30	-4.02	-3.90	0.12	5	2.36	30	1.00	2.25
30	844	-3.16	24	-3.84	-3.58	0.25	4	2.30	30	1.00	2.80
24	831	-3.16	24	-3.80	-3.58	0.22	4	2.32	30	1.00	2.98
29	780	-3.16	24	-3.78	-3.60	0.17	5	2.33	33	1.00	3.23
26	760	-3.16	24	-3.74	-3.56	0.17	4	2.32	30	1.00	3.14
22	754	-3.16	24	-3.77	-3.54	0.22	5	2.33	33	1.00	3.50
1	708	-3.17	24	-3.79	-3.54	0.24	5	2.32	32	1.00	3.36
18	692	-3.17	24	-3.74	-3.55	0.18	5	2.33	32	1.00	3.22
9	573	-3.18	24	-3.69	-3.49	0.19	5	2.35	34	1.00	3.19
4	565	-3.18	24	-3.76	-3.53	0.23	5	2.32	32	1.00	3.12
17	557	-3.18	24	-3.71	-3.49	0.22	5	2.32	32	1.00	2.97
3	537	-3.18	26	-3.79	-3.66	0.13	4	2.33	30	1.00	2.57
8	500	-3.19	24	-3.60	-3.41	0.18	5	2.38	36	1.00	2.39
12	499	-3.19	24	-3.71	-3.57	0.14	5	2.33	33	1.00	3.17
16	448	-3.19	24	-3.69	-3.45	0.24	4	2.32	32	1.00	3.08
23	377	-3.20	22	-3.51	-3.30	0.20	5	2.35	34	1.00	2.84
14	376	-3.20	24	-3.72	-3.52	0.19	5	2.34	33	1.00	3.06
28	357	-3.20	24	-3.80	-3.47	0.33	5	2.34	33	1.00	3.01
25	357	-3.20	24	-3.80	-3.47	0.33	5	2.34	33	1.00	3.01
31	345	-3.20	22	-3.55	-3.35	0.20	5	2.30	31	1.00	2.69
21	328	-3.20	24	-3.70	-3.47	0.22	5	2.33	31	1.00	3.27
2	271	-3.20	24	-3.68	-3.58	0.10	5	2.32	33	1.00	3.17
10	256	-3.21	24	-3.66	-3.46	0.19	5	2.33	35	1.00	2.68
27	251	-3.21	24	-3.79	-3.54	0.24	5	2.33	34	1.00	3.08
5	251	-3.21	24	-3.79	-3.54	0.24	5	2.33	33	1.00	3.08
6	203	-3.21	24	-3.70	-3.56	0.14	5	2.35	34	1.00	2.99
13	198	-3.21	24	-3.72	-3.52	0.20	5	2.36	34	1.00	2.82
19	156	-3.21	24	-3.65	-3.52	0.12	5	2.34	35	1.00	2.88
7	147	-3.21	24	-3.69	-3.49	0.19	5	2.34	35	1.00	2.99
15	110	-3.22	24	-3.73	-3.60	0.12	5	2.32	31	1.00	3.07
20	0	-3.23	24	-3.69	-3.49	0.20	5	2.33	33	1.00	2.76

Table SI10: Structural, energetic and electronic properties for Co₁₃ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
40	1548	-3.21	25	-3.72	-3.50	0.21	4	2.32	33	1.00	3.18
19	1547	-3.21	25	-3.66	-3.51	0.15	5	2.33	35	1.00	3.45
37	1488	-3.21	25	-3.79	-3.59	0.19	5	2.32	35	1.00	3.23
23	1403	-3.22	27	-3.91	-3.72	0.19	4	2.32	33	1.00	3.25
11	1352	-3.22	25	-3.64	-3.48	0.15	5	2.32	34	1.00	3.52
6	1285	-3.23	27	-3.92	-3.73	0.18	4	2.32	33	1.00	3.13
22	1252	-3.23	25	-3.66	-3.45	0.20	5	2.32	36	1.00	3.25
9	1247	-3.23	25	-3.63	-3.49	0.14	5	2.32	34	1.00	3.20
32	1222	-3.23	25	-3.63	-3.48	0.15	5	2.35	37	1.00	3.16
36	1219	-3.23	25	-3.53	-3.40	0.13	5	2.36	39	1.00	3.20
39	1217	-3.23	25	-3.70	-3.53	0.16	5	2.33	37	1.00	3.24
29	1193	-3.23	25	-3.67	-3.50	0.16	5	2.33	37	1.00	3.11
1	1162	-3.24	25	-3.59	-3.47	0.12	5	2.33	37	1.00	3.44
35	1154	-3.24	25	-3.66	-3.51	0.15	5	2.35	37	1.00	3.05
34	1045	-3.24	25	-3.62	-3.41	0.21	5	2.36	39	1.00	3.11
27	1030	-3.25	25	-3.65	-3.46	0.19	5	2.35	37	1.00	3.50
7	998	-3.25	25	-3.71	-3.52	0.18	5	2.33	34	1.00	3.20
26	991	-3.25	25	-3.62	-3.48	0.13	5	2.35	38	1.00	3.16
14	987	-3.25	27	-3.87	-3.68	0.18	5	2.32	33	1.00	3.19
20	985	-3.25	25	-3.72	-3.52	0.20	5	2.33	37	1.00	3.35
24	936	-3.25	25	-3.73	-3.52	0.21	5	2.33	36	1.00	3.08
15	899	-3.26	27	-3.76	-3.62	0.13	5	2.34	37	1.00	3.15
38	875	-3.26	25	-3.74	-3.42	0.31	5	2.33	36	1.00	2.84
8	860	-3.26	27	-3.83	-3.64	0.19	5	2.33	37	1.00	3.12
2	840	-3.26	25	-3.62	-3.50	0.12	5	2.35	38	1.00	3.00
28	791	-3.26	25	-3.67	-3.52	0.15	5	2.33	36	1.00	3.26
31	782	-3.26	27	-3.86	-3.68	0.17	5	2.34	38	1.00	3.12
18	772	-3.27	27	-3.78	-3.70	0.08	5	2.36	38	1.00	2.96
5	763	-3.27	25	-3.62	-3.50	0.12	5	2.35	36	1.00	2.97
13	740	-3.27	27	-3.80	-3.65	0.15	5	2.34	38	1.00	2.76
3	738	-3.27	27	-3.90	-3.63	0.27	5	2.35	36	1.00	2.63
10	717	-3.27	25	-3.61	-3.45	0.16	5	2.36	38	1.00	3.00
30	701	-3.27	25	-3.66	-3.52	0.13	5	2.33	37	1.00	3.21
12	661	-3.27	27	-3.78	-3.59	0.18	5	2.34	39	1.00	2.97
16	661	-3.27	27	-3.78	-3.59	0.18	5	2.34	39	1.00	2.97
21	586	-3.28	25	-3.60	-3.43	0.17	5	2.35	38	1.00	3.03
33	585	-3.28	27	-3.78	-3.65	0.13	5	2.34	39	1.00	3.15
4	585	-3.28	27	-3.79	-3.65	0.13	5	2.34	39	1.00	3.15
25	584	-3.28	27	-3.79	-3.65	0.13	5	2.34	39	1.00	3.16
17	0	-3.33	27	-3.89	-3.57	0.31	5	2.33	36	1.00	2.76

Table SI11: Structural, energetic and electronic properties for Co₁₄ cluster, as follows: configuration number (*i*), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).


<i>i</i>	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
29	1266	-3.26	28	-3.73	-3.62	0.11	5	2.33	38	1.00	3.40
1	1171	-3.27	28	-3.69	-3.52	0.17	5	2.33	38	1.00	3.35
18	1158	-3.27	28	-3.69	-3.54	0.14	5	2.34	39	1.00	3.45
32	957	-3.28	28	-3.69	-3.52	0.17	5	2.33	40	1.00	3.24
23	954	-3.28	28	-3.65	-3.49	0.15	5	2.34	38	1.00	3.42
5	939	-3.28	28	-3.85	-3.69	0.16	5	2.33	37	1.00	3.26
25	887	-3.29	28	-3.86	-3.67	0.18	5	2.33	37	1.00	3.28
21	805	-3.29	28	-3.86	-3.71	0.15	5	2.34	41	1.00	3.28
03	797	-3.29	28	-3.76	-3.54	0.21	5	2.35	41	1.00	2.82
17	795	-3.29	28	-3.75	-3.63	0.12	5	2.36	41	1.00	3.58
15	677	-3.30	30	-3.79	-3.69	0.09	6	2.40	45	1.00	3.13
20	667	-3.30	28	-3.73	-3.59	0.13	5	2.33	38	1.00	3.40
4	649	-3.30	28	-3.79	-3.66	0.13	5	2.35	39	1.00	3.31
7	638	-3.31	28	-3.63	-3.50	0.13	5	2.37	43	1.00	3.14
27	606	-3.31	28	-3.72	-3.59	0.12	5	2.34	43	1.00	2.59
33	570	-3.31	28	-3.79	-3.67	0.11	5	2.34	38	1.00	3.20
35	545	-3.31	28	-3.72	-3.55	0.17	5	2.35	41	1.00	3.06
19	514	-3.31	28	-3.74	-3.55	0.18	5	2.34	42	1.00	3.19
24	480	-3.32	27	-3.62	-3.62	0.00	5	2.36	42	1.00	3.04
30	460	-3.32	28	-3.74	-3.61	0.13	5	2.36	42	1.00	3.05
14	449	-3.32	28	-3.75	-3.61	0.13	5	2.34	43	1.00	3.22
31	448	-3.32	28	-3.75	-3.61	0.13	5	2.34	43	1.00	3.22
28	382	-3.32	26	-3.59	-3.42	0.17	5	2.36	42	1.00	3.43
9	370	-3.32	30	-3.90	-3.72	0.17	5	2.34	39	1.00	2.81
6	350	-3.33	28	-3.74	-3.60	0.13	5	2.34	40	1.00	3.29
13	324	-3.33	28	-3.74	-3.55	0.19	5	2.34	40	1.00	2.77
12	316	-3.33	28	-3.75	-3.62	0.12	5	2.34	39	1.00	3.10
16	316	-3.33	28	-3.78	-3.59	0.18	5	2.36	42	1.00	2.97
2	287	-3.33	28	-3.74	-3.58	0.15	5	2.34	39	1.00	3.48
22	248	-3.33	28	-3.78	-3.65	0.12	5	2.35	41	1.00	3.11
34	232	-3.33	26	-3.58	-3.37	0.20	5	2.36	42	1.00	3.07
26	205	-3.34	28	-3.84	-3.68	0.16	5	2.34	41	1.00	3.08
8	185	-3.34	28	-3.77	-3.65	0.12	5	2.36	42	1.00	3.07
11	120	-3.34	28	-3.76	-3.60	0.16	5	2.33	39	1.00	2.95
10	0	-3.35	28	-3.71	-3.56	0.15	5	2.33	39	1.00	3.22

*Co₁₄ configuration 24 was excluded from the set.

Table SI12: Structural, energetic and electronic properties for Co₁₅ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
12	2011	-3.26	29	-3.71	-3.55	0.16	5	2.32	42	1.00	3.71
28	1899	-3.27	31	-3.87	-3.72	0.14	5	2.34	43	1.00	3.66
13	1597	-3.29	29	-3.73	-3.58	0.15	5	2.34	42	1.00	3.83
37	1465	-3.30	29	-3.72	-3.55	0.17	5	2.36	45	1.00	3.84
36	1373	-3.31	29	-3.60	-3.48	0.11	5	2.34	44	1.00	3.57
27	1271	-3.31	31	-3.90	-3.73	0.16	5	2.34	44	1.00	3.43
32	1244	-3.31	29	-3.69	-3.56	0.13	5	2.34	44	1.00	3.13
11	929	-3.34	29	-3.69	-3.54	0.14	5	2.36	45	1.00	3.53
22	918	-3.34	31	-3.85	-3.75	0.09	5	2.35	43	1.00	3.36
30	908	-3.34	31	-3.85	-3.73	0.11	5	2.35	43	1.00	3.35
26	875	-3.34	33	-3.97	-3.90	0.07	5	2.34	44	1.00	3.43
31	833	-3.34	29	-3.69	-3.56	0.13	5	2.34	45	1.00	3.32
38	788	-3.34	29	-3.68	-3.56	0.11	6	2.39	48	1.00	3.49
16	700	-3.35	29	-3.71	-3.56	0.14	5	2.34	42	1.00	3.38
1	629	-3.36	29	-3.75	-3.62	0.12	5	2.34	45	1.00	3.32
40	599	-3.36	33	-3.95	-3.81	0.14	5	2.36	46	1.00	2.98
6	574	-3.36	29	-3.68	-3.50	0.18	5	2.34	43	1.00	3.29
21	510	-3.36	31	-3.82	-3.64	0.18	5	2.36	45	1.00	3.02
25	476	-3.37	31	-3.79	-3.75	0.04	5	2.36	46	1.00	3.12
7	468	-3.37	29	-3.73	-3.62	0.11	5	2.35	43	1.00	3.23
23	454	-3.37	29	-3.73	-3.58	0.14	5	2.34	42	1.00	3.39
24	454	-3.37	31	-3.86	-3.73	0.12	5	2.35	42	1.00	3.21
39	452	-3.37	29	-3.64	-3.51	0.13	6	2.39	49	1.00	3.08
33	443	-3.37	33	-3.93	-3.74	0.18	5	2.38	48	1.00	3.05
10	415	-3.37	31	-3.86	-3.69	0.16	5	2.37	47	1.00	2.97
18	408	-3.37	29	-3.84	-3.65	0.18	5	2.34	41	1.00	3.29
34	387	-3.37	29	-3.64	-3.47	0.16	5	2.36	46	1.00	3.17
35	367	-3.37	31	-3.88	-3.72	0.15	5	2.35	48	1.00	3.09
17	354	-3.37	29	-3.74	-3.61	0.13	5	2.34	45	1.00	3.17
19	348	-3.37	31	-3.79	-3.66	0.12	5	2.36	47	1.00	2.83
4	320	-3.38	33	-3.93	-3.75	0.18	5	2.37	48	1.00	2.98
3	319	-3.38	33	-3.93	-3.75	0.18	5	2.37	49	1.00	2.97
09	315	-3.38	31	-3.87	-3.74	0.12	5	2.36	44	1.00	2.90
20	310	-3.38	27	-3.50	-3.38	0.12	5	2.36	46	1.00	3.45
14	306	-3.38	29	-3.66	-3.52	0.14	5	2.34	43	1.00	3.25
5	200	-3.38	31	-3.81	-3.71	0.09	5	2.35	43	1.00	3.06
2	172	-3.39	29	-3.73	-3.58	0.14	5	2.35	44	1.00	3.24
29	113	-3.39	29	-3.72	-3.53	0.18	5	2.36	46	1.00	3.08
8	0	-3.40	29	-3.68	-3.55	0.13	5	2.34	43	1.00	3.21

Table SI13: Lowest energy configurations for Co_n clusters with $n = 2 - 15$.






Figure SI1: Binding energy (E_b) for Co_n clusters with $n = 2 - 15$.




Figure SI2: Total magnetic moment (M_{tot}) for Co_n clusters with $n = 2 - 15$.




Figure SI3: HOMO energy (E_{HOMO}) for Co_n clusters with $n = 2 - 15$.




Figure SI4: LUMO energy (E_{LUMO}) for Co_n clusters with $n = 2 - 15$.




Figure SI5: HOMO-LUMO energy gap (E_{gap}) for Co_n clusters with $n = 2 - 15$.




Figure SI6: Total number of bonds (N_b) for Co_n clusters with $n = 2 - 15$.




Figure SI7: Average chemical order parameter (σ_{av}) for Co_n clusters with $n = 2 - 15$.




Figure SI8: Average bond length (d_{av}) for Co_n clusters with $n = 2 - 15$.




Figure SI9: Average effective coordination number (ECN_{av}) for Co_n clusters with $n = 2 - 15$.




Figure SI10: Average radius R_{av} (in Å) for Co_n clusters ($n = 2-15$).

3 Gas-phase Mo_n Clusters

Table SI14: Structural, energetic and electronic properties for Mo_n cluster with $n = 1 - 5$, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

Mon	i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
Mo ₂	1	0	-2.03	0	-4.18	-2.30	1.87	1	1.91	1.00	1.00	0.95
Mo ₃	2	3265	-1.10	10	-3.19	-2.84	0.35	1	2.33	2.00	1.00	2.49
Mo ₃	2	3265	-1.10	10	-3.19	-2.84	0.35	1	2.33	2.00	1.00	2.49
Mo ₃	1	135	-2.14	2	-3.15	-2.80	0.34	2	2.21	3.00	1.00	1.19
Mo ₃	3	0	-2.18	2	-2.91	-2.34	0.56	1	2.21	3.00	1.00	1.27
Mo ₄	5	172	-2.66	0	-3.30	-2.67	0.63	2	2.26	5.00	1.00	1.72
Mo ₄	6	170	-2.66	0	-3.31	-2.68	0.63	2	2.26	5.00	1.00	1.72
Mo ₄	7	25	-2.70	0	-2.83	-2.14	0.68	1	2.09	6.00	1.00	1.42
Mo ₄	3	2	-2.71	0	-3.30	-2.38	0.91	2	2.21	4.00	1.00	1.51
Mo ₄	2	2	-2.71	0	-3.30	-2.38	0.91	2	2.21	4.00	1.00	1.51
Mo ₄	1	2	-2.71	0	-3.30	-2.38	0.91	2	2.21	4.00	1.00	1.51
Mo ₄	4	0	-2.71	0	-3.30	-2.39	0.91	2	2.21	4.00	1.00	1.51
Mo ₅	1	1574	-2.71	0	-3.60	-3.01	0.58	1	2.19	5.00	1.00	2.00
Mo ₅	4	1146	-2.80	0	-3.46	-2.78	0.67	1	2.16	6.00	1.00	2.27
Mo ₅	8	899	-2.85	0	-3.24	-2.66	0.57	2	2.22	8.00	1.00	2.22
Mo ₅	6	267	-2.97	0	-3.10	-2.58	0.52	2	2.35	9.00	1.00	1.65
Mo ₅	9	4	-3.03	0	-2.88	-2.33	0.55	2	2.33	9.00	1.00	1.81
Mo ₅	3	2	-3.03	0	-2.88	-2.33	0.55	2	2.33	9.00	1.00	1.81
Mo ₅	2	0	-3.03	0	-2.88	-2.33	0.55	2	2.33	9.00	1.00	1.81
Mo ₅	5	0	-3.03	0	-2.88	-2.33	0.55	2	2.33	9.00	1.00	1.81
Mo ₅	7	0	-3.03	0	-2.88	-2.33	0.55	2	2.33	9.00	1.00	1.81

Table SI15: Structural, energetic and electronic properties for Mo₆ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
4	3839	-2.72	0	-3.92	-3.16	0.75	1	1.95	3.00	1.00	2.50
10	1235	-3.16	0	-3.40	-2.59	0.80	2	2.27	11.00	1.00	2.47
8	1124	-3.17	0	-3.15	-2.61	0.53	3	2.42	12.00	1.00	2.02
2	1064	-3.18	2	-2.96	-2.65	0.31	3	2.42	12.00	1.00	2.05
11	1027	-3.19	0	-3.11	-2.47	0.63	2	2.28	9.00	1.00	2.05
9	1027	-3.19	0	-3.11	-2.47	0.63	2	2.28	9.00	1.00	2.05
5	1027	-3.19	0	-3.11	-2.48	0.63	2	2.28	9.00	1.00	2.05
6	1	-3.36	0	-2.98	-2.25	0.72	3	2.38	12.00	1.00	1.76
3	1	-3.36	0	-2.98	-2.25	0.72	3	2.38	12.00	1.00	1.76
12	1	-3.36	0	-2.98	-2.25	0.72	3	2.38	12.00	1.00	1.76
7	1	-3.36	0	-2.98	-2.25	0.72	3	2.38	12.00	1.00	1.76
1	0	-3.36	0	-2.98	-2.25	0.72	3	2.38	12.00	1.00	1.76

Table SI16: Structural, energetic and electronic properties for Mo₇ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
8	1948	-3.22	0	-3.30	-2.59	0.70	2	2.19	11.00	1.00	2.51
0	1947	-3.22	0	-3.30	-2.59	0.71	2	2.19	11.00	1.00	2.51
5	1713	-3.25	0	-3.25	-2.71	0.54	2	2.31	15.00	1.00	2.48
3	1713	-3.25	0	-3.25	-2.71	0.54	2	2.31	15.00	1.00	2.48
7	1250	-3.32	0	-3.05	-2.70	0.34	2	2.30	14.00	1.00	2.73
4	973	-3.36	0	-3.22	-2.81	0.41	2	2.34	15.00	1.00	2.62
2	758	-3.39	0	-3.07	-2.73	0.34	3	2.41	15.00	1.00	2.31
3	499	-3.43	0	-2.94	-2.69	0.24	3	2.45	16.00	1.00	2.18
6	482	-3.43	0	-3.05	-2.61	0.44	3	2.39	14.00	1.00	2.42
5	202	-3.47	0	-2.94	-2.29	0.64	3	2.44	16.00	1.00	2.06
8	10	-3.50	0	-2.99	-2.39	0.60	3	2.38	16.00	1.00	2.33
0	10	-3.50	0	-3.00	-2.39	0.60	3	2.38	16.00	1.00	2.33
9	9	-3.50	0	-2.99	-2.39	0.60	3	2.38	16.00	1.00	2.33
4	6	-3.50	0	-2.82	-2.42	0.39	3	2.41	15.00	1.00	2.16
9	6	-3.50	0	-2.82	-2.42	0.39	3	2.41	15.00	1.00	2.16
1	2	-3.50	0	-2.83	-2.38	0.45	3	2.43	14.00	1.00	1.98
7	2	-3.50	0	-2.83	-2.38	0.44	3	2.43	15.00	1.00	1.98
6	2	-3.50	0	-2.83	-2.38	0.45	3	2.43	15.00	1.00	1.98
2	0	-3.50	0	-2.83	-2.38	0.44	3	2.43	14.00	1.00	1.98

Table SI17: Structural, energetic and electronic properties for Mo₈ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
9	1918	-3.42	0	3.35	-3.07	0.28	3	2.38	18.00	1.00	2.53
15	1437	-3.48	0	3.17	-2.84	0.32	3	2.43	18.00	1.00	2.41
14	1024	-3.54	0	3.07	-2.63	0.43	3	2.41	18.00	1.00	2.60
10	743	-3.57	0	3.07	-2.64	0.43	3	2.41	19.00	1.00	2.74
19	693	-3.58	0	3.32	-2.70	0.61	3	2.42	19.00	1.00	2.81
16	693	-3.58	0	3.32	-2.70	0.61	3	2.42	19.00	1.00	2.81
7	475	-3.60	4	3.19	-2.85	0.33	3	2.45	18.00	1.00	2.61
6	474	-3.60	4	3.19	-2.85	0.33	3	2.45	18.00	1.00	2.61
8	472	-3.60	4	3.19	-2.85	0.33	3	2.45	18.00	1.00	2.61
3	180	-3.64	0	2.91	-2.67	0.23	3	2.44	18.00	1.00	2.47
13	177	-3.64	0	2.91	-2.67	0.24	3	2.44	18.00	1.00	2.47
18	177	-3.64	0	2.91	-2.67	0.24	3	2.44	18.00	1.00	2.47
11	161	-3.64	0	2.95	-2.75	0.19	3	2.45	19.00	1.00	2.44
5	134	-3.65	0	3.47	-2.64	0.83	3	2.45	18.00	1.00	2.19
17	125	-3.65	0	3.13	-2.33	0.80	3	2.46	16.00	1.00	1.97
4	123	-3.65	0	3.13	-2.33	0.80	3	2.46	16.00	1.00	1.97
2	121	-3.65	0	3.13	-2.33	0.79	3	2.46	16.00	1.00	1.97
12	95	-3.65	4	3.04	-2.68	0.35	3	2.43	18.00	1.00	2.11
1	0	-3.66	0	3.01	-2.43	0.58	3	2.42	18.00	1.00	2.36

Table SI18: Structural, energetic and electronic properties for Mo₉ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
23	2566	-3.51	0	-3.44	-2.95	0.48	2	2.28	18.00	1.00	2.97
5	2107	-3.56	0	-3.38	-2.89	0.48	3	2.40	21.00	1.00	3.26
21	1701	-3.61	0	-3.21	-2.88	0.32	3	2.39	22.00	1.00	3.36
30	1499	-3.63	0	-3.08	-2.78	0.30	3	2.45	21.00	1.00	2.97
18	1473	-3.63	0	-3.06	-2.75	0.31	3	2.41	22.00	1.00	2.79
27	1470	-3.63	0	-3.06	-2.75	0.31	3	2.41	22.00	1.00	2.79
28	1431	-3.64	0	-3.11	-2.73	0.38	3	2.41	22.00	1.00	3.19
19	1137	-3.67	0	-3.14	-2.58	0.55	3	2.42	21.00	1.00	3.09
01	979	-3.69	0	-2.89	-2.67	0.22	3	2.45	21.00	1.00	2.51
14	941	-3.69	0	-3.20	-2.79	0.41	3	2.45	22.00	1.00	3.00
4	896	-3.69	0	-3.06	-2.70	0.36	3	2.42	21.00	1.00	2.80
10	895	-3.69	0	-3.06	-2.69	0.36	3	2.42	21.00	1.00	2.80
26	859	-3.70	0	-2.84	-2.55	0.28	3	2.44	21.00	1.00	2.59
8	830	-3.70	0	-3.01	-2.73	0.27	3	2.46	21.00	1.00	2.61
13	804	-3.70	0	-3.14	-2.88	0.26	3	2.45	23.00	1.00	2.85
06	738	-3.71	0	-2.96	-2.57	0.38	3	2.41	21.00	1.00	2.79
16	736	-3.71	0	-2.96	-2.57	0.38	3	2.41	21.00	1.00	2.79
2	587	-3.73	4	-3.06	-2.90	0.15	4	2.49	21.00	1.00	2.49
3	573	-3.73	0	-3.11	-2.72	0.39	4	2.47	23.00	1.00	2.47
15	572	-3.73	0	-3.11	-2.72	0.39	4	2.47	23.00	1.00	2.47
22	567	-3.73	0	-2.93	-2.61	0.31	3	2.45	21.00	1.00	2.54
29	496	-3.74	0	-3.10	-2.66	0.43	3	2.43	21.00	1.00	2.71
11	496	-3.74	0	-3.09	-2.66	0.43	3	2.43	22.00	1.00	2.71
12	495	-3.74	0	-3.09	-2.66	0.42	3	2.43	22.00	1.00	2.70
20	494	-3.74	0	-2.96	-2.66	0.30	3	2.44	22.00	1.00	2.55
25	91	-3.78	0	-3.06	-2.53	0.52	3	2.45	21.00	1.00	2.51
7	90	-3.78	0	-3.06	-2.53	0.53	3	2.45	21.00	1.00	2.51
17	90	-3.78	0	-3.06	-2.53	0.53	3	2.45	21.00	1.00	2.51
24	2	-3.79	0	-2.64	-2.59	0.04	4	2.47	21.00	1.00	2.10
9	0	-3.79	0	-2.64	-2.59	0.04	4	2.47	21.00	1.00	2.10

Table SI19: Structural, energetic and electronic properties for Mo₁₀ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
17	2129	-3.67	0	-2.94	-2.56	0.37	2	2.36	20.00	1.00	2.30
12	1944	-3.69	0	-2.98	-2.86	0.12	4	2.49	23.00	1.00	3.23
15	1055	-3.78	0	-3.17	-2.87	0.29	4	2.48	25.00	1.00	3.33
1	1045	-3.78	0	-3.00	-2.74	0.25	3	2.43	24.00	1.00	3.15
10	987	-3.79	0	-3.17	-2.72	0.44	4	2.48	26.00	1.00	2.65
18	951	-3.79	0	-3.09	-2.63	0.45	4	2.48	26.00	1.00	2.94
14	861	-3.80	0	-2.97	-2.79	0.18	3	2.47	24.00	1.00	2.89
3	847	-3.80	0	-2.98	-2.74	0.23	4	2.48	25.00	1.00	2.71
11	846	-3.80	0	-2.97	-2.74	0.23	4	2.48	25.00	1.00	2.71
13	772	-3.81	0	-2.99	-2.63	0.35	3	2.45	24.00	1.00	3.10
2	732	-3.81	0	-3.01	-2.64	0.37	3	2.46	26.00	1.00	2.61
4	683	-3.82	0	-3.02	-2.80	0.21	3	2.46	24.00	1.00	2.65
9	667	-3.82	0	-3.16	-2.73	0.43	4	2.44	26.00	1.00	3.40
16	624	-3.82	0	-3.04	-2.63	0.40	4	2.46	25.00	1.00	3.05
7	378	-3.85	0	-3.00	-2.82	0.18	3	2.47	25.00	1.00	2.56
6	254	-3.86	0	-3.03	-2.35	0.68	3	2.43	23.00	1.00	2.91
5	0	-3.89	0	-2.98	-2.76	0.22	3	2.47	24.00	1.00	2.64

Table SI20: Structural, energetic and electronic properties for Mo₁₁ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
28	2654	-3.72	0	-3.33	-3.19	0.13	4	2.47	28.00	1.00	3.28
32	1830	-3.80	0	-3.24	-3.06	0.18	3	2.42	27.00	1.00	3.20
24	1669	-3.81	0	-3.13	-2.92	0.21	4	2.47	28.00	1.00	3.18
30	1585	-3.82	0	-3.05	-2.97	0.07	3	2.48	27.00	1.00	2.67
9	1363	-3.84	0	-3.06	-2.91	0.15	3	2.47	27.00	1.00	2.78
19	1296	-3.84	0	-2.98	-2.80	0.17	3	2.48	27.00	1.00	2.82
11	1294	-3.84	0	-2.97	-2.80	0.17	3	2.48	27.00	1.00	2.82
23	1197	-3.85	0	-3.21	-2.86	0.35	3	2.41	28.00	1.00	3.44
4	1139	-3.86	0	-3.16	-2.92	0.24	4	2.46	28.00	1.00	3.16
25	1113	-3.86	0	-3.15	-2.76	0.38	3	2.45	31.00	1.00	2.85
07	996	-3.87	0	-3.12	-2.87	0.24	4	2.49	28.00	1.00	3.08
15	798	-3.89	0	-3.12	-2.90	0.21	4	2.48	27.00	1.00	2.85
1	789	-3.89	0	-3.06	-2.81	0.25	4	2.47	27.00	1.00	3.07
6	755	-3.89	0	-2.88	-2.68	0.19	4	2.48	29.00	1.00	3.01
18	746	-3.89	0	-2.83	-2.70	0.13	3	2.46	29.00	1.00	3.05
16	732	-3.90	0	-3.06	-2.87	0.19	4	2.49	29.00	1.00	2.81
14	656	-3.90	0	-3.03	-2.83	0.20	4	2.48	27.00	1.00	2.69
10	646	-3.90	0	-3.09	-2.85	0.23	4	2.48	27.00	1.00	3.07
27	645	-3.90	0	-3.08	-2.85	0.23	4	2.48	27.00	1.00	3.06
26	633	-3.90	0	-3.03	-2.79	0.24	4	2.48	28.00	1.00	2.90
2	631	-3.90	0	-3.03	-2.79	0.24	4	2.48	28.00	1.00	2.90
29	631	-3.90	0	-3.04	-2.79	0.24	4	2.48	28.00	1.00	2.90
8	602	-3.91	0	-3.05	-2.83	0.22	3	2.47	28.00	1.00	3.00
13	191	-3.94	0	-2.97	-2.56	0.40	3	2.44	30.00	1.00	2.87
31	155	-3.95	0	-2.90	-2.57	0.33	4	2.46	27.00	1.00	3.08
21	154	-3.95	0	-2.90	-2.57	0.33	4	2.46	27.00	1.00	3.08
17	71	-3.96	0	-3.25	-2.98	0.27	4	2.49	28.00	1.00	2.66
22	0	-3.96	0	-3.02	-2.62	0.39	4	2.46	27.00	1.00	3.04

Table SI21: Structural, energetic and electronic properties for Mo₁₂ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
35	2333	-3.87	0	-3.22	-2.90	0.31	3	2.41	32.00	1.00	4.14
2	2172	-3.88	0	-3.07	-2.77	0.30	4	2.47	32.00	1.00	3.57
36	2084	-3.89	0	-3.39	-3.09	0.29	3	2.44	33.00	1.00	3.54
9	1867	-3.91	0	-3.23	-3.00	0.23	4	2.48	31.00	1.00	3.32
37	1842	-3.91	0	-3.26	-3.05	0.21	3	2.42	32.00	1.00	3.42
22	1755	-3.92	0	-3.18	-3.04	0.14	3	2.44	32.00	1.00	3.47
20	1736	-3.92	0	-3.26	-2.92	0.34	3	2.42	32.00	1.00	3.35
29	1634	-3.93	0	-2.99	-2.96	0.02	4	2.49	32.00	1.00	3.71
3	1623	-3.93	0	-3.09	-2.81	0.27	3	2.44	33.00	1.00	3.32
6	1608	-3.93	0	-2.89	-2.65	0.24	3	2.46	30.00	1.00	3.48
34	1589	-3.93	0	-3.13	-2.95	0.18	4	2.49	30.00	1.00	3.16
32	1563	-3.93	0	-3.27	-2.96	0.31	3	2.40	30.00	1.00	3.44
4	1455	-3.94	0	-3.08	-2.82	0.25	4	2.47	33.00	1.00	3.26
10	1452	-3.94	0	-3.09	-2.83	0.25	4	2.47	33.00	1.00	3.26
17	1449	-3.94	0	-3.19	-2.87	0.32	4	2.46	32.00	1.00	3.75
24	1401	-3.94	0	-3.30	-2.98	0.31	4	2.47	33.00	1.00	3.17
23	1395	-3.95	0	-3.07	-2.63	0.43	4	2.45	29.00	1.00	3.16
18	1314	-3.95	0	-3.14	-2.84	0.30	4	2.45	32.00	1.00	3.03
21	1290	-3.95	0	-3.03	-2.81	0.22	4	2.51	31.00	1.00	3.22
38	1221	-3.96	0	-2.95	-2.79	0.15	3	2.44	30.00	1.00	2.79
1	1165	-3.96	0	-3.09	-2.86	0.22	4	2.49	32.00	1.00	3.52
15	1133	-3.97	0	-2.89	-2.70	0.18	3	2.45	30.00	1.00	2.67
27	1118	-3.97	0	-3.07	-2.77	0.30	4	2.48	32.00	1.00	3.15
28	1118	-3.97	0	-3.03	-2.74	0.28	4	2.47	30.00	1.00	3.45
30	1052	-3.97	0	-3.14	-2.68	0.45	3	2.42	29.00	1.00	3.17
33	983	-3.98	0	-3.14	-2.78	0.36	4	2.48	31.00	1.00	3.09
14	976	-3.98	0	-3.03	-2.81	0.21	4	2.48	33.00	1.00	3.44
31	919	-3.98	0	-3.13	-2.95	0.17	4	2.46	32.00	1.00	3.05
13	888	-3.99	0	-3.18	-2.86	0.32	4	2.47	32.00	1.00	3.03
19	885	-3.99	0	-3.00	-2.69	0.31	4	2.47	32.00	1.00	3.19
8	841	-3.99	0	-3.03	-2.63	0.39	4	2.49	31.00	1.00	3.25
26	827	-3.99	0	-3.23	-2.72	0.51	4	2.45	32.00	1.00	2.87
25	776	-4.00	0	-3.19	-2.92	0.27	4	2.48	32.00	1.00	3.35
5	693	-4.00	0	-3.05	-2.80	0.24	4	2.47	31.00	1.00	3.23
11	677	-4.00	0	-2.93	-2.65	0.28	4	2.48	34.00	1.00	3.12
16	676	-4.00	0	-2.93	-2.64	0.28	4	2.48	32.00	1.00	3.12
7	571	-4.01	0	-3.05	-2.54	0.50	4	2.49	30.00	1.00	3.02
39	566	-4.01	0	-3.12	-2.92	0.20	4	2.50	32.00	1.00	3.03
12	0	-4.06	0	-3.13	-2.85	0.27	4	2.49	36.00	1.00	2.71

Table SI22: Structural, energetic and electronic properties for Mo₁₃ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
32	8047	-3.50	0	-3.09	-3.01	0.07	4	2.95	39.00	1.00	8.40
29	1952	-3.97	0	-3.31	-3.06	0.25	3	2.45	34.00	1.00	3.47
15	1921	-3.97	0	-3.25	-3.05	0.19	4	2.50	35.00	1.00	3.79
39	1802	-3.98	0	-3.34	-3.09	0.25	4	2.49	36.00	1.00	3.32
10	1645	-3.99	0	-3.21	-2.99	0.21	4	2.48	34.00	1.00	3.66
52	1590	-4.00	0	-3.18	-2.81	0.36	3	2.44	36.00	1.00	3.72
36	1542	-4.00	0	-3.15	-2.90	0.24	4	2.49	37.00	1.00	3.35
57	1530	-4.00	0	-3.19	-2.88	0.30	4	2.49	38.00	1.00	3.22
61	1523	-4.00	0	-3.21	-2.94	0.27	4	2.46	36.00	1.00	3.73
28	1510	-4.00	0	-3.20	-2.95	0.25	4	2.48	36.00	1.00	3.31
63	1484	-4.00	0	-3.18	-2.95	0.22	4	2.47	36.00	1.00	3.36
8	1457	-4.01	0	-3.15	-2.84	0.31	4	2.49	36.00	1.00	3.29
40	1416	-4.01	0	-3.17	-2.85	0.31	3	2.45	37.00	1.00	3.19
41	1416	-4.01	0	-3.26	-2.94	0.32	4	2.43	35.00	1.00	3.58
5	1388	-4.01	0	-3.07	-2.81	0.26	4	2.49	34.00	1.00	3.45
9	1372	-4.01	0	-3.21	-2.85	0.35	3	2.44	36.00	1.00	3.23
30	1366	-4.01	0	-3.24	-2.95	0.28	4	2.47	37.00	1.00	3.36
20	1365	-4.01	0	-3.08	-2.91	0.17	4	2.50	36.00	1.00	3.24
1	1352	-4.02	0	-2.92	-2.84	0.07	4	2.50	35.00	1.00	3.68
3	1340	-4.02	0	-3.21	-2.90	0.31	4	2.50	38.00	1.00	3.16
24	1305	-4.02	0	-3.22	-3.03	0.19	4	2.47	38.00	1.00	3.23
35	1300	-4.02	0	-3.08	-2.76	0.32	4	2.47	34.00	1.00	3.57
14	1299	-4.02	0	-3.35	-2.97	0.37	4	2.45	38.00	1.00	3.17
26	1293	-4.02	0	-3.25	-3.05	0.20	4	2.47	35.00	1.00	3.63
64	1273	-4.02	0	-3.24	-2.92	0.31	3	2.44	32.00	1.00	3.49
31	1208	-4.03	0	-3.27	-2.97	0.29	4	2.48	36.00	1.00	3.31
60	1198	-4.03	0	-3.26	-3.01	0.25	4	2.43	36.00	1.00	3.01
34	1195	-4.03	0	-3.00	-2.81	0.18	4	2.49	36.00	1.00	3.74
33	1108	-4.03	0	-2.95	-2.72	0.22	4	2.47	36.00	1.00	3.37
58	1090	-4.04	0	-3.24	-2.96	0.28	4	2.48	37.00	1.00	3.11
47	1054	-4.04	0	-3.10	-2.92	0.17	4	2.47	37.00	1.00	3.19
12	1053	-4.04	0	-3.12	-2.88	0.24	4	2.48	36.00	1.00	3.30
38	987	-4.04	0	-3.10	-2.82	0.27	4	2.48	35.00	1.00	3.30
4	982	-4.04	0	-3.06	-2.93	0.12	4	2.51	36.00	1.00	2.89
43	968	-4.04	0	-3.26	-3.00	0.26	4	2.46	35.00	1.00	3.25
37	963	-4.05	0	-3.09	-2.91	0.18	3	2.44	35.00	1.00	3.27
51	959	-4.05	0	-3.27	-2.93	0.34	4	2.49	37.00	1.00	3.09
22	959	-4.05	0	-3.27	-2.93	0.34	4	2.49	37.00	1.00	3.09
11	954	-4.05	0	-3.19	-2.91	0.28	4	2.47	35.00	1.00	3.23
62	899	-4.05	0	-2.94	-2.68	0.25	4	2.46	37.00	1.00	3.06
65	851	-4.05	0	-3.25	-2.87	0.37	4	2.46	35.00	1.00	3.10
45	820	-4.06	0	-3.38	-2.87	0.51	3	2.43	35.00	1.00	3.23
13	790	-4.06	0	-3.00	-2.77	0.22	4	2.50	38.00	1.00	2.86
19	773	-4.06	0	-3.04	-2.76	0.28	4	2.50	33.00	1.00	3.21
55	753	-4.06	0	-3.01	-2.82	0.18	4	2.48	36.00	1.00	3.37
42	684	-4.07	0	-3.15	-2.94	0.20	4	2.50	37.00	1.00	3.33
21	680	-4.07	0	-2.99	-2.79	0.19	4	2.49	35.00	1.00	3.28
25	678	-4.07	0	-2.99	-2.79	0.19	4	2.49	35.00	1.00	3.28
16	668	-4.07	0	-3.02	-2.81	0.20	4	2.47	35.00	1.00	3.16

27	666	-4.07	0	-3.02	-2.81	0.20	4	2.47	37.00	1.00	3.16
6	549	-4.08	0	-2.84	-2.72	0.12	4	2.49	35.00	1.00	3.29
44	518	-4.08	0	-3.11	-2.78	0.33	4	2.47	39.00	1.00	3.49
49	460	-4.08	0	-3.20	-2.92	0.28	4	2.51	34.00	1.00	3.16
50	440	-4.09	0	-3.21	-2.86	0.35	4	2.47	39.00	1.00	2.92
56	389	-4.09	0	-3.06	-2.75	0.30	4	2.47	34.00	1.00	3.14
53	387	-4.09	0	-3.08	-2.76	0.32	4	2.49	37.00	1.00	2.91
17	357	-4.09	0	-3.23	-2.79	0.43	4	2.49	36.00	1.00	3.04
48	307	-4.10	0	-3.09	-2.82	0.27	4	2.47	35.00	1.00	3.09
7	217	-4.10	0	-2.81	-2.60	0.21	4	2.49	33.00	1.00	3.20
54	179	-4.11	0	-3.00	-2.72	0.28	4	2.50	37.00	1.00	2.92
2	3	-4.12	0	-3.20	-2.85	0.34	4	2.48	39.00	1.00	2.75
59	2	-4.12	0	-3.20	-2.85	0.34	4	2.48	39.00	1.00	2.75
18	1	-4.12	0	-3.19	-2.85	0.34	4	2.48	39.00	1.00	2.75
23	0	-4.12	0	-3.20	-2.85	0.34	4	2.48	39.00	1.00	2.75

Table SI23: Structural, energetic and electronic properties for Mo₁₄ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).


i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
9	2117	-4.00	0	-3.32	-3.00	0.31	4	2.49	37.00	1.00	3.44
28	1827	-4.02	0	-3.26	-3.02	0.24	4	2.49	38.00	1.00	3.48
19	1575	-4.04	0	-3.27	-3.10	0.16	4	2.51	41.00	1.00	3.73
23	1570	-4.04	0	-3.10	-2.89	0.20	4	2.43	38.00	1.00	3.69
20	1568	-4.04	0	-3.20	-2.97	0.23	4	2.48	38.00	1.00	3.78
24	1388	-4.06	0	-3.17	-2.89	0.27	4	2.48	40.00	1.00	3.36
21	1261	-4.06	0	-3.35	-2.97	0.37	4	2.46	37.00	1.00	3.70
03	1222	-4.07	0	-3.28	-3.04	0.24	4	2.49	39.00	1.00	3.57
15	1112	-4.08	0	-3.12	-3.00	0.12	4	2.50	39.00	1.00	3.11
6	1104	-4.08	0	-3.24	-2.99	0.25	4	2.45	41.00	1.00	3.58
1	1104	-4.08	0	-3.02	-2.79	0.23	4	2.50	38.00	1.00	3.64
29	1072	-4.08	0	-3.16	-2.88	0.27	4	2.46	39.00	1.00	3.64
26	952	-4.09	0	-3.41	-3.01	0.40	4	2.46	41.00	1.00	3.22
25	935	-4.09	0	-3.09	-2.88	0.21	4	2.49	39.00	1.00	3.71
4	932	-4.09	0	-3.22	-2.69	0.53	4	2.46	38.00	1.00	2.97
40	839	-4.10	0	-3.20	-2.90	0.30	4	2.49	40.00	1.00	3.60
37	839	-4.10	0	-3.13	-2.96	0.16	4	2.46	38.00	1.00	3.66
35	836	-4.10	0	-3.15	-3.00	0.14	4	2.51	37.00	1.00	3.41
18	817	-4.10	0	-3.31	-2.91	0.39	4	2.51	42.00	1.00	3.26
33	813	-4.10	0	-3.07	-2.74	0.32	4	2.47	40.00	1.00	3.87
8	807	-4.10	0	-3.13	-2.83	0.30	4	2.48	41.00	1.00	3.63
12	786	-4.10	0	-3.11	-2.96	0.15	4	2.49	39.00	1.00	3.17
34	758	-4.10	0	-3.17	-2.93	0.23	4	2.49	40.00	1.00	3.30
31	737	-4.10	0	-3.22	-2.89	0.32	4	2.51	42.00	1.00	3.64
11	701	-4.11	0	-3.23	-2.78	0.44	4	2.46	39.00	1.00	3.08
27	643	-4.11	0	-3.27	-2.96	0.30	4	2.44	41.00	1.00	3.25
22	627	-4.11	0	-3.04	-2.80	0.24	4	2.48	40.00	1.00	3.38
13	511	-4.12	0	-3.09	-2.91	0.17	4	2.49	40.00	1.00	3.19
10	343	-4.13	0	-3.17	-2.82	0.35	4	2.49	40.00	1.00	3.28
36	338	-4.13	0	-2.99	-2.70	0.28	4	2.51	38.00	1.00	3.37
7	302	-4.13	0	-2.90	-2.75	0.14	4	2.50	37.00	1.00	3.40
5	217	-4.14	0	-3.12	-2.90	0.22	4	2.50	43.00	1.00	3.31
17	157	-4.14	0	-3.14	-2.89	0.24	4	2.49	41.00	1.00	3.41
14	126	-4.15	0	-3.08	-2.84	0.24	4	2.47	41.00	1.00	3.41
39	126	-4.15	0	-3.07	-2.69	0.37	4	2.45	36.00	1.00	3.23
2	35	-4.15	0	-3.22	-3.02	0.19	4	2.52	42.00	1.00	2.98
16	22	-4.15	0	-3.02	-2.84	0.18	4	2.50	40.00	1.00	3.23
38	0	-4.16	0	-3.02	-2.79	0.23	4	2.51	40.00	1.00	3.12

Table SI24: Structural, energetic and electronic properties for Mo₁₅ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average bond length (d_{av} , in Å), average chemical order parameter (σ_{av}), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	ECN_{av}	d_{av}	N_b	σ_{av}	R_{av}
35	3381	-4.04	0	-3.28	-3.10	0.18	4	2.49	42.00	1.00	3.91
16	2641	-4.09	0	-3.36	-3.05	0.31	4	2.51	42.00	1.00	3.75
31	2639	-4.09	0	-3.18	-2.96	0.22	4	2.51	42.00	1.00	4.41
18	2410	-4.10	0	-3.31	-3.01	0.30	4	2.50	42.00	1.00	4.13
24	2095	-4.12	0	-3.21	-3.02	0.19	4	2.52	41.00	1.00	3.46
9	2032	-4.13	0	-3.28	-2.91	0.36	4	2.49	42.00	1.00	3.52
10	1967	-4.13	0	-3.24	-2.96	0.27	4	2.52	46.00	1.00	3.39
21	1913	-4.14	0	-3.17	-2.87	0.29	4	2.50	42.00	1.00	3.97
29	1895	-4.14	0	-3.19	-2.88	0.31	4	2.45	42.00	1.00	3.51
26	1872	-4.14	0	-3.31	-2.92	0.38	4	2.48	43.00	1.00	3.75
38	1852	-4.14	0	-3.16	-2.79	0.36	4	2.49	43.00	1.00	3.55
15	1655	-4.15	0	-3.35	-3.09	0.25	4	2.51	46.00	1.00	3.22
01	1637	-4.15	0	-3.21	-2.88	0.32	4	2.49	42.00	1.00	3.52
34	1621	-4.16	0	-3.22	-2.97	0.25	4	2.46	42.00	1.00	3.63
33	1596	-4.16	0	-3.17	-2.86	0.30	4	2.50	42.00	1.00	3.64
6	1594	-4.16	0	-3.17	-2.87	0.30	4	2.50	42.00	1.00	3.64
23	1579	-4.16	0	-3.20	-3.01	0.19	4	2.50	44.00	1.00	3.57
20	1463	-4.17	0	-3.03	-2.79	0.23	4	2.51	41.00	1.00	3.67
28	1437	-4.17	0	-3.28	-2.96	0.32	4	2.49	44.00	1.00	3.50
22	1283	-4.18	0	-3.05	-2.84	0.21	4	2.50	43.00	1.00	3.46
12	1281	-4.18	0	-3.05	-2.84	0.21	4	2.50	43.00	1.00	3.46
7	1216	-4.18	0	-3.25	-2.96	0.29	4	2.51	42.00	1.00	3.37
37	1185	-4.19	0	-3.19	-2.95	0.24	4	2.51	43.00	1.00	3.65
36	1180	-4.19	0	-3.24	-2.85	0.39	4	2.45	40.00	1.00	3.74
40	1144	-4.19	0	-3.10	-2.84	0.26	4	2.50	45.00	1.00	3.38
32	1119	-4.19	0	-3.10	-2.92	0.17	4	2.51	46.00	1.00	3.52
8	1072	-4.19	0	-3.09	-2.88	0.20	4	2.47	39.00	1.00	3.36
11	1049	-4.19	0	-3.23	-2.93	0.29	4	2.49	46.00	1.00	3.52
2	1049	-4.19	0	-3.23	-2.93	0.29	4	2.49	46.00	1.00	3.52
19	1023	-4.20	0	-2.98	-2.81	0.16	4	2.51	40.00	1.00	3.39
25	941	-4.20	0	-3.20	-2.93	0.27	4	2.50	47.00	1.00	3.41
27	884	-4.21	0	-3.17	-2.97	0.19	4	2.51	44.00	1.00	3.27
17	752	-4.21	0	-2.91	-2.70	0.20	4	2.50	45.00	1.00	3.39
39	725	-4.22	0	-3.16	-2.97	0.18	4	2.49	49.00	1.00	3.15
14	659	-4.22	0	-3.18	-2.94	0.24	4	2.50	45.00	1.00	3.56
3	633	-4.22	0	-3.27	-2.93	0.34	4	2.44	44.00	1.00	3.53
5	502	-4.23	0	-3.14	-2.98	0.16	4	2.50	44.00	1.00	3.34
13	487	-4.23	0	-3.13	-2.96	0.16	5	2.54	49.00	1.00	3.05
4	0	-4.26	0	-3.14	-2.90	0.23	4	2.52	48.00	1.00	2.79

*Mo₁₅ configuration 30 was excluded from the set.

Table SI25: Lowest energy configurations for Mo_{*n*} clusters with *n* = 2 – 15.






Figure SI11: Binding energy (E_b) for Mo_n clusters with $n = 2 - 15$.




Figure SI12: HOMO energy (E_{HOMO}) for Mo_n clusters with $n = 2 - 15$.




Figure SI13: LUMO energy (E_{LUMO}) for Mo_n clusters with $n = 2 - 15$.




Figure SI14: HOMO-LUMO energy gap (E_{gap}) for Mo_n clusters with $n = 2 - 15$.




Figure SI15: Total magnetic moment (M_{tot}) for Mo_n clusters with $n = 2 - 15$.




Figure SI16: Average bond length (d_{av}) for Mo_n clusters with $n = 2 - 15$.




Figure SI17: Average effective coordination number (ECN_{av}) for Mo_n clusters with $n = 2 - 15$.




Figure SI18: Total number of bonds (N_b) for Mo_n clusters with $n = 2 - 15$.




Figure SI19: Average chemical order parameter (σ_{av}) for Mo_n clusters with $n = 2 - 15$.




Figure SI20: Average radius (R_{av}) for Mo_n clusters with $n = 2 - 15$.

4 Gas-phase Co_nMo_m Subnanoalloys

Table SI26: Structural, energetic and electronic properties for CoMo cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
2	0	-0.99	0.63	-0.99	3	-3.44	-3.05	0.38	1	-1.00	1.97	1.00	0.98
1	0	-0.99	0.63	-0.99	3	-3.44	-3.05	0.38	1	-1.00	1.97	1.00	0.98

Table SI27: Structural, energetic and electronic properties for Co_2Mo cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
2	121	-1.58	0.23	-0.74	4	-3.43	-3.03	0.39	3	-0.33	2.12	1.58	1.32
1	0	-1.62	0.19	-0.78	8	-3.64	-3.01	0.63	3	-0.33	2.22	1.85	1.28
3	0	-1.62	0.19	-0.78	8	-3.64	-3.01	0.63	3	-0.33	2.22	1.85	1.28

Table SI28: Structural, energetic and electronic properties for Co_2Mo_2 cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
2	724	-2.17	-0.12	-0.52	6	-3.04	-2.63	0.41	6	-0.33	2.28	2.71	1.40
5	723	-2.17	-0.12	-0.52	6	-3.04	-2.63	0.40	6	-0.33	2.28	2.71	1.40
6	1	-2.35	-0.05	-0.70	4	-3.29	-2.97	0.32	6	-0.33	2.20	2.14	1.49
3	0	-2.35	-0.05	-0.70	4	-3.29	-2.97	0.32	5	-0.20	2.20	2.13	1.49
4	0	-2.35	-0.05	-0.70	4	-3.29	-2.97	0.32	5	-0.20	2.20	2.13	1.49
1	0	-2.35	-0.05	-0.70	4	-3.29	-2.97	0.32	5	-0.20	2.20	2.14	1.49

Table SI29: Structural, energetic and electronic properties for Co_3Mo_2 cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
1	1315	-2.34	0.23	-0.52	7	-3.33	-3.20	0.12	9	-0.33	2.28	2.91	1.60
8	94	-2.59	-0.01	-0.76	5	-3.28	-2.83	0.45	9	-0.33	2.30	3.05	1.98
0	93	-2.59	-0.01	-0.76	5	-3.28	-2.83	0.45	9	-0.33	2.30	3.04	1.98
9	69	-2.59	-0.01	-0.77	7	-3.50	-3.25	0.24	9	-0.33	2.30	2.83	1.87
7	59	-2.59	-0.01	-0.77	7	-3.58	-3.22	0.36	9	-0.11	2.26	2.74	1.63
3	58	-2.59	-0.01	-0.77	7	-3.58	-3.22	0.35	9	-0.11	2.26	2.74	1.63
6	58	-2.59	-0.01	-0.77	7	-3.58	-3.22	0.36	9	-0.11	2.26	2.74	1.63
2	58	-2.59	-0.01	-0.77	7	-3.58	-3.22	0.36	9	-0.11	2.26	2.74	1.63
5	58	-2.59	-0.01	-0.77	7	-3.58	-3.22	0.36	9	-0.11	2.26	2.74	1.63
4	0	-2.61	-0.02	-0.78	7	-3.59	-3.36	0.22	9	-0.11	2.26	2.77	1.75

Table SI30: Structural, energetic and electronic properties for Co_3Mo_3 cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
19	643	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.28	12	-0.33	2.34	3.97	1.68
13	643	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.28	12	-0.33	2.34	3.97	1.68
5	643	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.27	12	-0.33	2.34	3.97	1.68
9	643	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.27	12	-0.33	2.34	3.97	1.68
3	643	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.28	12	-0.33	2.34	3.97	1.68
7	642	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.28	12	-0.33	2.34	3.97	1.68
12	642	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.27	12	-0.33	2.34	3.97	1.68
14	642	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.28	12	-0.33	2.34	3.97	1.68
18	642	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.28	12	-0.33	2.34	3.97	1.68
16	642	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.27	12	-0.33	2.34	3.97	1.68
8	642	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.27	12	-0.33	2.34	3.97	1.68
2	642	-2.92	-0.22	-0.99	5	-3.15	-2.87	0.27	12	-0.33	2.34	3.97	1.68
10	0	-3.03	-0.33	-1.09	5	-3.42	-3.10	0.31	12	0.00	2.34	3.98	1.66
11	0	-3.03	-0.33	-1.09	5	-3.42	-3.10	0.31	12	0.00	2.34	3.98	1.66
1	0	-3.03	-0.33	-1.09	5	-3.42	-3.11	0.31	12	0.00	2.34	3.98	1.66
6	0	-3.03	-0.33	-1.09	5	-3.42	-3.10	0.31	12	0.00	2.34	3.98	1.66
17	0	-3.03	-0.33	-1.09	5	-3.42	-3.10	0.31	12	0.00	2.34	3.98	1.66
4	0	-3.03	-0.33	-1.09	5	-3.42	-3.10	0.31	12	0.00	2.34	3.98	1.66
20	0	-3.03	-0.33	-1.09	5	-3.42	-3.11	0.31	12	0.00	2.34	3.98	1.66
15	0	-3.03	-0.33	-1.09	5	-3.42	-3.10	0.31	12	0.00	2.34	3.98	1.66

Table SI31: Structural, energetic and electronic properties for Co₄Mo₃ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
24	1616	-2.88	-0.09	-0.70	8	-3.64	-3.32	0.31	15	-0.20	2.33	4.18	2.25
30	1615	-2.88	-0.09	-0.70	8	-3.64	-3.32	0.31	15	-0.20	2.33	4.18	2.25
17	1615	-2.88	-0.09	-0.70	8	-3.64	-3.32	0.31	15	-0.20	2.33	4.18	2.25
20	1249	-2.93	-0.14	-0.75	6	-3.37	-3.06	0.30	15	-0.33	2.33	3.88	2.28
35	1249	-2.93	-0.14	-0.75	6	-3.37	-3.06	0.30	15	-0.33	2.33	3.88	2.28
7	1248	-2.93	-0.14	-0.75	6	-3.37	-3.06	0.30	15	-0.33	2.33	3.88	2.28
16	714	-3.01	-0.22	-0.82	8	-3.37	-3.09	0.27	15	-0.20	2.36	4.16	2.29
1	714	-3.01	-0.22	-0.82	8	-3.37	-3.09	0.27	15	-0.20	2.36	4.16	2.29
25	713	-3.01	-0.22	-0.82	8	-3.37	-3.09	0.27	15	-0.20	2.36	4.16	2.29
31	713	-3.01	-0.22	-0.82	8	-3.37	-3.09	0.27	15	-0.20	2.36	4.16	2.29
22	713	-3.01	-0.22	-0.82	8	-3.37	-3.09	0.27	15	-0.20	2.36	4.16	2.29
9	712	-3.01	-0.22	-0.82	8	-3.37	-3.09	0.27	15	-0.20	2.36	4.16	2.29
8	624	-3.02	-0.23	-0.84	6	-3.40	-3.14	0.25	15	-0.33	2.37	4.17	2.32
21	624	-3.02	-0.23	-0.84	6	-3.40	-3.14	0.26	15	-0.33	2.37	4.17	2.32
34	597	-3.02	-0.23	-0.84	8	-3.42	-3.14	0.28	15	-0.33	2.37	4.14	2.33
15	596	-3.02	-0.23	-0.84	8	-3.43	-3.14	0.28	15	-0.33	2.37	4.14	2.33
13	538	-3.03	-0.24	-0.85	8	-3.52	-3.27	0.24	15	0.06	2.35	3.97	2.27
32	537	-3.03	-0.24	-0.85	8	-3.52	-3.27	0.25	15	0.06	2.35	3.97	2.27
10	537	-3.03	-0.24	-0.85	8	-3.52	-3.26	0.25	15	0.06	2.35	3.97	2.27
3	497	-3.04	-0.25	-0.86	10	-3.32	-3.21	0.10	16	0.00	2.36	3.93	1.92
26	304	-3.06	-0.28	-0.88	8	-3.45	-3.12	0.33	16	0.00	2.36	4.06	1.89
23	304	-3.06	-0.28	-0.88	8	-3.46	-3.12	0.33	16	0.00	2.36	4.06	1.89
33	303	-3.06	-0.28	-0.88	8	-3.45	-3.12	0.33	16	0.00	2.36	4.06	1.89
29	303	-3.06	-0.28	-0.88	8	-3.46	-3.12	0.33	16	0.00	2.36	4.06	1.89
14	273	-3.07	-0.28	-0.89	8	-3.47	-3.16	0.30	15	0.06	2.34	3.83	2.07
05	272	-3.07	-0.28	-0.89	6	-3.27	-3.15	0.12	15	0.06	2.36	4.21	2.30
28	272	-3.07	-0.28	-0.89	6	-3.27	-3.15	0.11	15	0.06	2.36	4.21	2.30
4	135	-3.09	-0.30	-0.91	6	-3.35	-3.14	0.20	15	-0.06	2.36	4.19	2.22
12	134	-3.09	-0.30	-0.91	6	-3.35	-3.14	0.20	15	-0.06	2.36	4.19	2.21
27	97	-3.09	-0.30	-0.91	8	-3.56	-3.26	0.29	15	-0.06	2.37	4.08	2.19
18	84	-3.10	-0.31	-0.91	8	-3.48	-3.07	0.40	15	0.06	2.36	4.08	2.22
19	27	-3.10	-0.31	-0.92	8	-3.52	-3.15	0.37	15	0.20	2.36	4.21	2.25
11	0	-3.11	-0.32	-0.93	8	-3.68	-3.37	0.31	15	-0.20	2.39	4.25	2.35

Table SI32: Structural, energetic and electronic properties for Co₄Mo₄ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
53	1059	-3.14	-0.29	-0.69	6	-3.18	-3.01	0.17	20	-0.20	2.37	4.36	2.20
56	1059	-3.14	-0.29	-0.69	6	-3.18	-3.00	0.17	20	-0.20	2.37	4.36	2.20

68	1058	-3.14	-0.29	-0.69	6	-3.18	-3.00	0.17	20	-0.20	2.37	4.36	2.20
30	1056	-3.14	-0.29	-0.69	6	-3.18	-3.01	0.17	20	-0.20	2.37	4.36	2.20
57	866	-3.16	-0.31	-0.72	6	-3.27	-2.99	0.28	20	-0.40	2.39	4.22	2.29
31	865	-3.16	-0.31	-0.72	6	-3.27	-2.99	0.28	20	-0.40	2.39	4.22	2.29
40	864	-3.16	-0.31	-0.72	6	-3.27	-2.99	0.28	20	-0.40	2.39	4.22	2.29
14	864	-3.16	-0.31	-0.72	6	-3.27	-2.99	0.28	20	-0.40	2.39	4.22	2.29
60	714	-3.18	-0.33	-0.74	8	-3.29	-3.15	0.14	18	-0.00	2.35	3.73	2.11
70	713	-3.18	-0.33	-0.74	8	-3.29	-3.15	0.13	18	-0.00	2.35	3.73	2.11
52	705	-3.18	-0.33	-0.74	8	-3.46	-3.16	0.30	18	-0.33	2.39	4.14	2.19
16	704	-3.18	-0.33	-0.74	8	-3.46	-3.16	0.30	18	-0.33	2.39	4.14	2.19
55	703	-3.18	-0.33	-0.74	8	-3.46	-3.16	0.30	18	-0.33	2.39	4.14	2.19
20	703	-3.18	-0.33	-0.74	8	-3.46	-3.16	0.30	18	-0.33	2.39	4.14	2.19
63	700	-3.18	-0.33	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.98	2.23
58	700	-3.18	-0.33	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.99	2.23
46	700	-3.18	-0.33	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.99	2.23
28	699	-3.18	-0.33	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.98	2.23
33	699	-3.18	-0.33	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.98	2.23
50	699	-3.18	-0.33	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.98	2.23
26	699	-3.18	-0.33	-0.74	10	-3.36	-3.18	0.18	19	-0.05	2.36	3.81	2.12
69	699	-3.18	-0.33	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.99	2.23
66	698	-3.18	-0.33	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.99	2.23
48	697	-3.18	-0.33	-0.74	10	-3.36	-3.18	0.18	19	-0.05	2.36	3.81	2.12
44	642	-3.19	-0.34	-0.74	6	-3.37	-3.06	0.31	19	-0.15	2.38	4.16	2.23
27	641	-3.19	-0.34	-0.74	6	-3.37	-3.06	0.31	20	-0.20	2.38	4.15	2.23
35	641	-3.19	-0.34	-0.74	6	-3.37	-3.07	0.30	19	-0.15	2.38	4.15	2.23
10	640	-3.19	-0.34	-0.74	6	-3.37	-3.06	0.31	20	-0.20	2.38	4.16	2.23
9	640	-3.19	-0.34	-0.74	6	-3.37	-3.05	0.31	20	-0.20	2.38	4.16	2.23
61	639	-3.19	-0.34	-0.74	6	-3.37	-3.06	0.31	18	-0.11	2.38	4.16	2.23
36	639	-3.19	-0.34	-0.74	6	-3.37	-3.06	0.31	20	-0.20	2.38	4.16	2.23
62	639	-3.19	-0.34	-0.74	6	-3.37	-3.06	0.31	19	-0.15	2.38	4.16	2.23
67	608	-3.19	-0.35	-0.75	10	-3.40	-3.11	0.29	20	-0.20	2.36	4.07	2.21
22	559	-3.20	-0.35	-0.75	6	-3.27	-3.01	0.26	19	-0.26	2.39	4.41	2.15
49	558	-3.20	-0.35	-0.75	6	-3.27	-3.01	0.26	19	-0.26	2.39	4.41	2.15
17	337	-3.23	-0.38	-0.78	6	-3.32	-2.99	0.32	20	0.20	2.39	4.41	2.22
54	337	-3.23	-0.38	-0.78	6	-3.31	-2.99	0.32	20	0.20	2.39	4.41	2.22
41	206	-3.24	-0.40	-0.80	6	-3.36	-3.12	0.24	19	-0.15	2.40	4.37	2.29
23	199	-3.24	-0.40	-0.80	8	-3.40	-3.14	0.25	20	0.00	2.39	4.32	2.17
45	163	-3.25	-0.40	-0.80	6	-3.36	-3.14	0.22	19	0.05	2.40	4.43	2.18
1	163	-3.25	-0.40	-0.80	6	-3.36	-3.14	0.21	20	0.00	2.40	4.43	2.18
11	162	-3.25	-0.40	-0.80	6	-3.36	-3.14	0.22	20	0.00	2.40	4.43	2.18
38	161	-3.25	-0.40	-0.80	6	-3.42	-3.12	0.29	19	-0.15	2.42	4.45	2.26
65	161	-3.25	-0.40	-0.80	8	-3.18	-2.98	0.19	18	0.11	2.38	4.20	2.13
13	161	-3.25	-0.40	-0.80	6	-3.42	-3.12	0.29	19	-0.15	2.42	4.45	2.26
8	161	-3.25	-0.40	-0.80	6	-3.42	-3.12	0.29	19	-0.15	2.42	4.45	2.26
2	161	-3.25	-0.40	-0.80	6	-3.42	-3.12	0.29	19	-0.15	2.42	4.45	2.26
5	161	-3.25	-0.40	-0.80	6	-3.42	-3.12	0.29	19	-0.15	2.42	4.45	2.26
21	161	-3.25	-0.40	-0.80	6	-3.42	-3.12	0.29	19	-0.15	2.42	4.45	2.26
43	161	-3.25	-0.40	-0.80	6	-3.42	-3.12	0.29	19	-0.15	2.42	4.45	2.26
25	159	-3.25	-0.40	-0.80	6	-3.42	-3.12	0.29	19	-0.15	2.42	4.45	2.26
39	136	-3.25	-0.40	-0.81	8	-3.23	-3.00	0.22	19	0.05	2.38	4.20	2.16
06	135	-3.25	-0.40	-0.81	8	-3.23	-3.00	0.22	19	0.05	2.38	4.20	2.16
32	133	-3.25	-0.40	-0.81	8	-3.23	-3.00	0.22	18	0.11	2.38	4.20	2.16
15	118	-3.25	-0.41	-0.81	6	-3.40	-3.05	0.35	20	-0.20	2.38	4.09	2.31
18	118	-3.25	-0.41	-0.81	6	-3.40	-3.05	0.35	20	-0.20	2.38	4.09	2.31
12	75	-3.26	-0.41	-0.82	6	-3.26	-3.00	0.26	20	0.00	2.37	4.21	2.24
42	73	-3.26	-0.41	-0.82	6	-3.26	-3.00	0.26	20	0.00	2.37	4.21	2.24
64	73	-3.26	-0.41	-0.82	6	-3.26	-3.00	0.26	19	0.05	2.37	4.21	2.24

29	72	-3.26	-0.41	-0.82	6	-3.26	-3.00	0.25	20	0.00	2.37	4.21	2.24
37	72	-3.26	-0.41	-0.82	6	-3.26	-3.00	0.25	19	0.05	2.37	4.21	2.24
59	72	-3.26	-0.41	-0.82	6	-3.26	-3.00	0.25	19	0.05	2.37	4.21	2.24
34	72	-3.26	-0.41	-0.82	6	-3.26	-3.00	0.26	19	0.05	2.37	4.21	2.24
7	71	-3.26	-0.41	-0.82	6	-3.26	-3.00	0.26	20	0.00	2.37	4.21	2.24
4	0	-3.27	-0.42	-0.82	6	-3.42	-3.12	0.29	20	-0.20	2.40	4.47	2.18

Table SI33: Structural, energetic and electronic properties for Co_5Mo_4 cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
17	1335	-3.19	-0.28	-0.61	5	-3.23	-3.04	0.18	21	-0.23	2.35	4.36	2.20
91	1334	-3.19	-0.28	-0.61	5	-3.23	-3.04	0.19	21	-0.23	2.35	4.36	2.20
16	920	-3.24	-0.33	-0.66	5	-3.29	-3.11	0.17	21	-0.14	2.36	4.30	2.29
88	919	-3.24	-0.33	-0.66	5	-3.29	-3.11	0.17	21	-0.14	2.36	4.30	2.29
56	919	-3.24	-0.33	-0.66	5	-3.29	-3.11	0.17	21	-0.14	2.36	4.30	2.29
7	855	-3.24	-0.33	-0.66	5	-3.22	-3.17	0.05	21	-0.33	2.36	4.42	2.29
52	855	-3.24	-0.33	-0.66	5	-3.22	-3.17	0.05	21	-0.33	2.36	4.43	2.29
66	752	-3.25	-0.34	-0.67	7	-3.38	-3.21	0.17	21	-0.14	2.35	4.14	2.27
39	751	-3.25	-0.34	-0.67	7	-3.38	-3.21	0.17	21	-0.14	2.35	4.14	2.27
87	751	-3.25	-0.34	-0.67	7	-3.38	-3.21	0.17	21	-0.14	2.35	4.14	2.27
42	750	-3.25	-0.34	-0.67	7	-3.38	-3.21	0.17	21	-0.14	2.35	4.14	2.27
25	658	-3.26	-0.36	-0.68	7	-3.48	-3.11	0.37	21	-0.33	2.36	4.33	2.28
31	658	-3.26	-0.36	-0.68	7	-3.48	-3.11	0.37	21	-0.33	2.36	4.33	2.28
94	647	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.98	2.29
73	647	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.97	2.29
64	647	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.98	2.29
41	647	-3.27	-0.36	-0.69	5	-3.46	-3.04	0.41	21	-0.14	2.36	4.52	2.26
96	646	-3.27	-0.36	-0.69	5	-3.46	-3.04	0.41	21	-0.14	2.36	4.52	2.26
32	646	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.97	2.29
53	646	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.98	2.29
46	646	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.97	2.29
19	646	-3.27	-0.36	-0.69	5	-3.46	-3.05	0.41	21	-0.14	2.36	4.52	2.26
85	646	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.98	2.29
43	646	-3.27	-0.36	-0.69	9	-3.39	-3.15	0.23	21	-0.04	2.35	3.97	2.29
37	646	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.98	2.29
40	646	-3.27	-0.36	-0.69	5	-3.46	-3.05	0.41	21	-0.14	2.36	4.52	2.26
57	645	-3.27	-0.36	-0.69	5	-3.46	-3.05	0.41	21	-0.14	2.36	4.52	2.26
89	645	-3.27	-0.36	-0.69	9	-3.39	-3.16	0.23	21	-0.04	2.35	3.97	2.29
86	645	-3.27	-0.36	-0.69	5	-3.47	-3.05	0.41	21	-0.14	2.36	4.52	2.26
59	629	-3.27	-0.36	-0.69	7	-3.46	-3.20	0.26	21	-0.14	2.35	4.21	2.28
76	629	-3.27	-0.36	-0.69	7	-3.46	-3.20	0.26	21	-0.14	2.35	4.21	2.28
18	629	-3.27	-0.36	-0.69	7	-3.46	-3.20	0.26	21	-0.14	2.35	4.21	2.28
14	628	-3.27	-0.36	-0.69	9	-3.40	-3.20	0.20	21	-0.14	2.37	4.28	2.24
47	559	-3.28	-0.37	-0.70	7	-3.36	-3.05	0.31	21	-0.23	2.39	4.57	2.27
74	558	-3.28	-0.37	-0.70	7	-3.36	-3.05	0.31	21	-0.23	2.39	4.57	2.27
10	558	-3.28	-0.37	-0.70	7	-3.36	-3.05	0.31	21	-0.23	2.39	4.57	2.27
26	476	-3.28	-0.38	-0.70	5	-3.38	-3.12	0.25	21	-0.23	2.39	4.55	2.28
27	475	-3.29	-0.38	-0.70	5	-3.38	-3.12	0.25	21	-0.23	2.39	4.55	2.28

60	438	-3.29	-0.38	-0.71	5	-3.39	-3.17	0.21	21	-0.23	2.37	4.46	2.26
78	438	-3.29	-0.38	-0.71	5	-3.39	-3.17	0.21	21	-0.23	2.37	4.46	2.26
0	438	-3.29	-0.38	-0.71	5	-3.39	-3.17	0.21	21	-0.23	2.37	4.46	2.26
38	438	-3.29	-0.38	-0.71	5	-3.39	-3.17	0.21	21	-0.23	2.37	4.46	2.26
51	425	-3.29	-0.38	-0.71	7	-3.39	-3.12	0.26	21	-0.04	2.37	4.31	2.28
71	424	-3.29	-0.38	-0.71	7	-3.39	-3.12	0.26	21	-0.04	2.37	4.31	2.28
12	424	-3.29	-0.38	-0.71	7	-3.39	-3.12	0.26	21	-0.04	2.37	4.31	2.28
34	424	-3.29	-0.38	-0.71	7	-3.39	-3.12	0.26	21	-0.04	2.37	4.31	2.28
03	423	-3.29	-0.38	-0.71	7	-3.39	-3.12	0.26	21	-0.04	2.37	4.31	2.28
54	423	-3.29	-0.38	-0.71	7	-3.39	-3.12	0.26	21	-0.04	2.37	4.31	2.28
61	423	-3.29	-0.38	-0.71	7	-3.39	-3.12	0.26	21	-0.04	2.37	4.31	2.28
35	422	-3.29	-0.38	-0.71	7	-3.39	-3.12	0.26	21	-0.04	2.37	4.31	2.28
65	402	-3.29	-0.38	-0.71	7	-3.46	-3.25	0.20	21	-0.23	2.37	4.31	2.31
80	402	-3.29	-0.38	-0.71	7	-3.46	-3.25	0.20	21	-0.23	2.37	4.31	2.31
9	402	-3.29	-0.38	-0.71	7	-3.46	-3.25	0.20	21	-0.23	2.37	4.31	2.31
24	402	-3.29	-0.38	-0.71	7	-3.46	-3.25	0.20	21	-0.23	2.37	4.31	2.31
62	401	-3.29	-0.38	-0.71	7	-3.46	-3.25	0.20	21	-0.23	2.37	4.31	2.31
4	373	-3.30	-0.39	-0.72	5	-3.39	-3.08	0.31	22	-0.18	2.38	4.47	2.30
36	373	-3.30	-0.39	-0.72	5	-3.39	-3.08	0.31	22	-0.18	2.38	4.47	2.30
2	372	-3.30	-0.39	-0.72	5	-3.39	-3.08	0.31	22	-0.18	2.38	4.47	2.30
55	372	-3.30	-0.39	-0.72	5	-3.39	-3.08	0.31	21	-0.23	2.38	4.47	2.30
99	372	-3.30	-0.39	-0.72	5	-3.39	-3.08	0.31	21	-0.23	2.38	4.47	2.30
84	372	-3.30	-0.39	-0.72	5	-3.39	-3.08	0.31	21	-0.23	2.38	4.47	2.30
20	367	-3.30	-0.39	-0.72	7	-3.36	-3.16	0.20	21	-0.14	2.40	4.61	2.30
72	364	-3.30	-0.39	-0.72	7	-3.31	-3.26	0.05	21	-0.14	2.38	4.55	2.25
15	363	-3.30	-0.39	-0.72	7	-3.31	-3.26	0.05	21	-0.14	2.38	4.55	2.26
22	320	-3.30	-0.39	-0.72	5	-3.43	-3.24	0.18	21	-0.33	2.39	4.50	2.34
21	265	-3.31	-0.40	-0.73	9	-3.45	-3.18	0.27	21	-0.14	2.40	4.55	2.28
68	247	-3.31	-0.40	-0.73	7	-3.31	-3.02	0.28	21	-0.14	2.39	4.58	2.28
92	246	-3.31	-0.40	-0.73	7	-3.31	-3.02	0.28	22	-0.18	2.39	4.57	2.28
44	246	-3.31	-0.40	-0.73	7	-3.31	-3.02	0.28	22	-0.18	2.39	4.58	2.28
48	245	-3.31	-0.40	-0.73	7	-3.31	-3.02	0.28	22	-0.18	2.39	4.58	2.28
69	245	-3.31	-0.40	-0.73	7	-3.31	-3.02	0.28	22	-0.18	2.39	4.58	2.28
33	245	-3.31	-0.40	-0.73	7	-3.31	-3.02	0.28	21	-0.14	2.39	4.58	2.28
01	245	-3.31	-0.40	-0.73	7	-3.31	-3.02	0.28	21	-0.14	2.39	4.58	2.28
83	245	-3.31	-0.40	-0.73	7	-3.31	-3.02	0.28	21	-0.14	2.39	4.57	2.28
95	242	-3.31	-0.40	-0.73	5	-3.51	-3.17	0.33	21	-0.33	2.39	4.44	2.34
75	242	-3.31	-0.40	-0.73	5	-3.51	-3.17	0.33	21	-0.33	2.39	4.44	2.34
5	242	-3.31	-0.40	-0.73	5	-3.51	-3.17	0.33	21	-0.33	2.39	4.44	2.34
58	241	-3.31	-0.40	-0.73	5	-3.50	-3.17	0.33	21	-0.33	2.39	4.44	2.34
93	238	-3.31	-0.40	-0.73	5	-3.34	-3.15	0.18	23	-0.13	2.41	4.52	2.38
67	89	-3.33	-0.42	-0.75	7	-3.33	-3.08	0.24	21	-0.14	2.39	4.59	2.28
13	89	-3.33	-0.42	-0.75	7	-3.33	-3.08	0.24	21	-0.14	2.39	4.59	2.28
77	88	-3.33	-0.42	-0.75	7	-3.33	-3.08	0.24	21	-0.14	2.39	4.59	2.28
11	88	-3.33	-0.42	-0.75	7	-3.33	-3.08	0.24	21	-0.14	2.39	4.59	2.28
50	79	-3.33	-0.42	-0.75	7	-3.34	-3.06	0.27	21	-0.14	2.38	4.38	2.29
98	78	-3.33	-0.42	-0.75	7	-3.34	-3.06	0.27	21	-0.14	2.38	4.38	2.29
70	76	-3.33	-0.42	-0.75	7	-3.34	-3.06	0.27	21	-0.14	2.38	4.38	2.29
08	76	-3.33	-0.42	-0.75	7	-3.34	-3.06	0.27	21	-0.14	2.38	4.38	2.29
28	0	-3.34	-0.43	-0.76	9	-3.22	-2.90	0.31	21	-0.23	2.35	4.15	2.28
23	0	-3.34	-0.43	-0.76	9	-3.22	-2.90	0.31	21	-0.23	2.35	4.15	2.28
30	0	-3.34	-0.43	-0.76	9	-3.22	-2.90	0.31	21	-0.23	2.35	4.15	2.28

Table SI34: Structural, energetic and electronic properties for Co₅Mo₅ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
44	3006	-3.17	-0.16	-0.42	8	-3.41	-3.40	0.00	25	-0.20	2.31	4.94	2.63
42	2846	-3.18	-0.17	-0.43	9	-3.47	-3.43	0.04	25	0.12	2.31	4.94	2.63
45	2835	-3.19	-0.17	-0.43	7	-3.44	-3.43	0.01	25	0.12	2.31	4.94	2.63
96	2125	-3.26	-0.25	-0.50	7	-3.39	-3.34	0.04	25	-0.12	2.31	4.94	2.63
67	2125	-3.26	-0.25	-0.50	6	-3.36	-3.34	0.01	25	-0.12	2.31	4.94	2.63
27	1122	-3.36	-0.35	-0.60	11	-3.57	-3.50	0.07	27	-0.11	2.42	4.79	2.81
31	1021	-3.37	-0.36	-0.61	9	-3.33	-3.13	0.19	26	0.00	2.39	4.58	2.79
11	1015	-3.37	-0.36	-0.61	5	-3.14	-2.98	0.15	26	-0.23	2.38	4.84	2.73
61	1010	-3.37	-0.36	-0.61	7	-3.33	-3.11	0.22	26	-0.15	2.38	4.69	2.72
53	1009	-3.37	-0.36	-0.61	7	-3.33	-3.11	0.22	26	-0.15	2.38	4.69	2.72
50	964	-3.37	-0.36	-0.62	9	-3.41	-3.30	0.11	25	-0.36	2.40	4.81	2.80
04	963	-3.37	-0.36	-0.62	9	-3.41	-3.30	0.11	25	-0.36	2.40	4.81	2.79
12	940	-3.38	-0.36	-0.62	7	-3.10	-2.92	0.18	26	0.00	2.37	4.74	2.69
80	910	-3.38	-0.37	-0.62	11	-3.20	-3.09	0.11	25	-0.20	2.38	4.60	2.73
37	887	-3.38	-0.37	-0.63	5	-3.23	-3.10	0.12	25	0.04	2.38	4.80	2.79
70	886	-3.38	-0.37	-0.63	5	-3.23	-3.10	0.13	25	0.04	2.38	4.80	2.79
97	884	-3.38	-0.37	-0.63	5	-3.23	-3.10	0.13	25	0.04	2.38	4.80	2.79
06	882	-3.38	-0.37	-0.63	5	-3.49	-3.19	0.30	25	-0.20	2.37	4.66	2.81
26	875	-3.38	-0.37	-0.63	9	-3.15	-2.95	0.20	25	0.12	2.39	4.81	2.72
60	875	-3.38	-0.37	-0.63	9	-3.15	-2.95	0.20	25	0.12	2.39	4.81	2.72
46	862	-3.38	-0.37	-0.63	9	-3.38	-3.19	0.18	25	-0.12	2.39	4.59	2.81
29	860	-3.38	-0.37	-0.63	9	-3.22	-3.05	0.17	26	-0.15	2.37	4.53	2.77
65	859	-3.38	-0.37	-0.63	9	-3.38	-3.19	0.19	26	-0.07	2.39	4.60	2.80
52	842	-3.39	-0.37	-0.63	9	-3.18	-3.08	0.10	25	-0.20	2.37	4.56	2.74
83	842	-3.39	-0.37	-0.63	9	-3.18	-3.08	0.10	25	-0.20	2.37	4.56	2.74
35	841	-3.39	-0.37	-0.63	9	-3.18	-3.08	0.10	25	-0.20	2.37	4.56	2.74
84	841	-3.39	-0.37	-0.63	9	-3.18	-3.08	0.10	25	-0.20	2.37	4.56	2.74
05	811	-3.39	-0.38	-0.63	9	-3.43	-3.26	0.16	25	-0.28	2.39	4.65	2.75
81	811	-3.39	-0.38	-0.63	9	-3.43	-3.26	0.16	25	-0.28	2.39	4.66	2.75
23	791	-3.39	-0.38	-0.64	7	-3.39	-3.19	0.19	25	-0.28	2.41	4.67	2.82
51	788	-3.39	-0.38	-0.64	7	-3.39	-3.19	0.19	26	-0.23	2.41	4.67	2.82
30	769	-3.39	-0.38	-0.64	7	-3.28	-3.10	0.17	26	-0.30	2.38	4.54	2.84
69	745	-3.39	-0.38	-0.64	7	-3.41	-3.23	0.17	25	-0.20	2.41	4.67	2.78
57	745	-3.39	-0.38	-0.64	7	-3.41	-3.23	0.17	25	-0.20	2.41	4.67	2.78
95	744	-3.40	-0.38	-0.64	7	-3.41	-3.23	0.17	25	-0.20	2.41	4.67	2.78
32	721	-3.40	-0.39	-0.64	7	-3.33	-3.18	0.15	25	-0.28	2.39	4.73	2.78
82	721	-3.40	-0.39	-0.64	7	-3.33	-3.18	0.15	25	-0.28	2.39	4.73	2.78
59	721	-3.40	-0.39	-0.64	9	-3.48	-3.14	0.34	27	-0.18	2.41	4.46	2.81
20	720	-3.40	-0.39	-0.64	9	-3.48	-3.14	0.34	27	-0.18	2.41	4.46	2.81
01	656	-3.40	-0.39	-0.65	5	-3.27	-3.13	0.13	25	-0.12	2.38	4.67	2.83
08	623	-3.41	-0.40	-0.65	5	-3.21	-3.14	0.06	25	-0.20	2.39	4.68	2.78
75	621	-3.41	-0.40	-0.65	9	-3.39	-3.21	0.17	25	0.04	2.39	4.56	2.80
13	621	-3.41	-0.40	-0.65	9	-3.39	-3.21	0.17	26	0.07	2.39	4.56	2.80
92	620	-3.41	-0.40	-0.65	9	-3.39	-3.21	0.17	25	0.04	2.39	4.57	2.80
74	569	-3.41	-0.40	-0.66	9	-3.45	-3.24	0.20	25	-0.04	2.38	4.40	2.78
22	568	-3.41	-0.40	-0.66	9	-3.45	-3.24	0.20	25	-0.04	2.38	4.40	2.78
36	529	-3.42	-0.41	-0.66	9	-3.36	-3.15	0.21	25	0.12	2.38	4.56	2.78
77	526	-3.42	-0.41	-0.66	9	-3.36	-3.15	0.21	25	0.12	2.38	4.56	2.78

38	525	-3.42	-0.41	-0.66	7	-3.25	-3.03	0.21	25	-0.04	2.37	4.76	2.74
58	524	-3.42	-0.41	-0.66	7	-3.25	-3.03	0.21	25	-0.04	2.37	4.76	2.74
55	524	-3.42	-0.41	-0.66	7	-3.25	-3.03	0.21	25	-0.04	2.37	4.76	2.74
28	520	-3.42	-0.41	-0.66	7	-3.60	-3.42	0.17	25	-0.20	2.40	4.72	2.80
88	518	-3.42	-0.41	-0.66	7	-3.43	-3.23	0.19	25	-0.20	2.41	4.69	2.76
41	517	-3.42	-0.41	-0.66	7	-3.43	-3.23	0.19	25	-0.20	2.41	4.69	2.76
86	517	-3.42	-0.41	-0.66	7	-3.43	-3.23	0.19	25	-0.20	2.41	4.69	2.76
94	517	-3.42	-0.41	-0.66	7	-3.43	-3.24	0.18	25	-0.20	2.41	4.69	2.76
43	515	-3.42	-0.41	-0.66	7	-3.43	-3.23	0.19	26	-0.15	2.41	4.69	2.76
89	515	-3.42	-0.41	-0.66	7	-3.43	-3.23	0.19	25	-0.20	2.41	4.69	2.76
16	499	-3.42	-0.41	-0.67	5	-3.34	-3.07	0.26	25	-0.12	2.38	4.73	2.78
62	496	-3.42	-0.41	-0.67	5	-3.34	-3.07	0.26	25	-0.12	2.38	4.73	2.78
34	434	-3.43	-0.41	-0.67	9	-3.40	-3.17	0.22	25	-0.20	2.39	4.65	2.74
71	432	-3.43	-0.42	-0.67	9	-3.40	-3.17	0.22	25	-0.20	2.39	4.65	2.74
90	429	-3.43	-0.42	-0.67	9	-3.36	-3.12	0.24	25	-0.04	2.40	4.76	2.77
63	428	-3.43	-0.42	-0.67	9	-3.38	-3.18	0.19	25	0.12	2.40	4.75	2.78
64	428	-3.43	-0.42	-0.67	9	-3.36	-3.12	0.23	25	-0.04	2.40	4.76	2.77
99	426	-3.43	-0.42	-0.67	9	-3.38	-3.18	0.19	25	0.12	2.40	4.75	2.78
00	426	-3.43	-0.42	-0.67	9	-3.36	-3.12	0.24	25	-0.04	2.40	4.76	2.77
68	425	-3.43	-0.42	-0.67	9	-3.38	-3.18	0.19	25	0.12	2.40	4.75	2.78
47	423	-3.43	-0.42	-0.67	7	-3.58	-3.36	0.22	26	-0.15	2.39	4.50	2.92
56	423	-3.43	-0.42	-0.67	7	-3.58	-3.36	0.22	25	-0.20	2.39	4.49	2.92
10	412	-3.43	-0.42	-0.67	9	-3.46	-3.15	0.30	25	-0.36	2.39	4.65	2.73
25	408	-3.43	-0.42	-0.68	7	-3.30	-3.09	0.20	25	-0.04	2.38	4.58	2.77
03	407	-3.43	-0.42	-0.68	7	-3.30	-3.10	0.20	25	-0.04	2.38	4.58	2.78
21	406	-3.43	-0.42	-0.68	7	-3.30	-3.10	0.20	25	-0.04	2.38	4.58	2.78
66	399	-3.43	-0.42	-0.68	7	-3.15	-2.95	0.20	25	-0.12	2.37	4.68	2.72
24	397	-3.43	-0.42	-0.68	7	-3.16	-2.95	0.20	25	-0.12	2.37	4.68	2.73
76	386	-3.43	-0.42	-0.68	7	-3.25	-3.11	0.14	25	-0.20	2.39	4.61	2.76
72	385	-3.43	-0.42	-0.68	7	-3.25	-3.11	0.14	25	-0.20	2.39	4.61	2.76
14	385	-3.43	-0.42	-0.68	7	-3.25	-3.11	0.14	25	-0.20	2.39	4.61	2.76
02	384	-3.43	-0.42	-0.68	7	-3.25	-3.11	0.14	25	-0.20	2.39	4.61	2.77
78	371	-3.43	-0.42	-0.68	7	-3.17	-2.91	0.25	25	0.04	2.36	4.52	2.72
15	369	-3.43	-0.42	-0.68	7	-3.17	-2.91	0.25	25	0.04	2.36	4.52	2.72
54	130	-3.46	-0.45	-0.70	9	-3.48	-3.31	0.17	27	-0.03	2.42	4.65	2.83
73	130	-3.46	-0.45	-0.70	9	-3.60	-3.26	0.33	26	-0.15	2.41	4.62	2.79
07	130	-3.46	-0.45	-0.70	9	-3.59	-3.26	0.33	26	-0.15	2.41	4.63	2.79
91	129	-3.46	-0.45	-0.70	9	-3.59	-3.26	0.33	26	-0.15	2.41	4.63	2.79
09	129	-3.46	-0.45	-0.70	9	-3.48	-3.31	0.17	26	0.00	2.42	4.65	2.83
87	129	-3.46	-0.45	-0.70	9	-3.60	-3.26	0.33	26	-0.15	2.41	4.63	2.79
49	63	-3.46	-0.45	-0.71	9	-3.41	-3.23	0.17	26	0.07	2.40	4.48	2.82
79	63	-3.46	-0.45	-0.71	9	-3.41	-3.23	0.17	26	0.07	2.40	4.48	2.82
19	48	-3.46	-0.45	-0.71	9	-3.20	-2.96	0.24	26	0.23	2.38	4.32	2.75
48	47	-3.46	-0.45	-0.71	9	-3.20	-2.96	0.24	26	0.23	2.38	4.32	2.75
93	1	-3.47	-0.46	-0.72	9	-3.56	-3.35	0.20	25	0.04	2.42	4.62	2.75
17	1	-3.47	-0.46	-0.72	9	-3.55	-3.35	0.20	25	0.04	2.42	4.62	2.75
85	1	-3.47	-0.46	-0.72	9	-3.55	-3.35	0.20	25	0.04	2.42	4.62	2.75
98	0	-3.47	-0.46	-0.72	9	-3.56	-3.35	0.20	25	0.04	2.42	4.62	2.75

Table SI35: Structural, energetic and electronic properties for Co₆Mo₅ cluster, as follows: configuration number (*i*), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

<i>i</i>	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
55	2489	-3.29	-0.24	-0.37	8	-3.46	-3.25	0.21	29	-0.24	2.40	4.91	3.09
22	2050	-3.33	-0.28	-0.41	8	-3.41	-3.21	0.19	29	-0.03	2.40	4.98	3.14
12	1972	-3.33	-0.29	-0.41	8	-3.36	-3.13	0.23	30	-0.20	2.39	4.94	3.22
68	1951	-3.33	-0.29	-0.41	6	-3.23	-3.04	0.19	29	-0.03	2.37	5.02	3.16
51	1946	-3.34	-0.29	-0.42	10	-3.45	-3.29	0.16	30	0.13	2.40	4.90	3.20
89	1882	-3.34	-0.30	-0.42	10	-3.47	-3.34	0.12	29	-0.17	2.41	4.90	3.10
88	1787	-3.35	-0.31	-0.43	10	-3.43	-3.25	0.17	29	-0.17	2.38	4.82	3.22
34	1772	-3.35	-0.31	-0.43	6	-3.31	-3.14	0.16	29	0.03	2.39	4.97	3.16
36	1751	-3.35	-0.31	-0.43	8	-3.26	-2.99	0.26	30	-0.06	2.38	4.69	3.24
7	1731	-3.35	-0.31	-0.43	10	-3.41	-3.19	0.21	29	0.17	2.40	4.87	3.23
97	1701	-3.36	-0.32	-0.44	8	-3.43	-3.20	0.22	30	-0.26	2.38	4.84	3.23
64	1667	-3.36	-0.32	-0.44	8	-3.32	-3.17	0.15	29	0.03	2.39	4.75	3.14
31	1599	-3.37	-0.33	-0.45	10	-3.46	-3.23	0.23	29	-0.03	2.42	4.92	3.17
46	1593	-3.37	-0.33	-0.45	8	-3.22	-2.99	0.22	29	0.17	2.38	4.96	3.01
70	1590	-3.37	-0.33	-0.45	10	-3.53	-3.26	0.26	29	0.03	2.38	4.41	3.14
15	1573	-3.37	-0.33	-0.45	8	-3.34	-3.10	0.23	30	-0.13	2.37	4.53	3.29
77	1559	-3.37	-0.33	-0.45	8	-3.27	-3.14	0.13	29	-0.17	2.38	4.90	3.21
42	1547	-3.37	-0.33	-0.45	6	-3.16	-3.00	0.16	29	-0.03	2.35	4.57	3.36
71	1508	-3.38	-0.33	-0.46	8	-3.39	-3.15	0.23	29	0.03	2.38	4.80	3.16
54	1470	-3.38	-0.34	-0.46	10	-3.32	-3.18	0.13	29	0.10	2.37	4.42	3.22
41	1469	-3.38	-0.34	-0.46	10	-3.39	-3.20	0.19	29	-0.10	2.39	4.79	3.16
80	1463	-3.38	-0.34	-0.46	10	-3.48	-3.31	0.17	29	-0.17	2.40	4.61	3.19
26	1456	-3.38	-0.34	-0.46	10	-3.44	-3.26	0.18	29	-0.17	2.39	4.72	3.18
16	1404	-3.38	-0.34	-0.46	10	-3.44	-3.22	0.21	29	-0.31	2.38	4.74	3.32
95	1383	-3.39	-0.35	-0.47	8	-3.23	-2.99	0.23	30	0.06	2.35	4.60	3.34
63	1381	-3.39	-0.35	-0.47	8	-3.41	-3.15	0.26	29	-0.17	2.38	4.85	3.17
79	1380	-3.39	-0.35	-0.47	10	-3.37	-3.13	0.23	29	-0.10	2.38	4.70	3.11
29	1348	-3.39	-0.35	-0.47	12	-3.28	-3.18	0.09	29	0.17	2.39	4.79	3.20
21	1317	-3.39	-0.35	-0.47	8	-3.35	-3.23	0.12	29	-0.03	2.39	4.70	3.39
86	1313	-3.39	-0.35	-0.47	8	-3.31	-3.12	0.18	30	-0.20	2.38	4.74	3.24
76	1305	-3.39	-0.35	-0.47	10	-3.36	-3.06	0.30	29	0.17	2.38	4.93	3.20
6	1299	-3.39	-0.35	-0.47	10	-3.38	-3.19	0.19	30	-0.06	2.36	4.51	3.22
25	1284	-3.40	-0.35	-0.48	10	-3.36	-3.17	0.18	29	0.03	2.36	4.50	3.20
83	1275	-3.40	-0.36	-0.48	8	-3.58	-3.35	0.22	30	-0.20	2.40	4.84	3.22
23	1252	-3.40	-0.36	-0.48	10	-3.42	-3.17	0.25	29	-0.10	2.37	4.58	3.25
18	1245	-3.40	-0.36	-0.48	10	-3.29	-3.07	0.21	29	0.03	2.37	4.64	3.10
60	1242	-3.40	-0.36	-0.48	6	-3.29	-3.04	0.25	30	-0.20	2.38	4.70	3.24
9	1239	-3.40	-0.36	-0.48	10	-3.55	-3.30	0.25	29	-0.17	2.40	4.56	3.15
14	1227	-3.40	-0.36	-0.48	6	-3.33	-3.09	0.24	30	-0.06	2.38	4.67	2.95
84	1215	-3.40	-0.36	-0.48	8	-3.15	-2.91	0.24	29	-0.10	2.36	4.52	2.95
82	1208	-3.40	-0.36	-0.48	8	-3.25	-3.08	0.16	29	-0.24	2.37	4.66	3.23
78	1185	-3.40	-0.36	-0.48	8	-3.49	-3.24	0.24	29	-0.24	2.39	4.77	3.15
39	1172	-3.41	-0.36	-0.49	10	-3.43	-3.28	0.15	29	-0.03	2.39	4.55	3.27
20	1154	-3.41	-0.37	-0.49	6	-3.41	-3.17	0.24	30	-0.20	2.38	4.80	3.05
58	1128	-3.41	-0.37	-0.49	10	-3.55	-3.30	0.25	30	0.06	2.39	4.64	3.16
57	1117	-3.41	-0.37	-0.49	8	-3.50	-3.21	0.29	30	-0.20	2.38	4.62	3.31
50	1098	-3.41	-0.37	-0.49	10	-3.46	-3.21	0.24	29	0.03	2.40	4.81	3.13
30	1093	-3.41	-0.37	-0.49	8	-3.13	-2.96	0.16	29	0.10	2.36	4.76	3.04

53	1092	-3.41	-0.37	-0.49	10	-3.37	-3.19	0.18	29	0.10	2.37	4.50	3.35
8	1051	-3.42	-0.38	-0.50	10	-3.49	-3.30	0.19	29	-0.31	2.42	4.87	3.10
10	1042	-3.42	-0.38	-0.50	8	-3.32	-3.16	0.16	29	-0.17	2.38	4.78	3.23
33	1022	-3.42	-0.38	-0.50	8	-3.44	-3.18	0.25	29	-0.03	2.37	4.55	3.28
74	1003	-3.42	-0.38	-0.50	6	-3.41	-3.14	0.27	29	-0.24	2.38	4.81	3.32
98	995	-3.42	-0.38	-0.50	10	-3.48	-3.34	0.13	29	-0.03	2.39	4.68	3.12
1	992	-3.42	-0.38	-0.50	10	-3.45	-3.22	0.22	30	-0.13	2.38	4.57	3.32
75	954	-3.43	-0.38	-0.51	12	-3.59	-3.37	0.22	29	-0.10	2.42	4.73	3.04
13	938	-3.43	-0.39	-0.51	10	-3.49	-3.28	0.20	29	-0.24	2.43	4.94	3.19
93	938	-3.43	-0.39	-0.51	4	-3.42	-3.22	0.20	30	-0.26	2.40	4.93	3.26
17	934	-3.43	-0.39	-0.51	8	-3.23	-3.13	0.09	30	-0.20	2.37	4.59	2.81
99	931	-3.43	-0.39	-0.51	10	-3.51	-3.32	0.19	29	-0.24	2.42	4.75	2.99
94	909	-3.43	-0.39	-0.51	8	-3.21	-3.06	0.14	29	0.10	2.39	5.00	3.13
66	905	-3.43	-0.39	-0.51	10	-3.44	-3.29	0.15	29	-0.10	2.41	4.72	3.21
40	903	-3.43	-0.39	-0.51	8	-3.50	-3.19	0.30	30	-0.06	2.37	4.55	3.23
62	896	-3.43	-0.39	-0.51	8	-3.35	-3.13	0.22	29	0.03	2.35	4.61	3.26
24	883	-3.43	-0.39	-0.51	8	-3.51	-3.24	0.26	29	-0.17	2.38	4.65	3.23
69	857	-3.43	-0.39	-0.51	6	-3.35	-3.14	0.20	28	0.00	2.39	4.81	2.88
3	809	-3.44	-0.40	-0.52	8	-3.45	-3.20	0.25	30	-0.20	2.41	4.84	3.24
44	806	-3.44	-0.40	-0.52	10	-3.43	-3.19	0.24	29	-0.03	2.40	4.85	3.16
45	803	-3.44	-0.40	-0.52	10	-3.47	-3.26	0.21	29	0.03	2.41	4.80	3.25
61	786	-3.44	-0.40	-0.52	10	-3.32	-3.12	0.20	29	0.37	2.39	4.72	3.24
28	764	-3.44	-0.40	-0.52	10	-3.52	-3.23	0.28	30	-0.06	2.42	4.66	3.10
19	746	-3.44	-0.40	-0.52	8	-3.31	-3.15	0.16	30	0.20	2.41	4.77	3.15
92	741	-3.44	-0.40	-0.52	10	-3.44	-3.24	0.19	29	0.24	2.39	4.67	3.25
87	739	-3.44	-0.40	-0.53	10	-3.47	-3.21	0.26	30	0.00	2.41	4.66	3.15
11	734	-3.45	-0.40	-0.53	10	-3.44	-3.21	0.22	30	-0.13	2.42	4.71	2.75
5	716	-3.45	-0.41	-0.53	8	-3.52	-3.28	0.23	29	-0.10	2.42	4.89	3.25
32	693	-3.45	-0.41	-0.53	12	-3.53	-3.32	0.20	28	0.07	2.39	4.50	2.86
43	650	-3.45	-0.41	-0.53	10	-3.49	-3.30	0.18	29	0.03	2.39	4.48	3.28
49	649	-3.45	-0.41	-0.53	10	-3.35	-3.06	0.29	29	0.17	2.39	4.67	3.15
81	641	-3.45	-0.41	-0.53	10	-3.48	-3.22	0.25	30	0.20	2.40	4.67	3.20
38	598	-3.46	-0.42	-0.54	10	-3.51	-3.29	0.21	29	-0.10	2.40	4.61	3.32
47	558	-3.46	-0.42	-0.54	8	-3.29	-3.11	0.18	28	-0.07	2.39	4.73	2.80
56	530	-3.46	-0.42	-0.54	8	-3.40	-3.13	0.27	30	0.06	2.41	4.79	3.36
2	487	-3.47	-0.43	-0.55	8	-3.33	-3.03	0.30	29	-0.03	2.38	4.75	2.80
90	431	-3.47	-0.43	-0.55	10	-3.52	-3.27	0.24	30	-0.13	2.40	4.81	2.88
96	287	-3.49	-0.44	-0.57	8	-3.44	-3.33	0.10	29	0.03	2.42	4.82	3.34
4	284	-3.49	-0.45	-0.57	10	-3.48	-3.32	0.15	27	0.11	2.38	4.39	2.96
37	0	-3.51	-0.47	-0.59	10	-3.53	-3.26	0.26	29	-0.03	2.43	4.85	3.22

Table SI36: Structural, energetic and electronic properties for Co₆Mo₆ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
12	1775	-3.48	-0.34	-0.38	12	-3.40	-3.31	0.08	33	-0.21	2.42	5.06	2.91
72	1704	-3.48	-0.35	-0.39	8	-3.33	-3.11	0.22	33	0.03	2.38	4.72	2.88
50	1686	-3.49	-0.35	-0.39	6	-3.26	-3.03	0.22	32	0.06	2.38	4.93	2.77
99	1682	-3.49	-0.35	-0.39	6	-3.35	-3.20	0.15	33	-0.09	2.39	5.07	2.80

51	1682	-3.49	-0.35	-0.39	6	-3.35	-3.20	0.15	33	-0.09	2.39	5.07	2.80
0	1579	-3.49	-0.36	-0.40	8	-3.33	-3.21	0.12	33	-0.03	2.39	4.84	2.79
31	1541	-3.50	-0.36	-0.40	8	-3.29	-3.10	0.19	33	-0.03	2.38	4.79	2.80
23	1521	-3.50	-0.36	-0.40	10	-3.33	-3.13	0.20	34	-0.17	2.41	5.01	2.94
97	1510	-3.50	-0.36	-0.40	6	-3.39	-3.17	0.21	34	-0.05	2.39	4.92	2.96
8	1506	-3.50	-0.36	-0.40	8	-3.50	-3.20	0.30	32	-0.12	2.39	4.89	2.79
63	1456	-3.50	-0.37	-0.41	8	-3.34	-3.11	0.23	34	-0.05	2.40	4.83	2.98
95	1452	-3.51	-0.37	-0.41	4	-3.26	-3.08	0.17	33	0.09	2.39	5.05	2.82
34	1401	-3.51	-0.37	-0.41	8	-3.26	-3.07	0.19	33	-0.09	2.38	4.94	2.82
14	1400	-3.51	-0.37	-0.41	8	-3.53	-3.28	0.25	34	-0.17	2.39	4.83	2.87
61	1395	-3.51	-0.37	-0.41	10	-3.36	-3.18	0.17	34	-0.17	2.41	4.97	2.92
58	1319	-3.52	-0.38	-0.42	8	-3.45	-3.12	0.32	34	-0.05	2.39	4.76	3.00
71	1303	-3.52	-0.38	-0.42	8	-3.36	-3.15	0.21	34	-0.11	2.38	4.84	2.88
67	1293	-3.52	-0.38	-0.42	10	-3.33	-3.16	0.16	34	-0.11	2.39	4.76	3.00
16	1290	-3.52	-0.38	-0.42	8	-3.35	-3.17	0.17	34	-0.23	2.39	4.79	2.75
87	1287	-3.52	-0.38	-0.42	8	-3.41	-3.19	0.21	31	-0.22	2.38	4.77	2.80
88	1232	-3.52	-0.39	-0.43	8	-3.52	-3.32	0.20	33	-0.21	2.39	4.54	2.83
48	1226	-3.52	-0.39	-0.43	10	-3.44	-3.30	0.13	34	-0.17	2.41	4.95	2.90
24	1217	-3.52	-0.39	-0.43	8	-3.35	-3.19	0.16	34	-0.05	2.41	5.08	2.94
55	1188	-3.53	-0.39	-0.43	10	-3.35	-3.14	0.20	33	0.03	2.37	4.59	2.87
84	1184	-3.53	-0.39	-0.43	10	-3.42	-3.23	0.18	33	-0.09	2.42	4.93	2.91
11	1168	-3.53	-0.39	-0.43	8	-3.37	-3.04	0.33	32	-0.25	2.38	4.88	2.96
4	1142	-3.53	-0.39	-0.44	8	-3.49	-3.30	0.18	32	-0.06	2.41	4.92	2.95
40	1132	-3.53	-0.39	-0.44	8	-3.16	-3.04	0.11	33	-0.15	2.39	4.99	2.90
56	1103	-3.53	-0.40	-0.44	8	-3.40	-3.23	0.16	33	-0.21	2.41	4.87	2.91
20	1081	-3.54	-0.40	-0.44	8	-3.27	-3.15	0.11	34	-0.05	2.39	4.75	2.78
01	1080	-3.54	-0.40	-0.44	8	-3.37	-3.23	0.13	34	-0.29	2.40	4.87	2.82
13	1049	-3.54	-0.40	-0.44	8	-3.30	-3.15	0.14	33	-0.09	2.40	4.92	2.96
78	1047	-3.54	-0.40	-0.44	10	-3.30	-3.10	0.19	32	0.00	2.40	5.01	2.84
60	1021	-3.54	-0.40	-0.45	10	-3.39	-3.24	0.14	33	-0.15	2.43	4.99	2.76
81	1010	-3.54	-0.40	-0.45	8	-3.34	-3.14	0.20	33	-0.21	2.40	4.94	2.89
43	966	-3.55	-0.41	-0.45	8	-3.48	-3.32	0.15	33	-0.15	2.41	4.96	2.81
75	961	-3.55	-0.41	-0.45	10	-3.33	-3.19	0.13	34	0.05	2.41	4.89	2.94
37	942	-3.55	-0.41	-0.45	8	-3.40	-3.14	0.25	34	-0.29	2.41	4.95	2.85
92	930	-3.55	-0.41	-0.45	8	-3.34	-3.08	0.26	34	-0.05	2.39	4.85	2.88
85	929	-3.55	-0.41	-0.45	8	-3.37	-3.22	0.14	33	-0.09	2.42	4.91	2.96
73	929	-3.55	-0.41	-0.45	10	-3.45	-3.29	0.16	33	-0.03	2.42	4.85	2.83
64	925	-3.55	-0.41	-0.45	8	-3.41	-3.15	0.25	34	-0.23	2.40	4.87	2.82
45	903	-3.55	-0.41	-0.45	8	-3.46	-3.27	0.18	34	-0.11	2.41	4.74	2.78
22	900	-3.55	-0.41	-0.46	10	-3.46	-3.25	0.20	32	-0.12	2.43	4.88	2.90
74	861	-3.55	-0.42	-0.46	8	-3.37	-3.15	0.22	32	0.12	2.41	4.99	2.89
26	843	-3.56	-0.42	-0.46	8	-3.24	-3.04	0.20	33	-0.09	2.39	4.93	2.88
86	817	-3.56	-0.42	-0.46	10	-3.38	-3.20	0.18	33	0.03	2.39	4.83	2.89
42	798	-3.56	-0.42	-0.46	10	-3.41	-3.16	0.25	32	0.12	2.43	4.97	2.81
98	776	-3.56	-0.42	-0.47	10	-3.45	-3.19	0.26	32	0.00	2.41	4.99	2.87
79	776	-3.56	-0.42	-0.47	10	-3.45	-3.18	0.26	33	0.03	2.41	4.99	2.87
32	773	-3.56	-0.42	-0.47	10	-3.40	-3.18	0.21	35	-0.14	2.41	4.64	2.92
30	771	-3.56	-0.42	-0.47	8	-3.41	-3.20	0.20	34	-0.05	2.43	4.95	2.86
69	769	-3.56	-0.42	-0.47	8	-3.20	-3.02	0.18	34	0.29	2.39	4.85	2.82
53	765	-3.56	-0.42	-0.47	10	-3.32	-3.01	0.30	31	0.16	2.38	4.59	2.78
82	762	-3.56	-0.42	-0.47	8	-3.35	-3.09	0.25	31	-0.22	2.40	4.89	2.85
38	747	-3.56	-0.43	-0.47	10	-3.32	-3.25	0.06	32	-0.31	2.42	4.74	2.86
29	744	-3.56	-0.43	-0.47	10	-3.27	-3.07	0.19	34	0.17	2.41	4.98	2.91
3	708	-3.57	-0.43	-0.47	6	-3.27	-3.05	0.22	33	-0.03	2.41	4.98	2.87
25	705	-3.57	-0.43	-0.47	6	-3.27	-3.05	0.22	33	-0.03	2.41	4.98	2.87
93	684	-3.57	-0.43	-0.47	10	-3.40	-3.14	0.25	33	-0.03	2.42	4.85	2.97
10	667	-3.57	-0.43	-0.47	8	-3.26	-3.05	0.20	33	-0.09	2.40	5.06	2.88

33	663	-3.57	-0.43	-0.47	8	-3.32	-3.17	0.15	32	-0.06	2.41	5.01	2.90
9	642	-3.57	-0.43	-0.48	8	-3.50	-3.29	0.21	34	-0.23	2.39	4.76	2.96
89	586	-3.58	-0.44	-0.48	8	-3.33	-3.12	0.21	33	0.03	2.40	4.89	2.84
90	586	-3.58	-0.44	-0.48	8	-3.33	-3.12	0.21	33	0.03	2.40	4.89	2.84
47	584	-3.58	-0.44	-0.48	8	-3.41	-3.25	0.16	33	-0.21	2.41	4.79	2.89
52	583	-3.58	-0.44	-0.48	8	-3.55	-3.24	0.31	34	-0.23	2.43	4.84	2.96
36	576	-3.58	-0.44	-0.48	10	-3.26	-3.04	0.21	32	0.06	2.41	4.86	2.84
15	575	-3.58	-0.44	-0.48	8	-3.28	-3.17	0.11	32	0.00	2.39	4.78	2.83
5	551	-3.58	-0.44	-0.48	10	-3.34	-3.19	0.14	33	0.27	2.42	4.87	2.86
7	548	-3.58	-0.44	-0.48	8	-3.47	-3.25	0.22	32	-0.06	2.43	4.92	2.96
70	527	-3.58	-0.44	-0.49	10	-3.43	-3.25	0.18	33	0.09	2.44	4.90	2.98
6	519	-3.58	-0.44	-0.49	8	-3.43	-3.15	0.28	33	-0.09	2.39	4.92	2.88
65	508	-3.58	-0.45	-0.49	10	-3.59	-3.31	0.28	32	-0.12	2.40	4.66	2.85
94	501	-3.58	-0.45	-0.49	8	-3.39	-3.28	0.10	35	-0.20	2.43	4.79	3.00
59	425	-3.59	-0.45	-0.49	10	-3.52	-3.29	0.22	34	0.00	2.43	4.78	2.94
46	418	-3.59	-0.45	-0.50	10	-3.41	-3.21	0.19	34	0.29	2.40	4.84	2.91
80	417	-3.59	-0.45	-0.50	10	-3.44	-3.23	0.20	35	0.02	2.45	4.97	2.99
21	415	-3.59	-0.45	-0.50	8	-3.50	-3.30	0.20	34	0.00	2.42	4.71	2.94
28	408	-3.59	-0.45	-0.50	10	-3.51	-3.32	0.19	33	0.09	2.42	4.73	2.97
76	392	-3.59	-0.46	-0.50	10	-3.42	-3.21	0.20	33	-0.15	2.41	4.82	2.89
2	376	-3.59	-0.46	-0.50	10	-3.58	-3.37	0.21	32	-0.12	2.43	4.85	2.91
66	362	-3.60	-0.46	-0.50	10	-3.54	-3.28	0.26	33	0.03	2.41	4.81	2.90
17	360	-3.60	-0.46	-0.50	8	-3.41	-3.23	0.18	32	0.00	2.39	4.67	2.93
57	351	-3.60	-0.46	-0.50	8	-3.53	-3.29	0.24	33	-0.09	2.43	4.94	2.89
27	316	-3.60	-0.46	-0.50	10	-3.41	-3.19	0.22	33	-0.15	2.42	4.89	2.94
49	298	-3.60	-0.46	-0.51	8	-3.36	-3.10	0.25	33	0.03	2.41	4.74	2.93
91	288	-3.60	-0.46	-0.51	8	-3.43	-3.18	0.24	32	-0.12	2.43	5.00	2.85
18	282	-3.60	-0.46	-0.51	10	-3.52	-3.33	0.18	33	-0.09	2.44	4.96	3.02
35	105	-3.62	-0.48	-0.52	10	-3.54	-3.37	0.17	32	0.12	2.42	4.84	3.07
44	78	-3.62	-0.48	-0.52	10	-3.48	-3.21	0.26	33	0.03	2.44	4.79	2.97
83	16	-3.62	-0.49	-0.53	8	-3.52	-3.33	0.18	34	0.05	2.42	4.83	3.04
62	0	-3.63	-0.49	-0.53	8	-3.35	-3.10	0.25	32	0.18	2.42	5.04	2.83

Table SI37: Structural, energetic and electronic properties for Co₇Mo₆ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
99	1786	-3.55	-0.34	-0.45	11	-3.20	-3.05	0.14	36	0.05	2.38	5.13	2.88
36	1771	-3.55	-0.34	-0.45	9	-3.16	-3.05	0.11	36	0.05	2.39	5.18	2.85
16	1677	-3.56	-0.35	-0.45	9	-3.48	-3.27	0.20	36	0.05	2.40	5.30	2.91
7	1653	-3.56	-0.35	-0.46	13	-3.33	-3.22	0.11	36	-0.16	2.41	5.18	2.91
40	1641	-3.56	-0.35	-0.46	11	-3.21	-2.99	0.22	36	0.05	2.39	5.19	2.87
33	1639	-3.56	-0.35	-0.46	9	-3.37	-3.24	0.13	36	0.16	2.38	5.08	2.98
35	1594	-3.56	-0.35	-0.46	11	-3.45	-3.26	0.18	37	-0.02	2.42	5.39	2.93
28	1586	-3.57	-0.35	-0.46	9	-3.16	-3.05	0.11	36	-0.05	2.38	5.30	2.87
20	1583	-3.57	-0.36	-0.46	9	-3.42	-3.27	0.14	36	-0.11	2.40	5.36	2.92
44	1582	-3.57	-0.36	-0.46	9	-3.46	-3.29	0.17	36	-0.05	2.40	5.20	2.96
93	1537	-3.57	-0.36	-0.46	9	-3.31	-3.16	0.14	37	-0.24	2.41	5.27	2.91
43	1532	-3.57	-0.36	-0.47	9	-3.35	-3.17	0.17	36	-0.05	2.38	5.03	2.98

8	1528	-3.57	-0.36	-0.47	11	-3.40	-3.30	0.10	36	0.11	2.38	5.09	2.97
31	1506	-3.57	-0.36	-0.47	9	-3.39	-3.17	0.22	36	0.05	2.40	5.35	2.90
58	1488	-3.57	-0.36	-0.47	9	-3.39	-3.18	0.20	36	-0.05	2.39	5.23	2.89
1	1452	-3.58	-0.37	-0.47	9	-3.48	-3.29	0.18	36	-0.11	2.41	5.28	2.93
56	1446	-3.58	-0.37	-0.47	7	-3.37	-3.18	0.19	36	-0.05	2.38	5.26	2.98
86	1412	-3.58	-0.37	-0.47	9	-3.37	-3.20	0.17	36	-0.05	2.39	5.27	2.90
68	1404	-3.58	-0.37	-0.48	9	-3.24	-3.15	0.09	36	-0.05	2.39	5.16	2.89
50	1400	-3.58	-0.37	-0.48	11	-3.45	-3.21	0.24	37	-0.29	2.42	5.23	2.97
81	1389	-3.58	-0.37	-0.48	9	-3.35	-3.16	0.18	36	-0.11	2.40	5.33	2.89
41	1376	-3.58	-0.37	-0.48	11	-3.50	-3.32	0.18	36	-0.16	2.42	5.19	2.90
88	1363	-3.58	-0.37	-0.48	9	-3.31	-3.07	0.23	36	-0.22	2.40	5.23	2.88
95	1326	-3.59	-0.37	-0.48	9	-3.44	-3.34	0.09	38	-0.10	2.41	5.10	2.97
73	1324	-3.59	-0.38	-0.48	9	-3.38	-3.20	0.17	36	-0.16	2.41	5.23	2.91
94	1317	-3.59	-0.38	-0.48	9	-3.50	-3.26	0.24	36	-0.22	2.40	5.21	2.94
90	1314	-3.59	-0.38	-0.48	9	-3.40	-3.16	0.23	36	-0.11	2.39	5.26	2.95
21	1308	-3.59	-0.38	-0.48	9	-3.34	-3.14	0.20	36	-0.16	2.41	5.34	2.89
34	1297	-3.59	-0.38	-0.48	9	-3.33	-3.18	0.14	37	-0.02	2.40	5.08	2.91
54	1267	-3.59	-0.38	-0.49	11	-3.45	-3.27	0.17	38	-0.21	2.42	5.17	2.96
57	1261	-3.59	-0.38	-0.49	9	-3.47	-3.30	0.17	37	0.02	2.41	5.08	2.91
18	1256	-3.59	-0.38	-0.49	9	-3.50	-3.34	0.15	37	-0.13	2.41	5.03	2.94
98	1255	-3.59	-0.38	-0.49	9	-3.58	-3.34	0.23	36	-0.11	2.41	5.22	2.89
80	1242	-3.59	-0.38	-0.49	11	-3.40	-3.14	0.26	36	-0.11	2.38	5.02	2.96
59	1239	-3.59	-0.38	-0.49	11	-3.48	-3.29	0.19	36	0.11	2.40	5.11	2.91
26	1182	-3.60	-0.39	-0.49	11	-3.57	-3.30	0.26	37	-0.02	2.41	4.99	3.02
70	1168	-3.60	-0.39	-0.49	9	-3.34	-3.06	0.27	36	-0.16	2.40	5.28	2.88
10	1164	-3.60	-0.39	-0.49	9	-3.54	-3.33	0.21	37	-0.18	2.42	5.31	2.92
66	1162	-3.60	-0.39	-0.49	11	-3.45	-3.21	0.23	37	0.08	2.40	5.01	2.87
32	1157	-3.60	-0.39	-0.49	9	-3.48	-3.29	0.18	38	-0.21	2.42	5.13	2.93
84	1152	-3.60	-0.39	-0.49	7	-3.57	-3.30	0.27	38	-0.10	2.40	5.21	2.96
52	1149	-3.60	-0.39	-0.49	9	-3.62	-3.37	0.24	36	-0.11	2.42	5.23	2.88
13	1148	-3.60	-0.39	-0.49	9	-3.59	-3.40	0.19	37	-0.18	2.43	5.29	2.95
51	1140	-3.60	-0.39	-0.50	7	-3.31	-3.13	0.18	37	-0.08	2.40	5.27	2.87
75	1133	-3.60	-0.39	-0.50	9	-3.48	-3.17	0.30	37	-0.18	2.40	5.25	2.87
12	1098	-3.60	-0.39	-0.50	7	-3.36	-3.22	0.13	37	-0.18	2.40	5.34	2.90
72	1094	-3.60	-0.39	-0.50	7	-3.42	-3.15	0.27	37	-0.24	2.39	5.14	2.87
64	1090	-3.60	-0.39	-0.50	9	-3.38	-3.24	0.13	38	-0.05	2.40	5.03	2.92
3	1090	-3.60	-0.39	-0.50	9	-3.52	-3.31	0.20	37	-0.13	2.41	5.25	2.94
30	1089	-3.60	-0.39	-0.50	9	-3.41	-3.33	0.07	37	-0.13	2.42	5.13	2.91
78	1086	-3.60	-0.39	-0.50	7	-3.38	-3.28	0.10	37	-0.18	2.41	5.20	2.90
79	1077	-3.60	-0.39	-0.50	11	-3.44	-3.27	0.17	38	-0.05	2.40	5.15	2.87
37	1071	-3.61	-0.39	-0.50	7	-3.43	-3.27	0.15	37	-0.18	2.41	5.28	2.88
42	1052	-3.61	-0.40	-0.50	7	-3.36	-3.10	0.25	36	-0.22	2.39	5.18	2.93
91	1033	-3.61	-0.40	-0.50	9	-3.36	-3.20	0.15	36	0.00	2.40	5.28	2.89
23	1016	-3.61	-0.40	-0.50	11	-3.37	-3.14	0.22	36	0.16	2.40	5.15	2.93
25	1013	-3.61	-0.40	-0.51	9	-3.37	-3.20	0.17	37	-0.24	2.41	5.16	2.91
77	1006	-3.61	-0.40	-0.51	9	-3.43	-3.28	0.14	37	-0.02	2.42	5.13	2.96
60	1004	-3.61	-0.40	-0.51	9	-3.53	-3.30	0.23	36	-0.33	2.41	5.27	2.89
65	996	-3.61	-0.40	-0.51	11	-3.44	-3.29	0.15	36	-0.16	2.42	5.19	2.91
46	985	-3.61	-0.40	-0.51	11	-3.37	-3.19	0.17	37	-0.13	2.41	5.07	2.97
45	979	-3.61	-0.40	-0.51	11	-3.49	-3.34	0.15	37	-0.13	2.43	5.21	2.89
4	962	-3.61	-0.40	-0.51	11	-3.47	-3.23	0.24	36	0.22	2.40	5.09	3.04
15	959	-3.61	-0.40	-0.51	9	-3.42	-3.33	0.09	36	-0.05	2.41	5.20	2.94
89	933	-3.62	-0.41	-0.51	11	-3.54	-3.25	0.28	36	0.05	2.41	5.14	2.95
96	905	-3.62	-0.41	-0.51	11	-3.61	-3.36	0.25	36	-0.11	2.44	5.15	2.89
5	901	-3.62	-0.41	-0.51	9	-3.55	-3.42	0.13	36	0.11	2.42	5.25	2.95
6	890	-3.62	-0.41	-0.51	9	-3.36	-3.20	0.15	36	0.11	2.41	5.32	2.94
55	888	-3.62	-0.41	-0.51	9	-3.52	-3.41	0.10	36	0.11	2.42	5.25	2.97

47	873	-3.62	-0.41	-0.52	9	-3.51	-3.22	0.28	37	-0.18	2.40	5.05	2.99
83	853	-3.62	-0.41	-0.52	9	-3.27	-3.12	0.15	36	0.11	2.40	5.23	2.92
2	844	-3.62	-0.41	-0.52	11	-3.46	-3.22	0.23	38	0.05	2.41	5.06	2.95
38	814	-3.62	-0.41	-0.52	9	-3.45	-3.24	0.21	37	-0.24	2.41	5.25	2.88
29	787	-3.63	-0.42	-0.52	11	-3.39	-3.15	0.23	36	0.27	2.41	5.16	2.95
48	784	-3.63	-0.42	-0.52	11	-3.43	-3.20	0.22	39	0.12	2.41	4.86	2.93
62	776	-3.63	-0.42	-0.52	11	-3.56	-3.35	0.21	36	-0.05	2.42	5.22	2.98
24	768	-3.63	-0.42	-0.52	11	-3.52	-3.35	0.17	36	-0.22	2.43	5.30	2.91
71	768	-3.63	-0.42	-0.52	9	-3.31	-3.09	0.21	36	0.00	2.40	5.30	2.88
61	768	-3.63	-0.42	-0.52	9	-3.40	-3.21	0.18	37	-0.08	2.40	5.13	2.97
22	760	-3.63	-0.42	-0.52	9	-3.48	-3.27	0.20	37	-0.18	2.40	4.97	3.07
76	744	-3.63	-0.42	-0.53	9	-3.49	-3.27	0.21	37	-0.02	2.41	5.17	2.90
82	663	-3.64	-0.43	-0.53	11	-3.48	-3.24	0.24	36	-0.05	2.42	5.27	2.87
63	651	-3.64	-0.43	-0.53	9	-3.44	-3.28	0.16	37	-0.13	2.42	5.08	2.91
0	646	-3.64	-0.43	-0.53	9	-3.49	-3.36	0.12	36	-0.05	2.42	5.26	2.95
53	611	-3.64	-0.43	-0.54	11	-3.40	-3.24	0.15	36	0.16	2.41	4.95	2.95
97	588	-3.64	-0.43	-0.54	9	-3.24	-3.11	0.13	36	0.11	2.39	5.10	2.88
39	587	-3.64	-0.43	-0.54	11	-3.65	-3.33	0.32	36	-0.11	2.44	5.19	2.93
11	579	-3.64	-0.43	-0.54	9	-3.38	-3.12	0.26	37	-0.02	2.40	5.18	2.92
14	557	-3.64	-0.43	-0.54	9	-3.41	-3.30	0.10	37	-0.08	2.40	5.05	2.88
74	506	-3.65	-0.44	-0.54	11	-3.48	-3.18	0.29	36	-0.05	2.41	5.08	2.91
67	493	-3.65	-0.44	-0.55	13	-3.61	-3.36	0.24	36	0.27	2.41	4.91	3.06
85	482	-3.65	-0.44	-0.55	11	-3.56	-3.33	0.22	37	-0.13	2.42	5.06	2.93
87	467	-3.65	-0.44	-0.55	11	-3.52	-3.36	0.16	36	0.16	2.42	4.91	3.01
49	445	-3.65	-0.44	-0.55	9	-3.46	-3.22	0.24	36	-0.11	2.41	5.14	2.89
92	405	-3.66	-0.45	-0.55	9	-3.62	-3.37	0.24	36	-0.05	2.42	5.15	2.88
27	404	-3.66	-0.45	-0.55	11	-3.53	-3.38	0.14	36	-0.11	2.44	5.16	2.92
19	392	-3.66	-0.45	-0.55	11	-3.55	-3.33	0.22	37	-0.02	2.42	5.16	2.88
9	360	-3.66	-0.45	-0.56	9	-3.54	-3.30	0.24	37	-0.13	2.42	5.13	2.93
17	0	-3.69	-0.48	-0.58	9	-3.54	-3.45	0.08	36	0.05	2.44	5.13	2.99

Table SI38: Structural, energetic and electronic properties for Co₇Mo₇ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
47	1971	-3.60	-0.39	-0.41	9	-3.35	-3.26	0.09	40	0.00	2.39	5.16	3.25
27	1941	-3.60	-0.39	-0.41	9	-3.40	-3.20	0.19	40	-0.10	2.41	5.30	3.27
88	1938	-3.60	-0.39	-0.41	11	-3.35	-3.26	0.09	40	-0.05	2.40	5.09	3.20
28	1896	-3.61	-0.39	-0.42	11	-3.52	-3.31	0.21	39	-0.28	2.44	5.29	3.31
44	1864	-3.61	-0.40	-0.42	7	-3.45	-3.24	0.21	41	-0.21	2.40	5.13	3.18
59	1803	-3.61	-0.40	-0.42	7	-3.36	-3.26	0.10	40	0.05	2.39	5.20	3.26
57	1655	-3.62	-0.41	-0.43	9	-3.55	-3.34	0.20	39	-0.17	2.40	5.13	3.32
53	1587	-3.63	-0.41	-0.44	11	-3.31	-3.25	0.05	41	-0.21	2.42	5.15	3.25
74	1532	-3.63	-0.42	-0.44	9	-3.33	-3.07	0.25	40	-0.20	2.41	5.22	3.25
56	1515	-3.63	-0.42	-0.44	13	-3.51	-3.23	0.28	39	-0.02	2.42	5.18	3.28
30	1503	-3.63	-0.42	-0.44	7	-3.35	-3.14	0.21	42	-0.14	2.40	5.01	3.21
81	1502	-3.63	-0.42	-0.44	11	-3.49	-3.32	0.17	41	-0.12	2.42	5.22	3.31
96	1487	-3.64	-0.42	-0.44	9	-3.34	-3.13	0.20	41	-0.21	2.41	5.31	3.25
8	1451	-3.64	-0.42	-0.45	9	-3.52	-3.30	0.22	40	-0.25	2.42	5.14	3.23

99	1372	-3.64	-0.43	-0.45	9	-3.31	-3.18	0.13	39	0.17	2.40	5.10	3.33
95	1310	-3.65	-0.43	-0.46	5	-3.29	-3.07	0.22	39	-0.33	2.38	5.16	3.30
69	1306	-3.65	-0.44	-0.46	11	-3.27	-3.11	0.16	41	-0.02	2.41	5.21	3.23
04	1304	-3.65	-0.44	-0.46	11	-3.32	-3.07	0.25	40	-0.15	2.42	5.20	3.19
06	1294	-3.65	-0.44	-0.46	11	-3.40	-3.23	0.16	40	0.00	2.41	5.01	3.32
91	1279	-3.65	-0.44	-0.46	9	-3.60	-3.40	0.19	39	-0.07	2.42	5.12	3.27
24	1271	-3.65	-0.44	-0.46	9	-3.44	-3.29	0.15	42	-0.09	2.42	5.21	3.30
55	1248	-3.65	-0.44	-0.46	7	-3.28	-3.05	0.23	41	-0.12	2.40	5.21	3.25
11	1233	-3.65	-0.44	-0.46	5	-3.34	-3.16	0.17	40	-0.10	2.39	5.28	3.32
80	1226	-3.65	-0.44	-0.46	7	-3.39	-3.19	0.19	39	-0.17	2.40	5.20	3.32
3	1216	-3.66	-0.44	-0.46	9	-3.49	-3.21	0.28	41	-0.07	2.40	4.91	3.10
84	1204	-3.66	-0.44	-0.46	7	-3.32	-3.15	0.17	39	-0.28	2.41	5.28	3.34
37	1196	-3.66	-0.44	-0.47	9	-3.34	-3.15	0.19	41	-0.12	2.42	5.40	3.24
61	1174	-3.66	-0.44	-0.47	9	-3.45	-3.34	0.11	41	-0.17	2.42	5.20	3.35
16	1160	-3.66	-0.45	-0.47	11	-3.39	-3.13	0.25	40	0.00	2.42	5.28	3.27
40	1113	-3.66	-0.45	-0.47	9	-3.34	-3.19	0.14	40	0.05	2.42	5.25	3.36
77	1085	-3.66	-0.45	-0.47	9	-3.33	-3.15	0.18	40	-0.10	2.39	4.99	3.44
76	1046	-3.67	-0.45	-0.48	7	-3.42	-3.25	0.16	39	-0.07	2.40	5.25	3.40
63	1036	-3.67	-0.45	-0.48	9	-3.36	-3.12	0.24	40	-0.15	2.41	5.26	3.34
58	1036	-3.67	-0.45	-0.48	7	-3.27	-3.11	0.15	42	-0.04	2.41	5.21	2.96
51	1034	-3.67	-0.45	-0.48	7	-3.31	-3.14	0.17	40	-0.20	2.40	5.23	3.26
97	1028	-3.67	-0.45	-0.48	11	-3.55	-3.25	0.29	39	-0.02	2.42	5.17	3.33
38	1006	-3.67	-0.46	-0.48	11	-3.45	-3.29	0.16	41	0.07	2.42	4.99	3.31
22	993	-3.67	-0.46	-0.48	11	-3.45	-3.26	0.18	40	-0.15	2.41	5.03	3.29
62	978	-3.67	-0.46	-0.48	9	-3.27	-3.08	0.18	39	-0.02	2.38	5.06	3.40
19	976	-3.67	-0.46	-0.48	9	-3.36	-3.12	0.23	40	0.10	2.40	4.96	3.24
5	972	-3.67	-0.46	-0.48	7	-3.50	-3.32	0.17	39	-0.12	2.41	5.13	3.33
46	967	-3.67	-0.46	-0.48	11	-3.40	-3.24	0.16	41	0.02	2.43	5.00	3.18
85	963	-3.67	-0.46	-0.48	9	-3.54	-3.44	0.09	39	-0.07	2.43	5.21	3.40
21	953	-3.67	-0.46	-0.48	9	-3.39	-3.28	0.11	41	-0.21	2.42	5.27	3.25
9	944	-3.67	-0.46	-0.48	11	-3.56	-3.30	0.25	40	-0.20	2.44	5.23	3.23
42	928	-3.68	-0.46	-0.48	11	-3.49	-3.22	0.26	40	-0.05	2.43	5.14	3.35
98	918	-3.68	-0.46	-0.48	9	-3.40	-3.21	0.19	39	-0.02	2.41	5.24	3.27
10	915	-3.68	-0.46	-0.49	7	-3.36	-3.19	0.17	39	-0.28	2.41	5.18	3.28
29	885	-3.68	-0.47	-0.49	9	-3.43	-3.23	0.20	40	-0.10	2.41	5.20	3.35
45	882	-3.68	-0.47	-0.49	9	-3.40	-3.19	0.20	40	-0.10	2.42	5.14	3.32
26	874	-3.68	-0.47	-0.49	7	-3.25	-3.11	0.14	40	-0.10	2.41	5.12	3.23
52	872	-3.68	-0.47	-0.49	9	-3.36	-3.17	0.19	40	-0.15	2.42	5.22	3.31
65	865	-3.68	-0.47	-0.49	9	-3.43	-3.29	0.13	40	-0.15	2.42	5.17	3.30
90	860	-3.68	-0.47	-0.49	9	-3.46	-3.27	0.19	40	-0.10	2.41	5.10	3.30
54	854	-3.68	-0.47	-0.49	9	-3.36	-3.19	0.16	40	-0.10	2.42	5.03	3.31
72	805	-3.68	-0.47	-0.49	13	-3.44	-3.26	0.17	40	-0.05	2.40	4.81	3.23
79	803	-3.68	-0.47	-0.49	7	-3.42	-3.31	0.10	39	0.02	2.42	5.24	3.41
49	785	-3.69	-0.47	-0.49	9	-3.55	-3.34	0.20	40	-0.10	2.43	5.11	3.49
43	777	-3.69	-0.47	-0.50	7	-3.39	-3.21	0.18	40	-0.20	2.42	5.08	3.26
48	773	-3.69	-0.47	-0.50	9	-3.59	-3.38	0.20	39	-0.12	2.43	5.19	3.29
39	770	-3.69	-0.47	-0.50	7	-3.37	-3.18	0.18	40	-0.30	2.40	5.13	3.32
01	769	-3.69	-0.47	-0.50	11	-3.38	-3.27	0.11	40	-0.05	2.42	5.09	3.41
73	740	-3.69	-0.48	-0.50	9	-3.56	-3.36	0.19	40	-0.05	2.43	5.21	3.36
02	723	-3.69	-0.48	-0.50	7	-3.46	-3.25	0.20	43	-0.25	2.44	5.25	2.75
31	701	-3.69	-0.48	-0.50	11	-3.58	-3.33	0.25	40	-0.25	2.43	5.05	3.46
50	692	-3.69	-0.48	-0.50	9	-3.42	-3.22	0.20	41	-0.17	2.42	5.14	3.36
34	677	-3.69	-0.48	-0.50	7	-3.64	-3.36	0.27	39	-0.17	2.42	5.15	3.38
60	664	-3.69	-0.48	-0.50	9	-3.35	-3.15	0.19	39	-0.12	2.40	4.94	3.38
92	618	-3.70	-0.48	-0.51	11	-3.52	-3.41	0.10	40	-0.10	2.44	5.08	3.42
14	603	-3.70	-0.49	-0.51	11	-3.46	-3.36	0.10	40	-0.20	2.42	5.11	3.14
41	591	-3.70	-0.49	-0.51	9	-3.53	-3.36	0.16	39	-0.02	2.42	5.11	3.35

68	563	-3.70	-0.49	-0.51	9	-3.43	-3.28	0.15	40	0.05	2.44	5.22	3.17
66	554	-3.70	-0.49	-0.51	7	-3.48	-3.26	0.21	40	-0.05	2.41	5.19	3.33
64	547	-3.70	-0.49	-0.51	9	-3.44	-3.20	0.24	39	-0.17	2.43	5.24	3.49
23	519	-3.71	-0.49	-0.51	11	-3.39	-3.21	0.18	39	0.33	2.40	5.04	3.30
67	508	-3.71	-0.49	-0.51	11	-3.54	-3.44	0.10	39	0.07	2.43	5.00	3.48
70	490	-3.71	-0.49	-0.52	9	-3.42	-3.20	0.21	40	-0.05	2.42	5.10	3.31
86	480	-3.71	-0.49	-0.52	11	-3.47	-3.28	0.18	41	-0.02	2.44	5.12	2.84
12	457	-3.71	-0.50	-0.52	13	-3.61	-3.50	0.10	39	-0.12	2.44	5.06	3.28
32	448	-3.71	-0.50	-0.52	7	-3.41	-3.26	0.15	40	-0.10	2.41	5.20	3.25
82	446	-3.71	-0.50	-0.52	9	-3.44	-3.24	0.20	41	-0.02	2.43	5.10	3.29
20	350	-3.72	-0.50	-0.53	11	-3.49	-3.31	0.17	40	0.10	2.42	4.61	3.29
18	328	-3.72	-0.50	-0.53	9	-3.41	-3.24	0.17	40	-0.05	2.42	5.21	3.17
15	247	-3.72	-0.51	-0.53	9	-3.48	-3.24	0.24	39	-0.02	2.43	5.09	3.44
93	240	-3.73	-0.51	-0.53	9	-3.56	-3.41	0.14	41	-0.02	2.44	5.05	3.41
87	223	-3.73	-0.51	-0.53	9	-3.62	-3.42	0.19	39	-0.02	2.43	5.05	3.41
78	144	-3.73	-0.52	-0.54	9	-3.53	-3.30	0.22	39	0.02	2.42	5.14	3.40
75	123	-3.73	-0.52	-0.54	5	-3.36	-3.12	0.23	40	-0.15	2.38	4.91	3.05
71	0	-3.74	-0.53	-0.55	9	-3.49	-3.14	0.34	39	-0.07	2.42	5.20	3.44


Table SI39: Structural, energetic and electronic properties for Co_8Mo_7 cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
57	1788	-3.63	-0.40	-0.40	10	-3.44	-3.28	0.16	44	-0.09	2.40	5.27	3.41
40	1728	-3.63	-0.40	-0.41	10	-3.55	-3.38	0.16	43	-0.20	2.42	5.55	3.36
28	1668	-3.64	-0.40	-0.41	10	-3.48	-3.31	0.16	43	-0.06	2.40	5.34	3.40
20	1547	-3.65	-0.41	-0.42	10	-3.41	-3.32	0.08	44	-0.13	2.39	5.23	3.50
14	1471	-3.65	-0.42	-0.42	8	-3.51	-3.32	0.18	44	0.00	2.40	5.31	3.48
12	1394	-3.66	-0.42	-0.43	8	-3.50	-3.30	0.19	43	-0.25	2.40	5.34	3.32
21	1378	-3.66	-0.42	-0.43	8	-3.44	-3.32	0.11	44	-0.18	2.39	5.27	3.38
37	1320	-3.66	-0.43	-0.43	8	-3.53	-3.40	0.12	44	-0.27	2.40	5.14	3.41
35	1301	-3.66	-0.43	-0.43	12	-3.46	-3.30	0.16	45	-0.06	2.43	5.30	3.41
08	1287	-3.66	-0.43	-0.44	10	-3.50	-3.32	0.17	44	-0.13	2.41	5.31	3.46
97	1277	-3.66	-0.43	-0.44	10	-3.41	-3.32	0.09	46	-0.21	2.41	5.27	3.48
32	1251	-3.67	-0.43	-0.44	8	-3.48	-3.28	0.20	43	-0.11	2.41	5.40	3.41
1	1237	-3.67	-0.43	-0.44	8	-3.45	-3.25	0.19	43	-0.20	2.40	5.32	3.42
53	1229	-3.67	-0.43	-0.44	8	-3.42	-3.21	0.20	44	-0.09	2.39	5.40	3.34
25	1200	-3.67	-0.44	-0.44	10	-3.60	-3.34	0.25	44	-0.18	2.41	5.41	3.45
48	1198	-3.67	-0.44	-0.44	12	-3.64	-3.42	0.22	44	-0.22	2.44	5.32	3.56
70	1196	-3.67	-0.44	-0.44	12	-3.46	-3.25	0.20	44	0.04	2.41	5.32	3.36
4	1190	-3.67	-0.44	-0.44	10	-3.49	-3.25	0.24	44	-0.04	2.41	5.39	3.38
93	1189	-3.67	-0.44	-0.44	14	-3.57	-3.30	0.27	45	-0.06	2.42	5.40	3.39
50	1189	-3.67	-0.44	-0.44	10	-3.45	-3.25	0.20	44	-0.09	2.40	5.38	3.46
24	1188	-3.67	-0.44	-0.44	10	-3.41	-3.30	0.10	43	0.02	2.42	5.51	3.35
58	1149	-3.67	-0.44	-0.44	12	-3.50	-3.32	0.17	44	0.13	2.42	5.27	3.42
42	1130	-3.67	-0.44	-0.45	12	-3.53	-3.31	0.22	46	-0.04	2.41	5.26	3.47
47	1123	-3.67	-0.44	-0.45	10	-3.46	-3.26	0.20	44	-0.09	2.42	5.38	3.44
52	1089	-3.68	-0.44	-0.45	12	-3.53	-3.34	0.19	44	-0.09	2.42	5.35	3.37
82	1081	-3.68	-0.44	-0.45	12	-3.58	-3.36	0.22	43	-0.06	2.44	5.42	3.34

17	1061	-3.68	-0.45	-0.45	12	-3.45	-3.29	0.15	45	0.11	2.40	5.27	3.45
30	1056	-3.68	-0.45	-0.45	10	-3.62	-3.41	0.21	43	-0.06	2.41	5.13	3.39
90	1045	-3.68	-0.45	-0.45	10	-3.46	-3.31	0.15	44	-0.04	2.41	5.39	3.48
72	1042	-3.68	-0.45	-0.45	10	-3.44	-3.29	0.14	44	-0.13	2.42	5.21	3.41
15	1037	-3.68	-0.45	-0.45	10	-3.52	-3.35	0.17	45	0.02	2.43	5.37	3.46
13	1035	-3.68	-0.45	-0.45	10	-3.60	-3.35	0.24	44	-0.13	2.43	5.46	3.39
27	1026	-3.68	-0.45	-0.45	12	-3.37	-3.20	0.16	44	-0.09	2.40	5.29	3.46
67	1006	-3.68	-0.45	-0.45	8	-3.46	-3.27	0.18	44	0.00	2.41	5.34	3.31
54	995	-3.68	-0.45	-0.45	8	-3.46	-3.27	0.18	44	-0.04	2.42	5.43	3.44
38	989	-3.68	-0.45	-0.45	6	-3.38	-3.21	0.17	44	-0.13	2.40	5.45	3.40
0	981	-3.68	-0.45	-0.46	8	-3.40	-3.16	0.24	45	-0.20	2.40	5.27	3.45
36	980	-3.68	-0.45	-0.46	10	-3.50	-3.35	0.14	44	-0.04	2.41	5.29	3.37
56	958	-3.69	-0.45	-0.46	10	-3.50	-3.34	0.15	45	-0.11	2.43	5.25	3.34
75	951	-3.69	-0.45	-0.46	12	-3.45	-3.33	0.11	44	-0.04	2.41	5.26	3.45
49	934	-3.69	-0.45	-0.46	10	-3.57	-3.42	0.14	44	-0.09	2.43	5.33	3.30
19	933	-3.69	-0.45	-0.46	10	-3.41	-3.22	0.19	44	0.04	2.40	5.37	3.42
92	907	-3.69	-0.46	-0.46	12	-3.52	-3.36	0.16	43	-0.06	2.41	5.25	3.47
87	890	-3.69	-0.46	-0.46	10	-3.54	-3.35	0.18	45	-0.02	2.42	5.08	3.28
31	888	-3.69	-0.46	-0.46	10	-3.42	-3.30	0.11	44	-0.09	2.40	5.13	3.43
23	880	-3.69	-0.46	-0.46	10	-3.47	-3.27	0.20	43	-0.02	2.40	5.32	3.40
78	870	-3.69	-0.46	-0.46	12	-3.44	-3.26	0.17	44	0.13	2.40	5.31	3.43
71	848	-3.69	-0.46	-0.46	10	-3.37	-3.19	0.18	44	0.04	2.40	5.28	3.37
66	815	-3.69	-0.46	-0.47	10	-3.49	-3.30	0.19	45	-0.11	2.41	5.19	3.45
60	807	-3.70	-0.46	-0.47	8	-3.42	-3.25	0.17	44	-0.22	2.41	5.40	3.39
29	793	-3.70	-0.46	-0.47	12	-3.45	-3.29	0.15	44	0.09	2.42	5.38	3.43
79	747	-3.70	-0.47	-0.47	10	-3.55	-3.34	0.21	44	-0.13	2.41	5.26	3.42
84	722	-3.70	-0.47	-0.47	8	-3.32	-3.17	0.14	44	-0.22	2.40	5.23	3.39
99	713	-3.70	-0.47	-0.47	10	-3.45	-3.25	0.19	45	0.33	2.40	5.17	3.44
89	708	-3.70	-0.47	-0.47	10	-3.40	-3.30	0.10	43	0.11	2.42	5.44	3.41
85	708	-3.70	-0.47	-0.47	12	-3.57	-3.30	0.26	43	-0.02	2.43	5.48	3.43
51	701	-3.70	-0.47	-0.47	12	-3.57	-3.40	0.16	44	-0.09	2.41	5.15	3.33
16	672	-3.70	-0.47	-0.48	10	-3.60	-3.41	0.19	44	-0.13	2.43	5.23	3.40
68	650	-3.71	-0.47	-0.48	10	-3.55	-3.42	0.13	45	-0.15	2.43	5.23	3.43
44	635	-3.71	-0.47	-0.48	10	-3.45	-3.29	0.16	46	0.00	2.42	5.39	3.42
41	620	-3.71	-0.47	-0.48	12	-3.59	-3.40	0.19	45	-0.06	2.44	5.26	3.45
59	597	-3.71	-0.48	-0.48	12	-3.53	-3.30	0.23	44	0.00	2.40	5.05	3.41
83	592	-3.71	-0.48	-0.48	10	-3.47	-3.23	0.24	45	-0.06	2.41	5.22	3.36
33	530	-3.71	-0.48	-0.49	14	-3.47	-3.39	0.08	45	-0.06	2.42	5.23	3.36
91	521	-3.71	-0.48	-0.49	12	-3.49	-3.36	0.13	44	-0.09	2.43	5.34	3.43
74	505	-3.72	-0.48	-0.49	10	-3.43	-3.26	0.16	45	-0.11	2.44	5.31	3.40
34	497	-3.72	-0.48	-0.49	10	-3.57	-3.37	0.19	44	-0.04	2.43	5.29	3.42
6	467	-3.72	-0.48	-0.49	12	-3.50	-3.36	0.14	45	-0.06	2.43	5.15	3.46
63	459	-3.72	-0.49	-0.49	12	-3.44	-3.27	0.16	45	0.02	2.44	5.38	3.44
73	454	-3.72	-0.49	-0.49	10	-3.39	-3.18	0.21	46	-0.04	2.41	5.02	3.32
09	444	-3.72	-0.49	-0.49	10	-3.49	-3.32	0.17	44	-0.04	2.41	5.26	3.54
77	439	-3.72	-0.49	-0.49	12	-3.55	-3.35	0.20	45	-0.06	2.43	5.32	3.42
64	428	-3.72	-0.49	-0.49	10	-3.48	-3.28	0.19	46	-0.04	2.41	5.08	3.43
10	415	-3.72	-0.49	-0.49	12	-3.56	-3.37	0.18	45	0.11	2.40	5.21	3.58
86	397	-3.72	-0.49	-0.49	10	-3.52	-3.36	0.16	44	-0.18	2.42	5.10	3.38
2	381	-3.72	-0.49	-0.50	8	-3.43	-3.23	0.20	45	-0.11	2.41	5.05	3.27
3	364	-3.72	-0.49	-0.50	10	-3.51	-3.27	0.23	43	-0.06	2.42	5.36	3.31
7	247	-3.73	-0.50	-0.50	8	-3.46	-3.25	0.20	43	-0.16	2.41	5.21	3.31
81	238	-3.73	-0.50	-0.51	8	-3.39	-3.24	0.15	45	-0.11	2.43	5.12	3.38
88	225	-3.73	-0.50	-0.51	12	-3.60	-3.38	0.21	46	-0.04	2.41	4.75	3.31
43	224	-3.73	-0.50	-0.51	10	-3.49	-3.30	0.18	44	-0.13	2.43	5.42	3.45
76	215	-3.73	-0.50	-0.51	10	-3.50	-3.26	0.24	44	-0.27	2.42	5.20	3.31
65	200	-3.74	-0.50	-0.51	10	-3.52	-3.27	0.24	44	0.04	2.43	5.31	3.45

80	173	-3.74	-0.50	-0.51	10	-3.49	-3.31	0.18	44	-0.04	2.43	5.30	3.36
18	0	-3.75	-0.52	-0.52	12	-3.52	-3.38	0.14	44	-0.04	2.44	5.27	3.43

Table SI40: Lowest energy configurations for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.






Figure SI21: Binding energy (E_b) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI22: Excess energy (E_{exc}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI23: Stabilization energy (E_{stab}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI24: Total magnetic moment (M_{tot}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI25: HOMO energy (E_{HOMO}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI26: LUMO energy (E_{LUMO}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI27: HOMO-LUMO energy gap (E_{gap}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI28: Total number of bonds (N_b) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI29: Average chemical order parameter (σ_{av}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI30: Average bond length (d_{av}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI31: Average effective coordination number (ECN_{av}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI32: Average radius (R_{av}) for the near-equiatomic Co_nMo_m subnanoalloys with $n + m = 2 - 15$.

5 Gas-phase Mo_nCo_m Subnanoalloys

Table SI41: Structural, energetic and electronic properties for MoCo cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
2	0	-0.99	0.64	-0.99	3	-3.44	-3.05	0.38	1	-1.00	1.97	1.00	0.98
1	0	-0.99	0.64	-0.99	3	-3.44	-3.05	0.38	1	-1.00	1.97	1.00	0.98

Table SI42: Structural, energetic and electronic properties for Mo_2Co cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
3	2	-2.11	-0.09	-0.75	1	-2.90	-2.45	0.45	3	-0.33	2.16	1.66	1.32
1	1	-2.11	-0.09	-0.75	1	-2.89	-2.45	0.44	3	-0.33	2.16	1.66	1.31
2	0	-2.11	-0.09	-0.75	1	-2.90	-2.45	0.45	3	-0.33	2.16	1.65	1.32

Table SI43: Structural, energetic and electronic properties for Mo_2Co_2 cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
5	1659	-1.94	0.47	-0.29	8	-3.24	-2.96	0.28	5	-0.60	2.23	2.24	1.53
2	1658	-1.94	0.47	-0.29	8	-3.24	-2.96	0.28	5	-0.60	2.23	2.24	1.53
3	1	-2.35	0.06	-0.70	4	-3.29	-2.97	0.32	6	-0.33	2.20	2.14	1.49
4	1	-2.35	0.06	-0.70	4	-3.29	-2.97	0.32	5	-0.20	2.20	2.13	1.49
1	0	-2.35	0.06	-0.70	4	-3.29	-2.97	0.31	6	-0.33	2.20	2.14	1.49

Table SI44: Structural, energetic and electronic properties for Mo₃Co₂ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
6	292	-2.67	0.07	-0.85	6	-3.30	-2.89	0.40	9	-0.33	2.36	3.17	1.94
7	286	-2.67	0.07	-0.85	6	-3.20	-2.91	0.29	9	-0.11	2.28	2.56	1.80
0	285	-2.67	0.07	-0.85	6	-3.20	-2.91	0.28	9	-0.11	2.28	2.56	1.80
8	243	-2.68	0.06	-0.86	6	-3.20	-2.93	0.27	9	-0.11	2.33	3.00	1.88
1	243	-2.68	0.06	-0.86	6	-3.20	-2.93	0.27	9	-0.11	2.33	3.00	1.88
2	226	-2.68	0.05	-0.86	4	-3.20	-2.91	0.29	9	-0.33	2.28	2.75	1.62
3	1	-2.73	0.01	-0.91	4	-3.48	-2.89	0.59	8	0.00	2.29	2.84	1.69
5	0	-2.73	0.01	-0.91	4	-3.48	-2.89	0.59	8	0.00	2.29	2.84	1.69

Table SI45: Structural, energetic and electronic properties for Mo₃Co₃ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
6	787	-2.90	0.0613	-0.96	7	-3.25	-3.13	0.11	12	-0.33	2.35	3.68	1.78
5	786	-2.90	0.0612	-0.96	7	-3.25	-3.13	0.11	12	-0.33	2.35	3.68	1.78
11	683	-2.92	0.0439	-0.98	7	-3.28	-3.16	0.11	12	-0.33	2.36	3.97	1.75
18	683	-2.92	0.0438	-0.98	7	-3.28	-3.16	0.11	12	-0.33	2.36	3.97	1.75
3	680	-2.92	0.0435	-0.98	7	-3.28	-3.16	0.11	12	-0.33	2.36	3.97	1.75
10	680	-2.92	0.0435	-0.98	7	-3.28	-3.16	0.11	12	-0.33	2.36	3.97	1.75
13	605	-2.93	0.0310	-0.99	5	-3.12	-2.91	0.20	12	-0.33	2.35	3.87	1.77
16	603	-2.93	0.0306	-0.99	5	-3.12	-2.91	0.20	12	-0.33	2.35	3.87	1.77
15	591	-2.93	0.0286	-0.99	3	-3.07	-2.81	0.26	13	-0.23	2.34	3.86	1.76
12	0	-3.03	-0.0699	-1.09	7	-3.60	-3.31	0.29	12	0.00	2.35	3.78	1.68
20	0	-3.03	-0.0699	-1.09	7	-3.60	-3.31	0.29	12	0.00	2.35	3.78	1.68
19	0	-3.03	-0.0699	-1.09	7	-3.60	-3.31	0.29	12	0.00	2.35	3.78	1.68
9	0	-3.03	-0.0699	-1.09	7	-3.60	-3.31	0.29	12	0.00	2.35	3.78	1.68
14	0	-3.03	-0.0700	-1.09	7	-3.60	-3.31	0.29	12	0.00	2.35	3.78	1.68
1	0	-3.03	-0.0700	-1.09	7	-3.60	-3.31	0.29	12	0.00	2.35	3.78	1.68
7	0	-3.03	-0.0700	-1.09	7	-3.60	-3.31	0.29	12	0.00	2.35	3.78	1.68
2	0	-3.03	-0.0700	-1.09	7	-3.60	-3.31	0.29	12	0.00	2.35	3.78	1.68

Table SI46: Structural, energetic and electronic properties for Mo₄Co₃ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
25	558	-3.10	-0.01	-0.83	9	-3.32	-3.14	0.18	16	0.00	2.37	3.51	2.00
28	558	-3.10	-0.01	-0.83	9	-3.32	-3.14	0.18	16	0.00	2.37	3.50	2.00
5	537	-3.10	-0.02	-0.83	7	-3.18	-3.09	0.09	16	-0.25	2.39	3.92	1.96
12	518	-3.11	-0.02	-0.83	7	-3.27	-3.08	0.20	16	-0.25	2.37	3.73	2.00
15	518	-3.11	-0.02	-0.83	7	-3.27	-3.08	0.20	16	-0.25	2.37	3.73	2.00
11	465	-3.11	-0.03	-0.84	7	-3.36	-3.20	0.16	16	-0.25	2.39	3.98	1.93
34	465	-3.11	-0.03	-0.84	7	-3.36	-3.20	0.16	16	-0.25	2.39	3.98	1.93
29	435	-3.12	-0.03	-0.85	7	-3.37	-3.03	0.34	14	-0.29	2.36	3.48	2.01
20	434	-3.12	-0.03	-0.85	7	-3.37	-3.03	0.34	14	-0.29	2.36	3.48	2.01
31	431	-3.12	-0.03	-0.85	7	-3.39	-3.09	0.30	16	-0.25	2.38	3.71	1.99
8	430	-3.12	-0.03	-0.85	7	-3.39	-3.09	0.29	16	-0.25	2.38	3.72	1.99
22	430	-3.12	-0.03	-0.85	7	-3.39	-3.09	0.30	16	-0.25	2.38	3.71	1.99
2	430	-3.12	-0.03	-0.85	7	-3.39	-3.09	0.30	16	-0.25	2.38	3.71	1.99
9	365	-3.13	-0.04	-0.86	5	-3.24	-2.94	0.30	16	-0.25	2.38	3.97	1.93
32	337	-3.13	-0.05	-0.86	7	-3.27	-3.08	0.19	16	0.00	2.38	3.83	2.01
1	303	-3.14	-0.05	-0.86	7	-3.36	-3.13	0.23	15	0.20	2.38	4.03	2.14
26	255	-3.14	-0.06	-0.87	7	-3.38	-3.04	0.34	14	0.00	2.35	3.45	2.01
23	254	-3.14	-0.06	-0.87	7	-3.38	-3.04	0.34	14	0.00	2.35	3.45	2.01
10	141	-3.16	-0.07	-0.89	7	-3.29	-2.93	0.36	15	-0.07	2.39	3.94	2.18
13	141	-3.16	-0.07	-0.89	7	-3.29	-2.93	0.36	15	-0.07	2.39	3.94	2.18
30	139	-3.16	-0.07	-0.89	7	-3.29	-2.93	0.36	15	-0.07	2.39	3.94	2.18
24	139	-3.16	-0.07	-0.89	7	-3.29	-2.92	0.36	15	-0.07	2.40	3.94	2.18
4	114	-3.16	-0.08	-0.89	7	-3.26	-2.96	0.30	14	0.14	2.35	3.57	1.98
6	114	-3.16	-0.08	-0.89	7	-3.26	-2.96	0.30	14	0.14	2.35	3.57	1.98
17	93	-3.17	-0.08	-0.89	7	-3.43	-3.14	0.29	15	-0.20	2.42	4.17	2.33
19	67	-3.17	-0.08	-0.90	7	-3.30	-3.02	0.28	16	0.00	2.38	3.84	2.00
35	66	-3.17	-0.09	-0.90	7	-3.33	-3.03	0.30	14	0.14	2.34	3.42	2.01
33	66	-3.17	-0.09	-0.90	7	-3.33	-3.03	0.30	14	0.14	2.34	3.43	2.01
7	50	-3.17	-0.09	-0.90	7	-3.39	-3.01	0.39	15	-0.20	2.42	4.05	2.25
3	50	-3.17	-0.09	-0.90	7	-3.39	-3.01	0.39	15	-0.20	2.42	4.05	2.25
21	1	-3.18	-0.09	-0.91	5	-3.30	-2.99	0.31	16	-0.25	2.38	3.81	2.15
27	0	-3.18	-0.09	-0.91	5	-3.30	-2.99	0.31	16	-0.25	2.38	3.81	2.15

Table SI47: Structural, energetic and electronic properties for Mo₄Co₄ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
48	991	-3.14	0.02	-0.69	6	-3.27	-3.03	0.23	19	-0.26	2.38	4.36	2.19
41	990	-3.14	0.02	-0.69	6	-3.27	-3.03	0.23	19	-0.26	2.38	4.36	2.19

62	855	-3.15	0.01	-0.71	10	-3.41	-3.24	0.16	17	-0.29	2.37	3.92	2.08
9	854	-3.15	0.01	-0.71	10	-3.40	-3.24	0.16	17	-0.29	2.37	3.92	2.08
29	804	-3.16	0.00	-0.72	6	-3.27	-2.99	0.28	20	-0.40	2.39	4.22	2.29
42	793	-3.16	0.00	-0.72	8	-3.44	-3.17	0.27	17	-0.41	2.37	4.04	2.11
52	725	-3.17	-0.00	-0.73	10	-3.47	-3.31	0.15	19	-0.26	2.37	3.92	2.22
57	725	-3.17	-0.00	-0.73	10	-3.47	-3.31	0.15	19	-0.26	2.37	3.92	2.22
6	725	-3.17	-0.00	-0.73	10	-3.47	-3.31	0.15	20	-0.20	2.37	3.92	2.22
51	725	-3.17	-0.00	-0.73	10	-3.47	-3.31	0.15	20	-0.20	2.37	3.92	2.22
43	686	-3.17	-0.00	-0.73	8	-3.41	-3.16	0.24	18	-0.33	2.36	3.79	2.17
28	686	-3.17	-0.00	-0.73	8	-3.41	-3.16	0.24	18	-0.33	2.36	3.79	2.17
31	652	-3.18	-0.01	-0.74	10	-3.43	-3.23	0.20	18	-0.11	2.37	3.86	2.18
59	651	-3.18	-0.01	-0.74	10	-3.43	-3.23	0.20	18	-0.11	2.37	3.86	2.18
15	644	-3.18	-0.01	-0.74	8	-3.46	-3.16	0.30	18	-0.33	2.39	4.14	2.19
26	643	-3.18	-0.01	-0.74	8	-3.46	-3.16	0.30	18	-0.33	2.39	4.14	2.19
13	643	-3.18	-0.01	-0.74	8	-3.46	-3.16	0.30	18	-0.33	2.39	4.14	2.19
56	641	-3.18	-0.01	-0.74	8	-3.46	-3.16	0.30	18	-0.33	2.39	4.14	2.19
49	638	-3.18	-0.01	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.98	2.23
68	638	-3.18	-0.01	-0.74	10	-3.36	-3.18	0.18	19	0.05	2.36	3.81	2.12
54	638	-3.18	-0.01	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.98	2.23
11	638	-3.18	-0.01	-0.74	10	-3.36	-3.18	0.18	19	0.05	2.36	3.81	2.12
27	638	-3.18	-0.01	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.98	2.23
46	637	-3.18	-0.01	-0.74	10	-3.36	-3.18	0.18	19	0.05	2.36	3.81	2.12
36	637	-3.18	-0.01	-0.74	8	-3.39	-3.12	0.27	20	-0.20	2.35	3.98	2.23
38	637	-3.18	-0.01	-0.74	10	-3.36	-3.18	0.18	19	0.05	2.36	3.81	2.12
8	625	-3.18	-0.01	-0.74	8	-3.42	-3.11	0.31	19	-0.26	2.35	3.68	2.49
66	624	-3.18	-0.01	-0.74	8	-3.42	-3.11	0.31	19	-0.26	2.35	3.68	2.49
7	611	-3.18	-0.01	-0.74	8	-3.44	-3.16	0.28	18	-0.11	2.37	3.92	2.18
32	580	-3.19	-0.02	-0.74	6	-3.37	-3.06	0.31	20	-0.20	2.38	4.16	2.23
47	548	-3.19	-0.02	-0.75	10	-3.40	-3.11	0.29	20	-0.20	2.36	4.07	2.21
55	466	-3.20	-0.03	-0.76	8	-3.42	-3.16	0.25	18	-0.33	2.38	4.17	2.10
16	465	-3.20	-0.03	-0.76	8	-3.42	-3.16	0.25	18	-0.33	2.38	4.17	2.10
4	386	-3.21	-0.04	-0.77	10	-3.37	-3.19	0.17	18	0.11	2.39	4.05	2.10
67	386	-3.21	-0.04	-0.77	10	-3.37	-3.19	0.17	18	0.11	2.39	4.05	2.10
40	324	-3.22	-0.05	-0.78	8	-3.44	-3.22	0.21	17	-0.17	2.34	3.75	2.15
12	323	-3.22	-0.05	-0.78	8	-3.43	-3.22	0.21	17	-0.17	2.34	3.75	2.15
60	296	-3.22	-0.05	-0.78	10	-3.39	-3.28	0.11	18	0.00	2.38	3.89	2.27
25	296	-3.22	-0.05	-0.78	10	-3.39	-3.28	0.11	19	-0.05	2.38	3.90	2.27
53	182	-3.24	-0.07	-0.79	8	-3.15	-3.10	0.05	19	0.05	2.39	4.31	2.23
2	181	-3.24	-0.07	-0.79	8	-3.15	-3.10	0.05	20	0.00	2.39	4.31	2.23
39	140	-3.24	-0.07	-0.80	8	-3.40	-3.14	0.25	20	0.00	2.39	4.32	2.17
64	140	-3.24	-0.07	-0.80	8	-3.40	-3.14	0.25	20	0.00	2.39	4.32	2.17
65	131	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
20	130	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
45	129	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
44	129	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
14	129	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
17	129	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
58	129	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
22	128	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
35	128	-3.24	-0.07	-0.80	8	-3.40	-3.18	0.21	19	-0.15	2.42	4.44	2.26
3	118	-3.25	-0.08	-0.80	8	-3.37	-3.11	0.26	19	0.05	2.38	4.03	2.22
33	117	-3.25	-0.08	-0.80	8	-3.37	-3.11	0.26	20	0.00	2.38	4.03	2.22
10	75	-3.25	-0.08	-0.81	8	-3.23	-3.00	0.22	18	0.11	2.38	4.20	2.16
61	74	-3.25	-0.08	-0.81	8	-3.23	-3.00	0.22	18	0.11	2.38	4.20	2.16
37	73	-3.25	-0.08	-0.81	8	-3.23	-3.00	0.22	18	0.11	2.38	4.20	2.16
70	58	-3.25	-0.08	-0.81	8	-3.29	-3.02	0.26	19	0.05	2.37	4.04	2.21
21	58	-3.25	-0.08	-0.81	8	-3.29	-3.02	0.26	19	0.05	2.37	4.04	2.21
50	58	-3.25	-0.08	-0.81	8	-3.29	-3.02	0.26	19	0.05	2.37	4.04	2.21

1	57	-3.25	-0.08	-0.81	8	-3.29	-3.02	0.26	19	0.05	2.37	4.04	2.21
23	23	-3.26	-0.09	-0.81	8	-3.43	-3.14	0.28	19	-0.15	2.41	4.36	2.34
5	23	-3.26	-0.09	-0.81	8	-3.43	-3.15	0.28	19	-0.15	2.41	4.36	2.34
63	22	-3.26	-0.09	-0.81	8	-3.43	-3.15	0.28	19	-0.15	2.41	4.36	2.34
30	22	-3.26	-0.09	-0.81	8	-3.43	-3.15	0.28	19	-0.15	2.41	4.36	2.34
18	12	-3.26	-0.09	-0.82	6	-3.26	-3.00	0.26	19	0.05	2.37	4.21	2.24
24	0	-3.26	-0.09	-0.82	8	-3.35	-3.18	0.17	20	-0.20	2.41	4.33	2.27

Table SI48: Structural, energetic and electronic properties for Mo₅Co₄ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
20	1457	-3.26	0.07	-0.61	10	-3.30	-3.16	0.14	21	-0.14	2.41	4.29	2.17
17	1455	-3.26	0.07	-0.61	10	-3.30	-3.15	0.14	21	-0.14	2.41	4.29	2.17
59	877	-3.32	0.01	-0.67	10	-3.31	-3.14	0.17	21	-0.23	2.41	4.32	2.16
34	876	-3.32	0.01	-0.67	10	-3.31	-3.14	0.17	21	-0.23	2.41	4.32	2.17
93	876	-3.32	0.01	-0.67	10	-3.31	-3.14	0.17	21	-0.23	2.41	4.32	2.16
73	876	-3.32	0.01	-0.67	10	-3.31	-3.14	0.17	21	-0.23	2.41	4.32	2.16
8	876	-3.32	0.01	-0.67	10	-3.31	-3.14	0.17	21	-0.23	2.41	4.32	2.16
50	781	-3.34	0.00	-0.68	8	-3.38	-3.23	0.14	21	-0.14	2.38	4.22	2.09
91	780	-3.34	0.00	-0.68	8	-3.38	-3.24	0.14	21	-0.14	2.38	4.22	2.09
13	653	-3.35	-0.01	-0.70	10	-3.31	-3.11	0.19	21	0.23	2.40	4.15	2.14
16	652	-3.35	-0.01	-0.70	10	-3.30	-3.10	0.19	21	0.23	2.40	4.15	2.14
6	625	-3.35	-0.01	-0.70	8	-3.41	-3.08	0.32	21	-0.23	2.37	3.99	2.34
33	625	-3.35	-0.01	-0.70	8	-3.41	-3.08	0.32	21	-0.23	2.37	3.98	2.34
92	624	-3.35	-0.01	-0.70	8	-3.41	-3.08	0.32	21	-0.23	2.37	3.98	2.34
61	623	-3.35	-0.01	-0.70	8	-3.41	-3.08	0.33	21	-0.23	2.37	3.99	2.34
58	622	-3.35	-0.01	-0.70	8	-3.41	-3.08	0.33	21	-0.23	2.37	3.99	2.34
64	621	-3.35	-0.01	-0.70	8	-3.32	-3.03	0.28	20	-0.10	2.38	4.09	2.15
46	621	-3.35	-0.01	-0.70	8	-3.32	-3.03	0.28	20	-0.10	2.38	4.09	2.15
99	620	-3.35	-0.01	-0.70	8	-3.32	-3.03	0.29	20	-0.10	2.38	4.08	2.15
60	620	-3.35	-0.01	-0.70	8	-3.32	-3.03	0.28	20	-0.10	2.38	4.09	2.15
51	619	-3.35	-0.01	-0.70	8	-3.32	-3.03	0.29	20	-0.10	2.38	4.08	2.15
12	549	-3.36	-0.02	-0.71	10	-3.36	-3.18	0.18	21	-0.14	2.41	4.37	2.20
84	549	-3.36	-0.02	-0.71	10	-3.36	-3.18	0.18	21	-0.14	2.41	4.37	2.20
45	548	-3.36	-0.02	-0.71	10	-3.37	-3.18	0.18	21	-0.14	2.41	4.37	2.20
69	548	-3.36	-0.02	-0.71	10	-3.36	-3.18	0.18	21	-0.14	2.41	4.37	2.20
77	548	-3.36	-0.02	-0.71	10	-3.36	-3.18	0.18	21	-0.14	2.41	4.37	2.20
72	544	-3.36	-0.02	-0.71	10	-3.33	-3.21	0.11	21	-0.23	2.41	4.35	2.16
29	544	-3.36	-0.02	-0.71	10	-3.33	-3.22	0.11	21	-0.23	2.41	4.35	2.16
3	523	-3.36	-0.02	-0.71	8	-3.31	-3.04	0.27	21	-0.14	2.40	4.33	2.33
76	492	-3.37	-0.03	-0.72	8	-3.34	-3.10	0.24	21	-0.23	2.40	4.41	2.21
1	492	-3.37	-0.03	-0.72	8	-3.34	-3.10	0.24	21	-0.23	2.40	4.41	2.21
88	492	-3.37	-0.03	-0.72	8	-3.34	-3.09	0.24	21	-0.23	2.40	4.41	2.22
81	492	-3.37	-0.03	-0.72	8	-3.34	-3.10	0.24	21	-0.23	2.40	4.41	2.21
48	492	-3.37	-0.03	-0.72	8	-3.33	-3.10	0.23	21	-0.23	2.40	4.41	2.21
98	491	-3.37	-0.03	-0.72	8	-3.34	-3.10	0.24	21	-0.23	2.40	4.41	2.21
25	491	-3.37	-0.03	-0.72	8	-3.34	-3.09	0.24	21	-0.23	2.40	4.40	2.21
53	491	-3.37	-0.03	-0.72	8	-3.34	-3.10	0.24	21	-0.23	2.40	4.41	2.21
42	491	-3.37	-0.03	-0.72	8	-3.34	-3.09	0.24	21	-0.23	2.40	4.41	2.21

0	491	-3.37	-0.03	-0.72	10	-3.26	-3.06	0.19	20	0.20	2.39	4.17	2.13
95	491	-3.37	-0.03	-0.72	8	-3.34	-3.10	0.24	21	-0.23	2.40	4.41	2.21
79	491	-3.37	-0.03	-0.72	8	-3.34	-3.09	0.24	21	-0.23	2.40	4.41	2.21
30	491	-3.37	-0.03	-0.72	8	-3.34	-3.09	0.24	21	-0.23	2.40	4.41	2.21
54	490	-3.37	-0.03	-0.72	10	-3.26	-3.06	0.19	20	0.20	2.39	4.17	2.13
80	490	-3.37	-0.03	-0.72	8	-3.34	-3.10	0.24	21	-0.23	2.40	4.41	2.21
36	490	-3.37	-0.03	-0.72	8	-3.34	-3.09	0.24	21	-0.23	2.40	4.41	2.21
10	490	-3.37	-0.03	-0.72	10	-3.26	-3.07	0.19	20	0.20	2.39	4.17	2.13
62	486	-3.37	-0.03	-0.72	8	-3.35	-3.07	0.27	21	-0.04	2.38	4.18	2.27
97	486	-3.37	-0.03	-0.72	8	-3.35	-3.07	0.27	21	-0.04	2.38	4.18	2.27
63	486	-3.37	-0.03	-0.72	8	-3.35	-3.07	0.27	21	-0.04	2.38	4.18	2.27
18	484	-3.37	-0.03	-0.72	8	-3.35	-3.07	0.27	21	-0.04	2.38	4.18	2.27
96	477	-3.37	-0.03	-0.72	8	-3.38	-3.13	0.24	21	-0.04	2.37	4.07	2.29
21	476	-3.37	-0.03	-0.72	8	-3.38	-3.13	0.24	21	-0.04	2.37	4.06	2.29
41	476	-3.37	-0.03	-0.72	8	-3.38	-3.13	0.24	21	-0.04	2.37	4.07	2.29
15	475	-3.37	-0.03	-0.72	8	-3.38	-3.13	0.25	21	-0.04	2.37	4.07	2.29
26	460	-3.37	-0.03	-0.72	8	-3.35	-3.11	0.24	21	-0.23	2.41	4.26	2.19
5	459	-3.37	-0.03	-0.72	8	-3.36	-3.11	0.24	21	-0.23	2.41	4.26	2.19
66	459	-3.37	-0.03	-0.72	8	-3.36	-3.11	0.25	21	-0.23	2.41	4.25	2.19
27	453	-3.37	-0.03	-0.72	10	-3.27	-3.04	0.23	21	0.14	2.42	4.44	2.25
22	453	-3.37	-0.03	-0.72	10	-3.27	-3.04	0.23	21	0.14	2.42	4.44	2.25
78	452	-3.37	-0.03	-0.72	10	-3.27	-3.04	0.23	21	0.14	2.42	4.44	2.25
24	449	-3.37	-0.03	-0.72	6	-3.29	-2.98	0.30	21	-0.14	2.39	4.21	2.30
32	449	-3.37	-0.03	-0.72	6	-3.29	-2.98	0.30	21	-0.14	2.39	4.21	2.30
4	443	-3.37	-0.03	-0.72	8	-3.29	-2.99	0.30	20	-0.20	2.39	4.14	2.12
74	441	-3.37	-0.03	-0.72	8	-3.29	-2.99	0.30	20	-0.20	2.39	4.14	2.12
11	426	-3.37	-0.03	-0.72	4	-3.21	-2.88	0.32	21	-0.14	2.36	4.34	2.27
43	423	-3.37	-0.03	-0.72	6	-3.33	-3.09	0.23	21	-0.33	2.41	4.36	2.36
83	421	-3.38	-0.03	-0.72	6	-3.36	-3.10	0.26	21	-0.33	2.40	4.26	2.37
2	421	-3.38	-0.03	-0.72	6	-3.33	-3.10	0.23	21	-0.33	2.41	4.35	2.36
14	400	-3.38	-0.04	-0.73	8	-3.25	-3.07	0.17	21	-0.23	2.39	4.25	2.33
07	399	-3.38	-0.04	-0.73	8	-3.19	-3.00	0.18	21	-0.23	2.41	4.32	2.34
57	249	-3.39	-0.05	-0.74	8	-3.19	-3.00	0.19	21	0.14	2.39	4.23	2.26
94	249	-3.39	-0.05	-0.74	8	-3.19	-3.00	0.19	21	0.14	2.39	4.23	2.26
28	5	-3.42	-0.08	-0.77	6	-3.39	-2.99	0.40	21	-0.14	2.41	4.49	2.30
55	4	-3.42	-0.08	-0.77	6	-3.39	-2.99	0.40	21	-0.14	2.41	4.49	2.30
90	3	-3.42	-0.08	-0.77	6	-3.39	-2.99	0.40	21	-0.14	2.41	4.49	2.30
19	2	-3.42	-0.08	-0.77	6	-3.39	-2.99	0.40	21	-0.14	2.41	4.49	2.30
47	2	-3.42	-0.08	-0.77	6	-3.39	-2.99	0.40	21	-0.14	2.41	4.49	2.30
70	1	-3.42	-0.08	-0.77	8	-3.32	-3.04	0.28	21	0.04	2.40	4.35	2.28
9	1	-3.42	-0.08	-0.77	8	-3.32	-3.04	0.28	21	0.04	2.40	4.35	2.28
38	1	-3.42	-0.08	-0.77	8	-3.33	-3.04	0.28	21	0.04	2.40	4.35	2.28
68	1	-3.42	-0.08	-0.77	8	-3.32	-3.04	0.28	21	0.04	2.40	4.35	2.28
40	1	-3.42	-0.08	-0.77	8	-3.33	-3.04	0.28	21	0.04	2.40	4.35	2.28
89	0	-3.42	-0.08	-0.77	8	-3.32	-3.04	0.28	21	0.04	2.40	4.35	2.28
56	0	-3.42	-0.08	-0.77	8	-3.32	-3.04	0.28	21	0.04	2.40	4.35	2.28
44	0	-3.42	-0.08	-0.77	8	-3.33	-3.04	0.28	21	0.04	2.40	4.35	2.28
23	0	-3.42	-0.08	-0.77	8	-3.32	-3.04	0.28	21	0.04	2.40	4.35	2.28
82	0	-3.42	-0.08	-0.77	8	-3.32	-3.04	0.28	21	0.04	2.40	4.35	2.28
31	0	-3.42	-0.08	-0.77	8	-3.32	-3.04	0.28	21	0.04	2.40	4.35	2.28

Table SI49: Structural, energetic and electronic properties for Mo₅Co₅ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
30	1262	-3.34	-0.07	-0.58	7	-3.32	-3.09	0.23	24	-0.25	2.37	4.23	2.54
85	1218	-3.34	-0.08	-0.59	9	-3.25	-3.07	0.18	24	-0.25	2.36	3.98	2.48
63	1199	-3.34	-0.08	-0.59	7	-3.23	-3.07	0.15	24	-0.08	2.35	4.07	2.54
87	1193	-3.34	-0.08	-0.59	11	-3.37	-3.21	0.16	24	-0.25	2.37	4.05	2.44
55	1042	-3.36	-0.10	-0.61	9	-3.35	-3.18	0.17	25	-0.28	2.39	4.44	2.46
47	1029	-3.36	-0.10	-0.61	9	-3.17	-3.06	0.11	25	-0.04	2.35	3.99	2.77
88	922	-3.37	-0.11	-0.62	9	-3.44	-3.20	0.24	25	-0.12	2.40	4.39	2.63
36	848	-3.38	-0.12	-0.62	11	-3.42	-3.19	0.24	23	-0.04	2.37	4.01	2.46
86	846	-3.38	-0.12	-0.62	11	-3.42	-3.19	0.24	23	-0.04	2.37	4.01	2.46
14	833	-3.38	-0.12	-0.63	13	-3.38	-3.30	0.08	24	-0.08	2.42	4.45	2.61
67	822	-3.38	-0.12	-0.63	7	-3.24	-3.06	0.19	22	-0.18	2.35	4.11	2.56
48	781	-3.39	-0.12	-0.63	11	-3.34	-3.21	0.13	25	-0.28	2.42	4.44	2.89
54	772	-3.39	-0.12	-0.63	11	-3.38	-3.22	0.16	24	0.00	2.39	4.34	2.68
80	772	-3.39	-0.12	-0.63	11	-3.38	-3.22	0.17	24	0.00	2.39	4.34	2.67
1	757	-3.39	-0.12	-0.63	9	-3.32	-3.12	0.21	24	-0.17	2.40	4.35	2.65
28	749	-3.39	-0.13	-0.63	9	-3.38	-3.11	0.27	24	-0.17	2.41	4.34	2.90
17	724	-3.39	-0.13	-0.64	11	-3.29	-3.23	0.06	24	-0.25	2.42	4.61	2.37
29	710	-3.39	-0.13	-0.64	11	-3.38	-3.18	0.20	24	-0.17	2.40	4.26	2.72
79	705	-3.39	-0.13	-0.64	9	-3.36	-3.19	0.17	24	0.00	2.36	3.94	2.43
15	701	-3.39	-0.13	-0.64	9	-3.36	-3.19	0.18	24	-0.17	2.40	4.43	2.49
4	683	-3.39	-0.13	-0.64	11	-3.25	-3.20	0.05	24	-0.17	2.40	4.38	2.71
91	680	-3.40	-0.13	-0.64	9	-3.40	-3.12	0.28	25	-0.28	2.40	4.27	2.73
75	661	-3.40	-0.13	-0.64	9	-3.52	-3.36	0.16	22	-0.18	2.34	3.84	2.17
83	649	-3.40	-0.14	-0.64	11	-3.38	-3.15	0.23	23	0.22	2.38	4.05	2.52
31	648	-3.40	-0.14	-0.64	11	-3.37	-3.15	0.22	23	0.22	2.38	4.05	2.52
89	636	-3.40	-0.14	-0.65	11	-3.36	-3.19	0.17	24	-0.25	2.41	4.46	2.58
25	630	-3.40	-0.14	-0.65	9	-3.36	-3.19	0.17	23	-0.13	2.38	4.13	2.58
78	624	-3.40	-0.14	-0.65	11	-3.37	-3.20	0.17	24	-0.08	2.40	4.24	2.50
10	605	-3.40	-0.14	-0.65	9	-3.36	-3.13	0.22	25	-0.12	2.42	4.41	2.57
60	598	-3.40	-0.14	-0.65	9	-3.40	-3.19	0.21	23	-0.22	2.36	3.94	2.34
93	597	-3.40	-0.14	-0.65	11	-3.36	-3.19	0.17	26	-0.15	2.43	4.54	2.54
38	576	-3.41	-0.14	-0.65	9	-3.40	-3.09	0.31	24	-0.25	2.39	4.26	2.81
76	574	-3.41	-0.14	-0.65	9	-3.40	-3.22	0.18	22	-0.18	2.36	4.01	2.28
7	560	-3.41	-0.14	-0.65	9	-3.28	-3.09	0.19	24	-0.17	2.39	4.33	2.72
50	560	-3.41	-0.14	-0.65	9	-3.28	-3.09	0.19	24	-0.17	2.39	4.33	2.72
72	560	-3.41	-0.14	-0.65	9	-3.28	-3.09	0.19	24	-0.17	2.39	4.33	2.72
24	559	-3.41	-0.14	-0.65	9	-3.28	-3.09	0.19	24	-0.17	2.39	4.33	2.72
81	558	-3.41	-0.14	-0.65	9	-3.28	-3.09	0.19	24	-0.17	2.39	4.33	2.72
45	551	-3.41	-0.15	-0.65	9	-3.32	-3.09	0.23	25	-0.12	2.42	4.59	2.73
20	548	-3.41	-0.15	-0.65	9	-3.32	-3.09	0.23	25	-0.12	2.42	4.59	2.73
26	546	-3.41	-0.15	-0.66	9	-3.44	-3.14	0.30	25	-0.20	2.40	4.37	2.48
53	537	-3.41	-0.15	-0.66	7	-3.43	-3.15	0.27	21	-0.05	2.33	3.73	2.33
34	534	-3.41	-0.15	-0.66	11	-3.44	-3.17	0.27	24	-0.25	2.42	4.41	2.63
90	534	-3.41	-0.15	-0.66	11	-3.44	-3.17	0.27	24	-0.25	2.42	4.41	2.63
61	533	-3.41	-0.15	-0.66	11	-3.44	-3.17	0.27	24	-0.25	2.42	4.41	2.63
65	532	-3.41	-0.15	-0.66	11	-3.44	-3.17	0.27	24	-0.25	2.42	4.40	2.63
11	532	-3.41	-0.15	-0.66	11	-3.44	-3.17	0.27	24	-0.25	2.42	4.41	2.63
40	531	-3.41	-0.15	-0.66	9	-3.35	-3.20	0.16	23	-0.22	2.35	3.89	2.24

69	521	-3.41	-0.15	-0.66	11	-3.31	-3.06	0.25	24	0.17	2.39	4.31	2.69
37	521	-3.41	-0.15	-0.66	11	-3.31	-3.06	0.25	24	0.17	2.39	4.31	2.69
27	519	-3.41	-0.15	-0.66	11	-3.31	-3.06	0.25	24	0.17	2.39	4.31	2.69
62	500	-3.41	-0.15	-0.66	9	-3.47	-3.16	0.31	24	-0.25	2.39	4.19	2.45
46	469	-3.42	-0.15	-0.66	9	-3.44	-3.17	0.27	24	-0.25	2.39	4.30	2.60
92	467	-3.42	-0.15	-0.66	9	-3.36	-3.09	0.26	25	-0.04	2.41	4.37	2.98
13	456	-3.42	-0.15	-0.66	9	-3.43	-3.20	0.24	24	0.00	2.37	4.22	2.57
96	448	-3.42	-0.16	-0.66	11	-3.31	-3.01	0.30	24	0.25	2.41	4.45	2.37
66	446	-3.42	-0.16	-0.66	9	-3.47	-3.15	0.32	24	-0.25	2.41	4.47	2.58
21	397	-3.42	-0.16	-0.67	9	-3.42	-3.21	0.20	24	-0.17	2.42	4.52	2.51
18	369	-3.43	-0.16	-0.67	9	-3.37	-3.18	0.20	24	-0.33	2.43	4.63	2.45
39	368	-3.43	-0.16	-0.67	9	-3.37	-3.17	0.19	24	-0.33	2.43	4.63	2.45
97	344	-3.43	-0.17	-0.68	11	-3.33	-3.08	0.25	24	0.08	2.40	4.18	2.53
42	330	-3.43	-0.17	-0.68	11	-3.40	-3.22	0.17	22	0.27	2.38	4.24	2.44
52	330	-3.43	-0.17	-0.68	11	-3.40	-3.22	0.17	23	0.22	2.38	4.24	2.44
70	329	-3.43	-0.17	-0.68	11	-3.40	-3.22	0.17	22	0.27	2.38	4.24	2.45
77	301	-3.43	-0.17	-0.68	11	-3.34	-3.12	0.22	23	0.22	2.40	4.39	2.60
5	300	-3.43	-0.17	-0.68	11	-3.35	-3.13	0.22	23	0.22	2.40	4.39	2.60
8	300	-3.43	-0.17	-0.68	11	-3.34	-3.12	0.22	23	0.22	2.40	4.39	2.60
9	300	-3.43	-0.17	-0.68	11	-3.34	-3.12	0.22	23	0.22	2.40	4.39	2.60
23	294	-3.43	-0.17	-0.68	9	-3.28	-3.00	0.28	22	-0.09	2.38	4.29	2.48
32	290	-3.43	-0.17	-0.68	9	-3.28	-3.00	0.28	22	-0.09	2.38	4.29	2.48
6	270	-3.44	-0.17	-0.68	9	-3.39	-3.05	0.34	24	0.00	2.42	4.53	2.58
98	270	-3.44	-0.17	-0.68	9	-3.38	-3.05	0.34	24	0.00	2.42	4.53	2.58
58	268	-3.44	-0.17	-0.68	9	-3.35	-3.09	0.26	24	0.08	2.39	4.34	2.46
94	266	-3.44	-0.17	-0.68	9	-3.35	-3.09	0.26	24	0.08	2.39	4.34	2.46
19	254	-3.44	-0.18	-0.68	11	-3.36	-3.09	0.27	24	0.08	2.40	4.32	2.64
95	253	-3.44	-0.18	-0.68	11	-3.36	-3.09	0.27	24	0.08	2.40	4.32	2.64
2	16	-3.46	-0.20	-0.71	7	-3.35	-3.10	0.25	27	-0.04	2.45	4.89	2.56
12	1	-3.46	-0.20	-0.71	11	-3.28	-3.22	0.07	24	0.08	2.41	4.50	2.41
59	0	-3.46	-0.20	-0.71	11	-3.28	-3.22	0.06	24	0.08	2.41	4.51	2.40
22	0	-3.46	-0.20	-0.71	11	-3.28	-3.22	0.07	24	0.08	2.41	4.50	2.41

Table SI50: Structural, energetic and electronic properties for Mo₆Co₅ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
78	1625	-3.43	0.02	-0.47	7	-3.28	-3.14	0.13	28	-0.28	2.38	4.66	2.74
71	1446	-3.44	0.01	-0.48	11	-3.36	-3.27	0.09	28	-0.21	2.40	4.39	2.80
87	1438	-3.44	0.00	-0.48	9	-3.42	-3.20	0.21	28	-0.14	2.39	4.36	2.78
84	1438	-3.44	0.00	-0.48	11	-3.44	-3.34	0.09	28	-0.21	2.42	4.48	2.81
28	1434	-3.45	0.00	-0.48	5	-3.13	-2.96	0.16	28	-0.28	2.37	4.73	2.85
10	1423	-3.45	0.00	-0.49	11	-3.44	-3.26	0.17	28	-0.07	2.42	4.64	2.81
65	1359	-3.45	0.00	-0.49	9	-3.37	-3.18	0.19	28	-0.21	2.41	4.58	2.77
82	1300	-3.46	-0.00	-0.50	7	-3.26	-3.08	0.18	29	-0.31	2.37	4.53	2.87
61	1296	-3.46	-0.00	-0.50	11	-3.34	-3.21	0.13	28	-0.14	2.41	4.36	2.85
69	1292	-3.46	-0.00	-0.50	9	-3.34	-3.07	0.26	28	-0.14	2.40	4.49	2.79
01	1231	-3.46	-0.00	-0.50	9	-3.30	-3.19	0.11	28	-0.14	2.38	4.36	2.74
94	1214	-3.46	-0.01	-0.50	7	-3.31	-3.11	0.19	28	-0.14	2.39	4.88	2.81
37	1207	-3.47	-0.01	-0.50	7	-3.30	-3.13	0.17	27	-0.25	2.40	4.46	3.06

54	1201	-3.47	-0.01	-0.51	9	-3.50	-3.21	0.28	29	-0.10	2.38	4.33	2.76
76	1197	-3.47	-0.01	-0.51	9	-3.39	-3.20	0.18	28	-0.21	2.37	4.35	2.88
14	1158	-3.47	-0.01	-0.51	7	-3.29	-3.09	0.20	28	-0.28	2.37	4.37	2.71
06	1147	-3.47	-0.01	-0.51	11	-3.38	-3.22	0.16	28	-0.21	2.42	4.73	2.79
64	1129	-3.47	-0.01	-0.51	11	-3.36	-3.18	0.17	28	-0.07	2.42	4.55	2.83
50	1112	-3.47	-0.02	-0.51	5	-3.18	-2.91	0.26	29	-0.31	2.36	4.53	2.84
25	1086	-3.48	-0.02	-0.52	5	-3.33	-3.03	0.29	28	-0.21	2.38	4.64	2.74
62	1052	-3.48	-0.02	-0.52	7	-3.35	-3.10	0.24	27	-0.11	2.37	4.45	2.81
44	1042	-3.48	-0.02	-0.52	7	-3.21	-3.00	0.20	28	-0.28	2.36	4.33	2.79
59	1038	-3.48	-0.02	-0.52	7	-3.30	-3.09	0.20	27	-0.25	2.36	4.41	2.83
67	1034	-3.48	-0.02	-0.52	9	-3.23	-3.12	0.10	28	-0.14	2.38	4.30	2.73
4	1020	-3.48	-0.02	-0.52	11	-3.37	-3.16	0.21	29	0.10	2.41	4.49	2.71
19	1016	-3.48	-0.02	-0.52	9	-3.40	-3.14	0.26	28	-0.21	2.41	4.57	2.80
92	1013	-3.48	-0.02	-0.52	9	-3.22	-3.09	0.13	28	-0.14	2.39	4.41	2.68
21	997	-3.48	-0.03	-0.52	9	-3.44	-3.18	0.26	28	-0.28	2.41	4.56	2.78
66	994	-3.48	-0.03	-0.52	7	-3.40	-3.10	0.29	29	-0.17	2.38	4.41	2.80
00	989	-3.49	-0.03	-0.52	7	-3.26	-3.09	0.16	28	-0.07	2.35	4.20	2.88
36	987	-3.49	-0.03	-0.52	7	-3.32	-2.96	0.35	28	-0.14	2.36	4.39	2.84
68	958	-3.49	-0.03	-0.53	9	-3.34	-3.11	0.22	28	0.07	2.39	4.54	2.79
09	929	-3.49	-0.03	-0.53	7	-3.22	-3.04	0.17	28	-0.14	2.39	4.42	2.72
05	919	-3.49	-0.03	-0.53	9	-3.32	-3.15	0.16	29	-0.31	2.38	4.59	2.80
34	918	-3.49	-0.03	-0.53	9	-3.45	-3.18	0.26	27	0.11	2.42	4.43	2.92
80	903	-3.49	-0.03	-0.53	11	-3.39	-3.17	0.21	30	0.00	2.41	4.52	2.76
70	898	-3.49	-0.03	-0.53	7	-3.31	-2.97	0.33	28	-0.21	2.36	4.36	2.78
58	867	-3.50	-0.04	-0.54	9	-3.35	-3.09	0.25	28	-0.21	2.42	4.60	2.79
30	863	-3.50	-0.04	-0.54	9	-3.40	-3.12	0.28	28	0.07	2.44	4.56	2.89
73	835	-3.50	-0.04	-0.54	9	-3.40	-3.13	0.27	28	-0.28	2.42	4.56	2.96
46	817	-3.50	-0.04	-0.54	9	-3.27	-3.13	0.14	27	-0.03	2.41	4.59	2.71
26	815	-3.50	-0.04	-0.54	9	-3.33	-3.21	0.12	28	-0.21	2.44	4.72	2.86
48	798	-3.50	-0.04	-0.54	7	-3.41	-3.17	0.23	28	-0.07	2.38	4.37	2.92
81	790	-3.50	-0.04	-0.54	7	-3.41	-3.13	0.28	28	-0.21	2.42	4.69	2.74
40	777	-3.50	-0.05	-0.54	11	-3.50	-3.24	0.25	27	-0.18	2.40	4.24	3.06
49	756	-3.51	-0.05	-0.55	11	-3.24	-3.13	0.10	28	0.14	2.42	4.63	2.72
11	752	-3.51	-0.05	-0.55	11	-3.36	-3.20	0.15	28	-0.14	2.43	4.64	2.84
55	741	-3.51	-0.05	-0.55	7	-3.26	-3.04	0.22	27	-0.03	2.41	4.55	2.82
22	732	-3.51	-0.05	-0.55	7	-3.27	-3.02	0.24	28	-0.14	2.38	4.58	2.86
97	708	-3.51	-0.05	-0.55	11	-3.39	-3.22	0.17	28	0.21	2.38	4.32	2.90
89	703	-3.51	-0.05	-0.55	9	-3.09	-2.86	0.22	28	0.14	2.37	4.30	2.84
90	702	-3.51	-0.05	-0.55	7	-3.32	-3.14	0.18	29	-0.17	2.36	4.47	2.80
91	684	-3.51	-0.05	-0.55	9	-3.35	-3.20	0.15	28	0.07	2.43	4.77	2.84
63	680	-3.51	-0.05	-0.55	11	-3.32	-3.19	0.12	28	-0.07	2.44	4.81	2.85
77	649	-3.52	-0.06	-0.56	13	-3.29	-3.24	0.05	28	0.14	2.43	4.67	2.79
72	641	-3.52	-0.06	-0.56	9	-3.30	-3.14	0.15	30	-0.06	2.39	4.55	2.83
93	632	-3.52	-0.06	-0.56	7	-3.39	-3.11	0.27	28	-0.14	2.41	4.59	2.74
3	581	-3.52	-0.06	-0.56	5	-3.20	-2.91	0.29	28	-0.07	2.39	4.66	2.72
56	570	-3.52	-0.06	-0.56	9	-3.37	-3.10	0.26	29	0.03	2.40	4.50	2.80
43	556	-3.52	-0.07	-0.56	9	-3.48	-3.19	0.28	28	-0.14	2.43	4.72	2.82
85	549	-3.53	-0.07	-0.56	11	-3.31	-3.11	0.19	28	-0.07	2.42	4.50	2.83
75	542	-3.53	-0.07	-0.57	9	-3.36	-3.22	0.13	28	-0.14	2.42	4.62	2.75
18	541	-3.53	-0.07	-0.57	9	-3.48	-3.15	0.32	27	0.03	2.42	4.47	2.88
47	537	-3.53	-0.07	-0.57	9	-3.15	-3.01	0.13	27	-0.03	2.37	4.45	2.75
88	495	-3.53	-0.07	-0.57	9	-3.48	-3.24	0.24	27	-0.03	2.41	4.44	2.78
27	477	-3.53	-0.07	-0.57	9	-3.40	-3.10	0.29	29	-0.17	2.46	4.85	2.60
12	456	-3.53	-0.07	-0.57	9	-3.41	-3.24	0.16	29	-0.10	2.43	4.48	2.74
31	454	-3.53	-0.07	-0.57	7	-3.42	-3.09	0.32	29	-0.17	2.42	4.63	2.79
32	449	-3.53	-0.08	-0.57	9	-3.42	-3.15	0.27	28	-0.21	2.44	4.75	2.81
16	419	-3.54	-0.08	-0.58	11	-3.46	-3.12	0.33	28	-0.14	2.45	4.78	2.90
13	363	-3.54	-0.08	-0.58	11	-3.20	-3.12	0.07	28	0.21	2.42	4.55	2.77

23	353	-3.54	-0.08	-0.58	7	-3.34	-3.10	0.23	28	0.00	2.38	4.43	2.72
24	352	-3.54	-0.08	-0.58	11	-3.31	-3.17	0.14	28	-0.14	2.43	4.53	2.80
86	295	-3.55	-0.09	-0.59	11	-3.37	-3.25	0.12	29	0.03	2.43	4.54	2.72
20	289	-3.55	-0.09	-0.59	9	-3.37	-3.09	0.27	28	-0.07	2.42	4.59	2.78
79	255	-3.55	-0.09	-0.59	7	-3.47	-3.24	0.23	29	0.03	2.44	4.72	2.78
52	138	-3.56	-0.10	-0.60	9	-3.43	-3.15	0.27	28	0.00	2.46	4.84	2.86
96	0	-3.58	-0.12	-0.61	9	-3.21	-3.02	0.19	28	0.21	2.42	4.63	2.65

Table SI51: Structural, energetic and electronic properties for Mo₆Co₆ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
60	1624	-3.47	0.02	-0.37	12	-3.24	-3.11	0.12	36	0.06	2.40	4.84	2.64
54	1431	-3.48	0.00	-0.39	12	-3.40	-3.22	0.18	35	-0.26	2.43	4.93	2.62
20	1271	-3.50	-0.01	-0.40	12	-3.30	-3.08	0.22	36	-0.11	2.43	5.12	2.53
30	1106	-3.51	-0.02	-0.42	12	-3.28	-3.05	0.23	36	-0.06	2.42	4.98	2.64
100	1079	-3.51	-0.03	-0.42	12	-3.19	-3.04	0.15	36	-0.22	2.41	4.92	2.56
50	1055	-3.52	-0.03	-0.42	10	-3.20	-2.97	0.24	36	-0.11	2.40	4.84	2.59
45	1053	-3.52	-0.03	-0.42	14	-3.27	-3.16	0.11	35	-0.20	2.44	4.90	2.64
73	1043	-3.52	-0.03	-0.42	10	-3.17	-2.98	0.18	35	-0.14	2.40	4.93	2.54
63	1032	-3.52	-0.03	-0.42	10	-3.26	-3.07	0.19	35	-0.20	2.39	4.79	2.66
56	1022	-3.52	-0.03	-0.42	12	-3.38	-3.18	0.20	35	-0.03	2.42	4.75	2.66
81	1006	-3.52	-0.03	-0.42	10	-3.50	-3.24	0.25	33	-0.09	2.37	4.34	2.72
13	1003	-3.52	-0.03	-0.42	12	-3.14	-3.07	0.08	36	-0.17	2.44	5.25	2.56
11	979	-3.52	-0.03	-0.43	10	-3.19	-3.02	0.17	36	-0.11	2.40	4.78	2.67
10	973	-3.52	-0.03	-0.43	12	-3.29	-3.14	0.15	35	-0.14	2.40	4.78	2.72
92	962	-3.52	-0.04	-0.43	10	-3.36	-3.14	0.22	35	-0.03	2.40	4.94	2.59
2	956	-3.52	-0.04	-0.43	10	-3.22	-3.00	0.23	36	0.11	2.38	4.64	2.64
16	952	-3.52	-0.04	-0.43	10	-3.46	-3.23	0.23	32	0.13	2.37	4.42	2.83
52	947	-3.53	-0.04	-0.43	12	-3.44	-3.23	0.21	34	-0.24	2.42	4.74	2.66
23	930	-3.53	-0.04	-0.43	12	-3.21	-3.08	0.13	36	-0.11	2.43	5.10	2.56
33	924	-3.53	-0.04	-0.43	12	-3.46	-3.26	0.20	35	-0.14	2.43	4.95	2.72
22	914	-3.53	-0.04	-0.43	10	-3.19	-2.97	0.22	36	-0.17	2.40	4.89	2.58
44	914	-3.53	-0.04	-0.43	12	-3.46	-3.17	0.29	36	-0.17	2.43	4.72	2.71
88	910	-3.53	-0.04	-0.43	12	-3.21	-3.08	0.13	36	-0.11	2.39	4.59	2.66
25	901	-3.53	-0.04	-0.43	12	-3.21	-3.09	0.12	36	-0.22	2.42	5.05	2.56
29	893	-3.53	-0.04	-0.43	12	-3.32	-3.03	0.29	36	-0.22	2.42	5.04	2.58
98	886	-3.53	-0.04	-0.43	12	-3.41	-3.18	0.23	36	-0.17	2.44	4.88	2.66
9	880	-3.53	-0.04	-0.43	10	-3.27	-2.99	0.28	36	0.00	2.39	4.74	2.63
14	853	-3.53	-0.04	-0.44	10	-3.34	-3.16	0.17	36	-0.28	2.41	4.80	2.63
84	841	-3.53	-0.05	-0.44	10	-3.33	-3.15	0.18	35	-0.26	2.41	4.67	2.64
47	821	-3.54	-0.05	-0.44	12	-3.20	-3.08	0.12	36	-0.06	2.40	4.75	2.58
43	815	-3.54	-0.05	-0.44	12	-3.25	-3.05	0.20	36	-0.11	2.42	5.01	2.55
58	762	-3.54	-0.05	-0.44	10	-3.20	-2.99	0.20	36	0.00	2.41	4.95	2.59
59	762	-3.54	-0.05	-0.44	10	-3.44	-3.19	0.25	34	-0.24	2.41	4.55	2.86
35	748	-3.54	-0.05	-0.45	10	-3.44	-3.21	0.23	33	-0.21	2.39	4.50	2.79
8	740	-3.54	-0.05	-0.45	12	-3.39	-3.23	0.17	35	-0.26	2.45	5.00	2.61
6	730	-3.54	-0.05	-0.45	12	-3.29	-3.14	0.15	36	-0.22	2.43	5.12	2.54
28	722	-3.54	-0.06	-0.45	12	-3.40	-3.22	0.18	35	-0.20	2.44	4.78	2.66
18	720	-3.54	-0.06	-0.45	10	-3.35	-3.10	0.24	34	0.06	2.39	4.52	2.79

19	719	-3.54	-0.06	-0.45	12	-3.24	-3.12	0.11	36	-0.28	2.40	4.78	2.58
79	717	-3.54	-0.06	-0.45	10	-3.37	-3.17	0.20	35	-0.20	2.40	4.43	2.78
66	703	-3.55	-0.06	-0.45	10	-3.36	-3.11	0.25	36	0.11	2.41	4.62	2.67
87	701	-3.55	-0.06	-0.45	12	-3.44	-3.22	0.23	35	-0.14	2.43	4.76	2.68
89	660	-3.55	-0.06	-0.45	14	-3.28	-3.14	0.14	36	-0.11	2.44	5.12	2.55
70	644	-3.55	-0.06	-0.45	12	-3.45	-3.24	0.21	35	-0.20	2.43	4.68	2.74
77	643	-3.55	-0.06	-0.45	12	-3.33	-3.06	0.27	36	-0.11	2.42	4.97	2.57
12	640	-3.55	-0.06	-0.45	10	-3.36	-3.20	0.17	34	-0.12	2.42	4.79	2.71
21	627	-3.55	-0.06	-0.46	12	-3.41	-3.22	0.19	34	-0.06	2.42	4.73	2.73
37	622	-3.55	-0.06	-0.46	12	-3.23	-3.13	0.10	36	-0.06	2.40	4.61	2.60
26	589	-3.56	-0.07	-0.46	12	-3.44	-3.27	0.17	34	-0.18	2.42	4.71	2.78
53	588	-3.56	-0.07	-0.46	12	-3.25	-3.05	0.20	36	0.06	2.44	5.10	2.54
64	586	-3.56	-0.07	-0.46	12	-3.22	-3.00	0.22	36	0.17	2.43	5.19	2.59
85	584	-3.56	-0.07	-0.46	12	-3.22	-3.00	0.22	36	0.17	2.43	5.19	2.59
46	583	-3.56	-0.07	-0.46	12	-3.17	-3.04	0.13	36	0.00	2.42	5.00	2.55
80	576	-3.56	-0.07	-0.46	12	-3.32	-3.05	0.26	36	-0.17	2.42	4.96	2.57
71	569	-3.56	-0.07	-0.46	12	-3.21	-3.08	0.13	36	-0.06	2.45	5.30	2.52
40	553	-3.56	-0.07	-0.46	12	-3.29	-3.05	0.24	36	0.11	2.43	5.13	2.56
55	547	-3.56	-0.07	-0.46	14	-3.38	-3.29	0.08	36	0.00	2.45	4.85	2.63
36	525	-3.56	-0.07	-0.46	12	-3.42	-3.13	0.29	35	0.09	2.43	4.82	2.67
76	505	-3.56	-0.07	-0.47	14	-3.43	-3.31	0.13	35	-0.09	2.43	4.59	2.79
65	502	-3.56	-0.07	-0.47	10	-3.17	-2.97	0.19	35	0.03	2.40	4.97	2.57
83	497	-3.56	-0.07	-0.47	10	-3.25	-3.10	0.15	36	-0.11	2.44	4.88	2.74
86	492	-3.56	-0.07	-0.47	14	-3.47	-3.25	0.22	34	-0.06	2.45	4.81	2.79
34	477	-3.56	-0.08	-0.47	12	-3.18	-3.08	0.10	36	0.17	2.40	4.70	2.60
74	474	-3.56	-0.08	-0.47	10	-3.26	-2.98	0.28	36	-0.17	2.41	4.87	2.60
41	469	-3.57	-0.08	-0.47	14	-3.43	-3.32	0.12	35	-0.09	2.46	4.89	2.70
7	459	-3.57	-0.08	-0.47	12	-3.28	-3.10	0.18	36	-0.11	2.40	4.55	2.63
31	421	-3.57	-0.08	-0.47	14	-3.41	-3.23	0.18	35	-0.09	2.44	4.77	2.66
4	418	-3.57	-0.08	-0.47	12	-3.38	-3.16	0.22	35	-0.14	2.43	4.78	2.71
93	412	-3.57	-0.08	-0.47	12	-3.47	-3.33	0.14	34	-0.18	2.43	4.68	2.74
69	398	-3.57	-0.08	-0.47	10	-3.43	-3.22	0.21	35	-0.14	2.44	4.95	2.64
5	387	-3.57	-0.08	-0.48	10	-3.37	-3.09	0.28	35	-0.09	2.42	4.60	2.66
3	381	-3.57	-0.08	-0.48	10	-3.44	-3.23	0.21	35	-0.26	2.42	4.84	2.63
91	379	-3.57	-0.08	-0.48	12	-3.35	-3.15	0.20	36	-0.06	2.43	4.64	2.64
72	347	-3.58	-0.09	-0.48	12	-3.54	-3.30	0.24	35	-0.14	2.46	4.85	2.73
17	337	-3.58	-0.09	-0.48	12	-3.35	-3.15	0.20	36	-0.06	2.42	4.66	2.69
97	324	-3.58	-0.09	-0.48	14	-3.30	-3.22	0.08	35	0.03	2.49	5.10	2.64
94	306	-3.58	-0.09	-0.48	12	-3.32	-3.23	0.09	35	-0.03	2.44	4.72	2.67
90	288	-3.58	-0.09	-0.48	12	-3.47	-3.22	0.26	36	-0.06	2.45	4.80	2.69
96	242	-3.58	-0.10	-0.49	8	-3.19	-2.94	0.25	36	-0.22	2.41	5.20	2.48
51	128	-3.59	-0.11	-0.50	10	-3.36	-3.19	0.17	35	-0.14	2.41	4.53	2.65
1	112	-3.59	-0.11	-0.50	12	-3.29	-3.13	0.16	35	0.20	2.44	4.76	2.67
62	0	-3.60	-0.12	-0.51	14	-3.45	-3.28	0.17	36	0.11	2.46	4.91	2.63

Table SI52: Structural, energetic and electronic properties for Mo₇Co₆ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
90	1337	-3.60	-0.02	-0.41	14	-3.36	-3.23	0.12	39	-0.02	2.44	4.82	2.67

67	1181	-3.61	-0.03	-0.42	12	-3.38	-3.26	0.12	37	-0.13	2.44	4.95	2.71
74	1071	-3.62	-0.04	-0.43	10	-3.42	-3.26	0.16	36	-0.22	2.41	4.64	2.68
13	1050	-3.62	-0.04	-0.43	10	-3.25	-3.11	0.14	38	-0.10	2.41	4.68	2.74
49	1048	-3.62	-0.04	-0.43	10	-3.53	-3.35	0.17	37	-0.13	2.40	4.51	2.71
80	997	-3.62	-0.05	-0.43	10	-3.38	-3.06	0.32	38	-0.05	2.39	4.60	2.80
82	982	-3.62	-0.05	-0.43	14	-3.42	-3.31	0.10	38	-0.21	2.43	4.69	2.73
75	963	-3.63	-0.05	-0.43	8	-3.50	-3.34	0.15	34	-0.29	2.39	4.54	2.71
21	893	-3.63	-0.06	-0.44	10	-3.44	-3.25	0.18	37	-0.08	2.41	4.70	2.77
40	892	-3.63	-0.06	-0.44	10	-3.43	-3.25	0.18	37	-0.08	2.41	4.70	2.77
4	854	-3.63	-0.06	-0.44	12	-3.36	-3.21	0.14	37	0.02	2.44	4.76	2.78
12	845	-3.63	-0.06	-0.44	12	-3.41	-3.22	0.18	38	0.00	2.44	5.00	2.70
37	839	-3.63	-0.06	-0.44	10	-3.41	-3.24	0.17	38	-0.21	2.44	4.81	2.65
30	766	-3.64	-0.07	-0.45	8	-3.35	-3.11	0.23	38	-0.15	2.41	5.17	2.50
87	731	-3.64	-0.07	-0.45	12	-3.38	-3.23	0.15	39	-0.02	2.44	4.94	2.71
99	701	-3.65	-0.07	-0.45	12	-3.44	-3.26	0.18	36	-0.05	2.41	4.57	2.82
45	699	-3.65	-0.07	-0.46	12	-3.46	-3.24	0.22	38	-0.10	2.42	4.52	2.68
1	698	-3.65	-0.07	-0.46	8	-3.49	-3.27	0.22	38	-0.21	2.42	4.82	2.70
3	682	-3.65	-0.07	-0.46	10	-3.26	-3.08	0.17	41	-0.07	2.42	5.20	2.56
29	676	-3.65	-0.07	-0.46	12	-3.53	-3.29	0.23	37	-0.02	2.46	5.10	2.90
58	671	-3.65	-0.07	-0.46	8	-3.32	-3.11	0.21	38	-0.26	2.42	4.74	2.72
32	670	-3.65	-0.07	-0.46	8	-3.48	-3.24	0.24	35	-0.14	2.39	4.40	2.63
20	670	-3.65	-0.07	-0.46	14	-3.37	-3.23	0.13	38	0.05	2.43	4.64	2.71
57	665	-3.65	-0.07	-0.46	12	-3.17	-3.01	0.15	42	-0.14	2.46	5.64	2.53
25	640	-3.65	-0.08	-0.46	8	-3.25	-3.04	0.20	42	-0.14	2.41	5.17	2.48
54	618	-3.65	-0.08	-0.46	10	-3.41	-3.14	0.26	37	0.02	2.41	4.61	2.74
33	617	-3.65	-0.08	-0.46	10	-3.28	-3.08	0.19	42	-0.14	2.44	5.41	2.57
35	598	-3.65	-0.08	-0.46	12	-3.43	-3.26	0.16	39	-0.12	2.43	4.59	2.62
19	592	-3.65	-0.08	-0.46	12	-3.36	-3.22	0.13	38	0.21	2.42	4.63	2.80
63	590	-3.65	-0.08	-0.46	8	-3.25	-3.05	0.20	40	-0.10	2.43	5.32	2.54
69	589	-3.65	-0.08	-0.46	8	-3.26	-3.08	0.17	41	-0.17	2.41	5.07	2.56
24	584	-3.65	-0.08	-0.46	12	-3.22	-3.10	0.11	42	-0.04	2.44	5.49	2.47
64	558	-3.66	-0.08	-0.47	10	-3.37	-3.21	0.16	38	-0.05	2.42	4.79	3.02
50	552	-3.66	-0.08	-0.47	12	-3.40	-3.16	0.24	39	-0.02	2.42	4.69	2.78
81	528	-3.66	-0.08	-0.47	12	-3.25	-3.01	0.24	42	-0.14	2.45	5.42	2.50
0	519	-3.66	-0.08	-0.47	14	-3.32	-3.23	0.08	38	0.21	2.43	4.72	2.76
42	518	-3.66	-0.08	-0.47	14	-3.42	-3.26	0.15	40	0.10	2.44	4.63	2.68
97	506	-3.66	-0.09	-0.47	12	-3.40	-3.26	0.14	37	-0.08	2.45	4.93	2.76
27	502	-3.66	-0.09	-0.47	14	-3.22	-3.12	0.10	41	-0.02	2.46	5.65	2.52
89	498	-3.66	-0.09	-0.47	10	-3.40	-3.23	0.16	39	-0.07	2.43	4.85	2.79
76	491	-3.66	-0.09	-0.47	8	-3.24	-3.03	0.20	41	-0.02	2.43	5.36	2.55
15	456	-3.66	-0.09	-0.47	10	-3.36	-3.16	0.20	37	0.02	2.42	4.74	2.78
48	440	-3.67	-0.09	-0.48	10	-3.20	-3.01	0.19	42	-0.23	2.46	5.92	2.48
23	437	-3.67	-0.09	-0.48	8	-3.26	-3.04	0.21	42	-0.23	2.41	5.29	2.50
96	425	-3.67	-0.09	-0.48	10	-3.16	-2.99	0.16	42	-0.04	2.44	5.35	2.64
94	421	-3.67	-0.09	-0.48	10	-3.13	-2.95	0.17	42	-0.04	2.44	5.27	2.65
36	403	-3.67	-0.09	-0.48	12	-3.35	-3.05	0.29	40	-0.05	2.45	5.56	2.51
43	398	-3.67	-0.09	-0.48	10	-3.28	-3.07	0.20	40	-0.10	2.43	5.28	2.54
65	397	-3.67	-0.09	-0.48	10	-3.28	-3.07	0.20	40	-0.10	2.43	5.28	2.54
56	386	-3.67	-0.10	-0.48	8	-3.25	-3.13	0.12	38	-0.15	2.41	5.15	2.49
59	375	-3.67	-0.10	-0.48	8	-3.23	-3.00	0.23	42	-0.23	2.44	5.56	2.48
95	371	-3.67	-0.10	-0.48	10	-3.23	-2.95	0.28	42	-0.04	2.43	5.32	2.53
26	367	-3.67	-0.10	-0.48	12	-3.53	-3.29	0.23	37	-0.18	2.43	4.63	2.74
5	361	-3.67	-0.10	-0.48	12	-3.23	-3.12	0.11	42	-0.04	2.46	5.73	2.48
14	356	-3.67	-0.10	-0.48	12	-3.29	-3.04	0.24	42	0.04	2.45	5.51	2.52
39	348	-3.67	-0.10	-0.48	8	-3.28	-3.04	0.23	42	-0.04	2.45	5.72	2.47
9	317	-3.68	-0.10	-0.48	12	-3.36	-3.24	0.11	37	-0.02	2.42	4.48	2.82
11	309	-3.68	-0.10	-0.49	8	-3.14	-3.02	0.12	42	-0.23	2.42	5.26	2.52
41	301	-3.68	-0.10	-0.49	12	-3.35	-3.19	0.15	38	0.10	2.41	4.54	2.75

85	297	-3.68	-0.10	-0.49	8	-3.18	-2.96	0.22	42	-0.04	2.44	5.41	2.49
68	271	-3.68	-0.10	-0.49	10	-3.30	-3.06	0.23	42	-0.04	2.45	5.53	2.50
61	266	-3.68	-0.10	-0.49	10	-3.21	-3.13	0.08	37	-0.02	2.42	4.66	2.79
88	256	-3.68	-0.11	-0.49	10	-3.43	-3.19	0.23	35	0.14	2.39	4.37	2.76
47	253	-3.68	-0.11	-0.49	12	-3.17	-3.02	0.15	42	0.14	2.44	5.41	2.49
7	249	-3.68	-0.11	-0.49	10	-3.25	-2.99	0.26	42	-0.04	2.45	5.53	2.48
72	232	-3.68	-0.11	-0.49	6	-3.35	-3.07	0.27	38	-0.26	2.40	5.01	3.03
38	229	-3.68	-0.11	-0.49	10	-3.28	-3.06	0.21	42	-0.04	2.46	5.65	2.48
70	229	-3.68	-0.11	-0.49	10	-3.28	-3.06	0.21	42	-0.04	2.46	5.65	2.48
2	217	-3.68	-0.11	-0.49	10	-3.41	-3.19	0.21	39	-0.02	2.43	4.57	2.71
51	217	-3.68	-0.11	-0.49	10	-3.25	-3.02	0.23	42	0.14	2.47	5.77	2.48
92	201	-3.68	-0.11	-0.49	10	-3.29	-3.11	0.18	38	0.05	2.40	4.42	2.82
16	201	-3.68	-0.11	-0.49	12	-3.23	-3.08	0.14	42	0.14	2.44	5.37	2.52
28	200	-3.68	-0.11	-0.49	10	-3.16	-3.02	0.13	42	0.14	2.45	5.53	2.51
62	200	-3.68	-0.11	-0.49	12	-3.23	-3.08	0.14	42	0.14	2.44	5.37	2.52
6	175	-3.69	-0.11	-0.50	10	-3.37	-3.15	0.21	40	-0.05	2.42	4.59	2.78
46	167	-3.69	-0.11	-0.50	8	-3.35	-3.13	0.21	42	-0.14	2.44	5.43	2.49
60	144	-3.69	-0.11	-0.50	10	-3.14	-3.02	0.11	41	-0.17	2.46	5.64	2.53
73	143	-3.69	-0.11	-0.50	10	-3.14	-3.02	0.11	42	-0.14	2.46	5.64	2.53
79	82	-3.69	-0.12	-0.50	10	-3.24	-3.06	0.18	42	0.04	2.43	5.29	2.47
53	14	-3.70	-0.12	-0.51	12	-3.24	-3.10	0.13	42	-0.04	2.45	5.61	2.49
55	14	-3.70	-0.12	-0.51	12	-3.24	-3.10	0.13	42	-0.04	2.45	5.61	2.49
31	11	-3.70	-0.12	-0.51	12	-3.24	-3.10	0.13	42	-0.04	2.45	5.61	2.49
83	0	-3.70	-0.12	-0.51	8	-3.33	-3.08	0.25	38	0.10	2.41	4.80	2.96

Table SI53: Structural, energetic and electronic properties for Mo₇Co₇ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
10	2070	-3.61	-0.12	-0.42	13	-3.46	-3.29	0.17	41	-0.12	2.38	4.54	3.06
11	1974	-3.62	-0.12	-0.43	15	-3.54	-3.43	0.11	41	-0.22	2.46	5.30	3.00
97	1874	-3.63	-0.13	-0.44	13	-3.47	-3.34	0.14	41	-0.22	2.44	5.15	2.89
42	1840	-3.63	-0.13	-0.44	15	-3.41	-3.32	0.09	41	-0.02	2.43	4.93	3.10
16	1812	-3.63	-0.14	-0.44	13	-3.45	-3.33	0.12	41	-0.07	2.41	5.05	2.89
69	1758	-3.64	-0.14	-0.44	11	-3.57	-3.34	0.22	41	-0.27	2.44	5.19	2.87
46	1737	-3.64	-0.14	-0.45	11	-3.54	-3.33	0.21	40	-0.15	2.45	5.28	2.92
24	1641	-3.64	-0.15	-0.45	11	-3.46	-3.24	0.21	42	-0.14	2.42	5.23	2.95
59	1604	-3.65	-0.15	-0.46	9	-3.44	-3.18	0.26	42	0.00	2.40	5.06	2.91
8	1537	-3.65	-0.15	-0.46	11	-3.40	-3.23	0.18	42	0.00	2.43	5.12	2.98
56	1528	-3.65	-0.16	-0.46	11	-3.39	-3.25	0.15	40	-0.10	2.42	5.07	3.03
82	1494	-3.66	-0.16	-0.46	11	-3.48	-3.32	0.16	43	-0.02	2.41	5.20	3.04
36	1493	-3.66	-0.16	-0.46	13	-3.55	-3.48	0.07	40	-0.15	2.43	4.80	2.95
45	1487	-3.66	-0.16	-0.46	11	-3.41	-3.23	0.18	40	-0.20	2.43	5.13	2.92
44	1457	-3.66	-0.16	-0.47	11	-3.38	-3.20	0.18	42	-0.19	2.41	5.01	3.02
68	1439	-3.66	-0.16	-0.47	15	-3.42	-3.33	0.09	40	0.00	2.41	4.83	3.10
87	1422	-3.66	-0.16	-0.47	7	-3.35	-3.20	0.14	44	-0.32	2.41	5.29	2.95
99	1421	-3.66	-0.16	-0.47	15	-3.48	-3.33	0.15	41	-0.17	2.44	4.92	2.98
75	1409	-3.66	-0.16	-0.47	11	-3.52	-3.28	0.24	42	-0.10	2.44	4.99	2.84
84	1408	-3.66	-0.16	-0.47	9	-3.36	-3.15	0.21	41	-0.17	2.39	5.06	2.90
52	1384	-3.66	-0.17	-0.47	11	-3.39	-3.26	0.13	40	-0.15	2.42	5.01	2.97


96	1381	-3.66	-0.17	-0.47	13	-3.47	-3.31	0.16	41	-0.07	2.42	5.05	2.98
6	1377	-3.66	-0.17	-0.47	13	-3.42	-3.26	0.16	40	-0.05	2.40	4.77	2.92
17	1350	-3.67	-0.17	-0.47	13	-3.34	-3.26	0.08	43	-0.07	2.42	4.90	3.15
62	1349	-3.67	-0.17	-0.47	11	-3.39	-3.30	0.09	40	-0.05	2.40	5.10	2.95
21	1334	-3.67	-0.17	-0.48	11	-3.32	-3.17	0.15	42	-0.10	2.43	5.22	2.93
64	1330	-3.67	-0.17	-0.48	13	-3.36	-3.30	0.06	40	0.15	2.42	5.12	3.20
49	1321	-3.67	-0.17	-0.48	9	-3.50	-3.37	0.13	41	-0.27	2.41	5.20	2.90
77	1275	-3.67	-0.17	-0.48	13	-3.45	-3.24	0.21	42	-0.05	2.42	4.91	2.91
66	1271	-3.67	-0.17	-0.48	13	-3.50	-3.39	0.11	41	-0.07	2.43	5.13	3.06
93	1259	-3.67	-0.17	-0.48	13	-3.37	-3.29	0.08	42	0.00	2.44	5.02	3.02
41	1253	-3.67	-0.18	-0.48	13	-3.41	-3.27	0.14	41	-0.12	2.43	5.07	3.09
90	1247	-3.67	-0.18	-0.48	9	-3.35	-3.15	0.20	44	-0.09	2.42	5.42	2.91
85	1242	-3.67	-0.18	-0.48	11	-3.54	-3.37	0.17	40	-0.25	2.46	5.34	2.97
50	1232	-3.67	-0.18	-0.48	13	-3.43	-3.33	0.10	41	0.07	2.44	5.12	2.89
100	1210	-3.68	-0.18	-0.48	11	-3.36	-3.16	0.21	40	0.25	2.42	5.10	2.96
18	1187	-3.68	-0.18	-0.49	11	-3.48	-3.26	0.22	43	-0.12	2.43	5.04	3.26
86	1167	-3.68	-0.18	-0.49	11	-3.42	-3.21	0.21	41	-0.12	2.42	4.94	2.87
89	1164	-3.68	-0.18	-0.49	11	-3.41	-3.20	0.21	40	0.00	2.43	5.19	3.28
73	1164	-3.68	-0.18	-0.49	11	-3.38	-3.25	0.13	41	-0.02	2.43	5.19	2.95
25	1163	-3.68	-0.18	-0.49	11	-3.40	-3.22	0.18	41	-0.02	2.40	4.96	2.88
4	1151	-3.68	-0.18	-0.49	11	-3.32	-3.19	0.13	44	0.23	2.42	5.21	2.90
7	1143	-3.68	-0.18	-0.49	9	-3.43	-3.27	0.16	41	-0.17	2.42	5.00	2.94
91	1124	-3.68	-0.18	-0.49	9	-3.31	-3.14	0.17	41	-0.02	2.41	5.03	2.98
26	1116	-3.68	-0.19	-0.49	11	-3.35	-3.22	0.12	42	-0.05	2.44	5.01	2.89
81	1059	-3.69	-0.19	-0.49	9	-3.41	-3.20	0.21	44	-0.05	2.42	5.34	2.79
28	1058	-3.69	-0.19	-0.50	11	-3.41	-3.21	0.20	40	-0.30	2.42	5.03	2.97
60	1036	-3.69	-0.19	-0.50	11	-3.45	-3.31	0.14	43	-0.21	2.42	5.18	2.95
30	1000	-3.69	-0.19	-0.50	9	-3.36	-3.14	0.22	41	-0.07	2.41	5.00	3.10
80	992	-3.69	-0.19	-0.50	13	-3.55	-3.36	0.19	40	-0.20	2.46	5.15	3.00
55	985	-3.69	-0.19	-0.50	13	-3.51	-3.30	0.21	41	-0.02	2.43	4.83	2.99
51	974	-3.69	-0.20	-0.50	9	-3.34	-3.14	0.20	43	-0.21	2.40	5.03	3.09
40	959	-3.69	-0.20	-0.50	13	-3.34	-3.24	0.10	44	0.00	2.44	5.30	2.99
57	936	-3.70	-0.20	-0.50	13	-3.44	-3.28	0.16	41	-0.07	2.44	5.14	3.11
72	906	-3.70	-0.20	-0.51	13	-3.42	-3.31	0.11	41	0.02	2.43	4.96	3.01
78	895	-3.70	-0.20	-0.51	13	-3.45	-3.33	0.12	42	0.05	2.42	4.92	3.02
2	857	-3.70	-0.20	-0.51	11	-3.37	-3.24	0.13	41	-0.07	2.42	5.19	3.05
61	853	-3.70	-0.20	-0.51	13	-3.44	-3.35	0.10	42	0.10	2.44	5.16	3.14
58	837	-3.70	-0.20	-0.51	9	-3.38	-3.16	0.22	42	-0.14	2.40	5.05	3.10
71	827	-3.70	-0.21	-0.51	13	-3.43	-3.14	0.29	41	0.17	2.42	4.98	3.04
79	805	-3.70	-0.21	-0.51	13	-3.41	-3.18	0.22	41	0.07	2.44	5.17	2.95
37	799	-3.71	-0.21	-0.51	13	-3.40	-3.19	0.21	44	-0.09	2.44	5.50	2.99
53	795	-3.71	-0.21	-0.51	13	-3.58	-3.36	0.21	40	0.00	2.45	5.07	2.99
12	737	-3.71	-0.21	-0.52	13	-3.61	-3.38	0.24	41	-0.07	2.47	5.29	3.01
9	700	-3.71	-0.21	-0.52	11	-3.54	-3.29	0.25	41	-0.22	2.44	5.27	3.17
19	697	-3.71	-0.21	-0.52	9	-3.33	-3.20	0.13	44	-0.05	2.41	5.18	2.98
63	693	-3.71	-0.22	-0.52	9	-3.40	-3.19	0.20	42	-0.24	2.46	5.30	3.10
88	684	-3.71	-0.22	-0.52	11	-3.39	-3.26	0.14	44	-0.09	2.43	5.42	2.61
67	665	-3.71	-0.22	-0.52	11	-3.52	-3.33	0.19	41	-0.12	2.41	4.75	3.36
38	658	-3.72	-0.22	-0.52	11	-3.48	-3.27	0.21	41	-0.17	2.41	5.08	3.12
65	633	-3.72	-0.22	-0.53	11	-3.45	-3.32	0.12	40	-0.10	2.44	5.01	3.18
76	625	-3.72	-0.22	-0.53	9	-3.45	-3.22	0.23	40	-0.05	2.44	5.01	3.07
5	573	-3.72	-0.22	-0.53	11	-3.38	-3.18	0.20	45	0.02	2.43	5.47	2.59
13	504	-3.73	-0.23	-0.53	13	-3.55	-3.34	0.21	41	0.12	2.47	5.34	3.06
34	465	-3.73	-0.23	-0.54	11	-3.41	-3.14	0.27	45	-0.07	2.46	5.59	3.11
92	261	-3.74	-0.25	-0.55	9	-3.50	-3.28	0.22	41	-0.02	2.45	5.17	3.14
15	0	-3.76	-0.26	-0.57	13	-3.51	-3.21	0.31	39	0.18	2.43	4.81	2.84

Table SI54: Structural, energetic and electronic properties for Mo₈Co₇ cluster, as follows: configuration number (i), relative DFT total energy (ΔE_{tot}^{DFT} , in meV), binding energy (E_b , in eV), excess energy (E_{exc} , in eV), stabilization energy (E_{stab} , in eV), total magnetic moment (M_{tot} , in μ_B), HOMO energy (ϵ_{HOMO} , in eV), LUMO energy (ϵ_{LUMO} , in eV), HOMO-LUMO energy difference, (E_{gap} , in eV), total number of bonds (N_b), average chemical order parameter (σ_{av}), average bond length (d_{av} , in Å), average effective coordination number (ECN_{av} , NNN), and average radius (R_{av} , in Å).

i	ΔE_{tot}^{DFT}	E_b	E_{exc}	E_{stab}	M_{tot}	ϵ_{HOMO}	ϵ_{LUMO}	E_{gap}	N_b	σ_{av}	d_{av}	ECN_{av}	R_{av}
58	1232	-3.75	-0.04	-0.45	13	-3.36	-3.20	0.15	50	-0.16	2.44	5.44	2.69
45	1139	-3.75	-0.05	-0.45	13	-3.33	-3.23	0.09	49	-0.06	2.44	5.61	3.11
56	1035	-3.76	-0.06	-0.46	13	-3.36	-3.27	0.08	47	-0.06	2.43	5.05	2.81
60	980	-3.77	-0.06	-0.46	15	-3.51	-3.36	0.14	48	-0.12	2.46	5.24	2.80
13	953	-3.77	-0.06	-0.47	9	-3.48	-3.31	0.17	49	-0.22	2.43	5.39	2.85
59	915	-3.77	-0.06	-0.47	10	-3.53	-3.32	0.20	47	-0.10	2.44	5.20	2.74
93	890	-3.77	-0.07	-0.47	13	-3.40	-3.28	0.12	46	-0.21	2.44	5.18	2.82
42	839	-3.77	-0.07	-0.47	13	-3.48	-3.33	0.15	47	-0.14	2.45	5.16	2.75
36	790	-3.78	-0.07	-0.48	12	-3.33	-3.19	0.13	48	-0.08	2.45	5.64	3.08
64	790	-3.78	-0.07	-0.48	11	-3.23	-3.09	0.13	47	-0.02	2.43	5.39	3.14
96	771	-3.78	-0.07	-0.48	11	-3.43	-3.23	0.19	49	-0.06	2.44	5.27	2.80
68	760	-3.78	-0.08	-0.48	13	-3.41	-3.24	0.17	49	-0.10	2.44	5.59	3.06
41	758	-3.78	-0.08	-0.48	11	-3.49	-3.30	0.18	45	-0.20	2.41	4.88	2.76
53	750	-3.78	-0.08	-0.48	9	-3.37	-3.20	0.16	48	-0.16	2.42	5.41	2.64
83	733	-3.78	-0.08	-0.48	7	-3.49	-3.35	0.14	48	-0.12	2.41	4.98	2.95
44	698	-3.78	-0.08	-0.48	11	-3.45	-3.32	0.13	47	-0.23	2.43	5.24	2.70
70	675	-3.79	-0.08	-0.48	11	-3.52	-3.33	0.18	46	-0.13	2.44	5.25	2.80
29	641	-3.79	-0.08	-0.49	11	-3.34	-3.23	0.11	49	-0.14	2.44	5.44	2.97
91	639	-3.79	-0.08	-0.49	11	-3.39	-3.17	0.21	49	-0.06	2.43	5.43	2.70
16	631	-3.79	-0.08	-0.49	13	-3.38	-3.23	0.15	47	-0.10	2.45	5.25	2.81
02	630	-3.79	-0.08	-0.49	15	-3.49	-3.31	0.17	49	0.02	2.46	5.29	2.75
77	617	-3.79	-0.08	-0.49	11	-3.40	-3.28	0.12	49	-0.06	2.42	5.23	2.98
14	616	-3.79	-0.08	-0.49	11	-3.39	-3.19	0.19	48	-0.12	2.44	5.25	2.84
50	599	-3.79	-0.09	-0.49	11	-3.54	-3.31	0.22	47	-0.14	2.44	5.22	2.72
51	578	-3.79	-0.09	-0.49	11	-3.39	-3.18	0.21	48	-0.08	2.43	5.41	3.16
8	576	-3.79	-0.09	-0.49	15	-3.38	-3.32	0.05	47	-0.02	2.45	5.14	2.76
98	563	-3.79	-0.09	-0.49	9	-3.47	-3.26	0.21	46	0.00	2.42	4.88	2.80
43	554	-3.79	-0.09	-0.49	11	-3.47	-3.34	0.13	48	0.04	2.45	5.64	3.15
1	551	-3.79	-0.09	-0.49	13	-3.56	-3.37	0.18	46	-0.13	2.46	5.33	2.80
92	542	-3.79	-0.09	-0.49	7	-3.38	-3.16	0.22	50	-0.20	2.43	5.17	2.91
82	538	-3.79	-0.09	-0.49	11	-3.28	-3.24	0.04	49	0.02	2.44	5.53	3.16
21	534	-3.79	-0.09	-0.49	11	-3.52	-3.35	0.17	45	-0.11	2.45	5.29	2.84
81	533	-3.79	-0.09	-0.49	15	-3.44	-3.24	0.19	48	-0.04	2.46	5.31	2.81
62	525	-3.80	-0.09	-0.49	9	-3.45	-3.24	0.20	48	-0.04	2.42	5.14	3.14
57	522	-3.80	-0.09	-0.49	11	-3.43	-3.22	0.21	49	0.06	2.43	5.43	2.81
35	517	-3.80	-0.09	-0.50	13	-3.32	-3.27	0.05	47	0.06	2.43	5.12	2.76
86	509	-3.80	-0.09	-0.50	13	-3.48	-3.32	0.15	48	0.00	2.45	5.24	2.79
49	500	-3.80	-0.09	-0.50	12	-3.55	-3.33	0.21	46	-0.17	2.47	5.38	2.84
3	498	-3.80	-0.09	-0.50	11	-3.53	-3.30	0.23	47	-0.06	2.45	5.24	3.03
10	493	-3.80	-0.09	-0.50	11	-3.40	-3.21	0.18	47	-0.06	2.44	5.54	3.09
19	484	-3.80	-0.09	-0.50	9	-3.41	-3.20	0.20	48	-0.08	2.43	5.50	3.08
63	476	-3.80	-0.09	-0.50	10	-3.49	-3.32	0.17	49	-0.18	2.44	5.43	3.20
78	475	-3.80	-0.09	-0.50	13	-3.40	-3.25	0.14	47	0.10	2.45	5.26	2.78
95	471	-3.80	-0.09	-0.50	11	-3.22	-3.15	0.06	46	-0.08	2.43	5.57	2.99
74	469	-3.80	-0.09	-0.50	11	-3.44	-3.23	0.20	48	-0.12	2.43	5.45	3.10
23	469	-3.80	-0.09	-0.50	13	-3.34	-3.23	0.11	48	0.00	2.45	5.18	2.78
34	459	-3.80	-0.10	-0.50	11	-3.44	-3.27	0.17	49	-0.06	2.45	5.30	2.73
52	441	-3.80	-0.10	-0.50	13	-3.46	-3.29	0.16	48	-0.16	2.46	5.62	3.14

6	437	-3.80	-0.10	-0.50	13	-3.47	-3.29	0.18	46	0.04	2.44	5.01	2.76
12	431	-3.80	-0.10	-0.50	11	-3.48	-3.28	0.20	47	-0.10	2.45	5.36	2.79
94	392	-3.80	-0.10	-0.50	11	-3.40	-3.25	0.14	49	-0.06	2.42	5.32	3.18
80	381	-3.81	-0.10	-0.50	13	-3.47	-3.29	0.17	48	-0.04	2.45	5.61	3.17
31	377	-3.81	-0.10	-0.50	9	-3.46	-3.25	0.20	49	0.02	2.43	5.00	2.83
88	373	-3.81	-0.10	-0.50	11	-3.34	-3.18	0.15	47	-0.02	2.43	5.41	3.03
32	368	-3.81	-0.10	-0.51	13	-3.54	-3.40	0.13	48	-0.04	2.45	5.22	3.17
40	343	-3.81	-0.10	-0.51	15	-3.40	-3.28	0.11	47	0.19	2.45	5.17	2.78
25	342	-3.81	-0.10	-0.51	8	-3.37	-3.23	0.13	47	-0.06	2.42	5.38	3.11
73	335	-3.81	-0.10	-0.51	11	-3.33	-3.22	0.10	48	-0.08	2.43	5.43	3.07
27	324	-3.81	-0.10	-0.51	9	-3.45	-3.20	0.25	49	-0.26	2.41	5.13	3.31
11	302	-3.81	-0.11	-0.51	9	-3.51	-3.26	0.25	47	-0.06	2.45	5.64	3.09
61	291	-3.81	-0.11	-0.51	11	-3.38	-3.27	0.11	48	-0.12	2.44	5.50	3.05
17	261	-3.81	-0.11	-0.51	13	-3.40	-3.28	0.11	46	0.17	2.46	5.35	2.85
69	244	-3.81	-0.11	-0.51	9	-3.47	-3.24	0.22	49	-0.14	2.44	5.20	2.92
22	237	-3.81	-0.11	-0.51	11	-3.34	-3.23	0.11	48	-0.12	2.43	5.51	3.16
85	222	-3.82	-0.11	-0.51	11	-3.31	-3.20	0.11	46	-0.04	2.42	4.93	3.13
39	185	-3.82	-0.11	-0.52	11	-3.34	-3.19	0.15	48	0.00	2.45	5.67	3.13
37	183	-3.82	-0.11	-0.52	9	-3.35	-3.22	0.13	48	-0.16	2.44	5.54	3.16
0	163	-3.82	-0.12	-0.52	7	-3.39	-3.18	0.20	46	-0.08	2.42	5.05	2.76
48	42	-3.83	-0.12	-0.53	11	-3.31	-3.24	0.06	47	0.14	2.43	5.50	3.05
24	33	-3.83	-0.12	-0.53	8	-3.42	-3.30	0.12	45	-0.02	2.43	4.95	3.01
47	24	-3.83	-0.12	-0.53	13	-3.42	-3.23	0.18	46	0.17	2.43	5.13	2.79
46	22	-3.83	-0.12	-0.53	13	-3.42	-3.23	0.18	46	0.17	2.43	5.14	2.78
89	0	-3.83	-0.13	-0.53	11	-3.40	-3.21	0.19	48	0.00	2.44	5.54	3.16

Table SI55: Lowest energy configurations for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.






Figure SI33: Binding energy (E_b) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI34: Excess energy (E_{exc}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI35: Stabilization energy (E_{stab}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI36: Total magnetic moment (M_{tot}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI37: HOMO energy (E_{HOMO}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI38: LUMO energy (E_{LUMO}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI39: HOMO-LUMO energy gap (E_{gap}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI40: Total number of bonds (N_b) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI41: Average chemical order parameter (σ_{av}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI42: Average bond length (d_{av}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI43: Average effective coordination number (ECN_{av}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.




Figure SI44: Average radius (R_{av}) for the near-equiatomic Mo_nCo_m subnanoalloys with $n + m = 2 - 15$.

6 Data Availability

All DFT calculations were done using the FHI-aims package, which can be used under a non-free academic license. Additional details can be obtained from the link, <https://fhi-aims.org/>. Furthermore, additional details are provided within the supporting information, while raw (XYZ files) and processed data required to reproduce the above findings are available to download from <https://github.com/\karlandriani/ConMom.git>.

References

- 1 Felício-Sousa, P.; Mucelini, J.; Zibordi-Besse, L.; Andriani, K. F.; Seminovski, Y.; Prati, R. C.; Da Silva, J. L. F. *Ab initio* Insights Into the Structural, Energetic, Electronic, and Stability Properties of Mixed $Ce_nZr_{15-n}O_{30}$ Nanoclusters. *Phys. Chem. Chem. Phys.* **2019**, *21*, 26637–26646, DOI: 10.1039/c9cp04762j.
- 2 Andriani, K. F.; Felício-Sousa, P.; Morais, F. O.; Da Silva, J. L. F. Role of quantum-size effects in the dehydrogenation of CH_4 on 3d TM_n clusters: DFT calculations combined with data mining. *Catal. Sci. Technol.* **2022**, *12*, 916–926, DOI: 10.1039/D1CY01785C.
- 3 Hoppe, R. The Coordination Number - An “Inorganic Chameleon”. *Angew. Chem. Int. Ed.* **1970**, *9*, 25–34, DOI: 10.1002/anie.197000251.
- 4 Da Silva, J. L. F. Effective Coordination Concept Applied for Phase Change $(GeTe)_m(Sb_2Te_3)_n$ Compounds. *J. Appl. Phys.* **2011**, *109*, 023502, DOI: 10.1063/1.3533422.