

## Exploring the A-Site Chemistry of $A_2LiTiCl_6$ (A= K, Rb, and Cs) Double Perovskites: Structural Stability, Electronic Structure, and Transport Properties

Syed Hatim Shah<sup>1\*</sup>, Dost Muhammad<sup>2</sup>, Baseerat Bibi<sup>1</sup>, Wafa S Aljuaid<sup>3</sup>, Najah Alwadie<sup>4</sup>, Muncerah Alomar<sup>4</sup>, Muhammad Faizan<sup>5,\*</sup>

<sup>1</sup>*Department of Physics, School of Physics and Astronomy, Yunnan University, Kunming, 650504, China*

<sup>2</sup>*Faculty of Material Science and Engineering, Kunming University of Science and Technology, Kunming 650093, China*

<sup>3</sup>*Department of Chemistry, Taif University, Taif 26571, Saudi Arabia*

<sup>4</sup>*Department of Physics, College of Science, Princess Nourah bint Abdulrahman University, P. O. Box 84428, Riyadh 11671, Saudi Arabia*

<sup>5</sup>*School of Materials Science and Engineering, Jilin University, Changchun, 130012, China*


### Supplementary Information

**Table. S1** The calculated elastic constant and related parameters derived from elastic constants using GGA-PBESol.


Parameters	$K_2LiTiCl_6$	$Rb_2LiTiCl_6$	$Cs_2LiTiCl_6$	Other work
$C_{11}$	47.6	43.7	42.6	42.7 [1], 66.9 [2], 39.3 [3]
$C_{12}$	16.1	15.8	15.12	16.52 [2], 16.8 [1], 13.7 [3]
$C_{44}$	12.1	11.6	12.2	21.98 [2], 9.10 [1], 8.7 [3]
$B = (C_{11} + 2C_{12}) / 3$	26.5	25.1	24.29	32.5 [1], 29.9 [2], 22.2 [3]
$Y = 9BG_v / (3B + G_v)$	34.8	32.2	32.8	28.7 [1], 56.5 [2], 26.4 [3]
$G = (G_v + G_R) / 2$	13.5	12.5	12.8	23.2 [2], 7.29 [1], 10.1 [3]
B/G	1.97	2.01	1.89	1.43 [2], 3.10 [1], 2.19 [3]
$C_p = C_{12} - C_{44}$	4.0	4.18	2.92	5.05 [3], -5.46 [2]
$\nu = 3B - 2G / 2(3B + G)$	0.28	0.28	0.27	0.35 [1], 0.21 [2]
$A = 2 C_{44} / (C_{11} - C_{12})$	0.76	0.72	0.88	0.70 [1], 0.87 [2]
$T_m = (553K + (5.91 \text{ K/GPa}) C_{11}) \pm 300K$	(834 ± 300) K	(811.26 ± 300) K	(804.76 ± 300) K	(785.6 ± 300) K [3], (959.7 ± 300) K [4]
$V_t = \left(\frac{\rho}{G}\right)^{-1/2}$	2124.99	1905.8	1832.9	1581 [3], 2259.6 [4]
$V_l = \left(\frac{3B + 4G}{3\rho}\right)^{1/2}$	3865.12	3486.97	3290.5	2969 [3], 4086.7 [4]
$V_m = \left[\frac{1}{3}\left(\frac{2}{V_t^3} + \frac{1}{V_l^3}\right)\right]^{-1/3}$	2368.6	2125.3	2040.9	1766 [3], 2514.6 [4]
$\theta_D(K) = \frac{h}{k_B} \left[\frac{3nN_A\rho}{4\pi M}\right]^{1/3} V_m$	232.3	206.6	195.6	274 [3], 249.5 [4]
$\gamma = 3(1+\nu) / 2(2-3\nu)$	1.65	1.65	1.60	0.94 [4], 0.91 [4]

**Table S2.** The optical and transport properties such as; ( $\sigma/\tau$ ) electrical conductivity, (S) Seebeck coefficient, ( $\kappa_e/\tau$ ) electronic thermal conductivity, and (ZT) Figure of merit of  $\text{K}_2\text{LiTiCl}_6$ ,  $\text{Rb}_2\text{LiTiCl}_6$  and  $\text{Cs}_2\text{LiTiCl}_6$  were computed mBJ-GGA-PBEsol functional


Materials Properties		$\text{K}_2\text{LiTiCl}_6$	$\text{Rb}_2\text{LiTiCl}_6$	$\text{Cs}_2\text{LiTiCl}_6$	Other work	
Optical Properties	$\epsilon_1(0)$	2.31	2.32	2.40	2.93 [5], 2.41 [6]	
	$n(0)$	1.52	1.52	1.54	1.71 [5], 1.55 [6]	
	$R(0)$	0.042	0.043	0.046	0.07 [5], 0.05 [6]	
Transport properties	S ( $\mu\text{V/K}$ )	300 K	222.67	208.53	202.71	170 [7], 250 [8]
		800 K	193.61	185.69	189.13	238 [8], 147 [7]
	$\kappa_e 10^{14}$ (W/mKs)	300 K	0.98	0.96	0.93	0.11 [8], 0.7 [7]
		800 K	5.68	5.11	5.28	2.1 [7], 3.8 [8]
	$\sigma/\tau 10^{18}$ ( $\Omega\text{ms}$ ) <sup>-1</sup>	300 K	0.50	0.55	0.56	0.46 [7], 0.15 [8]
		800 K	1.39	1.32	1.32	0.89 [7], 0.59 [8]
	$S^2\sigma/\tau$ ( $10^{11}\text{W/K}^2\text{ms}$ )	300 K	2.51	2.43	2.31	1.5 [7], 1.25 [8]
		800 K	5.24	4.56	4.73	1.9 [7], 3.8 [8]
	ZT	300 K	0.76	0.75	0.74	0.75 [8], 0.62 [7]
800 K		0.73	0.71	0.71	0.78 [8], 0.21 [7]	




**Figure. S1** (a–c) TB-mBJ-SOC calculated band structures of  $\text{K}_2\text{LiTiCl}_6$ ,  $\text{Rb}_2\text{LiTiCl}_6$ , and  $\text{Cs}_2\text{LiTiCl}_6$  with band gaps of 2.81, 2.71, and 2.62 eV, respectively.




**Figure. S2** The plot of (a) Optical conductivity:  $\sigma(\omega)$ , (b) Energy Loss:  $E_{\text{Loss}}(\omega)$  of  $A_2\text{LiTiCl}_6$  ( $A = \text{K}, \text{Rb}, \text{and Cs}$ ).




**Figure. S3** Calculated electrical conductivity presented as a function of chemical potential between -2 and +3.5 eV of  $A_2\text{LiTiCl}_6$  ( $A = \text{Rb}, \text{and Cs}$ ).




**Figure. S4** Calculated electronic thermal conductivity presented as a function of chemical potential between -2 and +3.5 eV of  $A_2\text{LiTiCl}_6$  ( $A = \text{Rb}, \text{and Cs}$ ).



**Figure. S5** Calculated Seebeck coefficient presented as a function of chemical potential between -2 and +3.5 eV of  $A_2\text{LiTiCl}_6$  ( $A = \text{Rb}, \text{and Cs}$ ).



**Figure. S6** Calculated power factor presented as a function of chemical potential between -2 and +3.5 eV of  $\text{A}_2\text{LiTiCl}_6$  (A= Rb, and Cs).



**Figure. S7** Calculated Figure of merit presented as a function of chemical potential between -2 and +3.5 eV of  $\text{A}_2\text{LiTiCl}_6$  (A= Rb, and Cs).

## Reference

1. Rahman N, Husain M, Ahmad Y, Azzouz-Rached A, Al-khamiseh BM, Asad M, et al. First-principles investigation of  $\text{Cs}_2\text{TlGaX}_6$  ( $X = \text{Cl, F}$ ) double perovskites: structural and dynamical stability, elastic properties, and optoelectronic characteristics for applications in semiconductor technology. *Optical and Quantum Electronics*. 2024;56(8):1298.
2. Khan NU, Khan UA, Zaman A, Algahtani A, Al-Humaidi JY, Tirth V, et al. Insight into structural, electronic, optical and elastic properties of double perovskites  $\text{Rb}_2\text{XCrCl}_6$  ( $X = \text{K, Na}$ ) via DFT study. *Journal of Physics and Chemistry of Solids*. 2023;181:111479.
3. Ghebouli M, Chihi T, Ghebouli B, Fatmi M. Study of the structural, elastic, electronic and optical properties of lead free halide double perovskites  $\text{Cs}_2\text{AgBiX}_6$  ( $X = \text{Br, Cl}$ ). *Chinese journal of physics*. 2018;56(1):323-30.
4. Saeed M, Jehangir MA, Murtaza G, Chaudhry AR, Khan KA, Albaqami MD, et al. Optical and transport properties of novel  $\text{X}_2\text{BAGCl}_6$  (where  $X = \text{K, Rb, Cs}$ , and  $B = \text{Sc, Y}$ ) double perovskites. *Materials Science and Engineering: B*. 2024;308:117556.
5. Sholagberu A, Yahya W, Adewale A. Pressure effects on the opto-electronic and mechanical properties of the double perovskite  $\text{Cs}_2\text{AgInCl}_6$ . *Physica Scripta*. 2022;97(8):085824.
6. Khan J, Khan M, Sharma T, Boukhris I, Al-Buriahi M. Advanced Computational Insights Into  $\text{Cs}_2\text{NaScX}_6$  ( $X = \text{Cl, Br}$ ) Double Perovskites: Structural Stability, Elastic Properties, and Optical Characteristics for Next-Generation Photovoltaics. *Journal of Computational Chemistry*. 2025;46(1):e70010.
7. Albalawi H, Mustafa GM, Saba S, Kattan NA, Mahmood Q, Somaily H, et al. Study of optical and thermoelectric properties of double perovskites  $\text{Cs}_2\text{KTlX}_6$  ( $X = \text{Cl, Br, I}$ ) for solar cell and energy harvesting. *Materials Today Communications*. 2022;32:104083.
8. Iqbal MW, Manzoor M, Gouadria S, Asghar M, Zainab M, Ahamd NN, et al. DFT insights on the opto-electronic and thermoelectric properties of double perovskites  $\text{K}_2\text{AgSbX}_6$  ( $X = \text{Cl, Br}$ ) via halides substitutions for solar cell applications. *Materials Science and Engineering: B*. 2023;290:116338.