

## Supporting Information

### **Bimetallic CuRu/Al<sub>2</sub>O<sub>3</sub> catalyst for highly selective hydrogenation of furfural to furfuryl alcohol**

Meichen Pan,<sup>†a</sup> Zhenduo Huang,<sup>†a</sup> Yuhao Yang,<sup>b</sup> Yongzhen Gao,<sup>a</sup> Meng Zhang,<sup>\*a</sup> and Zhongyi Liu<sup>\*ac</sup>


<sup>a</sup> College of Chemistry, Zhengzhou University, Zhengzhou, 450001, PR China.

<sup>b</sup> Shandong Institute of Non-metallic Materials, Jinan, 250031, PR China.


<sup>c</sup> State Key Laboratory of Coking Coal Resources Green Exploitation, Zhengzhou University, Zhengzhou, 450001, PR China.

\* Corresponding authors. College of Chemistry, Zhengzhou University, Zhengzhou, 450001, PR China. *Emails:* zhangmeng1991@zzu.edu.cn; liuzhongyi@zzu.edu.cn.

<sup>†</sup> These authors contributed equally to this work.



**Fig. S1**  $\text{N}_2$  physisorption isotherms (a) and pore size distribution plots (b) of  $\text{Al}_2\text{O}_3$  support and the supported catalysts.



**Fig. S2** Relationship between  $\ln(c_t/c_0)$  and reaction time at various reaction temperatures of (a) 5Cu/Al<sub>2</sub>O<sub>3</sub>, (b) 1Ru/Al<sub>2</sub>O<sub>3</sub>, and (c) 5Cu1Ru/Al<sub>2</sub>O<sub>3</sub>.

**Table S1** Effect of stirring rate on the hydrogenation of FAL over 5Cu1Ru/Al<sub>2</sub>O<sub>3</sub> catalyst.

Entry	Stirring rate (rpm)	FAL conv. (%)	FA sel. (%)
1	400	86.5	99.5
2	600	98.6	99.9
3	800	99.9	99.9
4	1000	99.9	99.9

Reaction conditions: catalyst (0.1 g), furfural (0.5 g), isopropanol (30 mL), time (4 h), H<sub>2</sub> pressure (1 MPa).

**Table S2** Calculation data of apparent activation energy for 5Cu/Al<sub>2</sub>O<sub>3</sub> in the selective hydrogenation of FAL.

T (K)	Conv. (%)	k (min <sup>-1</sup> )	lnk (min <sup>-1</sup> )	1/T (K <sup>-1</sup> )	1000/T (K <sup>-1</sup> )	Ea (kJ/mol)
353	7.9	0.0003429	-7.978072	0.002833	2.833	
358	15.0	0.0006772	-7.297603	0.002793	2.793	132.5
363	22.6	0.0011876	-6.735838	0.002755	2.755	

Reaction conditions: catalyst (0.1 g), furfural (0.5 g), isopropanol (30 mL), time (4 h), H<sub>2</sub> pressure (1 MPa).

**Table S3** Calculation data of apparent activation energy for 1Ru/Al<sub>2</sub>O<sub>3</sub> in the selective hydrogenation of FAL.

T (K)	Conv. (%)	k (min <sup>-1</sup> )	lnk (min <sup>-1</sup> )	1/T (K <sup>-1</sup> )	1000/T (K <sup>-1</sup> )	Ea (kJ/mol)
353	11.8	0.000523	-7.555929	0.002833	2.833	
358	19.6	0.000909	-7.003165	0.002793	2.793	125.9
363	33.6	0.001706	-6.373604	0.002755	2.755	

Reaction conditions: catalyst (0.1 g), furfural (0.5 g), isopropanol (30 mL), time (4 h), H<sub>2</sub> pressure (1 MPa).

**Table S4** Calculation data of apparent activation energy for 5Cu1Ru/Al<sub>2</sub>O<sub>3</sub> in the selective hydrogenation of FAL.

T (K)	Conv. (%)	k (min <sup>-1</sup> )	lnk (min <sup>-1</sup> )	1/T (K <sup>-1</sup> )	1000/T (K <sup>-1</sup> )	Ea (kJ/mol)
333	3.8	0.0001634	-8.719309	0.003003	3.003	
343	12.8	0.0005723	-7.463204	0.002915	2.915	118.4
353	38.7	0.0020334	-6.190444	0.002833	2.833	
363	99.9	0.0287823	-3.555384	0.002755	2.755	

Reaction conditions: catalyst (0.1 g), furfural (0.5 g), isopropanol (30 mL), time (4 h), H<sub>2</sub> pressure (1 MPa).

**Table S5** Comparison of Catalytic Performance for Selective Hydrogenation of FAL to FA Using Different Catalysts.

Catalyst	Reaction Conditions	Conv.(%)	Sel.(%)	Ref.
Pd-CuO <sub>x</sub>	120 °C, 1.0 MPa H <sub>2</sub> , 4 h	100	100	1
Cu <sub>3</sub> Ni <sub>1</sub> /SiO <sub>2</sub>	60 °C, 2.0 MPa H <sub>2</sub> , 3 h	99.9	99.9	2
(tH <sub>2</sub> )Ru <sub>x</sub> Co <sub>100</sub>	120 °C, 1.0 MPa H <sub>2</sub> , 4 h	100	98	3
CuFe700	200 °C, 2 h	96.1	93.2	4
PtFe <sub>0.6</sub> -TiO <sub>2</sub>	40 °C, 2.0 MPa H <sub>2</sub> , 4 h	99	99	5
Pd-Au/Cp-butyl	50 °C, 0.5 MPa H <sub>2</sub> , 5 h	75	74	6
CuCoAlO <sub>x</sub>	90 °C, 2.0 MPa H <sub>2</sub> , 5 h	99	98	7
Pt-(SnO <sub>2</sub> ) <sub>0.3</sub> /Al <sub>2</sub> O <sub>3</sub>	100 °C, 1.0 MPa H <sub>2</sub> , 3 h	99.7	98.5	8
Cu@Mg/γ-Al <sub>2</sub> O <sub>3</sub>	170 °C, 2.0 MPa H <sub>2</sub> , 3 h	99	94	9
2.5%CuO/MCM-41	210 °C, 0.1 MPa H <sub>2</sub> , 20 h	92.5	88	10
NiCoCuZnFe/C-800	90 °C, 3.0 MPa H <sub>2</sub> , 9 h	87.3	100	11
Cu <sub>2</sub> Ni <sub>1</sub> AlO <sub>y</sub>	120 °C, 1.6 MPa H <sub>2</sub> , 1.5 h	98	99	12
Cu <sub>2</sub> Zn/SiO <sub>2</sub> -IS	120 °C, 2.5 MPa H <sub>2</sub> , 4 h	81.9	94.8	13
Cu/t-ZrO <sub>2</sub> -300	120 °C, 2 MPa H <sub>2</sub> , 4 h	100	100	14
5Cu1Ru/Al <sub>2</sub> O <sub>3</sub>	90 °C, 1 MPa H <sub>2</sub> , 4 h	99.9	99.9	This work

## References

- (1) Zhang, W.; Wang, Y.; Gu, B.; Tang, Q.; Cao, Q.-E.; Fang, W. Regulating the interaction within Pd-Cu dual metal sites for selective hydrogenation of furfural using ambient H<sub>2</sub> pressure. *ACS Sustainable Chemistry & Engineering* 2023, 11 (34), 12798-12808.
- (2) Liao, X.; Zhao, H.; Liu, R.; Luo, H.; Lv, Y.; Liu, P. Highly efficient and selective hydrogenation of furfural to furfuryl alcohol and cyclopentanone over Cu-Ni bimetallic Catalysts: The crucial role of Cu-Ni alloys and Cu<sup>+</sup> species. *Journal of Catalysis* 2024, 436, 115603.
- (3) Wang, Y.; Gao, T.; Lu, Y.; Wang, Y.; Cao, Q.; Fang, W. Efficient hydrogenation of furfural to furfuryl alcohol by magnetically recoverable RuCo bimetallic catalyst. *Green Energy & Environment* 2022, 7 (2), 275-287.
- (4) Kalong, M.; Srifa, A.; Hongmanorom, P.; Cholsuk, C.; Klysubun, W.; Ratchahat, S.; Koo-amornpattana, W.; Khemthong, P.; Assabumrungrat, S.; Kawi, S. Catalytic transfer hydrogenation of furfural to furfuryl alcohol and 2-methylfuran over CuFe catalysts: Ex situ observation of simultaneous structural phase transformation. *Fuel Processing Technology* 2022, 231, 107256.
- (5) Zhao, Z.; Li, X.; Liu, X.; Gao, H.; Jia, A.; Xie, S.; Song, X.; Liu, X.; Yang, F.; Yang, Q. Pt/Fe-TiO<sub>2</sub>-catalyzed selective carbonyl hydrogenation: Fe-promoted hydrogen spillover. *ACS Catalysis* 2024, 14 (7), 4478-4488.
- (6) German, D.; Kolobova, E.; Pakrieva, E.; Carabineiro, S. A.; Sviridova, E.; Perevezentsev, S.; Alijani, S.; Villa, A.; Prati, L.; Postnikov, P. The effect of sibunit carbon surface modification with diazonium tosylate salts of Pd and Pd-Au catalysts on furfural hydrogenation. *Materials* 2022, 15 (13), 4695.
- (7) Stepanova, L.N.; Mironenko, R.M.; Kobzar, E.O.; Leont'eva, N.N.; Gulyaeva, T.I.; Vasilevich, A.V.; Serkova, A.N.; Salanov, A.N.; Lavrenov, A.V. Synthesis of CuAl-, CoAl-, and CuCoAl-catalysts from layered hydroxides for furfural hydrogenation. *Eng* 2022, 3 (4), 400-411.
- (8) Wang, Y.; Wang, Z.; Xu, C.; Zhou, S. Synthesis of alumina supported Pt-SnO<sub>2</sub> hybrid nanostructures by in situ transformation of PtSn alloy nanoparticles and their application as

highly efficient catalysts for selective hydrogenation of furfural. *The Journal of Physical Chemistry C* 2023, 127 (8), 4033-4041.

(9) Arundhathi, R.; Reddy, P. L.; Samanta, C.; Newalkar, B. L. Chromium-free Cu@Mg/ $\gamma$ -Al<sub>2</sub>O<sub>3</sub>—an active catalyst for selective hydrogenation of furfural to furfuryl alcohol. *RSC advances* 2020, 10 (67), 41120-41126.

(10) Yandrati, L. P.; Kaladi, S. S.; Gundebayina, R.; Pothu, R.; Moli, V.; Rao, B. V.; Boddula, R.; Devulapalli, R.; Mitta, H. Tailoring Cu immobilized MCM-41-based mesostructured catalysts for selective hydrogenolysis of biomass-derived furfural. *Catalysis Communications* 2024, 187, 106898.

(11) Tu, R.; Liang, K.; Sun, Y.; Wu, Y.; Lv, W.; Jia, C. Q.; Jiang, E.; Wu, Y.; Fan, X.; Zhang, B. Ultra-Dilute high-entropy alloy catalyst with core-shell structure for high-active hydrogenation of furfural to furfuryl alcohol at mild temperature. *Chemical Engineering Journal* 2023, 452, 139526.

(12) Luo, L.; Yuan, F.; Zaera, F.; Zhu, Y. Catalytic hydrogenation of furfural to furfuryl alcohol on hydrotalcite-derived Cu<sub>x</sub>Ni<sub>3-x</sub>AlO<sub>y</sub> mixed-metal oxides. *Journal of Catalysis* 2021, 404, 420-429.

(13) Zhang, J.; Wu, D. Aqueous phase catalytic hydrogenation of furfural to furfuryl alcohol over in-situ synthesized Cu-Zn/SiO<sub>2</sub> catalysts. *Materials Chemistry and Physics* 2021, 260, 124152.

(14) Yang, X.; Chen, Z.; Tan, J.; Zhang, Y.; Cui, J.; Wang, C.; Fang, L.; Zhu, Y.; Huang, L.; Shi, H. Understanding the synergistic catalysis of balanced Cu<sup>0</sup>-Cu<sup>+</sup> sites and oxygen vacancies in Cu/ZrO<sub>2</sub> catalysts for the efficient hydrogenation of furfural. *Chemical Engineering Journal* 2024, 501, 157796.