

Supplementary Material

Supplementary Methods

Preparation of pcRPI/Gg gels

The total biopolymer concentration was maintained at 55 mg/mL with pcRPI/Gg mass ratios of 30:1, 20:1, 15:1, 10:1, 5:1. The mixed solution was stirred at room temperature for 30 min, and heated at 85 °C for 20 min to induce gel formation. The resulting gels were then stored at -4 °C until further analysis.




Figure S1 Rheological properties of pcRPI/Gg gels at different mass ratios.