

Supplementary Information (SI) for Industrial Chemistry & Materials.
This journal is © Institute of Process Engineering of CAS 2026

	SEV Control	SEV CuMA 1/16	SEV CuMA 1/8	SEV CuMA 1/4
	$v_{\text{phy}} / \text{mol cm}^{-3}$	$v_{\text{phy}} / \text{mol cm}^{-3}$	$v_{\text{phy}} / \text{mol cm}^{-3}$	$v_{\text{phy}} / \text{mol cm}^{-3}$
<i>Pristine</i>	$1.95 \times 10^{-4} \pm 8.13 \times 10^{-6}$	$1.61 \times 10^{-4} \pm 6.00 \times 10^{-7}$	$1.66 \times 10^{-4} \pm 9.35 \times 10^{-7}$	$1.60 \times 10^{-4} \pm 1.34 \times 10^{-6}$
<i>R90V10</i>	$2.20 \times 10^{-4} \pm 5.83 \times 10^{-6}$	$1.91 \times 10^{-4} \pm 1.66 \times 10^{-6}$	$1.98 \times 10^{-4} \pm 2.15 \times 10^{-6}$	$1.80 \times 10^{-4} \pm 1.45 \times 10^{-6}$
<i>R80V20</i>	$2.15 \times 10^{-4} \pm 1.22 \times 10^{-5}$	$1.83 \times 10^{-4} \pm 8.66 \times 10^{-7}$	$1.93 \times 10^{-4} \pm 2.29 \times 10^{-6}$	$1.71 \times 10^{-4} \pm 2.37 \times 10^{-6}$
<i>R70V30</i>	$2.00 \times 10^{-4} \pm 1.55 \times 10^{-6}$	$1.78 \times 10^{-4} \pm 1.18 \times 10^{-6}$	$1.67 \times 10^{-4} \pm 2.55 \times 10^{-7}$	$1.68 \times 10^{-4} \pm 6.65 \times 10^{-7}$