

Preparation of N&O-doping and microporous carbon granules for effective CH₄ adsorption and separation from low-concentration coal-bed methane

Yao Li^a, Xiaohua Wang^a, Lanyun Wang^c, Ran Xu^{b*}, Binbin Wang^{d*}

^a School of Safety Science and Engineering, Henan Polytechnic University, Jiaozuo, Henan 454000, China

^b School of Safety and Management Engineering, Hunan Institute of Technology, Hengyang 421002, China

^c School of Safety Science and Engineering, Changzhou University, Changzhou 213164, China

^d School of Materials Science and Engineering, Henan Polytechnic University, Jiaozuo, Henan 454000, China

* Corresponding authors.

E-mail addresses: rxu@hnit.edu.cn (R. X.); wangbb@hpu.edu.cn. (B.W.)




Fig. S1. Photograph of CKCGs-900-1 hydrothermal 2 h.




Fig. S2. Photographs of CKCGs-800-1, CKCGs-900-N₂, CKCGs-900-0.5, CKCGs-900-1.5, and CKCGs-1000-1.




Fig. S3. Photographs of the KOH-A-1 and KOH-A-2




Fig. S4. High-resolution XPS spectra of C1s for CKCGs.




Fig. S5. (a) SEM image of CKCGs-900-1, and EDS elemental mapping images of (b) C, (c) N, and (d) O in CKCGs-900-1.




Fig. S6. The relationship of CH₄ adsorption capacity with (a) $V_{0.55 \text{ nm}}$, (b) S_{BET} , (c) O-content, (d) N-content, (e) surface C-OH&C-OOH total concentration and (f) surface N-5&N-6 total concentration.




Fig. S7. Different hydrothermal duration affecting the CH₄ adsorption capacity. (Red marking hydrothermal 1 h, black marking hydrothermal 0.5 h, blue marking hydrothermal 2 h)




Fig. S8. CH₄ adsorption performance comparison of CKCGs-1, KOH-A-1 and KOH-A-2 at 25 °C and 1 bar.




Fig. S9. The adsorption isotherms of (a) CH₄ and (b) N₂ on CKCGs-900-1 at 0, 25, and 45 °C.




Fig. S10. The initial slopes of CH₄ and N₂ adsorption isotherms (0-0.12 bar) for (a) CKCGs-800-1, (b) CKCGs-900-0, (c) CKCGs-9-0.5, (d) CKCGs-900-1, (e) CKCGs-900-1.5 and (f) CKCGs-1000-1, at 25 °C.




Fig. S11. Comparison of CH_4/N_2 selectivity and CH_4 adsorption capacity with some other adsorbents at 1 bar and 25 °C (red symbols present particle and column samples, black symbols represent powder samples, the orange values annotate the CH_4/N_2 proportion).




Fig. S12. Breakthrough curves for CH_4/N_2 (30/70 v/v) binary mixture on (a) CKCGs-800-1, (b) CKCGs-1000-1 at 25 °C and 1 bar.

Table S1. The mechanical strength and yield of these granular carbon samples.

Samples	Mechanical strength (N/granule)	Yields ^a (%)
CKCGs-800-1	25.95	21.07
CKCGs-900-N ₂	37.18	16.13
CKCGs-900-0.5	31.07	19.24
CKCGs-900-1	21.61	17.57
CKCGs-900-1.5	12.03	13.85
CKCGs-1000-1	11.66	12.80

^a Calculated by considering the mass change of the original precursor (corn kernels) upon the final obtained carbon granules.

Table S2. Average particle size and Standard Deviation of Corn Kernels and the derived carbon granules.

Samples	Corn kernel size (cm)	carbon granule size (cm)					
		CKCGs-900-N ₂	CKCGs-800-1	CKCGs-900-0.5	CKCGs-900-1	CKCGs-900-1.5	CKCGs-1000-1
No. 1	0.9	0.75	0.80	0.71	0.7	0.62	0.50
No. 2	0.91	0.78	0.79	0.72	0.68	0.65	0.48
No. 3	0.86	0.76	0.81	0.69	0.69	0.64	0.49
No. 4	0.91	0.75	0.82	0.71	0.71	0.59	0.51
No. 5	0.9	0.74	0.79	0.69	0.69	0.60	0.48
No. 6	0.88	0.76	0.81	0.68	0.68	0.61	0.52
No. 7	0.87	0.74	0.82	0.73	0.68	0.62	0.49
No. 8	0.89	0.75	0.78	0.73	0.7	0.63	0.50
No. 9	0.88	0.76	0.84	0.74	0.68	0.62	0.51
No. 10	0.92	0.77	0.82	0.70	0.73	0.59	0.48
No. 11	0.91	0.75	0.81	0.71	0.71	0.64	0.49
No. 12	0.89	0.74	0.80	0.69	0.67	0.62	0.49
.....							
Average particle size	0.89	0.75	0.82	0.71	0.70	0.61	0.49
.....							
Standard deviation	0.018	0.013	0.018	0.018	0.017	0.019	0.013

Table S3. Content of different O-containing functional groups in O1s spectra of CKCGs samples.

Samples	O/at. (%)	O groups ratio ^b (%)				O groups ratio ^c			
		C=O	C-OH	-COOH	O ₂ /H ₂ O	C=O	C-OH	-COOH	O ₂ /H ₂ O
CKCGs-800-1	14.92	43.29	47.62	6.93	2.16	6.46	7.10	1.03	0.33
CKCGs-900-N ₂	15.04	47.54	49.18	1.23	2.05	7.15	7.40	0.18	0.31
CKCGs-900-0.5	14.46	43.54	45.80	7.51	3.15	6.30	6.62	1.09	0.45
CKCGs-900-1	14.33	41.35	46.41	8.44	3.80	5.93	6.65	1.21	0.54
CKCGs-900-1.5	14.00	41.17	47.32	8.71	2.80	5.76	6.62	1.22	0.40
CKCGs-1000-1	13.09	31.03	48.97	15.86	4.14	4.06	6.41	2.08	0.54

^a The surface total O concentration (at.%) obtained from XPS analysis;

^b Percentage of each deconvoluted peak in relation to O1s total area (%);

^c The surface concentration (at.%) of each O-containing group is calculated by multiplying the percentage of deconvolution peak of each O group in the O1s spectra by the total O concentration. In the case of CKCG-900-1, for example, the C-OH percentage in O1s spectra of 46.41 % multiplied by the O content of 14.33 at. % is calculated to be 6.65 at. %.

Table S4. Content of different N-containing functional groups in O1s spectra of CKCGs samples.

Samples	N/at. (%)	N species ratio ^b (%)				N species ratio ^c			
		N-6	N-5	N-Q	N-X	N-6	N-5	N-Q	N-X
CKCGs-800-1	2.41	31.72	57.27	6.17	4.84	0.76	1.38	0.15	0.12
CKCGs-900-N ₂	2.42	31.22	57.71	6.81	4.26	0.76	1.40	0.16	0.10
CKCGs-900-0.5	2.33	30.45	58.77	6.13	4.65	0.71	1.37	0.14	0.11
CKCGs-900-1	2.31	29.67	60.28	5.74	4.31	0.69	1.39	0.13	0.10
CKCGs-900-1.5	2.14	27.50	63.50	5.00	4.00	0.59	1.36	0.11	0.08
CKCGs-1000-1	1.81	18.09	64.82	9.55	7.54	0.33	1.17	0.17	0.14

^a The surface total N concentration (at. %) obtained from XPS analysis;

^b Percentage of each deconvoluted peak in relation to N1s total area (%);

^c The surface concentration (at.%) of each N-containing group is calculated by multiplying the percentage of deconvolution peaks of each N group in the N1s spectra by the total N concentration. In the case of CKCG-900-1, for example, the N-5 percentage in N1s spectra of 60.28 % multiplied by the N content of 2.31 at. % is calculated to be 1.39 at. %.

Table S6. The comparison between CKCGs-900-1 and other representative adsorbents on CH₄ adsorption capacity and CH₄/N₂ IAST selectivity at 25 °C and 1 bar.

Adsorbent	Physical form	CH ₄ uptake	CH ₄ /N ₂	Ratio of	Ref.
		(mmol g ⁻¹)	IAST Selectivity	CH ₄ /N ₂	
@ 25 °C, 1 bar					
HCK4.5	Powdery	1.39	4.51	20/80	[S1]
Al-FUM-Me	Powdery	1.21	8.60	50/50	[S2]
SBMOF-1	Powdery	0.92	11.5	50/50	[S3]
nano-ZK-5	Powdery	1.34	4.2	20/80	[S4]
SA-1-700	Powdery	1.53	5.00	50/50	[S5]

Table S5. Langmuir-Freundlich parameters for the CH₄ and N₂ adsorption isotherms on the porous carbon granules.

Samples	Gas	Temperature	q _m	b	n	R ²
CKCGs-800-1	CH ₄	25 °C	2.56065	0.39922	1.23015	0.99990
	N ₂	25 °C	2.29363	0.14119	1.21101	0.99963
CKCGs-900-N ₂	CH ₄	25 °C	2.34149	0.21258	1.13587	0.99957
	N ₂	25 °C	2.10798	0.13734	1.2235	0.99413
CKCGs-900-0.5	CH ₄	25 °C	3.00275	0.54049	1.21938	0.99996
	N ₂	25 °C	2.22188	0.17667	1.16042	0.99988
CKCGs-900-1	CH ₄	0 °C	4.0012	0.8210	1.21851	0.99983
		25 °C	3.05675	0.70716	1.17389	0.99988
	45 °C	2.49156	0.56251	1.0713	0.99981	
	0 °C	2.36322	0.30752	1.12021	0.99968	
	N ₂	25 °C	1.89563	0.24963	1.06393	0.99996
		45 °C	1.67176	0.18734	1.02128	0.99996
CKCGs-900-1.5	CH ₄	25 °C	3.59313	0.47987	1.14975	0.99995
	N ₂	25 °C	1.94714	0.26263	1.04394	0.99993
CKCGs-1000-1	CH ₄	25 °C	3.5588	0.44928	1.10175	0.99983
	N ₂	25 °C	2.6300	0.16395	1.09866	0.99981

N-WAPC	Powdery	1.01	11.76	15/85	[S6]
CICTF-1-650	Powdery	1.47	8.60	50/50	[S7]
PS-1-550	Powdery	1.44	6.60	50/50	[S8]
sOMC	Powdery	0.90	3.80	50/50	[S9]
[Ni ₃ (HCOO) ₆]	Powdery	0.82	6.18	50/50	[S10]
PCNPs	Powdery	1.17	10.0	30/70	[S11]
CSK-7	Powdery	1.25	3.64	50/50	[S12]
Cu-MOF	Powdery	0.47	6.9	50/50	[S13]
CGUC-1-8	Powdery	1.34	5.0	50/50	[S14]
PCF-Co-0.5	Powdery	0.97	6.8	30/70	[S15]
O-Cell-113-a	Powdery	1.69	12.64	15/85	[S16]
10 %Ni/C	Powdery	1.26	5.3	30/70	[S17]
OTS-2-450	Powdery	0.93	4.9	50/50	[S18]
OAC-2	Powdery	0.84	4.6	50/50	[S19]
Ni/DOBDC	Powdery	~1.16	~1.5	50/50	[S20]
[Mg ₃ (HCOO) ₆]	Powdery	0.74	5.5	50/50	[S21]
Na-CHA-4.0	Powdery	1.34	-----	-----	[S22]
PAF-1-SO ₃ H	Powdery	0.62	-----	-----	[S23]
PRC-850 binder-free	Shaped	1.12	5.5	15/85	[S24]
KOH0.5TP50 binder-containing	Shaped	1.459	-----	-----	[S25]
ACB-5 binder-containing	Shaped	1.125	-----	-----	[S26]
ACB-2 binder-containing	Shaped	1.094	-----	-----	[S26]
CGC-1.5 binder-containing	Shaped	0.87	10.3	30/70	[S27]
CKCGs-900-1	Granule	1.31	17.62	10/90	<i>this work</i>
CKCGs-900-1	Granule	1.31	11.59	15/85	<i>this work</i>
CKCGs-900-1	Granule	1.31	5.21	30/70	<i>this work</i>
CKCGs-900-1	Granule	1.31	2.40	20/50	<i>this work</i>

References

- [S1] H. Lian, Y. Q. Zhao, L. P. Wang, Y. Wang, G. J. Zhang, Y. F. Zhang, Low-corrosion preparation of porous carbons with narrow micropores for efficient separation of CH₄/N₂, Mater. Today. Commun. 39 (2024) 108818.
- [S2] M. Chang, T. G. Yan, Y. Wei, J. X. Wang, D. H. Liu, J. F. Chen, Enhancing CH₄ Capture from Coalbed Methane through Tuning van der Waals Affinity within Isoreticular Al-Based Metal-Organic Frameworks, ACS Appl. Mater. Interfaces. 14 (2022) 25374–25384

- [S3] M. Chang, J. H. Ren, Q.Y. Yang, D. H. Liu, A robust calcium-based microporous metal-organic framework for efficient CH₄/N₂ separation, *Chem. Eng. J.* 408 (2021) 127294.
- [S4] J. F. Yang, X. Tang, J. Q. Liu, J. Wang, H. Shang, L. G. Wu, J. P. Lia, S. G. Deng, Downsizing the crystal size of ZK-5 zeolite for its enhanced CH₄ adsorption and CH₄/N₂ separation performances, *Chem. Eng. J.* 406 (2021) 126599.
- [S5] F.Q. Yang, J. Wang, L. Liu, P.X. Zhang, W.K. Yu, Q. Deng, Z.L. Zeng, S.G. Deng, Synthesis of porous carbons with high N-content from shrimp shells for efficient CO₂-capture and gas separation, *ACS Sustainable Chem. Eng.* 6 (2018) 15550-15559.
- [S6] Y. Li, R. Xu, B.B. Wang, J.P. Wei, L.Y. Wang, M.Q. Shen, J. Yang, Enhanced N-doped porous carbon derived from KOH-activated waste wool: A promising material for selective adsorption of CO₂/CH₄ and CH₄/N₂, *Nanomaterials.* 9 (2019) 266.
- [S7] K.X. Yao, Y.L. Chen, Y. Lu, Y.F. Zhao, Y. Ding, Ultramicroporous carbon with extremely narrow pore distribution and very high nitrogen doping for efficient methane mixture gases upgrading, *Carbon* 122 (2017) 258-265.
- [S8] F. Liu, Y. Zhang, P.X. Zhang, M. Xu, T. Tan, J. Wang, Q. Deng, L.Y. Zhang, Y.Q. Wan, S.G. Deng, Facile preparation of N and O-rich porous carbon from palm sheath for highly selective separation of CO₂/CH₄/N₂ gas-mixture, *Chem. Eng. J.* 399 (2020) 125812.
- [S9] B. Yuan, X.F. Wu, Y.X. Chen, J.H. Huang, H.M. Luo, S.G. Deng, Adsorption of CO₂, CH₄, and N₂ on ordered mesoporous carbon: Approach for greenhouse gases capture and biogas upgrading, *Environ. Sci. Technol.* 47 (2013) 5474-5480.
- [S10] Y. Guo, J. L. Hua, X. W. Liu, T. J. Sun, S. S. Zhao, S. D. Wang, Scalable solvent-free preparation of [Ni₃(HCOO)₆] frameworks for highly efficient separation of CH₄ from N₂, *Chem. Eng. J.* 327 (2017) 564-572.
- [S11] S. Xu, W. C. Li, C. T. Wang, L. Tang, G. P. Hao, A. H. Lu, Self-Pillared Ultramicroporous Carbon Nanoplates for Selective Separation of CH₄/N₂, *Angew. Chem. Int. Ed.* 60 (2021) 6339-6343.
- [S12] W. Su, L. Yao, M. Ran, Y. Sun, J. Liu, X.J. Wang, Adsorption properties of N₂, CH₄, and CO₂ on sulfur-doped microporous carbons, *J. Chem. Eng. Data* 63 (2018) 2914-2920.
- [S13] X. F. Wu, B. Yuan, Z. B. Bao, S. G. Deng, Adsorption of carbon dioxide, methane and nitrogen on an ultramicroporous copper metal-organic framework, *J. Colloid Interface Sci.* 430(2014)78-84.
- [S14] P.X. Zhang, J. Wang, W. Fan, Y. Zhong, Y. Zhang, Q. Deng, Z.L. Zeng, S.G. Deng, Ultramicroporous carbons with extremely narrow pore size distribution via in-situ ionic activation for efficient gas-mixture separation, *Chem. Eng. J.* 375 (2019) 121931.
- [S15] T.Y. Li, Y.S. Wang, M.Y. Zhang, B.Y. Liu, Z. Zheng, G.P. Hao, A.H. Lu, Carbon nanofibers with gas selective layer containing rich and accessible ultramicropores for methane/nitrogen separation, *Chem. Eng. J.* 462 (2023) 142118.
- [S16] R. B. Mujmule, M. M. Rajpure, U. Kim, H. Kim, Engineered cellulose-based porous carbon

- adsorbents for superior gas adsorption and selective separation of CH₄/H₂ and CH₄/N₂, *Sep. Purif. Technol.* 327 (2023) 124922.
- [S17] S. H. Li, S. G. Fu, Y.Q. Gong, L. Wang, Y. X. Wu, L. Wang, Y. P. Cheng, New insight into efficient CH₄/N₂ separation based on Ni-decorated porous carbon functional composites, *Fuel* 347 (2023) 128480.
- [S18] Y. Zhang, L. Liu, P.X. Zhang, J. Wang, M. Xu, Q. Deng, Z.L. Zeng, S.G. Deng, Ultra-high surface area and nitrogen-rich porous carbons prepared by a low-temperature activation method with superior gas selective adsorption and outstanding supercapacitance performance, *Chem. Eng. J.* 355 (2019) 309-319.
- [S19] J. Wang, R. Krishna, J.F. Yang, S.G. Deng, Hydroquinone and quinone-grafted porous carbons for highly selective CO₂ capture from flue gases and natural gas upgrading, *Environ. Sci. Technol.* 49 (2015) 9364-9373.
- [S20] L.B. Li, J.F. Yang, J.M. Li, Y. Chen, J.P. Li, Separation of CO₂/CH₄ and CH₄/N₂ mixtures by M/DOBDC: A detailed dynamic comparison with MIL-100(Cr) and activated carbon, *Micropor. Mesopor. Mat.* 198 (2014) 236-246.
- [S21] J. L. Hua, T. J. Sun, X. Y. Ren, S. D. Wang, HF-assisted synthesis of ultra-microporous [Mg₃(OOCH)₆] frameworks for selective adsorption of CH₄ over N₂, *Microporous Mesoporous Mater.* 204 (2015) 73-80.
- [S22] Y. Guo, T. J. Sun, Y. M. Gu, X. W. Liu, Q. L. Ke, X. L. Wei, S. D. Wang, Rational Synthesis of Chabazite (CHA) Zeolites with Controlled Si/Al Ratio and Their CO₂/CH₄/N₂ Adsorptive Separation Performances, *Chem. Asian J.* 13 (2018) 3222-3230.
- [S23] W. C. Zhang, Y. H. Cheng, C. S. Guo, C. P. Xie, Z. H. Xiang, Cobalt Incorporated Porous Aromatic Framework for CO₂/CH₄, *Ind.Eng.Chem.Res.* 57 (2018) 10985-10991.
- [S24] R. L. Tang, Q. B. Dai, W.W. Liang, Y. Wu, X. Zhou, H.Y. Pan, Z. Li, Synthesis of novel particle rice-based carbon materials and its excellent CH₄/N₂ adsorption selectivity for methane enrichment from Low-rank natural gas, *Chem. Eng. J.* 384 (2020) 123388.
- [S25] A. A. Niya, T. E. Rufford, Z. H. Zhu, Activated carbon monoliths with hierarchical pore structure from tar pitch and coal powder for the adsorption of CO₂, CH₄ and N₂, *Carbon.* 103 (2016) 115e124.
- [S26] X. H. Shao, Z. H. Feng, R. S. Xue, C. C. Ma, W. H. Wang, X. Peng, D. P. Cao, Adsorption of CO₂, CH₄, CO₂/N₂ and CO₂/CH₄ in Novel Activated Carbon Beads: Preparation, Measurements and Simulation, *AIChE J.* 57 (2011) 3042-3051.
- [S27] Y. Z. Gao, S. Xu, C. T. Wang, X. J. Zhang, R. S. Liu, A. H. Lu, Preparation of molded biomass carbon from coffee grounds and its CH₄/N₂ separation performance, *New Carbon Mater.* 37 (2022) 1145-1153.