

Electrochemically derived nanoporous Bi from plasma-structured BiOCl for high-efficiency CO₂ electroreduction

Yaxin Xu^a, Zhongshuang Xu^a, Huanran Miao^a, Zhimao Yang^a, Chuncai Kong^{a†}, Qikui Fan^{a†}

a.MOE Key Laboratory for Non-Equilibrium Synthesis and Modulation of Condensed Matter,
Key Laboratory for Advanced Materials and Mesoscopic Physics of Shaanxi Province,
School of Physics, Xi'an Jiaotong University, Xi'an, 710049, China

† Address correspondence to Third C. Kong, kongcc@xjtu.edu.cn; Fourth Q. Fan,
fanqikui@xjtu.edu.cn

Table S1. Comparison of CO₂RR performance to formate for P-BiOCl and other state-of-the-art catalysts.

Formula reference:

$$j_{HCOOH} = j_{total} \times FE_{HCOOH}$$

The unit for current density is uniformly defined as mA cm⁻².

Sample Name	$j_{total}/ \text{mA cm}^{-2}$	$j_{HCOOH}/ \text{mA cm}^{-2}$
P-Bi	50	41
	92	83
	200	186
	300	280
	400	365
	500	451
HT-Bi	50	30
	100	76
	200	161
	300	247
	400	290
	500	259

Table S2. Performance comparison of state-of-the-art Bi-based catalysts for CO₂ electroreduction to formate in flow cells.

Catalyst	Electrolyte	Current density (mA cm ⁻²)	Potential (V vs. RHE)	FE _{formate} (%)	Stability (h) @ condition	Reference
P-Bi (nanoporous Bi, this work)	1.0 M KOH	300	0.90	93.4	40 @ 100 mA cm⁻² (4.73% FE loss)	This work
Bi NS-L (lattice-compressed Bi nanosheets)	1.0 M KOH	150	-1.0	94	15 @ 100 mA cm ⁻² (negligible decay)	Nano Lett. 2025 , 25, DOI: 10.1021/acs.nanolett.5c02163
BOC-NC-900 °C (Bi ₂ O ₂ CO ₃ /N-doped carbon)	1.0 M KOH	91	-1.0	90.5	10 @ -1.0 V (FE >90%)	Nanoscale 2023 , 17, 9588-9598 DOI:10.1039/d4nr05343e
Bi-Cl derived (halide-guided)	1.0 M KOH	300	N/A	95	20 @ 200 mA cm ⁻² (FE decay <5%)	Nat. Catal. 2023 , 6, 796–806 DOI:10.1038/s41929-023-01008-0
Bi NSs (Bi nanosheets)	1.0 M KOH	300	-0.52	>90	10h @ 197 mA cm ⁻² (FE =90%)	Adv. Energy Mater. 2020 , 10, 2001709 DOI: 10.1002/aenm.202001709