

Supporting Information

Thermal protocol-driven oxidative etching of ZrC embedded carbon nanofibers to unlock ZrOxCy nanodomains for superior H₂O₂ production

Changho Lee^{a,b,†}, Soobin Lee^{c,†}, Haeun Baeg^{d,†}, Wenjun Zhang^e, Hyunmin Na^c, Su Yeon Bae^{a,b}, Min Soo Kim^f, Il-Doo Kim^f, Wonchang Choi^g, Tae-Gwang Yun^h, Jong Min Kimⁱ, Ki Ro Yoon^{a,c,j,*} and Ji-Won Jung^{c,j,*}

^a Innovation Texture R&D Department, Korea Institute of Industrial Technology, 143, Hanggaul-ro, Sangnok-gu, Ansan-si, Gyeonggi-do, 15588, Republic of Korea.

^b HYU-KITECH Joint Department, Hanyang University, 143, Hanggaul-ro, Sangnok-gu, Ansan-si, Gyeonggi-do, 15588, Republic of Korea.

^c Advanced Materials Program, Department of Materials Science and Engineering, Konkuk University, Seoul 05029, Republic of Korea.

^d Department of Material Science and Engineering, University of Ulsan, Ulsan 44610, Republic of Korea.

^e Extreme Materials Research Center, Korea Institute of Science and Technology (KIST), 14-gil 5 Hwarang-ro, Seongbuk-gu, Seoul 02792, Republic of Korea.

^f Department of Materials Science and Engineering, Korea Advanced Institute of Science and Technology (KAIST), Daejeon, Republic of Korea.

^g Department of Chemical Engineering, Konkuk University, 120, Neungdong-ro, Gwangjin-gu, Seoul 05029, Republic of Korea

^h Department of Molecular Science and Technology, Ajou University, Suwon 16499, Republic of Korea

ⁱ Extreme Materials Research Center, Korea Institute of Science and Technology (KIST), 14-gil 5 Hwarang-ro, Seongbuk-gu, Seoul 02792, Republic of Korea

^j Department of Materials Science and Engineering, Konkuk University, 120, Neungdong-ro, Gwangjin-gu, Seoul 05029, Republic of Korea




Figure S1. SEM images of as-spun nanofibers: (a) low magnified and (b) high magnified images.




Figure S2. STEM-EDS mapping analysis of (a,b) ZrC@CNF, (c,d) ZrC_xO_y@CNF, and (e,f) ZrO₂@CNF.




Figure S3. EDS results of (a) ZrC@CNF, (b) ZrO_xC_y@CNF, and (c) ZrO₂@CNF catalysts.




Figure S4. High-magnification TEM images of Zr-containing nanodomains embedded in the CNF matrix.

Figure S5. (a) TGA and DSC graphs of ZrC@CNF, ZrO_xC_y@CNF, and ZrO₂@CNF.




Figure S6. BJH plots of ZrC@CNF, ZrO_xC_y@CNF, and ZrO₂@CNF for pore size distribution.




Figure S7. Chronoamperometry test of ZrC@CNF, ZrC_xO_y@CNF, and ZrO₂@CNF.

Table S1. Comparison of the electrochemical performance between the ZrO₂@CNF and the recently reported electrocatalysts.

Samples	Electrolytes	H ₂ O ₂ selectivity (%)	Mass activity (A g ⁻¹)	Electro transfer number	Onset potential (V vs. RHE)	Ref
Au-Pt-Ni	0.1M KOH	95	192.9	2.11	0.73	1
Fe-C-O	0.1M KOH	95	N/A	2.09	0.822	2
Ba _{0.5} Sr _{0.5} Fe _(1-x) Cu _x O _{3-δ}	0.1M KOH	65	N/A	3.1	0.7	3
BCN	0.1M KOH	70	N/A	2.5	0.83	4
O-CNTs	0.1M KOH	90	N/A	N/A	0.75	5
Co-NG(O)	0.1M KOH	82	284±22	N/A	0.85	6
Co-Nx-C	0.1M KOH	80	N/A	N/A	0.84	7
ZrO ₂ @CNF	0.1M KOH	85.3	14.0	2.3	0.75	This work

Table S2. Atomic percentage (at%) values obtained from XPS peak deconvolution.

	ZrC@CNF (At %)	ZrC_xO_y@CNF (At %)	ZrO₂@CNF (At %)
Zr 3d			
Zr-O	52.48	87.97	100
Zr-C	47.52	12.03	-
O 1s			
-OH	24.24	10.74	5.50
O_v	27.87	39.31	41.11
O_L	47.89	49.95	53.39
C 1s			
sp²	76.22	27.78	37.21
sp³	4.62	29.61	28.49
C-O	10.04	33.94	25.64
O-C=O	9.12	8.67	8.66

Supporting reference

1. Zheng Z, Ng YH, Wang D, Amal R. Epitaxial Growth of Au–Pt–Ni Nanorods for Direct High Selectivity H₂O₂ Production., *Adv. Mater.*, **2016**, 28, 9949–9955. doi:10.1002/adma.201603662.
2. Jiang K, Back S, Akey AJ, Xia C, Hu Y, Liang W, Schaak D, Stavitski E, Nørskov JK, Siahrostami S, et al., Highly selective oxygen reduction to hydrogen peroxide on transition metal single atom coordination., *Nat. Commun.*, **2019**, 10, 3997, doi:10.1038/s41467-019-11992-2.
3. Venkatesan SV, Mostaghimi AHB, Thangadurai V, Siahrostami S. Cu-doped Ba_{0.5}Sr_{0.5}FeO_{3-δ} for electrochemical synthesis of hydrogen peroxide via a 2-electron oxygen reduction reaction., *Electrochemical Science Advances*, **2023**, 3, doi:10.1002/elsa.202100140.
4. Liu Z, Gao D, Hu L, Liu F, Liu H, Li Y, Zhang J, Xue Y, Tang C. Metal-Free Boron-Rich Borocarbonitride Catalysts for High-Efficient Oxygen Reduction to Produce Hydrogen Peroxide., *Chemistry Select*, **2022**, 7, doi:10.1002/slct.202104203.
5. Lu Z, Chen G, Siahrostami S, Chen Z, Liu K, Xie J, Liao L, Wu T, Lin D, Liu Y, et al. High-efficiency oxygen reduction to hydrogen peroxide catalysed by oxidized carbon materials. *Nat. Catal.*, **2018**, 1, 156–162, doi:10.1038/s41929-017-0017-x.
6. Jung E, Shin H, Lee B-H, Efremov V, Lee S, Lee HS, Kim J, Hooch Antink W, Park S, Lee K-S, et al. Atomic-level tuning of Co–N–C catalyst for high-performance electrochemical H₂O₂ production. *Nat. Mater.*, **2020**, 19, 436–442, doi:10.1038/s41563-019-0571-5.
7. Li B, Zhao C, Liu J, Zhang Q. Electrosynthesis of Hydrogen Peroxide Synergistically Catalyzed by Atomic Co–Nx–C Sites and Oxygen Functional Groups in Noble-Metal-Free Electrocatalysts., *Advanced Materials*, **2019**, 31, doi:10.1002/adma.201808173.