

Supporting Information

Penicillamine-Loaded MIL-100(Fe) for Precise Targeting Copper

Chelation in Wilson's Disease

Wei Fang^{a, c, #}, Qian Wang^{a, #}, Houyuan Yang^{a, #}, Hao Lv^a, Mengqi Li^a, Yaowu Liu^b,
Chenglin Shu^{a, *}, Dianlei Wang^{a, c, *}

^a School of Pharmacy, Anhui University of Chinese Medicine, Hefei, Anhui 230012,
China

^b Bozhou Vocational and Technical College, Bozhou, Anhui, 230031, China

^c Anhui Province Key Laboratory of Active Natural products, Hefei, Anhui 230012,
China

[#]These authors contributed equally to this work.

^{*}Corresponding author:

Dianlei Wang (dlwang@ahtcm.edu.cn); Chenglin Shu (shuchenglin@ahtcm.edu.cn)




Fig. S1 Drug loading efficiency at different molar ratios




Fig. S2 The elemental distribution energy spectrum in MIL-100(Fe)-DPA

Table. S1 Changes in surface area and pore volume

Samples	Surface area (SBET/m ² ·g ⁻¹)	Pore volume (Vt/cm ³ ·g ⁻¹)
MIL-100(Fe)	1343	0.556
MIL-100(Fe)-DPA	969	0.425