

Supporting Information

In situ generation of hydrogen peroxide using a schwertmannite/nickel foam catalyst for enhanced heterogenous Fenton degradation of dye wastewater

Kun Feng^a, Shuping Zhang^a, Yanni Liu^b, Yongjun Shen^a, Pin Zhou^a, Jiayu Gu^a, Mingjie Yin^a, Neng Tao^{a,*}

^a Research Center of Secondary Resources and Environment, School of Chemical Engineering and Materials, Changzhou Institute of Technology, Changzhou 213022, China

^b Shandong Wandou Inspection Services Co., Ltd, Weifang 261205, China

***Corresponding author.**

E-mail address: SZHCH99@163.com (Neng Tao).

Table S1 The catalytic systems for in-situ production H₂O₂ and organic pollutant degradation.

Materials	Reaction conditions	Contaminants	H ₂ O ₂ generation	Removal efficiency (%)	Refs
Sch/NF	Heterogenous Fenton, [RhB] = 20 mg/L, [Catalysts] = 3*3 cm ² , pH = 2, 180 rpm	RhB	559.8 μM/h	99 (15 min)	--
ACNN	Photocatalytic, [Catalysts] = 0.5 g/L, 300 W Xenon lamp (λ > 420 nm)	--	10.2 mM/h (1 g)	--	1,2
Cv-g-C ₃ N ₄	Photocatalytic, [Catalysts] = 1 g/L, 300 W Xenon lamp (λ > 420 nm)	--	96 μM/h (100 mg)	--	3
KLCN (lignin-derived carbon ring-embedded and nitrogen defect co-doped g-C ₃ N ₄)	Photocatalytic, [Catalysts] = 1 g/L, 300 W xenon lamp (λ > 420 nm)	--	1856.8 μM/h (50 mg)	--	4
α-Fe ₂ O ₃ /ZnFe ₂ O ₄ @Ti ₃ C ₂	Photo Fenton, [RhB] = 8 mg/L, [Catalysts] = 0.5 g/L, 500 W Xe lamp (λ > 420 nm)	RhB	--	88.3 (50 min)	5,6
α-Fe ₂ O ₃ /g-C ₃ N ₄	Photo Fenton, [Catalysts] = 1 g/L, [RhB] = 10 mg/L, 300 W Xenon lamp	RhB	--	96 (90 min)	7
Fe-CHI/Ni ACF Fe-CHI/Ni sandwich film cathode	Electro-Fenton, [RhB] = 5 mg/L, pH = 6.2, I = 10 mA, Na ₂ SO ₄ = 0.05 M, air flow rate = 0.1 m ³ /h	RhB	--	92 (120 min)	8,9
FeS	Fenton-like, [Phenol] = 5 mg/L, [FeS] = 1 g/L, pH = 7	Phenol	--	35 (120 min)	10




Fig. S1 SEM diagrams of NF (a, b, c,) and Sch/NF composite catalyst (d, e, f).




Fig. S2 XPS spectra of Sch/NF and Sch. XPS broad scan survey spectra of Sch/NF (a). High resolution of Fe2p of Sch (b).




Fig. S3 The degradation efficiency of tetracycline hydrochloride, methylene blue and aniline blue using Sch/NF. (Tetracycline hydrochloride: 20 mg/L, methylene blue: 20 mg/L and aniline blue: 20 mg/L, a piece of Sch/NF (3 cm*3 cm), pH = 2, rotation rate: 180 rpm).




Fig. S4 Effect of light irradiation (a) and different dosage (b) of Sch/NF composite catalyst on degradation rate of RhB. Experimental conditions: Rhodamine B: 20 mg/L, pH: 2.0, rotation rate: 180 rpm.




Fig. S5 Content change of Fe²⁺ in the degradation of RhB by Sch/NF catalyst (a). Reaction

condition: RhB: 20 mg/L, a piece of Sch/NF (3 cm*3 cm), pH = 2, rotation rate: 180 rpm.

Degradation of MB in the homogeneous Fenton system of Fe²⁺-H₂O₂ system (b). Experimental

conditions: RhB = 20 mg/L, H₂O₂ = 10 mg/L, Fe²⁺ = 0.2 mg/L, pH = 2.




Fig. S6 Stability and reusability of Sch/NF catalyst. RhB degradation efficiency during three

successive batches of degradation experiments by Sch/NF catalyst. Experimental conditions: RhB:

20 mg/L, a piece of Sch/NF (3 cm*3 cm), pH: 2.0.




Fig.S7 EDS spectra of Sch/NF before (a) and after reaction (b).




Fig. S8 SEM images and EDS elemental mapping of Ni, Fe, S, and O elements for Sch/NF catalyst after 3th reaction.

References

- 1 S. Wu, H. Yu, S. Chen and X. Quan, *ACS Catal*, 2020, **10**, 14380–14389.
- 2 Y. Zhang, D. Wu, X. Zeng, B. Qiu, Q. Zhu and J. Zhang, *Adv Sci*, 2025, **12**, e07913.
- 3 S. Li, G. Dong, R. Hailili, L. Yang, Y. Li, F. Wang, Y. Zeng and C. Wang, *Appl Catal B*, 2016, **190**, 26–35.
- 4 Y. Xu, G. Wang, W. Li, Z. Yuan and C. Si, *Chem Eng J*, 2025, **503**, 158655.
- 5 H. Zhang, M. Li, C. Zhu, Q. Tang, P. Kang and J. Cao, *Ceram Int*, 2020, **46**, 81–88.
- 6 Y. Liu, Y. Zhao and J. Wang, *J Hazard Mater*, 2021, **404**, 124191.
- 7 Y. Wang, H. Song, J. Chen, S. Chai, L. Shi, C. Chen, Y. Wang and C. He, *Appl Surf Sci*, 2020, **512**, 145650.
- 8 Y. Fan, Z. Ai and L. Zhang, *J Hazard Mater*, 2010, **176**, 678–684.
- 9 Y. Chen, Y. Xu, Z. Ma, H. Wang, Q. Chen, S. Zhang, K. Feng, X. Chen and X. Kong, *Org Biomol Chem*, 2026
- 10 D. Cheng, A. Neumann, S. Yuan, W. Liao and A. Qian, *Environ Sci Technol*, 2020, **54**, 4091–4101.