

Cyclohexylmethylammonium iodide-based bilateral interface engineering for efficient perovskite solar cells with improved stability and negligible hysteresis

Litong Zhou[‡], Yu Huo[‡], Guangmei Zhai^{}, Zhuoyu Zhao, Chunyan Yu^{*}, Wei Jia, Bingshe Xu*

Key Laboratory of Interface Science and Engineering in Advanced Materials of Ministry of Education, College of Materials Science and Engineering, Taiyuan University of Technology, Taiyuan, Shanxi 030024, China

[‡] These authors contribute equally to this work.

*Corresponding Authors: E-mail: zhaiguangmei@tyut.edu.cn (G. Zhai); yuchunyan@tyut.edu.cn (C. Yu)

Table S1 Photovoltaic performance parameters of Control, B-1, S-3 and B-1+S-3

Sample	V_{oc} [V]	J_{sc} [$\text{mA}\cdot\text{cm}^{-2}$]	FF [%]	PCE [%]
Control	1.04±0.02	22.97±0.43	68.36±2.37	16.36±0.71
B-1	1.08±0.01	23.64±0.27	72.02±1.33	18.42±0.30
S-3	1.09±0.01	23.57±0.55	73.39±2.89	18.90±0.56
B-1+S-3	1.10±0.01	24.17±0.31	75.70±2.31	20.01±0.42