

## Supplementary Materials

### **Design of Al decorated C<sub>24</sub>N<sub>24</sub> fullerene for efficient adsorption and removal of methylene blue dye from water**

Habib Ullah<sup>a</sup>, Zakir Zaman Khan<sup>b</sup>, Akif Safeen<sup>c</sup>, Adnan Ali Khan<sup>d</sup>, Noor Ul Islam<sup>e</sup>, Ghafar Ali<sup>f</sup>, Basit Ali<sup>\*g</sup>, Imran Shakir<sup>h</sup>, and Yi Xie<sup>\*a</sup>

<sup>a</sup>State Key Laboratory of Silicate Materials for Architectures, Wuhan University of Technology, Wuhan 430070, P.R. China

<sup>b</sup>Department of Chemistry, University of Malakand, Chakdara, Dir Lower 18800, Khyber Pakhtunkhwa, Pakistan

<sup>c</sup>Department of Physics, University of Poonch Rawalakot, Rawalakot, 12350, Pakistan

<sup>d</sup>School of Science, Harbin Institute of Technology (Shenzhen), Shenzhen, China

<sup>e</sup>Government Degree Collage Lalqilla Dir Lower, Lalqilla 18350, Khyber Pakhtunkhwa, Pakistan; and Higher Education Department Khyber Pakhtunkhwa, Peshawar, Pakistan

<sup>f</sup>Nanomaterials Research Group (NRG), Physics Division, PINSTECH, Nilore, Islamabad, Pakistan


<sup>g</sup>Department of Chemistry and Materials Science, Aalto University, P.O. Box 16100, FI-00076 Aalto, Finland

<sup>h</sup>Department of Physics, Faculty of Science, Islamic University of Madinah, Madinah 42351, Saudi Arabia


\*Correspondence authors

[basit.ali@aalto.fi](mailto:basit.ali@aalto.fi) (Basit Ali)






[xiex@whut.edu.cn](mailto:xiex@whut.edu.cn) (Yi Xie)




**Fig. S1.** Optimized geometry of pristine  $C_{24}N_{24}$  fullerene (a), MB dye (b), and their corresponding molecular-electrostatic potential map (c, d).



**Fig. S2.** Optimized geometry of the single Al incorporated C<sub>24</sub>N<sub>24</sub> fullerene (Al@C<sub>24</sub>N<sub>24</sub>) from the top view (a) and front view (b), along with the corresponding partial density of state plot (c).




HOMO  
-3.88 eV




LUMO  
-2.91 eV


**Fig. S3.** Molecular-electrostatic potential map (a), charge-density difference contour (b), deformation-charge density map (c), AIM molecular graph (d), and HOMO-LUMO (e, f) of  $\text{Al}_6@C_{24}N_{24}$  system




**Fig. S4.** Charge-density difference (a) and molecular-electrostatic potential map (b) plot for  $\text{Al}@C_{24}N_{24}$  fullerene




**Fig. S5.** Graphical representation of AIM plot of the Al@C<sub>24</sub>N<sub>24</sub> fullerene. The orange color dots encircled with blue dotted line show the bond critical points between Al–N bond




**Fig. S6.** Structure of Al<sub>6</sub>@C<sub>24</sub>N<sub>24</sub> after AIMD simulations performed at 500 K (a) and 1000 K (b) for 2 ps




**Fig. S7.** Structure of  $\text{Al}_6@C_{24}N_{24}$  after AIMD simulations performed at 500 K (a) and 1000 K (b) for 10 ps




**Fig. S8.** Optimized geometry of  $C_{24}N_{24}$  nanocage with adsorbed MB dye (a), corresponding Charge-density difference map (b) and partial density of state plot (c). All distances are in Å



**Fig. S9.** AIM plot for MB adsorption over bare C<sub>24</sub>N<sub>24</sub> fullerene. Golden color line and ball represent the bond critical points



**Fig. S10.** Optimized geometry of the MB adsorption over the OH-Al@C<sub>24</sub>N<sub>24</sub> system. All distances are in Å



**Fig. S11.** Relaxed structure of Rhodamine B dye adsorbed over Al@C<sub>24</sub>N<sub>24</sub> through Xanthene oxygen (a) and carboxyl oxygen (b). All distances are in Å

**Table S1.** The computed electron density ( $\rho(r)$  a.u.), its Laplacian ( $\nabla^2\rho(r)$  a.u.) and total electron energy density ( $H(r)$  a.u.) (au) for N–Al bonds in Al@C<sub>24</sub>N<sub>24</sub> system

Bond	$\rho(r)$	$\nabla^2\rho(r)$	$H(r)$
N–Al (1)	0.072	0.450	–0.0017
N–Al (2)	0.072	0.450	–0.0017
N–Al (3)	0.072	0.450	–0.0017
N–Al (4)	0.072	0.450	–0.0017

**Table S2.** The computed electron density ( $\rho(r)$  a.u.), its Laplacian ( $\nabla^2\rho(r)$  a.u.) and total electron energy density ( $H(r)$  a.u.) for N–Al bonds in Al<sub>6</sub>@C<sub>24</sub>N<sub>24</sub> system

Bond	$\rho(r)$	$\nabla^2\rho(r)$	$H(r)$
N–Al (1)	0.077	0.422	–0.0094
N–Al (2)	0.077	0.422	–0.0094
N–Al (3)	0.077	0.422	–0.0094
N–Al (4)	0.077	0.422	–0.0094

**Table S3.** Calculated intermolecular bond length ( $\text{\AA}$ ), adsorption energy ( $E_{\text{ad}}$  eV), charge density transfer ( $Q_{\text{CT}}$  e), electron density ( $\rho(\mathbf{r})$  a.u.), Laplacian of electron the density ( $\nabla^2\rho(\mathbf{r})$  a.u.), and energy density ( $H(\mathbf{r})$  a.u.) for adsorption of MB over the bare  $\text{C}_{24}\text{N}_{24}$  nanocage

Complex	H---B	$E_{\text{ad}}$	$Q_{\text{CT}}$	$\rho(\mathbf{r})$	$\nabla^2\rho(\mathbf{r})$	$H(\mathbf{r})$
MB- $\text{C}_{24}\text{N}_{24}$	2.42, 2.38	-0.49	0.001, 0.004	0.008,	0.033	0.0017
				0.008	0.031	0.0012

**Table S4.** Comparative analysis of the adsorption of various competitive species over the  $\text{Al@C}_{24}\text{N}_{24}$  adsorbent.  $R$  ( $\text{\AA}$ ) for intermolecular distance and  $E_{\text{ad}}$  (eV) for adsorption energy

System	$R$ ( $\text{\AA}$ )	$E_{\text{ad}}$ (eV)
Ca- $\text{Al@C}_{24}\text{N}_{24}$	3.57	0.24
Cl- $\text{Al@C}_{24}\text{N}_{24}$	2.34	-0.31
Na- $\text{Al@C}_{24}\text{N}_{24}$	2.94	-0.11
$\text{SO}_4$ - $\text{Al@C}_{24}\text{N}_{24}$	1.89	-2.51
$\text{H}_2\text{O}$ - $\text{Al@C}_{24}\text{N}_{24}$	1.94	-1.54
OH- $\text{Al@C}_{24}\text{N}_{24}$	1.71	-5.05
RB- $\text{Al@C}_{24}\text{N}_{24}$	*2.12/♦2.05	*-1.89/♦-2.43

\* Xanthene oxygen interaction of RB with the adsorbent

♦ Carboxyl Oxygen interaction of RB with the adsorbent

**Table S5.** Desorption time ( $\tau$ ) of MB from the  $\text{Al@C}_{24}\text{N}_{24}$  surface at various temperature (K)

Complex	$E_{\text{ad-D3}}$ (eV)	$\tau$ @ 298 K (s)	$\tau$ @ 398 K (s)	$\tau$ @ 498 K (s)
MB- $\text{Al@C}_{24}\text{N}_{24}$ -N(1)	-2.97	$1.63 \times 10^{38}$	$3.95 \times 10^{25}$	$1.13 \times 10^{18}$
MB- $\text{Al@C}_{24}\text{N}_{24}$ -N(2)	-2.03	$2.03 \times 10^{21}$	$4.20 \times 10^{13}$	$2.58 \times 10^8$
MB- $\text{Al@C}_{24}\text{N}_{24}$ -S	-2.18	$7.40 \times 10^{24}$	$3.70 \times 10^{15}$	$1.15 \times 10^{10}$