

TABLE 1. Summary of Verified Fiber Count of Amosite Slides

Amosite Slide No.	PAT Sample No.	PAT Reference Values (f/ mm ²)	PAT Proficiency Ranges (f/ mm ²)	Verified Fibers per No. of Fileds Examined	Verified Fibers Densities (f/ mm ²)
6	102-1	369.30	194.7--599.5	115.5/39	377.27
8	102-1	369.30	194.7--599.5	124/40	394.90
29	102-1	369.30	194.7--599.5	100.5/30	426.75
39	102-2	573.20	201.4--1135.2	102.5/32	408.04
40	102-2	573.20	201.4--1135.2	107/32	425.96
41	104-1	238.00	107.6--419.5	111/80	176.75
42	104-1	238.00	107.6--419.5	129.5/80	206.21
43	104-1	238.00	107.6--419.5	120/80	191.08
44	106-1	231.1	115.8--395.9	105.5/80	167.99
45	106-3	805.6	422.2--1311.6	143.5/20	914.01
46	106-3	805.6	422.2--1311.6	107.5/20	684.71
47	108-2	495.8	282--769.6	121/20	513.80
25	124-2	639.14	382.56 --961.22	117/20	745.22
26	124-2	639.14	382.56 --961.22	121/20	770.70
27	124-2	639.14	382.56 --961.22	114/20	726.11
28	124-3	502.61	263.75--817.8	121.5/30	515.92
30	124-3	502.61	263.75--817.8	86.5/22	500.87
31	124-4	422.90	208.8--711-76	113/40	359.87
36	136-1	113.05	22.4 -- 191.06	55.5/100	70.70
37	136-1	113.05	22.4 -- 191.06	74.5/100	94.90
38	136-1	113.05	22.4 -- 191.06	78.5/100	100.00
1	136-3	337.3	189.1 -- 528.1	93/40	296.18
2	136-3	337.3	189.1 -- 528.1	106.5/40	339.17
3	136-3	337.3	189.1 -- 528.1	103.5/40	329.62
4	136-3	337.3	189.1 -- 528.1	115.5/60	245.22
5	136-3	337.3	189.1 -- 528.1	137.5/60	291.93
7	136-3	337.3	189.1 -- 528.1	105/50	267.52
22	136-3	337.3	189.1 -- 528.1	104.5/50	266.24
9	136-4	537.86	316.54 -- 817.12	105/30	445.86
10	136-4	537.86	316.54 -- 817.12	87.5/30	371.55
11	136-4	537.86	316.54 -- 817.12	111.5/30	473.46
12	136-4	537.86	316.54 -- 817.12	118.5/30	503.18
13	136-4	537.86	316.54 -- 817.12	100.5/30	426.75
34	148-1	226.26	119.36 --367.04	104.5/60	221.87
35	148-1	226.26	119.36 --367.04	107/60	227.18
19	152-1	378.48	215.13--587.61	118/60	250.53
33	152-1	378.48	215.13--587.61	110.5/60	234.61
14	154-1	222.94	117.3--362.22	129.5/80	206.21
15	154-1	222.94	117.3--362.22	99.5/70	181.07
16	154-1	222.94	117.3--362.22	93/80	148.09
32	154-1	222.94	117.3--362.22	119/70	216.56
18	154-3	252.38	135.66--405.04	109/70	198.36
20	154-3	252.38	135.66--405.04	110/60	233.55
21	154-3	252.38	135.66--405.04	90/60	191.08
23	154-3	252.38	135.66--405.04	104.5/80	166.40
24	154-3	252.38	135.66--405.04	121.5/70	221.11
17	156-1	133.94	73.95--211.63	98/100	124.84