

TABLE II. Summary of Verified Fiber Count of Chrysotile Slides

Chrysotile Slide No.	PAT Sample No.	PAT Reference Values (f/ mm ²)	PAT Proficiency Ranges (f/ mm ²)	Verified Fibers per No. of Fields Examined	Verified Fibers Densities (f/ mm ²)
1	109-1	245	67.5--533.2	109.5/50	278.98
2	109-3	490.1	173.9--968.4	112.5/24	597.13
3	109-3	490.1	173.9--968.4	135/24	716.56
5	109-4	279.4	85.7--584.3	110/34	412.14
6	127-1	223.4	76.30--447.72	119.560	253.72
7	127-1	223.4	76.30--447.72	117.550	299.36
8	127-1	223.4	76.30--447.72	110.560	234.61
9	127-1	223.4	76.30--447.72	101/50	257.32
10	127-2	348.5	113.96--710.88	106/40	337.58
11	127-2	348.5	113.96--710.88	97/38	325.18
12	127-2	348.5	113.96--710.88	138/40	439.49
27	127-2	348.52	113.96--710.88	108.5/40	345.54
16	127-3	213.63	61.66--457.10	97.5/60	207.01
14	143-1	102.77	50.36--173.68	108/80	171.97
15	143-1	102.77	50.36--173.68	116/80	184.71 ^A
17	143-1	102.77	50.36--173.68	129.5/80	206.21 ^A
18	143-1	102.77	50.36--173.68	111/80	176.75 ^A
19	143-1	102.77	50.36--173.68	96/80	152.87
20	143-1	102.77	50.36--173.68	94/80	149.68
21	143-2	223.43	109.48--377.60	126/60	267.52
22	143-2	223.43	109.48--377.60	54/30	229.30
23	143-2	223.43	109.48--377.60	105/40	334.39
24	143-3	458.46	224.65--774.80	134.5/24	713.91
25	143-3	458.46	224.65--774.80	141.5/24	751.06
29	143-3	458.46	224.65--774.80	138.5/24	735.14
30	143-3	458.46	224.65--774.80	138.5/24	735.14
28	147-1	262.42	128.59--443.49	103.5/40	329.62
26	151-1	150.25	73.62--253.92	91.5/80	145.70
13	153-1	59.55	29.18--100.64	43/97	56.47
31	153-1	59.55	29.18--100.64	54.5/100	69.43
32	153-1	59.55	29.18--100.64	56.5/100	71.97
33	153-2	115.31	56.5--194.88	133/100	169.42
4	157-2	91.77	20.59--213.81	46/100	58.60

^A Above PAT proficiency range