


**ESI for “Synthesis of polymer bearing cyclic carbonate group by selective gas-solid phase reaction of carbon dioxide into oxirane-containing polymers” by Bungo Ochiai, Tokinori Iwamoto and Takeshi Endo**

**Relationship between time and  $\ln([Ox]_0/[Ox])$  (conversion <85%).**



Temp (°C)	90	100	110	120
$k \times 10^3$ (min <sup>-1</sup> )	9.74	17.6	32.1	45.5
$r^2$	0.958	0.964	0.972	0.985

### Relationship between $1/T$ and $\log k$

