

Electronic supplementary information (ESI)




Figure S1 (Electronic supplementary information): A representative EDAX spectrum of the TL film sample after final alloy formation at 750 °C in H₂-Ar. An atomic ratio of Au:Cu ≈ 0.52:48 has been estimated from the signals of Au and Cu.