

Supplementary data

Dual-Shape Properties of Triple-Shape Polymer Networks with Crystallizable Network Segments and Grafted Side Chains

Ingo Bellin^{†1}, Steffen Kelch[†], and Andreas Lendlein^{†*}

[†]Center for Biomaterial Development, Institute of Polymer Research, GKSS Research Center
Geesthacht, Kantstr. 55, 14513 Teltow, Germany

*Corresponding author. E-mail: andreas.lendlein@gkss.de

Table S1 Results from swelling experiments performed in chloroform.^[a]

Network ^[b]	G [%]	Q [%]
PCL(20)PEG	95.0 ± 0.3	1140 ± 10
PCL(30)PEG	92.5 ± 0.8	1110 ± 10
PCL(40)PEG	91.5 ± 0.3	1080 ± 10
PCL(50)PEG	90.4 ± 0.3	1140 ± 10
PCL(60)PEG	88.5 ± 0.3	1150 ± 20
PCL(70)PEG	86.2 ± 0.2	1110 ± 20
PCL(80)PEG	85.4 ± 0.3	1050 ± 10
PCL(100)PEG	82.2 ± 0.1	1060 ± 10

[a] G : gel content, Q : degree of swelling, w_{PCL} : weight fraction of PCL in the extracted polymer network. [b] The number in parentheses gives the weight fraction of PCLDMA in the educt mixture.

¹ Present address: Global Polymer Research – Foams, BASF AG, 67056 Ludwigshafen, Germany