

The Synthesis and Structural Investigation of Mixed Lithium / Sodium Amides

Rebecca L. Lowton, Martin O. Jones, William I. F. David, Simon R. Johnson, Marco Sommariva, and
 Peter. P. Edwards

Supplementary Crystallographic Information for System I

x = 1.0

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH2_00 – LiNH2_10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH2_00 – LiNH2_10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH2_00 – LiNH2_10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name		LiNH2_00					
Space Group		I – 4					
Scale		0.000092(2)					
Lattice Parameter		a = b = a _{liam_00} = 1.0*aLi ₀ + 0.0*aLi ₁₀ = 5.03701(3) Å					
		c = c _{liam_00} = 1.0*cLi ₀ + 0.0*cLi ₁₀ = 10.25577(3) Å					
Occupancy Parameter		oLi00 = 1.0* yLi ₀ + 0.0*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH2_01					
Space Group		I – 4					
Scale		0.000879(4)					
Lattice Parameter		a = b = a _{liam_01} = 0.9*aLi ₀ + 0.1*aLi ₁₀ = 5.03750(2) Å					
		c = c _{liam_01} = 0.9*cLi ₀ + 0.1*cLi ₁₀ = 10.26342(5) Å					
Occupancy Parameter		oLi01 = 0.9* yLi ₀ + 0.1*yLi ₁₀ = 0.983(4)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.983(4)	b _{eq} = 3.0(1)

Site	Na 2	0.0	0.5	-0.25	occ (1-oLi01)	0.017(3)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I - 4					
Scale		0.000110(3)					
Lattice Parameter		$a = b = a_{\text{liam_02}} = 0.8*a_{Li_{10}} + 0.2*a_{Li_0} = 5.03800(2)\text{\AA}$					
		$c = c_{\text{liam_02}} = 0.8*c_{Li_{10}} + 0.2*c_{Li_0} = 10.27106(6)\text{\AA}$					
Occupancy Parameter		$oLi_{02} = 0.8* y_{Li_{10}} + 0.2*y_{Li_0} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi02)	0.021(5)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000013(2)					
Lattice Parameter		$a = b = a_{\text{liam_03}} = 0.7*a_{Li_{10}} + 0.3*a_{Li_0} = 5.03849(3)\text{\AA}$					
		$c = c_{\text{liam_03}} = 0.7*c_{Li_{10}} + 0.3*c_{Li_0} = 10.27871(8)\text{\AA}$					
Occupancy Parameter		$oLi_{03} = 0.7* y_{Li_{10}} + 0.3*y_{Li_0} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam_04}} = 0.6*a_{Li_{10}} + 0.4*a_{Li_0} = 5.03899(3)\text{\AA}$					
		$c = c_{\text{liam_04}} = 0.6*c_{Li_{10}} + 0.4*c_{Li_0} = 10.28635(9)\text{\AA}$					
Occupancy Parameter		$oLi_{04} = 0.6* y_{Li_{10}} + 0.4*y_{Li_0} = 0.972(7)$					

Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.0000010(9)					
Lattice Parameter		$a = b = a_{liam_05} = 0.5*aLi_0 + 0.5*aLi_{10} = 5.03948(4)\text{\AA}$					
		$c = c_{liam_05} = 0.5*cLi_0 + 0.5*cLi_{10} = 10.2940(1)\text{\AA}$					
Occupancy Parameter		$oLi05 = 0.5* yLi_0 + 0.5*yLi_{10} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.0000010(8)					
Lattice Parameter		$a = b = a_{liam_06} = 0.4*aLi_0 + 0.6*aLi_{10} = 5.03997(4)\text{\AA}$					
		$c = c_{liam_06} = 0.4*cLi_0 + 0.6*cLi_{10} = 10.3016(1)\text{\AA}$					
Occupancy Parameter		$oLi06 = 0.4* yLi_0 + 0.6*yLi_{10} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.0000010(7)					
Lattice Parameter		$a = b = a_{liam_07} = 0.3*aLi_0 + 0.7*aLi_{10} = 5.04047(5)\text{\AA}$					

		$c = c_{\text{liam } 07} = 0.3 * c_{\text{Li}_0} + 0.7 * c_{\text{Li}_{10}} = 10.3093(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}07} = 0.3 * y_{\text{Li}_0} + 0.7 * y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi07)	0.040(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.0000010(7)					
Lattice Parameter		$a = b = a_{\text{liam } 08} = 0.2 * a_{\text{Li}_0} + 0.8 * a_{\text{Li}_{10}} = 5.04096(5) \text{ \AA}$					
		$c = c_{\text{liam } 08} = 0.2 * c_{\text{Li}_0} + 0.8 * c_{\text{Li}_{10}} = 10.3169(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}08} = 0.2 * y_{\text{Li}_0} + 0.8 * y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi08)	0.04(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					
Scale		0.0000010(6)					
Lattice Parameter		$a = b = a_{\text{liam } 09} = 0.1 * a_{\text{Li}_0} + 0.9 * a_{\text{Li}_{10}} = 5.04146(6) \text{ \AA}$					
		$c = c_{\text{liam } 09} = 0.1 * c_{\text{Li}_0} + 0.9 * c_{\text{Li}_{10}} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}09} = 0.1 * y_{\text{Li}_0} + 0.9 * y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi09)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_10					
-------------------	--	----------	--	--	--	--	--

Space Group		I – 4					
Scale		0.0000010(4)					
Lattice Parameter		$a = b = a_{\text{Li10}} = 0.0 \cdot a_{\text{Li0}} + 1.0 \cdot a_{\text{Li10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{\text{Li10}} = 0.0 \cdot c_{\text{Li0}} + 1.0 \cdot c_{\text{Li10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li10}} = 0.0 \cdot y_{\text{Li0}} + 1.0 \cdot y_{\text{Li10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		Li2O					
Space Group		Fm3m					
Scale		0.000126(2)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{\text{eq}} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.8$

Phase Name		LiNa2(NH2)3					
Space Group		P42/m					
Scale		0.00000013(5)					
Lattice Parameter		$a = b = 6.2838(1) \text{ \AA}$					
		$c = 11.1485(2) \text{ \AA}$					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{\text{eq}} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{\text{eq}} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{\text{eq}} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{\text{eq}} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{\text{eq}} = 2.0455$

Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_0 = 5.0828(4)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_0 = 11.5415(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{\text{N}0} = 0.0997(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{\text{N}10} = 0.1014(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{\text{Na}0} = 0.938(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{\text{Na}10} = 0.79(2)$

Phase Name		Li ₃ Na(NH ₂) ₄ _00					
Space Group		I – 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₀ = 1.0*a ₀ + 0.0*a ₁₀ = 5.08280(4) Å					
		c = c ₀₀ = 1.0*c ₀ + 0.0*c ₁₀ = 11.5415(2) Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 1.0* z _{N0} + 0.0* z _{N10} = 0.0997(2)					
Occupancy Parameter		oNa00 = 1.0* yNa ₀ + 0.0*yNa ₁₀ = 0.938(7)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₀)	0.983(7)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₀)	0.062(7)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _01					
Space Group		I – 4					
Scale		0.0000001(6)					
Lattice Parameter		a = b = a ₀₁ = 0.9*a ₀ + 0.1*a ₁₀ = 5.08152(6) Å					
		c = c ₀₁ = 0.9*c ₀ + 0.1*c ₁₀ = 11.5130(3) Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.9* z _{N0} + 0.1* z _{N10} = 0.0998(3)					
Occupancy Parameter		oNa01 = 0.9* yNa ₀ + 0.1*yNa ₁₀ = 0.923(8)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₁)	0.923(8)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₁)	0.077(8)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _02					
Space Group		I – 4					
Scale		0.0000001(6)					
Lattice Parameter		a = b = a ₀₂ = 0.8*a ₁₀ + 0.2*a ₁₀ = 5.08024(7) Å					
		c = c ₀₂ = 0.8*c ₁₀ + 0.2*c ₁₀ = 11.4844(3) Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.8* z _{N0} + 0.2* z _{N10} = 0.1000(3)					
Occupancy Parameter		oNa02 = 0.8* yNa ₀ + 0.2*yNa ₁₀ = 0.91(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₂)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₂)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I – 4					

Scale		0.0000001(6)					
Lattice Parameter		$a = b = a_{03} = 0.7*a_{10} + 0.3*a_{10} = 5.07896(9) \text{ \AA}$					
		$c = c_{03} = 0.7*c_{10} + 0.3*c_{10} = 11.4559(4) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.7*z_{N_0} + 0.3*z_{N_{10}} = 0.1002(4)$					
Occupancy Parameter		$oNa_{03} = 0.7*y_{Na_0} + 0.3*y_{Na_{10}} = 0.89(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₃)	0.89(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₃)	0.11(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _04					
Space Group		I - 4					
Scale		0.0000001(6)					
Lattice Parameter		$a = b = a_{04} = 0.6*a_{10} + 0.4*a_{10} = 5.0777(1) \text{ \AA}$					
		$c = c_{04} = 0.6*c_{10} + 0.4*c_{10} = 11.4274(5) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.6*z_{N_0} + 0.4*z_{N_{10}} = 0.1003(4)$					
Occupancy Parameter		$oNa_{04} = 0.6*y_{Na_0} + 0.4*y_{Na_{10}} = 0.88(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₄)	0.88(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₄)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _05					
Space Group		I - 4					
Scale		0.0000001(6)					
Lattice Parameter		$a = b = a_{05} = 0.5*a_{10} + 0.5*a_{10} = 5.0764(1) \text{ \AA}$					
		$c = c_{05} = 0.5*c_{10} + 0.5*c_{10} = 11.3989(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.5*z_{N_0} + 0.5*z_{N_{10}} = 0.1005(5)$					
Occupancy Parameter		$oNa_{05} = 0.5*y_{Na_0} + 0.5*y_{Na_{10}} = 0.87(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₅)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₅)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _06					
Space Group		I - 4					
Scale		0.0000001(6)					
Lattice Parameter		$a = b = a_{06} = 0.4*a_{10} + 0.6*a_{10} = 5.0751(1) \text{ \AA}$					

$c = c_{06} = 0.4 \cdot c_{10} + 0.6 \cdot c_{10} = 11.3703(6) \text{ \AA}$							
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.4 \cdot z_{N_0} + 0.6 \cdot z_{N_{10}} = 0.1007(5)$					
Occupancy Parameter		$oNa_{06} = 0.4 \cdot y_{Na_0} + 0.6 \cdot y_{Na_{10}} = 0.85(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₆)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₆)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _07					
Space Group		I - 4					
Scale		0.0000001(5)					
Lattice Parameter		$a = b = a_{07} = 0.3 \cdot a_{10} + 0.7 \cdot a_{10} = 5.0738(2) \text{ \AA}$					
		$c = c_{07} = 0.3 \cdot c_{10} + 0.7 \cdot c_{10} = 11.3418(7) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.3 \cdot z_{N_0} + 0.7 \cdot z_{N_{10}} = 0.1008(6)$					
Occupancy Parameter		$oNa_{07} = 0.3 \cdot y_{Na_0} + 0.7 \cdot y_{Na_{10}} = 0.83(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₇)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₇)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.0000001(6)					
Lattice Parameter		$a = b = a_{08} = 0.2 \cdot a_{10} + 0.8 \cdot a_{10} = 5.0726(2) \text{ \AA}$					
		$c = c_{08} = 0.2 \cdot c_{10} + 0.8 \cdot c_{10} = 11.3133(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.2 \cdot z_{N_0} + 0.8 \cdot z_{N_{10}} = 0.1010(6)$					
Occupancy Parameter		$oNa_{08} = 0.2 \cdot y_{Na_0} + 0.8 \cdot y_{Na_{10}} = 0.82(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₈)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₈)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _09					
Space Group		I - 4					
Scale		0.0000001(6)					
Lattice Parameter		$a = b = a_{09} = 0.1 \cdot a_{10} + 0.9 \cdot a_{10} = 5.0713(2) \text{ \AA}$					
		$c = c_{09} = 0.1 \cdot c_{10} + 0.9 \cdot c_{10} = 11.2847(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.1 \cdot z_{N_0} + 0.9 \cdot z_{N_{10}} = 0.1012(7)$					

Occupancy Parameter			oNa09= 0.1* yNa ₀ + 0.9*yNa ₁₀ = 0.81(2)				
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name			Li ₃ Na(NH ₂) ₄ _10				
Space Group			I - 4				
Scale			0.0000001(5)				
Lattice Parameter			a = b = a_10 = 0.0*a ₁₀ + 1.0*a ₁₀ = 5.0700(2)Å				
			c = c_10 = 0.0*c ₁₀ + 1.0*c ₁₀ = 11.2562(9)Å				
Nitrogen Z Coordinate			z N = z N ₀ = 0.0* z N ₀ + 1.0* z N ₁₀ = 0.1014(7)				
Occupancy Parameter			oNa10= 0.0* yNa ₀ + 1.0*yNa ₁₀ = 0.79(2)				
Site	Na 1	0.0	0.50	0.25	occ (oNa_10)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_10)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name			NaNH ₂				
Space Group			Fddd				
Scale			0.00000009(2)				
Lattice Parameter			a = 8.95853(2) Å				
			b = 10.4344(3) Å				
			c = 8.07177(2) Å				
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

$$x = 0.917$$

R_expected	4.521	R_expected'	9.452
R_weighted pattern	14.989	R_weighted pattern'	31.342
R Pattern	9.839	R Pattern'	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH ₂ _00 – LiNH ₂ _10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH ₂ _00 – LiNH ₂ _10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH ₂ _00 – LiNH ₂ _10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH ₂ _00 – LiNH ₂ _10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH ₂ _00 – LiNH ₂ _10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH ₂ _00 – LiNH ₂ _10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name		LiNH ₂ _00					
Space Group		I - 4					
Scale		0.000012(3)					
Lattice Parameter		a = b = a _{liam_00} = 1.0*aLi ₀ + 0.0*aLi ₁₀ = 5.03701(3) Å					
		c = c _{liam_00} = 1.0*cLi ₀ + 0.0*cLi ₁₀ = 10.25577(3) Å					
Occupancy Parameter		oLi00 = 1.0* yLi ₀ + 0.0*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH ₂ _01					
Space Group		I - 4					
Scale		0.000349(5)					
Lattice Parameter		a = b = a _{liam_01} = 0.9*aLi ₀ + 0.1*aLi ₁₀ = 5.03750(2) Å					
		c = c _{liam_01} = 0.9*cLi ₀ + 0.1*cLi ₁₀ = 10.26342(5) Å					
Occupancy Parameter		oLi01 = 0.9* yLi ₀ + 0.1*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH ₂ _02					
Space Group		I - 4					
Scale		0.000249(5)					
Lattice Parameter		a = b = a _{liam_02} = 0.8*aLi ₁₀ + 0.2*aLi ₀ = 5.03800(2) Å					
		c = c _{liam_02} = 0.8*cLi ₀ + 0.2*cLi ₁₀ = 10.27106(6) Å					
Occupancy Parameter		oLi02 = 0.8* yLi ₀ + 0.2*yLi ₁₀ = 0.979(5)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)

Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000143(4)					
Lattice Parameter		$a = b = a_{liam_03} = 0.7*aLi_0 + 0.3*aLi_{10} = 5.03849(3) \text{ \AA}$					
		$c = c_{liam_03} = 0.7*cLi_0 + 0.3*cLi_{10} = 10.27871(8) \text{ \AA}$					
Occupancy Parameter		$oLi03 = 0.7* yLi_0 + 0.3*yLi_{10} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000090(4)					
Lattice Parameter		$a = b = a_{liam_04} = 0.6*aLi_0 + 0.4*aLi_{10} = 5.03899(3) \text{ \AA}$					
		$c = c_{liam_04} = 0.6*cLi_0 + 0.4*cLi_{10} = 10.28635(9) \text{ \AA}$					
Occupancy Parameter		$oLi04 = 0.6* yLi_0 + 0.4*yLi_{10} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000060(3)					
Lattice Parameter		$a = b = a_{liam_05} = 0.5*aLi_0 + 0.5*aLi_{10} = 5.03948(4) \text{ \AA}$					
		$c = c_{liam_05} = 0.5*cLi_0 + 0.5*cLi_{10} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$oLi05 = 0.5* yLi_0 + 0.5*yLi_{10} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-	0.032(8)	$b_{eq} = 3.0(1)$

					oLi05)		
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000037(2)					
Lattice Parameter		$a = b = a_{liam_06} = 0.4*aLi_0 + 0.6*aLi_{10} = 5.03997(4)\text{Å}$					
		$c = c_{liam_06} = 0.4*cLi_0 + 0.6*cLi_{10} = 10.3016(1)\text{Å}$					
Occupancy Parameter		$oLi06 = 0.4* yLi_0 + 0.6*yLi_{10} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000027(2)					
Lattice Parameter		$a = b = a_{liam_07} = 0.3*aLi_0 + 0.7*aLi_{10} = 5.04047(5)\text{Å}$					
		$c = c_{liam_07} = 0.3*cLi_0 + 0.7*cLi_{10} = 10.3093(1)\text{Å}$					
Occupancy Parameter		$oLi07 = 0.3* yLi_0 + 0.7*yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000019(2)					
Lattice Parameter		$a = b = a_{liam_08} = 0.2*aLi_0 + 0.8*aLi_{10} = 5.04096(5)\text{Å}$					
		$c = c_{liam_08} = 0.2*cLi_0 + 0.8*cLi_{10} = 10.3169(2)\text{Å}$					
Occupancy Parameter		$oLi08 = 0.2* yLi_0 + 0.8*yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$

Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					
Scale		0.000012(2)					
Lattice Parameter		$a = b = a_{\text{liam}}_{09} = 0.1 * a_{\text{Li}_0} + 0.9 * a_{\text{Li}_{10}} = 5.04146(6) \text{ \AA}$					
		$c = c_{\text{liam}}_{09} = 0.1 * c_{\text{Li}_0} + 0.9 * c_{\text{Li}_{10}} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}09} = 0.1 * y_{\text{Li}_0} + 0.9 * y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_10					
Space Group		I - 4					
Scale		0.000022(1)					
Lattice Parameter		$a = b = a_{\text{liam}}_{10} = 0.0 * a_{\text{Li}_0} + 1.0 * a_{\text{Li}_{10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{\text{liam}}_{10} = 0.0 * c_{\text{Li}_0} + 1.0 * c_{\text{Li}_{10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}10} = 0.0 * y_{\text{Li}_0} + 1.0 * y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		Li2O					
Space Group		Fm3m					
Scale		0.000193(4)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{eq} = 0.9148$

Site	O	0.0	0.0	0.0	occ	1	$b_{eq} = 0.8$
------	---	-----	-----	-----	-----	---	----------------

Phase Name		LiNa ₂ (NH ₂) ₃					
Space Group		P4 ₂ /m					
Scale		0.0000361(3)					
Lattice Parameter		a = b = 6.2838(1) Å					
		c = 11.1485(2) Å					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{eq} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{eq} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{eq} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{eq} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$a_0 = 5.0828(4)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_0 = 11.5415(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name		Li ₃ Na(NH ₂) ₄ 00					
Space Group		I – 4					
Scale		0.0000012(8)					
Lattice Parameter		a = b = a ₀₀ = 1.0*a ₀ + 0.0*a ₁₀ = 5.08280(4) Å					
		c = c ₀₀ = 1.0*c ₀ + 0.0*c ₁₀ = 11.5415(2) Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 1.0* z _{N₀} + 0.0* z _{N₁₀} = 0.0997(2)					
Occupancy Parameter		o _{Na00} = 1.0* y _{Na₀} + 0.0*y _{Na₁₀} = 0.938(7)					
Site	Na 1	0.0	0.50	0.25	occ (o _{Na₀₀})	0.983(7)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-o _{Na₀₀})	0.062(7)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name		Li ₃ Na(NH ₂) ₄ 01					
Space Group		I – 4					
Scale		0.000019(1)					
Lattice Parameter		a = b = a ₀₁ = 0.9*a ₀ + 0.1*a ₁₀ = 5.08152(6) Å					
		c = c ₀₁ = 0.9*c ₀ + 0.1*c ₁₀ = 11.5130(3) Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.9* z _{N₀} + 0.1* z _{N₁₀} = 0.0998(3)					

Occupancy Parameter			$oNa01 = 0.9 * yNa_0 + 0.1 * yNa_{10} = 0.923(8)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_01)	0.923(8)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_01)	0.077(8)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_02				
Space Group			I - 4				
Scale			0.000033				
Lattice Parameter			$a = b = a_{02} = 0.8 * a_{10} + 0.2 * a_{10} = 5.08024(7) \text{ \AA}$				
			$c = c_{02} = 0.8 * c_{10} + 0.2 * c_{10} = 11.4844(3) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.8 * z_{N_0} + 0.2 * z_{N_{10}} = 0.1000(3)$				
Occupancy Parameter			$oNa02 = 0.8 * yNa_0 + 0.2 * yNa_{10} = 0.91(1)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_02)	0.91(1)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_02)	0.09(1)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_03				
Space Group			I - 4				
Scale			0.000020(1)				
Lattice Parameter			$a = b = a_{03} = 0.7 * a_{10} + 0.3 * a_{10} = 5.07896(9) \text{ \AA}$				
			$c = c_{03} = 0.7 * c_{10} + 0.3 * c_{10} = 11.4559(4) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.7 * z_{N_0} + 0.3 * z_{N_{10}} = 0.1002(4)$				
Occupancy Parameter			$oNa03 = 0.7 * yNa_0 + 0.3 * yNa_{10} = 0.89(1)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_03)	0.89(1)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_03)	0.11(1)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_04				
Space Group			I - 4				
Scale			0.000016(1)				
Lattice Parameter			$a = b = a_{04} = 0.6 * a_{10} + 0.4 * a_{10} = 5.0777(1) \text{ \AA}$				
			$c = c_{04} = 0.6 * c_{10} + 0.4 * c_{10} = 11.4274(5) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.6 * z_{N_0} + 0.4 * z_{N_{10}} = 0.1003(4)$				
Occupancy Parameter			$oNa04 = 0.6 * yNa_0 + 0.4 * yNa_{10} = 0.88(1)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_04)	0.88(1)	b_{eq} 2.2484

Site	Li 1	0.0	0.50	0.25	occ (1-oNa_04)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_05					
Space Group		I - 4					
Scale		0.000012(1)					
Lattice Parameter		a = b = a_05 = 0.5*a ₁₀ + 0.5*a ₁₀ = 5.0764(1)Å					
		c = c_05 = 0.5*c ₁₀ + 0.5*c ₁₀ = 11.3989(6)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.5* z N ₀ + 0.5* z N ₁₀ = 0.1005(5)					
Occupancy Parameter		oNa05 = 0.5* yNa ₀ + 0.5*yNa ₁₀ = 0.87(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_05)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_05)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_06					
Space Group		I - 4					
Scale		0.000014(1)					
Lattice Parameter		a = b = a_06 = 0.4*a ₁₀ + 0.6*a ₁₀ = 5.0751(1)Å					
		c = c_06 = 0.4*c ₁₀ + 0.6*c ₁₀ = 11.3703(6)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.4* z N ₀ + 0.6* z N ₁₀ = 0.1007(5)					
Occupancy Parameter		oNa06 = 0.4* yNa ₀ + 0.6*yNa ₁₀ = 0.85(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_06)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_06)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_07					
Space Group		I - 4					
Scale		0.000010(1)					
Lattice Parameter		a = b = a_07 = 0.3*a ₁₀ + 0.7*a ₁₀ = 5.0738(2)Å					
		c = c_07 = 0.3*c ₁₀ + 0.7*c ₁₀ = 11.3418(7)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.3* z N ₀ + 0.7* z N ₁₀ = 0.1008(6)					
Occupancy Parameter		oNa07 = 0.3* yNa ₀ + 0.7*yNa ₁₀ = 0.83(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_07)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_07)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484

Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.000012(1)					
Lattice Parameter		a = b = a ₀₈ = 0.2*a ₁₀ + 0.8*a ₁₀ = 5.0726(2)Å					
		c = c ₀₈ = 0.2*c ₁₀ + 0.8*c ₁₀ = 11.3133(8)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.2* z N ₀ + 0.8* z N ₁₀ = 0.1010(6)					
Occupancy Parameter		oNa08 = 0.2* yNa ₀ + 0.8*yNa ₁₀ = 0.82(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₈)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₈)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _09					
Space Group		I - 4					
Scale		0.000010(1)					
Lattice Parameter		a = b = a ₀₉ = 0.1*a ₁₀ + 0.9*a ₁₀ = 5.0713(2)Å					
		c = c ₀₉ = 0.1*c ₁₀ + 0.9*c ₁₀ = 11.2847(8)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.1* z N ₀ + 0.9* z N ₁₀ = 0.1012(7)					
Occupancy Parameter		oNa09 = 0.1* yNa ₀ + 0.9*yNa ₁₀ = 0.81(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₉)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₉)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _10					
Space Group		I - 4					
Scale		0.000013(1)					
Lattice Parameter		a = b = a ₁₀ = 0.0*a ₁₀ + 1.0*a ₁₀ = 5.0700(2)Å					
		c = c ₁₀ = 0.0*c ₁₀ + 1.0*c ₁₀ = 11.2562(9)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.0* z N ₀ + 1.0* z N ₁₀ = 0.1014(7)					
Occupancy Parameter		oNa10 = 0.0* yNa ₀ + 1.0*yNa ₁₀ = 0.79(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₁₀)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₁₀)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484

Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH ₂					
Space Group		Fddd					
Scale		0.00000085(5)					
Lattice Parameter		a = 8.95853(2) Å					
		b = 10.4344(3) Å					
		c = 8.07177(2) Å					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

x = 0.833

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted Durbin Watson	7.430		
Goodness of fit	3.316		

LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name		LiNH ₂ _00					
Space Group		I – 4					
Scale		0.000001(2)					
Lattice Parameter		a = b = a _{liam_00} = 1.0*aLi ₀ + 0.0*aLi ₁₀ = 5.03701(3) Å					
		c = c _{liam_00} = 1.0*cLi ₀ + 0.0*cLi ₁₀ = 10.25577(3) Å					
Occupancy Parameter		oLi00 = 1.0* yLi ₀ + 0.0*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH ₂ _01					
Space Group		I – 4					
Scale		0.000282(4)					
Lattice Parameter		a = b = a _{liam_01} = 0.9*aLi ₀ + 0.1*aLi ₁₀ = 5.03750(2) Å					

$c = c_{\text{liam}_01} = 0.9 \cdot c_{\text{Li}_0} + 0.1 \cdot c_{\text{Li}_{10}} = 10.26342(5) \text{ \AA}$							
Occupancy Parameter		$o_{\text{Li01}} = 0.9 \cdot y_{\text{Li}_0} + 0.1 \cdot y_{\text{Li}_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi01)	0.017(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I - 4					
Scale		0.000174(4)					
Lattice Parameter		$a = b = a_{\text{liam}_02} = 0.8 \cdot a_{\text{Li}_0} + 0.2 \cdot a_{\text{Li}_{10}} = 5.03800(2) \text{ \AA}$					
Lattice Parameter		$c = c_{\text{liam}_02} = 0.8 \cdot c_{\text{Li}_0} + 0.2 \cdot c_{\text{Li}_{10}} = 10.27106(6) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li02}} = 0.8 \cdot y_{\text{Li}_0} + 0.2 \cdot y_{\text{Li}_{10}} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi02)	0.021(5)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000098(4)					
Lattice Parameter		$a = b = a_{\text{liam}_03} = 0.7 \cdot a_{\text{Li}_0} + 0.3 \cdot a_{\text{Li}_{10}} = 5.03849(3) \text{ \AA}$					
Lattice Parameter		$c = c_{\text{liam}_03} = 0.7 \cdot c_{\text{Li}_0} + 0.3 \cdot c_{\text{Li}_{10}} = 10.27871(8) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li03}} = 0.7 \cdot y_{\text{Li}_0} + 0.3 \cdot y_{\text{Li}_{10}} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi07)	0.025(6)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_04					
-------------------	--	----------	--	--	--	--	--

Space Group		I – 4					
Scale		0.000063(3)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.6 \cdot a_{\text{Li}_0} + 0.4 \cdot a_{\text{Li}_{10}} = 5.03899(3) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.6 \cdot c_{\text{Li}_0} + 0.4 \cdot c_{\text{Li}_{10}} = 10.28635(9) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li04}} = 0.6 \cdot y_{\text{Li}_0} + 0.4 \cdot y_{\text{Li}_{10}} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _05					
Space Group		I – 4					
Scale		0.00042(3)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.5 \cdot a_{\text{Li}_0} + 0.5 \cdot a_{\text{Li}_{10}} = 5.03948(4) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.5 \cdot c_{\text{Li}_0} + 0.5 \cdot c_{\text{Li}_{10}} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li05}} = 0.5 \cdot y_{\text{Li}_0} + 0.5 \cdot y_{\text{Li}_{10}} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _06					
Space Group		I – 4					
Scale		0.00027(2)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.4 \cdot a_{\text{Li}_0} + 0.6 \cdot a_{\text{Li}_{10}} = 5.03997(4) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.4 \cdot c_{\text{Li}_0} + 0.6 \cdot c_{\text{Li}_{10}} = 10.3016(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li06}} = 0.4 \cdot y_{\text{Li}_0} + 0.6 \cdot y_{\text{Li}_{10}} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$

Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$
------	-----	--------	--------	--------	-----	---	--------------------

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000019(2)					
Lattice Parameter		$a = b = a_{\text{liam}_07} = 0.3*a_{Li_0} + 0.7*a_{Li_{10}} = 5.04047(5)\text{\AA}$					
		$c = c_{\text{liam}_07} = 0.3*c_{Li_0} + 0.7*c_{Li_{10}} = 10.3093(1)\text{\AA}$					
Occupancy Parameter		$o_{Li07} = 0.3* y_{Li_0} + 0.7*y_{Li_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000011(2)					
Lattice Parameter		$a = b = a_{\text{liam}_08} = 0.2*a_{Li_0} + 0.8*a_{Li_{10}} = 5.04096(5)\text{\AA}$					
		$c = c_{\text{liam}_08} = 0.2*c_{Li_0} + 0.8*c_{Li_{10}} = 10.3169(2)\text{\AA}$					
Occupancy Parameter		$o_{Li08} = 0.2* y_{Li_0} + 0.8*y_{Li_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					
Scale		0.000010(2)					
Lattice Parameter		$a = b = a_{\text{liam}_09} = 0.1*a_{Li_0} + 0.9*a_{Li_{10}} = 5.04146(6)\text{\AA}$					
		$c = c_{\text{liam}_09} = 0.1*c_{Li_0} + 0.9*c_{Li_{10}} = 10.3246(2)\text{\AA}$					
Occupancy Parameter		$o_{Li09} = 0.1* y_{Li_0} + 0.9*y_{Li_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{eq} = 3.0(1)$

Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH ₂ _10					
Space Group		I - 4					
Scale		0.000013(1)					
Lattice Parameter		a = b = a _{liam_10} = 0.0*aLi ₀ + 1.0*aLi ₁₀ = 5.04195(6)Å					
		c = c _{liam_10} = 0.0*cLi ₀ + 1.0*cLi ₁₀ = 10.3311(2)Å					
Occupancy Parameter		oLi10 = 0.0* yLi ₀ + 1.0*yLi ₁₀ = 0.95(1)					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		Li ₂ O					
Space Group		Fm3m					
Scale		0.000121(3)					
Lattice Parameter		a = b = c = 4.61589(5) Å					
Site	Li	0.25	0.25	0.25	occ	1	$b_{eq} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{eq} = 0.8$

Phase Name		LiNa ₂ (NH ₂) ₃					
Space Group		P4 ₂ /m					
Scale		0.0000669(3)					
Lattice Parameter		a = b = 6.2838(1)Å					
		c = 11.1485(2)Å					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{eq} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{eq} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{eq} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{eq} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	$a_0 = 5.0828(4)$
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	$c_0 = 11.5415(2)$

Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name		Li3Na(NH2)4_00					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{00} = 1.0*a_0 + 0.0*a_{10} = 5.08280(4)\text{Å}$					
		$c = c_{00} = 1.0*c_0 + 0.0*c_{10} = 11.5415(2)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 1.0*z_{N_0} + 0.0*z_{N_{10}} = 0.0997(2)$					
Occupancy Parameter		$o_{Na00} = 1.0*y_{Na_0} + 0.0*y_{Na_{10}} = 0.938(7)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_00)	0.983(7)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_00)	0.062(7)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name		Li3Na(NH2)4_01					
Space Group		I – 4					
Scale		0.000019(1)					
Lattice Parameter		$a = b = a_{01} = 0.9*a_0 + 0.1*a_{10} = 5.08152(6)\text{Å}$					
		$c = c_{01} = 0.9*c_0 + 0.1*c_{10} = 11.5130(3)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.9*z_{N_0} + 0.1*z_{N_{10}} = 0.0998(3)$					
Occupancy Parameter		$o_{Na01} = 0.9*y_{Na_0} + 0.1*y_{Na_{10}} = 0.923(8)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_01)	0.923(8)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_01)	0.077(8)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name		Li3Na(NH2)4_02					
Space Group		I – 4					
Scale		0.000028(1)					
Lattice Parameter		$a = b = a_{02} = 0.8*a_{10} + 0.2*a_0 = 5.08024(7)\text{Å}$					
		$c = c_{02} = 0.8*c_{10} + 0.2*c_0 = 11.4844(3)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.8*z_{N_0} + 0.2*z_{N_{10}} = 0.1000(3)$					
Occupancy Parameter		$o_{Na02} = 0.8*y_{Na_0} + 0.2*y_{Na_{10}} = 0.91(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_02)	0.91(1)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_02)	0.09(1)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$

Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I - 4					
Scale		0.000021(1)					
Lattice Parameter		a = b = a ₀₃ = 0.7*a ₁₀ + 0.3*a ₁₀ = 5.07896(9) Å					
		c = c ₀₃ = 0.7*c ₁₀ + 0.3*c ₁₀ = 11.4559(4) Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.7* z _{N0} + 0.3* z _{N10} = 0.1002(4)					
Occupancy Parameter		oNa03 = 0.7* yNa ₀ + 0.3*yNa ₁₀ = 0.89(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₃)	0.89(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₃)	0.11(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _04					
Space Group		I - 4					
Scale		0.000015(1)					
Lattice Parameter		a = b = a ₀₄ = 0.6*a ₁₀ + 0.4*a ₁₀ = 5.0777(1)Å					
		c = c ₀₄ = 0.6*c ₁₀ + 0.4*c ₁₀ = 11.4274(5)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.6* z _{N0} + 0.4* z _{N10} = 0.1003(4)					
Occupancy Parameter		oNa04 = 0.6* yNa ₀ + 0.4*yNa ₁₀ = 0.88(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₄)	0.88(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₄)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _05					
Space Group		I - 4					
Scale		0.000010(1)					
Lattice Parameter		a = b = a ₀₅ = 0.5*a ₁₀ + 0.5*a ₁₀ = 5.0764(1)Å					
		c = c ₀₅ = 0.5*c ₁₀ + 0.5*c ₁₀ = 11.3989(6)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.5* z _{N0} + 0.5* z _{N10} = 0.1005(5)					
Occupancy Parameter		oNa05 = 0.5* yNa ₀ + 0.5*yNa ₁₀ = 0.87(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₅)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₅)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484

Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484
------	-----	-------	----------	----------	-----	---	------------------------

Phase Name		Li ₃ Na(NH ₂) ₄ 06					
Space Group		I - 4					
Scale		0.000012(1)					
Lattice Parameter		a = b = a ₀₆ = 0.4*a ₁₀ + 0.6*a ₁₀ = 5.0751(1)Å					
		c = c ₀₆ = 0.4*c ₁₀ + 0.6*c ₁₀ = 11.3703(6)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.4* z N ₀ + 0.6* z N ₁₀ = 0.1007(5)					
Occupancy Parameter		oNa06= 0.4* yNa ₀ + 0.6*yNa ₁₀ = 0.85(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₆)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₆)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ 07					
Space Group		I - 4					
Scale		0.000009(1)					
Lattice Parameter		a = b = a ₀₇ = 0.3*a ₁₀ + 0.7*a ₁₀ = 5.0738(2)Å					
		c = c ₀₇ = 0.3*c ₁₀ + 0.7*c ₁₀ = 11.3418(7)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.3* z N ₀ + 0.7* z N ₁₀ = 0.1008(6)					
Occupancy Parameter		oNa07= 0.3* yNa ₀ + 0.7*yNa ₁₀ = 0.83(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₇)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₇)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ 08					
Space Group		I - 4					
Scale		0.000010(1)					
Lattice Parameter		a = b = a ₀₈ = 0.2*a ₁₀ + 0.8*a ₁₀ = 5.0726(2)Å					
		c = c ₀₈ = 0.2*c ₁₀ + 0.8*c ₁₀ = 11.3133(8)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.2* z N ₀ + 0.8* z N ₁₀ = 0.1010(6)					
Occupancy Parameter		oNa08= 0.2* yNa ₀ + 0.8*yNa ₁₀ = 0.82(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₈)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₈)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_09					
Space Group		I - 4					
Scale		0.000008(1)					
Lattice Parameter		$a = b = a_{09} = 0.1 * a_{10} + 0.9 * a_{10} = 5.0713(2) \text{ \AA}$					
		$c = c_{09} = 0.1 * c_{10} + 0.9 * c_{10} = 11.2847(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.1 * z_{N_0} + 0.9 * z_{N_{10}} = 0.1012(7)$					
Occupancy Parameter		$oNa_{09} = 0.1 * yNa_0 + 0.9 * yNa_{10} = 0.81(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_10					
Space Group		I - 4					
Scale		0.000008(1)					
Lattice Parameter		$a = b = a_{10} = 0.0 * a_{10} + 1.0 * a_{10} = 5.0700(2) \text{ \AA}$					
		$c = c_{10} = 0.0 * c_{10} + 1.0 * c_{10} = 11.2562(9) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.0 * z_{N_0} + 1.0 * z_{N_{10}} = 0.1014(7)$					
Occupancy Parameter		$oNa_{10} = 0.0 * yNa_0 + 1.0 * yNa_{10} = 0.79(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_10)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_10)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH2					
Space Group		Fddd					
Scale		0.00000495(7)					
Lattice Parameter		$a = 8.95853(2) \text{ \AA}$					
		$b = 10.4344(3) \text{ \AA}$					
		$c = 8.07177(2) \text{ \AA}$					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

$$x = 0.75$$

R _{expected}	4.521	R _{expected'}	9.452
R _{weighted pattern}	14.989	R _{weighted pattern'}	31.342
R _{Pattern}	9.839	R _{Pattern'}	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH2_00 – LiNH2_10 Lattice Parameter	$a_{Li_0} = 5.03701(3) \text{ \AA}$
LiNH2_00 – LiNH2_10 Lattice Parameter	$a_{Li_{10}} = 5.04195(6) \text{ \AA}$
LiNH2_00 – LiNH2_10 Lattice Parameter	$c_{Li_0} = 10.25577(3) \text{ \AA}$
LiNH2_00 – LiNH2_10 Lattice Parameter	$c_{Li_{10}} = 10.3311(2) \text{ \AA}$
LiNH2_00 – LiNH2_10 Occ. Parameter	$y_{Li_0} = 0.987(3)$
LiNH2_00 – LiNH2_10 Occ. Parameter	$y_{Li_{10}} = 0.95(1)$

Phase Name		LiNH2_00					
Space Group		I – 4					
Scale		0.000001(2)					
Lattice Parameter		$a = b = a_{\text{liam}_00} = 1.0*a_{Li_0} + 0.0*a_{Li_{10}} = 5.03701(3) \text{ \AA}$					
		$c = c_{\text{liam}_00} = 1.0*c_{Li_0} + 0.0*c_{Li_{10}} = 10.25577(3) \text{ \AA}$					
Occupancy Parameter		$o_{Li00} = 1.0* y_{Li_0} + 0.0*y_{Li_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_01					
Space Group		I – 4					
Scale		0.000150(3)					
Lattice Parameter		$a = b = a_{\text{liam}_01} = 0.9*a_{Li_0} + 0.1*a_{Li_{10}} = 5.03750(2) \text{ \AA}$					
		$c = c_{\text{liam}_01} = 0.9*c_{Li_0} + 0.1*c_{Li_{10}} = 10.26342(5) \text{ \AA}$					
Occupancy Parameter		$o_{Li01} = 0.9* y_{Li_0} + 0.1*y_{Li_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I – 4					
Scale		0.000128(4)					
Lattice Parameter		$a = b = a_{\text{liam}_02} = 0.8*a_{Li_{10}} + 0.2*a_{Li_0} = 5.03800(2) \text{ \AA}$					
		$c = c_{\text{liam}_02} = 0.8*c_{Li_0} + 0.2*c_{Li_{10}} = 10.27106(6) \text{ \AA}$					
Occupancy		$o_{Li02} = 0.8* y_{Li_0} + 0.2*y_{Li_{10}} = 0.979(5)$					

Parameter							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_03							
Space Group							
I - 4							
Scale							
0.000061(3)							
Lattice Parameter							
$a = b = a_{liam_03} = 0.7*aLi_0 + 0.3*aLi_{10} = 5.03849(3) \text{ \AA}$							
$c = c_{liam_03} = 0.7*cLi_0 + 0.3*cLi_{10} = 10.27871(8) \text{ \AA}$							
Occupancy Parameter							
$oLi03 = 0.7* yLi_0 + 0.3*yLi_{10} = 0.975(6)$							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_04							
Space Group							
I - 4							
Scale							
0.000042(3)							
Lattice Parameter							
$a = b = a_{liam_04} = 0.6*aLi_0 + 0.4*aLi_{10} = 5.03899(3) \text{ \AA}$							
$c = c_{liam_04} = 0.6*cLi_0 + 0.4*cLi_{10} = 10.28635(9) \text{ \AA}$							
Occupancy Parameter							
$oLi04 = 0.6* yLi_0 + 0.4*yLi_{10} = 0.972(7)$							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_05							
Space Group							
I - 4							
Scale							
0.000032(3)							

Lattice Parameter		$a = b = a_{\text{liam}_05} = 0.5 * a_{\text{Li}_0} + 0.5 * a_{\text{Li}_{10}} = 5.03948(4) \text{ \AA}$					
		$c = c_{\text{liam}_05} = 0.5 * c_{\text{Li}_0} + 0.5 * c_{\text{Li}_{10}} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}05} = 0.5 * y_{\text{Li}_0} + 0.5 * y_{\text{Li}_{10}} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000021(2)					
Lattice Parameter		$a = b = a_{\text{liam}_06} = 0.4 * a_{\text{Li}_0} + 0.6 * a_{\text{Li}_{10}} = 5.03997(4) \text{ \AA}$					
		$c = c_{\text{liam}_06} = 0.4 * c_{\text{Li}_0} + 0.6 * c_{\text{Li}_{10}} = 10.3016(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}06} = 0.4 * y_{\text{Li}_0} + 0.6 * y_{\text{Li}_{10}} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000017(2)					
Lattice Parameter		$a = b = a_{\text{liam}_07} = 0.3 * a_{\text{Li}_0} + 0.7 * a_{\text{Li}_{10}} = 5.04047(5) \text{ \AA}$					
		$c = c_{\text{liam}_07} = 0.3 * c_{\text{Li}_0} + 0.7 * c_{\text{Li}_{10}} = 10.3093(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}07} = 0.3 * y_{\text{Li}_0} + 0.7 * y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _08					
Space Group		I – 4					
Scale		0.000010(2)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2\text{08}} = 0.2*a_{\text{Li}_0} + 0.8*a_{\text{Li}_{10}} = 5.04096(5) \text{ \AA}$					
		$c = c_{\text{LiNH}_2\text{08}} = 0.2*c_{\text{Li}_0} + 0.8*c_{\text{Li}_{10}} = 10.3169(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li08}} = 0.2* y_{\text{Li}_0} + 0.8*y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _09					
Space Group		I – 4					
Scale		0.000011(2)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2\text{09}} = 0.1*a_{\text{Li}_0} + 0.9*a_{\text{Li}_{10}} = 5.04146(6) \text{ \AA}$					
		$c = c_{\text{LiNH}_2\text{09}} = 0.1*c_{\text{Li}_0} + 0.9*c_{\text{Li}_{10}} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li09}} = 0.1* y_{\text{Li}_0} + 0.9*y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _10					
Space Group		I – 4					
Scale		0.000013(1)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2\text{10}} = 0.0*a_{\text{Li}_0} + 1.0*a_{\text{Li}_{10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{\text{LiNH}_2\text{10}} = 0.0*c_{\text{Li}_0} + 1.0*c_{\text{Li}_{10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li10}} = 0.0* y_{\text{Li}_0} + 1.0*y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$

Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		Li2O					
Space Group		Fm3m					
Scale		0.000223(4)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{eq} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{eq} = 0.8$

Phase Name		LiNa2(NH2)3					
Space Group		P42/m					
Scale		0.0001032(4)					
Lattice Parameter		$a = b = 6.2838(1) \text{ \AA}$ $c = 11.1485(2) \text{ \AA}$					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{eq} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{eq} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{eq} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{eq} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_0 = 5.0828(4)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_0 = 11.5415(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name		Li3Na(NH2)4_00					
Space Group		I – 4					
Scale		0.000000(1)					
Lattice Parameter		$a = b = a_{00} = 1.0*a_0 + 0.0*a_{10} = 5.08280(4) \text{ \AA}$ $c = c_{00} = 1.0*c_0 + 0.0*c_{10} = 11.5415(2) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 1.0*z_{N_0} + 0.0*z_{N_{10}} = 0.0997(2)$					
Occupancy Parameter		$o_{Na00} = 1.0*y_{Na_0} + 0.0*y_{Na_{10}} = 0.938(7)$					
Site	Na 1	0.0	0.50	0.25	occ ($o_{Na_{00}}$)	0.983(7)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ ($1-o_{Na_{00}}$)	0.062(7)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$

Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484
------	-----	-------	----------	----------	-----	---	------------------------

Phase Name		Li3Na(NH2)4_01					
Space Group		I - 4					
Scale		0.000059(2)					
Lattice Parameter		a = b = a_01 = 0.9*a ₀ + 0.1*a ₁₀ = 5.08152(6) Å					
		c = c_01 = 0.9*c ₀ + 0.1*c ₁₀ = 11.5130(3) Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.9* z N ₀ + 0.1* z N ₁₀ = 0.0998(3)					
Occupancy Parameter		oNa01 = 0.9* yNa ₀ + 0.1*yNa ₁₀ = 0.923(8)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_01)	0.923(8)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_01)	0.077(8)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_02					
Space Group		I - 4					
Scale		0.000081(2)					
Lattice Parameter		a = b = a_02 = 0.8*a ₁₀ + 0.2*a ₁₀ = 5.08024(7) Å					
		c = c_02 = 0.8*c ₁₀ + 0.2*c ₁₀ = 11.4844(3) Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.8* z N ₀ + 0.2* z N ₁₀ = 0.1000(3)					
Occupancy Parameter		oNa02 = 0.8* yNa ₀ + 0.2*yNa ₁₀ = 0.91(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_02)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_02)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_03					
Space Group		I - 4					
Scale		0.000041(2)					
Lattice Parameter		a = b = a_03 = 0.7*a ₁₀ + 0.3*a ₁₀ = 5.07896(9) Å					
		c = c_03 = 0.7*c ₁₀ + 0.3*c ₁₀ = 11.4559(4) Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.7* z N ₀ + 0.3* z N ₁₀ = 0.1002(4)					
Occupancy Parameter		oNa03 = 0.7* yNa ₀ + 0.3*yNa ₁₀ = 0.89(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_03)	0.89(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_03)	0.11(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _04					
Space Group		I – 4					
Scale		0.000033(2)					
Lattice Parameter		$a = b = a_{04} = 0.6 \cdot a_{10} + 0.4 \cdot a_{10} = 5.0777(1) \text{ \AA}$					
		$c = c_{04} = 0.6 \cdot c_{10} + 0.4 \cdot c_{10} = 11.4274(5) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.6 \cdot z_{N_0} + 0.4 \cdot z_{N_{10}} = 0.1003(4)$					
Occupancy Parameter		$o_{Na04} = 0.6 \cdot y_{Na_0} + 0.4 \cdot y_{Na_{10}} = 0.88(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₄)	0.88(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₄)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _05					
Space Group		I – 4					
Scale		0.000021(2)					
Lattice Parameter		$a = b = a_{05} = 0.5 \cdot a_{10} + 0.5 \cdot a_{10} = 5.0764(1) \text{ \AA}$					
		$c = c_{05} = 0.5 \cdot c_{10} + 0.5 \cdot c_{10} = 11.3989(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.5 \cdot z_{N_0} + 0.5 \cdot z_{N_{10}} = 0.1005(5)$					
Occupancy Parameter		$o_{Na05} = 0.5 \cdot y_{Na_0} + 0.5 \cdot y_{Na_{10}} = 0.87(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₅)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₅)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _06					
Space Group		I – 4					
Scale		0.000024(1)					
Lattice Parameter		$a = b = a_{06} = 0.4 \cdot a_{10} + 0.6 \cdot a_{10} = 5.0751(1) \text{ \AA}$					
		$c = c_{06} = 0.4 \cdot c_{10} + 0.6 \cdot c_{10} = 11.3703(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.4 \cdot z_{N_0} + 0.6 \cdot z_{N_{10}} = 0.1007(5)$					
Occupancy Parameter		$o_{Na06} = 0.4 \cdot y_{Na_0} + 0.6 \cdot y_{Na_{10}} = 0.85(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₆)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₆)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _07					
Space Group		I – 4					

Scale		0.000016(1)					
Lattice Parameter		$a = b = a_{07} = 0.3 \cdot a_{10} + 0.7 \cdot a_{10} = 5.0738(2) \text{ \AA}$					
		$c = c_{07} = 0.3 \cdot c_{10} + 0.7 \cdot c_{10} = 11.3418(7) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.3 \cdot z_{N_0} + 0.7 \cdot z_{N_{10}} = 0.1008(6)$					
Occupancy Parameter		$o_{Na07} = 0.3 \cdot y_{Na_0} + 0.7 \cdot y_{Na_{10}} = 0.83(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₇)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₇)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.000018(1)					
Lattice Parameter		$a = b = a_{08} = 0.2 \cdot a_{10} + 0.8 \cdot a_{10} = 5.0726(2) \text{ \AA}$					
		$c = c_{08} = 0.2 \cdot c_{10} + 0.8 \cdot c_{10} = 11.3133(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.2 \cdot z_{N_0} + 0.8 \cdot z_{N_{10}} = 0.1010(6)$					
Occupancy Parameter		$o_{Na08} = 0.2 \cdot y_{Na_0} + 0.8 \cdot y_{Na_{10}} = 0.82(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₈)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₈)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _09					
Space Group		I - 4					
Scale		0.000012(1)					
Lattice Parameter		$a = b = a_{09} = 0.1 \cdot a_{10} + 0.9 \cdot a_{10} = 5.0713(2) \text{ \AA}$					
		$c = c_{09} = 0.1 \cdot c_{10} + 0.9 \cdot c_{10} = 11.2847(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.1 \cdot z_{N_0} + 0.9 \cdot z_{N_{10}} = 0.1012(7)$					
Occupancy Parameter		$o_{Na09} = 0.1 \cdot y_{Na_0} + 0.9 \cdot y_{Na_{10}} = 0.81(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₉)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₉)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _10					
Space Group		I - 4					
Scale		0.000017(1)					
Lattice Parameter		$a = b = a_{10} = 0.0 \cdot a_{10} + 1.0 \cdot a_{10} = 5.0700(2) \text{ \AA}$					

$c = c_{10} = 0.0 * c_{10} + 1.0 * c_{10} = 11.2562(9) \text{ \AA}$							
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.0 * z_{N_0} + 1.0 * z_{N_{10}} = 0.1014(7)$					
Occupancy Parameter		$oNa_{10} = 0.0 * y_{Na_0} + 1.0 * y_{Na_{10}} = 0.79(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₁₀)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₁₀)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH ₂					
Space Group		Fddd					
Scale		0.00000306(6)					
Lattice Parameter		$a = 8.95853(2) \text{ \AA}$					
		$b = 10.4344(3) \text{ \AA}$					
		$c = 8.07177(2) \text{ \AA}$					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

$$x = 0.667$$

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH₂_00 – LiNH₂_10 Lattice Parameter	$aLi_0 = 5.03701(3) \text{ \AA}$
LiNH₂_00 – LiNH₂_10 Lattice Parameter	$aLi_{10} = 5.04195(6) \text{ \AA}$
LiNH₂_00 – LiNH₂_10 Lattice Parameter	$cLi_0 = 10.25577(3) \text{ \AA}$
LiNH₂_00 – LiNH₂_10 Lattice Parameter	$cLi_{10} = 10.3311(2) \text{ \AA}$
LiNH₂_00 – LiNH₂_10 Occ. Parameter	$yLi_0 = 0.987(3)$
LiNH₂_00 – LiNH₂_10 Occ. Parameter	$yLi_{10} = 0.95(1)$

Phase Name		LiNH ₂ _00					
Space Group		I – 4					
Scale		0.000004(1)					
Lattice Parameter		$a = b = a_{liam_00} = 1.0 * aLi_0 + 0.0 * aLi_{10} = 5.03701(3) \text{ \AA}$					
		$c = c_{liam_00} = 1.0 * cLi_0 + 0.0 * cLi_{10} = 10.25577(3) \text{ \AA}$					
Occupancy Parameter		$oLi00 = 1.0 * yLi_0 + 0.0 * yLi_{10} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1-	0.013(3)	b _{eq} = 3.0(1)

					oLi00)		
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_01					
Space Group		I - 4					
Scale		0.000061(2)					
Lattice Parameter		$a = b = a_{liam_01} = 0.9*aLi_0 + 0.1*aLi_{10} = 5.03750(2)\text{\AA}$					
		$c = c_{liam_01} = 0.9*cLi_0 + 0.1*cLi_{10} = 10.26342(5)\text{\AA}$					
Occupancy Parameter		$oLi01 = 0.9* yLi_0 + 0.1*yLi_{10} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I - 4					
Scale		0.000042(2)					
Lattice Parameter		$a = b = a_{liam_02} = 0.8*aLi_{10} + 0.2*aLi_0 = 5.03800(2)\text{\AA}$					
		$c = c_{liam_02} = 0.8*cLi_0 + 0.2*cLi_{10} = 10.27106(6)\text{\AA}$					
Occupancy Parameter		$oLi02 = 0.8* yLi_0 + 0.2*yLi_{10} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000024(2)					
Lattice Parameter		$a = b = a_{liam_03} = 0.7*aLi_0 + 0.3*aLi_{10} = 5.03849(3)\text{\AA}$					
		$c = c_{liam_03} = 0.7*cLi_0 + 0.3*cLi_{10} = 10.27871(8)\text{\AA}$					
Occupancy Parameter		$oLi03 = 0.7* yLi_0 + 0.3*yLi_{10} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$

Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000020(2)					
Lattice Parameter		$a = b = a_{\text{liam}_04} = 0.6*a_{\text{Li}_0} + 0.4*a_{\text{Li}_{10}} = 5.03899(3)\text{\AA}$					
		$c = c_{\text{liam}_04} = 0.6*c_{\text{Li}_0} + 0.4*c_{\text{Li}_{10}} = 10.28635(9)\text{\AA}$					
Occupancy Parameter		$o_{\text{Li}04} = 0.6* y_{\text{Li}_0} + 0.4*y_{\text{Li}_{10}} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000011(2)					
Lattice Parameter		$a = b = a_{\text{liam}_05} = 0.5*a_{\text{Li}_0} + 0.5*a_{\text{Li}_{10}} = 5.03948(4)\text{\AA}$					
		$c = c_{\text{liam}_05} = 0.5*c_{\text{Li}_0} + 0.5*c_{\text{Li}_{10}} = 10.2940(1)\text{\AA}$					
Occupancy Parameter		$o_{\text{Li}05} = 0.5* y_{\text{Li}_0} + 0.5*y_{\text{Li}_{10}} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000009(2)					
Lattice Parameter		$a = b = a_{\text{liam}_06} = 0.4*a_{\text{Li}_0} + 0.6*a_{\text{Li}_{10}} = 5.03997(4)\text{\AA}$					
		$c = c_{\text{liam}_06} = 0.4*c_{\text{Li}_0} + 0.6*c_{\text{Li}_{10}} = 10.3016(1)\text{\AA}$					

Occupancy Parameter		$oLi06 = 0.4 * yLi_0 + 0.6 * yLi_{10} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi06)	0.036(9)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000007(2)					
Lattice Parameter		$a = b = a_{liam_07} = 0.3 * aLi_0 + 0.7 * aLi_{10} = 5.04047(5) \text{ \AA}$					
		$c = c_{liam_07} = 0.3 * cLi_0 + 0.7 * cLi_{10} = 10.3093(1) \text{ \AA}$					
Occupancy Parameter		$oLi07 = 0.3 * yLi_0 + 0.7 * yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000006(1)					
Lattice Parameter		$a = b = a_{liam_08} = 0.2 * aLi_0 + 0.8 * aLi_{10} = 5.04096(5) \text{ \AA}$					
		$c = c_{liam_08} = 0.2 * cLi_0 + 0.8 * cLi_{10} = 10.3169(2) \text{ \AA}$					
Occupancy Parameter		$oLi08 = 0.2 * yLi_0 + 0.8 * yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					

Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{Li09}} = 0.1 \cdot a_{\text{Li0}} + 0.9 \cdot a_{\text{Li10}} = 5.04146(6) \text{ \AA}$					
		$c = c_{\text{Li09}} = 0.1 \cdot c_{\text{Li0}} + 0.9 \cdot c_{\text{Li10}} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li09}} = 0.1 \cdot y_{\text{Li0}} + 0.9 \cdot y_{\text{Li10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ 10					
Space Group		I - 4					
Scale		0.000006(1)					
Lattice Parameter		$a = b = a_{\text{Li10}} = 0.0 \cdot a_{\text{Li0}} + 1.0 \cdot a_{\text{Li10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{\text{Li10}} = 0.0 \cdot c_{\text{Li0}} + 1.0 \cdot c_{\text{Li10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li10}} = 0.0 \cdot y_{\text{Li0}} + 1.0 \cdot y_{\text{Li10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		Li ₂ O					
Space Group		Fm $\bar{3}$ m					
Scale		0.000089(3)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{\text{eq}} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.8$

Phase Name		LiNa ₂ (NH ₂) ₃					
Space Group		P4 ₂ /m					
Scale		0.0000529(3)					
Lattice Parameter		$a = b = 6.2838(1) \text{ \AA}$					
		$c = 11.1485(2) \text{ \AA}$					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{\text{eq}} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{\text{eq}} = 1.5810$

Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_0 = 5.0828(4)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_0 = 11.5415(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name	Li3Na(NH2)4_00						
Space Group	I – 4						
Scale	0.000012(1)						
Lattice Parameter	$a = b = a_{00} = 1.0*a_0 + 0.0*a_{10} = 5.08280(4)\text{Å}$						
	$c = c_{00} = 1.0*c_0 + 0.0*c_{10} = 11.5415(2)\text{Å}$						
Nitrogen Z Coordinate	$z_N = z_{N_0} = 1.0*z_{N_0} + 0.0*z_{N_{10}} = 0.0997(2)$						
Occupancy Parameter	$o_{Na00} = 1.0*y_{Na_0} + 0.0*y_{Na_{10}} = 0.938(7)$						
Site	Na 1	0.0	0.50	0.25	occ (oNa_00)	0.983(7)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_00)	0.062(7)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name	Li3Na(NH2)4_01						
Space Group	I – 4						
Scale	0.000014(1)						
Lattice Parameter	$a = b = a_{01} = 0.9*a_0 + 0.1*a_{10} = 5.08152(6)\text{Å}$						
	$c = c_{01} = 0.9*c_0 + 0.1*c_{10} = 11.5130(3)\text{Å}$						
Nitrogen Z Coordinate	$z_N = z_{N_0} = 0.9*z_{N_0} + 0.1*z_{N_{10}} = 0.0998(3)$						
Occupancy Parameter	$o_{Na01} = 0.9*y_{Na_0} + 0.1*y_{Na_{10}} = 0.923(8)$						
Site	Na 1	0.0	0.50	0.25	occ (oNa_01)	0.923(8)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_01)	0.077(8)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name	Li3Na(NH2)4_02						
Space Group	I – 4						

Scale		0.000017(1)					
Lattice Parameter		$a = b = a_{02} = 0.8 \cdot a_{10} + 0.2 \cdot a_{10} = 5.08024(7) \text{ \AA}$					
		$c = c_{02} = 0.8 \cdot c_{10} + 0.2 \cdot c_{10} = 11.4844(3) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.8 \cdot z_{N_0} + 0.2 \cdot z_{N_{10}} = 0.1000(3)$					
Occupancy Parameter		$o_{Na02} = 0.8 \cdot y_{Na_0} + 0.2 \cdot y_{Na_{10}} = 0.91(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_02)	0.91(1)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_02)	0.09(1)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I - 4					
Scale		0.000012(1)					
Lattice Parameter		$a = b = a_{03} = 0.7 \cdot a_{10} + 0.3 \cdot a_{10} = 5.07896(9) \text{ \AA}$					
		$c = c_{03} = 0.7 \cdot c_{10} + 0.3 \cdot c_{10} = 11.4559(4) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.7 \cdot z_{N_0} + 0.3 \cdot z_{N_{10}} = 0.1002(4)$					
Occupancy Parameter		$o_{Na03} = 0.7 \cdot y_{Na_0} + 0.3 \cdot y_{Na_{10}} = 0.89(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_03)	0.89(1)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_03)	0.11(1)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name		Li ₃ Na(NH ₂) ₄ _04					
Space Group		I - 4					
Scale		0.000009(1)					
Lattice Parameter		$a = b = a_{04} = 0.6 \cdot a_{10} + 0.4 \cdot a_{10} = 5.0777(1) \text{ \AA}$					
		$c = c_{04} = 0.6 \cdot c_{10} + 0.4 \cdot c_{10} = 11.4274(5) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.6 \cdot z_{N_0} + 0.4 \cdot z_{N_{10}} = 0.1003(4)$					
Occupancy Parameter		$o_{Na04} = 0.6 \cdot y_{Na_0} + 0.4 \cdot y_{Na_{10}} = 0.88(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_04)	0.88(1)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_04)	0.12(1)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name		Li ₃ Na(NH ₂) ₄ _05					
Space Group		I - 4					
Scale		0.000008(1)					
Lattice Parameter		$a = b = a_{05} = 0.5 \cdot a_{10} + 0.5 \cdot a_{10} = 5.0764(1) \text{ \AA}$					

$c = c_{05} = 0.5 * c_{10} + 0.5 * c_{10} = 11.3989(6) \text{ \AA}$							
Nitrogen Z Coordinate		$z_{N} = z_{N_0} = 0.5 * z_{N_0} + 0.5 * z_{N_{10}} = 0.1005(5)$					
Occupancy Parameter		$oNa_{05} = 0.5 * y_{Na_0} + 0.5 * y_{Na_{10}} = 0.87(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₅)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₅)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _06					
Space Group		I - 4					
Scale		0.000005(1)					
Lattice Parameter		$a = b = a_{06} = 0.4 * a_{10} + 0.6 * a_{10} = 5.0751(1) \text{ \AA}$					
		$c = c_{06} = 0.4 * c_{10} + 0.6 * c_{10} = 11.3703(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_{N} = z_{N_0} = 0.4 * z_{N_0} + 0.6 * z_{N_{10}} = 0.1007(5)$					
Occupancy Parameter		$oNa_{06} = 0.4 * y_{Na_0} + 0.6 * y_{Na_{10}} = 0.85(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₆)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₆)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _07					
Space Group		I - 4					
Scale		0.000007(1)					
Lattice Parameter		$a = b = a_{07} = 0.3 * a_{10} + 0.7 * a_{10} = 5.0738(2) \text{ \AA}$					
		$c = c_{07} = 0.3 * c_{10} + 0.7 * c_{10} = 11.3418(7) \text{ \AA}$					
Nitrogen Z Coordinate		$z_{N} = z_{N_0} = 0.3 * z_{N_0} + 0.7 * z_{N_{10}} = 0.1008(6)$					
Occupancy Parameter		$oNa_{07} = 0.3 * y_{Na_0} + 0.7 * y_{Na_{10}} = 0.83(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₇)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₇)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.000006(1)					
Lattice Parameter		$a = b = a_{08} = 0.2 * a_{10} + 0.8 * a_{10} = 5.0726(2) \text{ \AA}$					
		$c = c_{08} = 0.2 * c_{10} + 0.8 * c_{10} = 11.3133(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_{N} = z_{N_0} = 0.2 * z_{N_0} + 0.8 * z_{N_{10}} = 0.1010(6)$					

Occupancy Parameter			$oNa08 = 0.2 * yNa_0 + 0.8 * yNa_{10} = 0.82(2)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_08)	0.82(2)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_08)	0.18(2)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li ₃ Na(NH ₂) ₄ _09				
Space Group			I - 4				
Scale			0.000006(1)				
Lattice Parameter			$a = b = a_{09} = 0.1 * a_{10} + 0.9 * a_{10} = 5.0713(2) \text{ \AA}$				
			$c = c_{09} = 0.1 * c_{10} + 0.9 * c_{10} = 11.2847(8) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.1 * z_{N_0} + 0.9 * z_{N_{10}} = 0.1012(7)$				
Occupancy Parameter			$oNa09 = 0.1 * yNa_0 + 0.9 * yNa_{10} = 0.81(2)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li ₃ Na(NH ₂) ₄ _10				
Space Group			I - 4				
Scale			0.000005(1)				
Lattice Parameter			$a = b = a_{10} = 0.0 * a_{10} + 1.0 * a_{10} = 5.0700(2) \text{ \AA}$				
			$c = c_{10} = 0.0 * c_{10} + 1.0 * c_{10} = 11.2562(9) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.0 * z_{N_0} + 1.0 * z_{N_{10}} = 0.1014(7)$				
Occupancy Parameter			$oNa10 = 0.0 * yNa_0 + 1.0 * yNa_{10} = 0.79(2)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_10)	0.79(2)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_10)	0.21(2)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			NaNH ₂				
Space Group			Fddd				
Scale			0.00000208(5)				
Lattice Parameter			$a = 8.95853(2) \text{ \AA}$				
			$b = 10.4344(3) \text{ \AA}$				
			$c = 8.07177(2) \text{ \AA}$				
Site	Na 1	0.0	0.14841	0.0	occ	1	b_{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b_{eq} 3.2183

Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556
------	-----	---------	---------	---------	-----	---	------------------------

$$x = 0.583$$

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH2_00 – LiNH2_10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH2_00 – LiNH2_10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH2_00 – LiNH2_10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name		LiNH2_00					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a _{liam_00} = 1.0*aLi ₀ + 0.0*aLi ₁₀ = 5.03701(3) Å					
		c = c _{liam_00} = 1.0*cLi ₀ + 0.0*cLi ₁₀ = 10.25577(3) Å					
Occupancy Parameter		oLi00 = 1.0* yLi ₀ + 0.0*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH2_01					
Space Group		I – 4					
Scale		0.000011(2)					
Lattice Parameter		a = b = a _{liam_01} = 0.9*aLi ₀ + 0.1*aLi ₁₀ = 5.03750(2) Å					
		c = c _{liam_01} = 0.9*cLi ₀ + 0.1*cLi ₁₀ = 10.26342(5) Å					
Occupancy Parameter		oLi01 = 0.9* yLi ₀ + 0.1*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)

Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I - 4					
Scale		0.000001(2)					
Lattice Parameter		$a = b = a \text{ liam}_{02} = 0.8*aLi_{10} + 0.2*aLi_0 = 5.03800(2)\text{\AA}$					
		$c = c \text{ liam}_{02} = 0.8*cLi_0 + 0.2*cLi_{10} = 10.27106(6)\text{\AA}$					
Occupancy Parameter		$oLi02 = 0.8* yLi_0 + 0.2*yLi_{10} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000001(2)					
Lattice Parameter		$a = b = a \text{ liam}_{03} = 0.7*aLi_0 + 0.3*aLi_{10} = 5.03849(3)\text{\AA}$					
		$c = c \text{ liam}_{03} = 0.7*cLi_0 + 0.3*cLi_{10} = 10.27871(8)\text{\AA}$					
Occupancy Parameter		$oLi03 = 0.7* yLi_0 + 0.3*yLi_{10} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000001(2)					
Lattice Parameter		$a = b = a \text{ liam}_{04} = 0.6*aLi_0 + 0.4*aLi_{10} = 5.03899(3)\text{\AA}$					
		$c = c \text{ liam}_{04} = 0.6*cLi_0 + 0.4*cLi_{10} = 10.28635(9)\text{\AA}$					
Occupancy Parameter		$oLi04 = 0.6* yLi_0 + 0.4*yLi_{10} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$

Site	Na 2	0.0	0.5	-0.25	occ (1-oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000001(2)					
Lattice Parameter		$a = b = a_{\text{liam}_05} = 0.5 * a_{Li_0} + 0.5 * a_{Li_{10}} = 5.03948(4) \text{ \AA}$					
		$c = c_{\text{liam}_05} = 0.5 * c_{Li_0} + 0.5 * c_{Li_{10}} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$oLi05 = 0.5 * y_{Li_0} + 0.5 * y_{Li_{10}} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi05)	0.032(8)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_06} = 0.4 * a_{Li_0} + 0.6 * a_{Li_{10}} = 5.03997(4) \text{ \AA}$					
		$c = c_{\text{liam}_06} = 0.4 * c_{Li_0} + 0.6 * c_{Li_{10}} = 10.3016(1) \text{ \AA}$					
Occupancy Parameter		$oLi06 = 0.4 * y_{Li_0} + 0.6 * y_{Li_{10}} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi06)	0.036(9)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_07} = 0.3 * a_{Li_0} + 0.7 * a_{Li_{10}} = 5.04047(5) \text{ \AA}$					
		$c = c_{\text{liam}_07} = 0.3 * c_{Li_0} + 0.7 * c_{Li_{10}} = 10.3093(1) \text{ \AA}$					
Occupancy Parameter		$oLi07 = 0.3 * y_{Li_0} + 0.7 * y_{Li_{10}} = 0.960(1)$					

Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.960(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_08} = 0.2*aLi_0 + 0.8*aLi_{10} = 5.04096(5) \text{ \AA}$					
		$c = c_{liam_08} = 0.2*cLi_0 + 0.8*cLi_{10} = 10.3169(2) \text{ \AA}$					
Occupancy Parameter		$oLi08 = 0.2 * yLi_0 + 0.8 * yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_09} = 0.1*aLi_0 + 0.9*aLi_{10} = 5.04146(6) \text{ \AA}$					
		$c = c_{liam_09} = 0.1*cLi_0 + 0.9*cLi_{10} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$oLi09 = 0.1 * yLi_0 + 0.9 * yLi_{10} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_10					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_10} = 0.0*aLi_0 + 1.0*aLi_{10} = 5.04195(6) \text{ \AA}$					

		$c = c_{\text{Li10}} = 0.0 \cdot c_{\text{Li}_0} + 1.0 \cdot c_{\text{Li}_{10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li10}} = 0.0 \cdot y_{\text{Li}_0} + 1.0 \cdot y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi10)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		Li2O					
Space Group		Fm3m					
Scale		0.000135(4)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{\text{eq}} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.8$

Phase Name		LiNa2(NH2)3					
Space Group		P42/m					
Scale		0.0001670(6)					
Lattice Parameter		$a = b = 6.2838(1) \text{ \AA}$					
		$c = 11.1485(2) \text{ \AA}$					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{\text{eq}} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{\text{eq}} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{\text{eq}} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{\text{eq}} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{\text{eq}} = 2.0455$

Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_0 = 5.0828(4)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_0 = 11.5415(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{\text{N}_0} = 0.0997(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{\text{N}_{10}} = 0.1014(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{\text{Na}_0} = 0.938(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{\text{Na}_{10}} = 0.79(2)$

Phase Name	Li3Na(NH2)4_00
Space Group	I – 4
Scale	0.000017(2)

Lattice Parameter		$a = b = a_{00} = 1.0*a_0 + 0.0*a_{10} = 5.08280(4)\text{Å}$					
		$c = c_{00} = 1.0*c_0 + 0.0*c_{10} = 11.5415(2)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 1.0*z_{N_0} + 0.0*z_{N_{10}} = 0.0997(2)$					
Occupancy Parameter		$oNa_{00} = 1.0*y_{Na_0} + 0.0*y_{Na_{10}} = 0.938(7)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₀)	0.983(7)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₀)	0.062(7)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _01					
Space Group		I – 4					
Scale		0.000254(3)					
Lattice Parameter		$a = b = a_{01} = 0.9*a_0 + 0.1*a_{10} = 5.08152(6)\text{Å}$					
		$c = c_{01} = 0.9*c_0 + 0.1*c_{10} = 11.5130(3)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.9*z_{N_0} + 0.1*z_{N_{10}} = 0.0998(3)$					
Occupancy Parameter		$oNa_{01} = 0.9*y_{Na_0} + 0.1*y_{Na_{10}} = 0.923(8)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₁)	0.923(8)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₁)	0.077(8)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _02					
Space Group		I – 4					
Scale		0.000062(2)					
Lattice Parameter		$a = b = a_{02} = 0.8*a_{10} + 0.2*a_{10} = 5.08024(7)\text{Å}$					
		$c = c_{02} = 0.8*c_{10} + 0.2*c_{10} = 11.4844(3)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.8*z_{N_0} + 0.2*z_{N_{10}} = 0.1000(3)$					
Occupancy Parameter		$oNa_{02} = 0.8*y_{Na_0} + 0.2*y_{Na_{10}} = 0.91(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₂)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₂)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I – 4					
Scale		0.000022(2)					
Lattice Parameter		$a = b = a_{03} = 0.7*a_{10} + 0.3*a_{10} = 5.07896(9)\text{Å}$					
		$c = c_{03} = 0.7*c_{10} + 0.3*c_{10} = 11.4559(4)\text{Å}$					

Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.7 * z_{N_0} + 0.3 * z_{N_{10}} = 0.1002(4)$					
Occupancy Parameter		$oNa03 = 0.7 * yNa_0 + 0.3 * yNa_{10} = 0.89(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_03)	0.89(1)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_03)	0.11(1)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name		Li3Na(NH2)4_04					
Space Group		I - 4					
Scale		0.000013(2)					
Lattice Parameter		$a = b = a_{04} = 0.6 * a_{10} + 0.4 * a_{10} = 5.0777(1) \text{ \AA}$					
		$c = c_{04} = 0.6 * c_{10} + 0.4 * c_{10} = 11.4274(5) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.6 * z_{N_0} + 0.4 * z_{N_{10}} = 0.1003(4)$					
Occupancy Parameter		$oNa04 = 0.6 * yNa_0 + 0.4 * yNa_{10} = 0.88(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_04)	0.88(1)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_04)	0.12(1)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name		Li3Na(NH2)4_05					
Space Group		I - 4					
Scale		0.000007(1)					
Lattice Parameter		$a = b = a_{05} = 0.5 * a_{10} + 0.5 * a_{10} = 5.0764(1) \text{ \AA}$					
		$c = c_{05} = 0.5 * c_{10} + 0.5 * c_{10} = 11.3989(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.5 * z_{N_0} + 0.5 * z_{N_{10}} = 0.1005(5)$					
Occupancy Parameter		$oNa05 = 0.5 * yNa_0 + 0.5 * yNa_{10} = 0.87(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_05)	0.87(1)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_05)	0.13(1)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name		Li3Na(NH2)4_06					
Space Group		I - 4					
Scale		0.000004(1)					
Lattice Parameter		$a = b = a_{06} = 0.4 * a_{10} + 0.6 * a_{10} = 5.0751(1) \text{ \AA}$					
		$c = c_{06} = 0.4 * c_{10} + 0.6 * c_{10} = 11.3703(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.4 * z_{N_0} + 0.6 * z_{N_{10}} = 0.1007(5)$					
Occupancy Parameter		$oNa06 = 0.4 * yNa_0 + 0.6 * yNa_{10} = 0.85(1)$					

Site	Na 1	0.0	0.50	0.25	occ (oNa_06)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_06)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _07					
Space Group		I - 4					
Scale		0.000003(1)					
Lattice Parameter		a = b = a_07 = 0.3*a ₁₀ + 0.7*a ₁₀ = 5.0738(2)Å					
		c = c_07 = 0.3*c ₁₀ + 0.7*c ₁₀ = 11.3418(7)Å					
Nitrogen Z Coordinate		z_N = z_N0 = 0.3* z_N0 + 0.7* z_N10 = 0.1008(6)					
Occupancy Parameter		oNa07= 0.3* yNa0 + 0.7*yNa10 = 0.83(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_07)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_07)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.000002(1)					
Lattice Parameter		a = b = a_08 = 0.2*a ₁₀ + 0.8*a ₁₀ = 5.0726(2)Å					
		c = c_08 = 0.2*c ₁₀ + 0.8*c ₁₀ = 11.3133(8)Å					
Nitrogen Z Coordinate		z_N = z_N0 = 0.2* z_N0 + 0.8* z_N10 = 0.1010(6)					
Occupancy Parameter		oNa08= 0.2* yNa0 + 0.8*yNa10 = 0.82(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_08)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_08)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _09					
Space Group		I - 4					
Scale		0.000002(1)					
Lattice Parameter		a = b = a_09 = 0.1*a ₁₀ + 0.9*a ₁₀ = 5.0713(2)Å					
		c = c_09 = 0.1*c ₁₀ + 0.9*c ₁₀ = 11.2847(8)Å					
Nitrogen Z Coordinate		z_N = z_N0 = 0.1* z_N0 + 0.9* z_N10 = 0.1012(7)					
Occupancy Parameter		oNa09= 0.1* yNa0 + 0.9*yNa10 = 0.81(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b _{eq} 2.2484

Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ 10					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a ₁₀ = 0.0*a ₁₀ + 1.0*a ₁₀ = 5.0700(2) Å					
		c = c ₁₀ = 0.0*c ₁₀ + 1.0*c ₁₀ = 11.2562(9) Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.0*z _{N0} + 1.0*z _{N10} = 0.1014(7)					
Occupancy Parameter		oNa ₁₀ = 0.0*yNa ₀ + 1.0*yNa ₁₀ = 0.79(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₁₀)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₁₀)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH ₂					
Space Group		Fddd					
Scale		0.00000000(5)					
Lattice Parameter		a = 8.95853(2) Å					
		b = 10.4344(3) Å					
		c = 8.07177(2) Å					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

x = 0.5

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name	LiNH ₂ _00
-------------------	-----------------------

Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}}_{00} = 1.0 * a_{\text{Li}_0} + 0.0 * a_{\text{Li}_{10}} = 5.03701(3) \text{ \AA}$					
		$c = c_{\text{liam}}_{00} = 1.0 * c_{\text{Li}_0} + 0.0 * c_{\text{Li}_{10}} = 10.25577(3) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}00} = 1.0 * y_{\text{Li}_0} + 0.0 * y_{\text{Li}_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_01					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}}_{01} = 0.9 * a_{\text{Li}_0} + 0.1 * a_{\text{Li}_{10}} = 5.03750(2) \text{ \AA}$					
		$c = c_{\text{liam}}_{01} = 0.9 * c_{\text{Li}_0} + 0.1 * c_{\text{Li}_{10}} = 10.26342(5) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}01} = 0.9 * y_{\text{Li}_0} + 0.1 * y_{\text{Li}_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}}_{02} = 0.8 * a_{\text{Li}_{10}} + 0.2 * a_{\text{Li}_0} = 5.03800(2) \text{ \AA}$					
		$c = c_{\text{liam}}_{02} = 0.8 * c_{\text{Li}_0} + 0.2 * c_{\text{Li}_{10}} = 10.27106(6) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}02} = 0.8 * y_{\text{Li}_0} + 0.2 * y_{\text{Li}_{10}} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$

Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$
------	-----	--------	--------	--------	-----	---	--------------------

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_03} = 0.7*a_{Li_0} + 0.3*a_{Li_{10}} = 5.03849(3) \text{ \AA}$					
		$c = c_{\text{liam}_03} = 0.7*c_{Li_0} + 0.3*c_{Li_{10}} = 10.27871(8) \text{ \AA}$					
Occupancy Parameter		$oLi03 = 0.7* y_{Li_0} + 0.3*y_{Li_{10}} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_04} = 0.6*a_{Li_0} + 0.4*a_{Li_{10}} = 5.03899(3) \text{ \AA}$					
		$c = c_{\text{liam}_04} = 0.6*c_{Li_0} + 0.4*c_{Li_{10}} = 10.28635(9) \text{ \AA}$					
Occupancy Parameter		$oLi04 = 0.6* y_{Li_0} + 0.4*y_{Li_{10}} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_05} = 0.5*a_{Li_0} + 0.5*a_{Li_{10}} = 5.03948(4) \text{ \AA}$					
		$c = c_{\text{liam}_05} = 0.5*c_{Li_0} + 0.5*c_{Li_{10}} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$oLi05 = 0.5* y_{Li_0} + 0.5*y_{Li_{10}} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{eq} = 3.0(1)$

Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_06} = 0.4*aLi_0 + 0.6*aLi_{10} = 5.03997(4)\text{\AA}$ $c = c_{liam_06} = 0.4*cLi_0 + 0.6*cLi_{10} = 10.3016(1)\text{\AA}$					
Occupancy Parameter		$oLi06 = 0.4 * yLi_0 + 0.6 * yLi_{10} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_07} = 0.3*aLi_0 + 0.7*aLi_{10} = 5.04047(5)\text{\AA}$ $c = c_{liam_07} = 0.3*cLi_0 + 0.7*cLi_{10} = 10.3093(1)\text{\AA}$					
Occupancy Parameter		$oLi07 = 0.3 * yLi_0 + 0.7 * yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_08} = 0.2*aLi_0 + 0.8*aLi_{10} = 5.04096(5)\text{\AA}$ $c = c_{liam_08} = 0.2*cLi_0 + 0.8*cLi_{10} = 10.3169(2)\text{\AA}$					
Occupancy Parameter		$oLi08 = 0.2 * yLi_0 + 0.8 * yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ	0.96(1)	$b_{eq} = 3.0(1)$

					(oLi08)		
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_{09}} = 0.1 * a_{\text{Li}_0} + 0.9 * a_{\text{Li}_{10}} = 5.04146(6) \text{ \AA}$					
		$c = c_{\text{liam}_{09}} = 0.1 * c_{\text{Li}_0} + 0.9 * c_{\text{Li}_{10}} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}09} = 0.1 * y_{\text{Li}_0} + 0.9 * y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi09)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_10					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_{10}} = 0.0 * a_{\text{Li}_0} + 1.0 * a_{\text{Li}_{10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{\text{liam}_{10}} = 0.0 * c_{\text{Li}_0} + 1.0 * c_{\text{Li}_{10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}10} = 0.0 * y_{\text{Li}_0} + 1.0 * y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi10)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		Li2O					
Space Group		Fm3m					
Scale		0.000277(5)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{eq} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{eq} = 0.8$

Phase Name		LiNa ₂ (NH ₂) ₃					
Space Group		P4 ₂ /m					
Scale		0.0002494(7)					
Lattice Parameter		a = b = 6.2838(1) Å c = 11.1485(2) Å					
Site	N 1	0.66317	0.27595	0.0	occ	1	b _{eq} = 1.5810
Site	H 1	0.73697	0.29827	0.056	occ	1	b _{eq} = 1.5810
Site	N 2	0.20732	0.27336	0.15765	occ	1	b _{eq} = 1.5810
Site	H 2	0.16362	0.18116	0.21186	occ	1	b _{eq} = 1.5810
Site	H 3	0.10362	0.32316	0.14126	occ	1	b _{eq} = 1.5810
Site	Na 1	0.50	0.0	0.14216	occ	1	b _{eq} = 2.2740
Site	Na 2	0.0	0.0	0.0	occ	1	b _{eq} = 2.2740
Site	Na 3	0.50	0.50	0.25	occ	1	b _{eq} = 2.2740
Site	Li 1	0.35356	0.36094	0.0	occ	1	b _{eq} = 2.0455

Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	a ₀ = 5.0828(4)
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	a ₁₀ = 5.0700(2)
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	c ₀ = 11.5415(2)
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	c ₁₀ = 11.2562(9)
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	z N ₀ = 0.0997(2)
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	z N ₁₀ = 0.1014(7)
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Occ. Parameter	yNa ₀ = 0.938(7)
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Occ. Parameter	yNa ₁₀ = 0.79(2)

Phase Name		Li ₃ Na(NH ₂) ₄ _00					
Space Group		I – 4					
Scale		0.000000(1)					
Lattice Parameter		a = b = a ₀₀ = 1.0*a ₀ + 0.0*a ₁₀ = 5.08280(4) Å c = c ₀₀ = 1.0*c ₀ + 0.0*c ₁₀ = 11.5415(2) Å					
Nitrogen Z Coordinate		z N = z N ₀ = 1.0* z N ₀ + 0.0* z N ₁₀ = 0.0997(2)					
Occupancy Parameter		oNa ₀₀ = 1.0* yNa ₀ + 0.0*yNa ₁₀ = 0.938(7)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₀)	0.983(7)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₀)	0.062(7)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _01					
Space Group		I – 4					
Scale		0.000179(3)					
Lattice Parameter		a = b = a ₀₁ = 0.9*a ₀ + 0.1*a ₁₀ = 5.08152(6) Å c = c ₀₁ = 0.9*c ₀ + 0.1*c ₁₀ = 11.5130(3) Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.9* z N ₀ + 0.1* z N ₁₀ = 0.0998(3)					
Occupancy Parameter		oNa ₀₁ = 0.9* yNa ₀ + 0.1*yNa ₁₀ = 0.923(8)					

Site	Na 1	0.0	0.50	0.25	occ (oNa_01)	0.923(8)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_01)	0.077(8)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _02					
Space Group		I - 4					
Scale		0.000010(2)					
Lattice Parameter		a = b = a_02 = 0.8*a ₁₀ + 0.2*a ₁₀ = 5.08024(7) Å					
		c = c_02 = 0.8*c ₁₀ + 0.2*c ₁₀ = 11.4844(3) Å					
Nitrogen Z Coordinate		z_N = z_N ₀ = 0.8* z_N ₀ + 0.2* z_N ₁₀ = 0.1000(3)					
Occupancy Parameter		oNa02= 0.8* yNa ₀ + 0.2*yNa ₁₀ = 0.91(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_02)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_02)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I - 4					
Scale		0.000008(1)					
Lattice Parameter		a = b = a_03 = 0.7*a ₁₀ + 0.3*a ₁₀ = 5.07896(9) Å					
		c = c_03 = 0.7*c ₁₀ + 0.3*c ₁₀ = 11.4559(4) Å					
Nitrogen Z Coordinate		z_N = z_N ₀ = 0.7* z_N ₀ + 0.3* z_N ₁₀ = 0.1002(4)					
Occupancy Parameter		oNa03= 0.7* yNa ₀ + 0.3*yNa ₁₀ = 0.89(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_03)	0.89(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_03)	0.11(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _04					
Space Group		I - 4					
Scale		0.000002(1)					
Lattice Parameter		a = b = a_04 = 0.6*a ₁₀ + 0.4*a ₁₀ = 5.0777(1) Å					
		c = c_04 = 0.6*c ₁₀ + 0.4*c ₁₀ = 11.4274(5) Å					
Nitrogen Z Coordinate		z_N = z_N ₀ = 0.6* z_N ₀ + 0.4* z_N ₁₀ = 0.1003(4)					
Occupancy Parameter		oNa04= 0.6* yNa ₀ + 0.4*yNa ₁₀ = 0.88(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_04)	0.88(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_04)	0.12(1)	b _{eq} 2.2484

Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ 05					
Space Group		I - 4					
Scale		0.000003(1)					
Lattice Parameter		a = b = a ₀₅ = 0.5*a ₁₀ + 0.5*a ₁₀ = 5.0764(1)Å					
		c = c ₀₅ = 0.5*c ₁₀ + 0.5*c ₁₀ = 11.3989(6)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.5* z _{N0} + 0.5* z _{N10} = 0.1005(5)					
Occupancy Parameter		oNa05 = 0.5* yNa ₀ + 0.5*yNa ₁₀ = 0.87(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₅)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₅)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ 06					
Space Group		I - 4					
Scale		0.000000(1)					
Lattice Parameter		a = b = a ₀₆ = 0.4*a ₁₀ + 0.6*a ₁₀ = 5.0751(1)Å					
		c = c ₀₆ = 0.4*c ₁₀ + 0.6*c ₁₀ = 11.3703(6)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.4* z _{N0} + 0.6* z _{N10} = 0.1007(5)					
Occupancy Parameter		oNa06 = 0.4* yNa ₀ + 0.6*yNa ₁₀ = 0.85(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₆)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₆)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ 07					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a ₀₇ = 0.3*a ₁₀ + 0.7*a ₁₀ = 5.0738(2)Å					
		c = c ₀₇ = 0.3*c ₁₀ + 0.7*c ₁₀ = 11.3418(7)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.3* z _{N0} + 0.7* z _{N10} = 0.1008(6)					
Occupancy Parameter		oNa07 = 0.3* yNa ₀ + 0.7*yNa ₁₀ = 0.83(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₇)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₇)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484

Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a ₀₈ = 0.2*a ₁₀ + 0.8*a ₁₀ = 5.0726(2)Å					
		c = c ₀₈ = 0.2*c ₁₀ + 0.8*c ₁₀ = 11.3133(8)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.2* z _{N0} + 0.8* z _{N10} = 0.1010(6)					
Occupancy Parameter		oNa08 = 0.2* yNa ₀ + 0.8*yNa ₁₀ = 0.82(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₈)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₈)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _09					
Space Group		I - 4					
Scale		0.000000(1)					
Lattice Parameter		a = b = a ₀₉ = 0.1*a ₁₀ + 0.9*a ₁₀ = 5.0713(2)Å					
		c = c ₀₉ = 0.1*c ₁₀ + 0.9*c ₁₀ = 11.2847(8)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.1* z _{N0} + 0.9* z _{N10} = 0.1012(7)					
Occupancy Parameter		oNa09 = 0.1* yNa ₀ + 0.9*yNa ₁₀ = 0.81(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₉)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₉)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _10					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a ₁₀ = 0.0*a ₁₀ + 1.0*a ₁₀ = 5.0700(2)Å					
		c = c ₁₀ = 0.0*c ₁₀ + 1.0*c ₁₀ = 11.2562(9)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.0* z _{N0} + 1.0* z _{N10} = 0.1014(7)					
Occupancy Parameter		oNa10 = 0.0* yNa ₀ + 1.0*yNa ₁₀ = 0.79(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₁₀)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₁₀)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484

Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484
------	-----	-------	----------	----------	-----	---	------------------------

Phase Name		NaNH ₂					
Space Group		Fddd					
Scale		0.00000000(4)					
Lattice Parameter		a = 8.95853(2) Å					
		b = 10.4344(3) Å					
		c = 8.07177(2) Å					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

$$x = 0.417$$

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted Durbin Watson	7.430		
Goodness of fit	3.316		

LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name		LiNH ₂ _00					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a _{liam_00} = 1.0*aLi ₀ + 0.0*aLi ₁₀ = 5.03701(3) Å					
		c = c _{liam_00} = 1.0*cLi ₀ + 0.0*cLi ₁₀ = 10.25577(3) Å					
Occupancy Parameter		oLi00 = 1.0* yLi ₀ + 0.0*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH ₂ _01					
Space Group		I – 4					
Scale		0.000001(1)					

Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.9 \cdot a_{\text{Li}_0} + 0.1 \cdot a_{\text{Li}_{10}} = 5.03750(2) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.9 \cdot c_{\text{Li}_0} + 0.1 \cdot c_{\text{Li}_{10}} = 10.26342(5) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li01}} = 0.9 \cdot y_{\text{Li}_0} + 0.1 \cdot y_{\text{Li}_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.8 \cdot a_{\text{Li}_0} + 0.2 \cdot a_{\text{Li}_{10}} = 5.03800(2) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.8 \cdot c_{\text{Li}_0} + 0.2 \cdot c_{\text{Li}_{10}} = 10.27106(6) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li02}} = 0.8 \cdot y_{\text{Li}_0} + 0.2 \cdot y_{\text{Li}_{10}} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.7 \cdot a_{\text{Li}_0} + 0.3 \cdot a_{\text{Li}_{10}} = 5.03849(3) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.7 \cdot c_{\text{Li}_0} + 0.3 \cdot c_{\text{Li}_{10}} = 10.27871(8) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li03}} = 0.7 \cdot y_{\text{Li}_0} + 0.3 \cdot y_{\text{Li}_{10}} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{LiNH2}_04} = 0.6 \cdot a_{\text{Li}_0} + 0.4 \cdot a_{\text{Li}_{10}} = 5.03899(3) \text{ \AA}$					
		$c = c_{\text{LiNH2}_04} = 0.6 \cdot c_{\text{Li}_0} + 0.4 \cdot c_{\text{Li}_{10}} = 10.28635(9) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li04}} = 0.6 \cdot y_{\text{Li}_0} + 0.4 \cdot y_{\text{Li}_{10}} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{LiNH2}_05} = 0.5 \cdot a_{\text{Li}_0} + 0.5 \cdot a_{\text{Li}_{10}} = 5.03948(4) \text{ \AA}$					
		$c = c_{\text{LiNH2}_05} = 0.5 \cdot c_{\text{Li}_0} + 0.5 \cdot c_{\text{Li}_{10}} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li05}} = 0.5 \cdot y_{\text{Li}_0} + 0.5 \cdot y_{\text{Li}_{10}} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{LiNH2}_06} = 0.4 \cdot a_{\text{Li}_0} + 0.6 \cdot a_{\text{Li}_{10}} = 5.03997(4) \text{ \AA}$					
		$c = c_{\text{LiNH2}_06} = 0.4 \cdot c_{\text{Li}_0} + 0.6 \cdot c_{\text{Li}_{10}} = 10.3016(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li06}} = 0.4 \cdot y_{\text{Li}_0} + 0.6 \cdot y_{\text{Li}_{10}} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$

Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_07} = 0.3*a_{\text{Li}_0} + 0.7*a_{\text{Li}_{10}} = 5.04047(5)\text{\AA}$					
		$c = c_{\text{liam}_07} = 0.3*c_{\text{Li}_0} + 0.7*c_{\text{Li}_{10}} = 10.3093(1)\text{\AA}$					
Occupancy Parameter		$o_{\text{Li}07} = 0.3* y_{\text{Li}_0} + 0.7*y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_08} = 0.2*a_{\text{Li}_0} + 0.8*a_{\text{Li}_{10}} = 5.04096(5)\text{\AA}$					
		$c = c_{\text{liam}_08} = 0.2*c_{\text{Li}_0} + 0.8*c_{\text{Li}_{10}} = 10.3169(2)\text{\AA}$					
Occupancy Parameter		$o_{\text{Li}08} = 0.2* y_{\text{Li}_0} + 0.8*y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_09} = 0.1*a_{\text{Li}_0} + 0.9*a_{\text{Li}_{10}} = 5.04146(6)\text{\AA}$					
		$c = c_{\text{liam}_09} = 0.1*c_{\text{Li}_0} + 0.9*c_{\text{Li}_{10}} = 10.3246(2)\text{\AA}$					
Occupancy Parameter		$o_{\text{Li}09} = 0.1* y_{\text{Li}_0} + 0.9*y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-	0.05(1)	$b_{eq} = 3.0(1)$

					oLi09)		
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH ₂ 10					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a _{liam 10} = 0.0*aLi ₀ + 1.0*aLi ₁₀ = 5.04195(6)Å					
		c = c _{liam 10} = 0.0*cLi ₀ + 1.0*cLi ₁₀ = 10.3311(2)Å					
Occupancy Parameter		oLi10 = 0.0* yLi ₀ + 1.0*yLi ₁₀ = 0.95(1)					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi10)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		Li ₂ O					
Space Group		Fm3m					
Scale		0.000351(5)					
Lattice Parameter		a = b = c = 4.61589(5) Å					
Site	Li	0.25	0.25	0.25	occ	1	$b_{eq} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{eq} = 0.8$

Phase Name		LiNa ₂ (NH ₂) ₃					
Space Group		P4 ₂ /m					
Scale		0.000383(1)					
Lattice Parameter		a = b = 6.2838(1)Å					
		c = 11.1485(2)Å					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{eq} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{eq} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{eq} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{eq} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$a_0 = 5.0828(4)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_0 = 11.5415(2)$

Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name		Li3Na(NH2)4_00					
Space Group		I – 4					
Scale		0.000010(1)					
Lattice Parameter		$a = b = a_{00} = 1.0*a_0 + 0.0*a_{10} = 5.08280(4)\text{Å}$					
		$c = c_{00} = 1.0*c_0 + 0.0*c_{10} = 11.5415(2)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 1.0*z_{N_0} + 0.0*z_{N_{10}} = 0.0997(2)$					
Occupancy Parameter		$o_{Na00} = 1.0*y_{Na_0} + 0.0*y_{Na_{10}} = 0.938(7)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_00)	0.983(7)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_00)	0.062(7)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_01					
Space Group		I – 4					
Scale		0.000151(3)					
Lattice Parameter		$a = b = a_{01} = 0.9*a_0 + 0.1*a_{10} = 5.08152(6)\text{Å}$					
		$c = c_{01} = 0.9*c_0 + 0.1*c_{10} = 11.5130(3)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.9*z_{N_0} + 0.1*z_{N_{10}} = 0.0998(3)$					
Occupancy Parameter		$o_{Na01} = 0.9*y_{Na_0} + 0.1*y_{Na_{10}} = 0.923(8)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_01)	0.923(8)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_01)	0.077(8)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_02					
Space Group		I – 4					
Scale		0.000000(2)					
Lattice Parameter		$a = b = a_{02} = 0.8*a_{10} + 0.2*a_{10} = 5.08024(7)\text{Å}$					
		$c = c_{02} = 0.8*c_{10} + 0.2*c_{10} = 11.4844(3)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.8*z_{N_0} + 0.2*z_{N_{10}} = 0.1000(3)$					
Occupancy Parameter		$o_{Na02} = 0.8*y_{Na_0} + 0.2*y_{Na_{10}} = 0.91(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_02)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_02)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484

Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I - 4					
Scale		0.000006(1)					
Lattice Parameter		a = b = a ₀₃ = 0.7*a ₁₀ + 0.3*a ₁₀ = 5.07896(9) Å					
		c = c ₀₃ = 0.7*c ₁₀ + 0.3*c ₁₀ = 11.4559(4) Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.7* z _{N0} + 0.3* z _{N10} = 0.1002(4)					
Occupancy Parameter		oNa03 = 0.7* yNa ₀ + 0.3*yNa ₁₀ = 0.89(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₃)	0.89(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₃)	0.11(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _04					
Space Group		I - 4					
Scale		0.000002(1)					
Lattice Parameter		a = b = a ₀₄ = 0.6*a ₁₀ + 0.4*a ₁₀ = 5.0777(1)Å					
		c = c ₀₄ = 0.6*c ₁₀ + 0.4*c ₁₀ = 11.4274(5)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.6* z _{N0} + 0.4* z _{N10} = 0.1003(4)					
Occupancy Parameter		oNa04 = 0.6* yNa ₀ + 0.4*yNa ₁₀ = 0.88(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₄)	0.88(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₄)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _05					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a ₀₅ = 0.5*a ₁₀ + 0.5*a ₁₀ = 5.0764(1)Å					
		c = c ₀₅ = 0.5*c ₁₀ + 0.5*c ₁₀ = 11.3989(6)Å					
Nitrogen Z Coordinate		z _N = z _{N0} = 0.5* z _{N0} + 0.5* z _{N10} = 0.1005(5)					
Occupancy Parameter		oNa05 = 0.5* yNa ₀ + 0.5*yNa ₁₀ = 0.87(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₅)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₅)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484

Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484
------	-----	-------	----------	----------	-----	---	------------------------

Phase Name		Li ₃ Na(NH ₂) ₄ 06					
Space Group		I - 4					
Scale		0.000000(1)					
Lattice Parameter		a = b = a ₀₆ = 0.4*a ₁₀ + 0.6*a ₁₀ = 5.0751(1)Å					
		c = c ₀₆ = 0.4*c ₁₀ + 0.6*c ₁₀ = 11.3703(6)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.4* z N ₀ + 0.6* z N ₁₀ = 0.1007(5)					
Occupancy Parameter		oNa06= 0.4* yNa ₀ + 0.6*yNa ₁₀ = 0.85(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₆)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₆)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ 07					
Space Group		I - 4					
Scale		0.000000(1)					
Lattice Parameter		a = b = a ₀₇ = 0.3*a ₁₀ + 0.7*a ₁₀ = 5.0738(2)Å					
		c = c ₀₇ = 0.3*c ₁₀ + 0.7*c ₁₀ = 11.3418(7)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.3* z N ₀ + 0.7* z N ₁₀ = 0.1008(6)					
Occupancy Parameter		oNa07= 0.3* yNa ₀ + 0.7*yNa ₁₀ = 0.83(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₇)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₇)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ 08					
Space Group		I - 4					
Scale		0.000000(1)					
Lattice Parameter		a = b = a ₀₈ = 0.2*a ₁₀ + 0.8*a ₁₀ = 5.0726(2)Å					
		c = c ₀₈ = 0.2*c ₁₀ + 0.8*c ₁₀ = 11.3133(8)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.2* z N ₀ + 0.8* z N ₁₀ = 0.1010(6)					
Occupancy Parameter		oNa08= 0.2* yNa ₀ + 0.8*yNa ₁₀ = 0.82(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₈)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₈)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_09					
Space Group		I - 4					
Scale		0.000000(1)					
Lattice Parameter		$a = b = a_{09} = 0.1 * a_{10} + 0.9 * a_{10} = 5.0713(2) \text{ \AA}$					
		$c = c_{09} = 0.1 * c_{10} + 0.9 * c_{10} = 11.2847(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N0} = 0.1 * z_{N0} + 0.9 * z_{N10} = 0.1012(7)$					
Occupancy Parameter		$oNa09 = 0.1 * yNa0 + 0.9 * yNa10 = 0.81(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_10					
Space Group		I - 4					
Scale		0.000000(1)					
Lattice Parameter		$a = b = a_{10} = 0.0 * a_{10} + 1.0 * a_{10} = 5.0700(2) \text{ \AA}$					
		$c = c_{10} = 0.0 * c_{10} + 1.0 * c_{10} = 11.2562(9) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N0} = 0.0 * z_{N0} + 1.0 * z_{N10} = 0.1014(7)$					
Occupancy Parameter		$oNa10 = 0.0 * yNa0 + 1.0 * yNa10 = 0.79(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_10)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_10)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH2					
Space Group		Fddd					
Scale		0.00000000(5)					
Lattice Parameter		$a = 8.95853(2) \text{ \AA}$					
		$b = 10.4344(3) \text{ \AA}$					
		$c = 8.07177(2) \text{ \AA}$					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

$$x = 0.333$$

R _{expected}	4.521	R _{expected'}	9.452
R _{weighted pattern}	14.989	R _{weighted pattern'}	31.342
R _{Pattern}	9.839	R _{Pattern'}	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH2_00 – LiNH2_10 Lattice Parameter	$a_{Li_0} = 5.03701(3) \text{ \AA}$
LiNH2_00 – LiNH2_10 Lattice Parameter	$a_{Li_{10}} = 5.04195(6) \text{ \AA}$
LiNH2_00 – LiNH2_10 Lattice Parameter	$c_{Li_0} = 10.25577(3) \text{ \AA}$
LiNH2_00 – LiNH2_10 Lattice Parameter	$c_{Li_{10}} = 10.3311(2) \text{ \AA}$
LiNH2_00 – LiNH2_10 Occ. Parameter	$y_{Li_0} = 0.987(3)$
LiNH2_00 – LiNH2_10 Occ. Parameter	$y_{Li_{10}} = 0.95(1)$

Phase Name		LiNH2_00					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam}_00} = 1.0*a_{Li_0} + 0.0*a_{Li_{10}} = 5.03701(3) \text{ \AA}$					
		$c = c_{\text{liam}_00} = 1.0*c_{Li_0} + 0.0*c_{Li_{10}} = 10.25577(3) \text{ \AA}$					
Occupancy Parameter		$o_{Li00} = 1.0* y_{Li_0} + 0.0*y_{Li_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_01					
Space Group		I – 4					
Scale		0.000021(2)					
Lattice Parameter		$a = b = a_{\text{liam}_01} = 0.9*a_{Li_0} + 0.1*a_{Li_{10}} = 5.03750(2) \text{ \AA}$					
		$c = c_{\text{liam}_01} = 0.9*c_{Li_0} + 0.1*c_{Li_{10}} = 10.26342(5) \text{ \AA}$					
Occupancy Parameter		$o_{Li01} = 0.9* y_{Li_0} + 0.1*y_{Li_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I – 4					
Scale		0.000020(2)					
Lattice Parameter		$a = b = a_{\text{liam}_02} = 0.8*a_{Li_{10}} + 0.2*a_{Li_0} = 5.03800(2) \text{ \AA}$					
		$c = c_{\text{liam}_02} = 0.8*c_{Li_0} + 0.2*c_{Li_{10}} = 10.27106(6) \text{ \AA}$					
Occupancy		$o_{Li02} = 0.8* y_{Li_0} + 0.2*y_{Li_{10}} = 0.979(5)$					

Parameter							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_03							
Space Group							
I - 4							
Scale							
0.000006(2)							
Lattice Parameter							
$a = b = a_{liam_03} = 0.7*aLi_0 + 0.3*aLi_{10} = 5.03849(3) \text{ \AA}$							
$c = c_{liam_03} = 0.7*cLi_0 + 0.3*cLi_{10} = 10.27871(8) \text{ \AA}$							
Occupancy Parameter							
$oLi03 = 0.7* yLi_0 + 0.3*yLi_{10} = 0.975(6)$							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_04							
Space Group							
I - 4							
Scale							
0.000007(2)							
Lattice Parameter							
$a = b = a_{liam_04} = 0.6*aLi_0 + 0.4*aLi_{10} = 5.03899(3) \text{ \AA}$							
$c = c_{liam_04} = 0.6*cLi_0 + 0.4*cLi_{10} = 10.28635(9) \text{ \AA}$							
Occupancy Parameter							
$oLi04 = 0.6* yLi_0 + 0.4*yLi_{10} = 0.972(7)$							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_05							
Space Group							
I - 4							
Scale							
0.000003(2)							

Lattice Parameter		$a = b = a_{\text{liam}_05} = 0.5 \cdot a_{\text{Li}_0} + 0.5 \cdot a_{\text{Li}_{10}} = 5.03948(4) \text{ \AA}$					
		$c = c_{\text{liam}_05} = 0.5 \cdot c_{\text{Li}_0} + 0.5 \cdot c_{\text{Li}_{10}} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}05} = 0.5 \cdot y_{\text{Li}_0} + 0.5 \cdot y_{\text{Li}_{10}} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000004(2)					
Lattice Parameter		$a = b = a_{\text{liam}_06} = 0.4 \cdot a_{\text{Li}_0} + 0.6 \cdot a_{\text{Li}_{10}} = 5.03997(4) \text{ \AA}$					
		$c = c_{\text{liam}_06} = 0.4 \cdot c_{\text{Li}_0} + 0.6 \cdot c_{\text{Li}_{10}} = 10.3016(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}06} = 0.4 \cdot y_{\text{Li}_0} + 0.6 \cdot y_{\text{Li}_{10}} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000004(2)					
Lattice Parameter		$a = b = a_{\text{liam}_07} = 0.3 \cdot a_{\text{Li}_0} + 0.7 \cdot a_{\text{Li}_{10}} = 5.04047(5) \text{ \AA}$					
		$c = c_{\text{liam}_07} = 0.3 \cdot c_{\text{Li}_0} + 0.7 \cdot c_{\text{Li}_{10}} = 10.3093(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}07} = 0.3 \cdot y_{\text{Li}_0} + 0.7 \cdot y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _08					
Space Group		I – 4					
Scale		0.000002(2)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2\text{08}} = 0.2*a_{\text{Li}_0} + 0.8*a_{\text{Li}_{10}} = 5.04096(5) \text{ \AA}$					
		$c = c_{\text{LiNH}_2\text{08}} = 0.2*c_{\text{Li}_0} + 0.8*c_{\text{Li}_{10}} = 10.3169(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li08}} = 0.2* y_{\text{Li}_0} + 0.8*y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _09					
Space Group		I – 4					
Scale		0.000002(1)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2\text{09}} = 0.1*a_{\text{Li}_0} + 0.9*a_{\text{Li}_{10}} = 5.04146(6) \text{ \AA}$					
		$c = c_{\text{LiNH}_2\text{09}} = 0.1*c_{\text{Li}_0} + 0.9*c_{\text{Li}_{10}} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li09}} = 0.1* y_{\text{Li}_0} + 0.9*y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _10					
Space Group		I – 4					
Scale		0.000003(1)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2\text{10}} = 0.0*a_{\text{Li}_0} + 1.0*a_{\text{Li}_{10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{\text{LiNH}_2\text{10}} = 0.0*c_{\text{Li}_0} + 1.0*c_{\text{Li}_{10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li10}} = 0.0* y_{\text{Li}_0} + 1.0*y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$

Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		Li2O					
Space Group		Fm3m					
Scale		0.000241(5)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{eq} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{eq} = 0.8$

Phase Name		LiNa2(NH2)3					
Space Group		P42/m					
Scale		0.0002066(6)					
Lattice Parameter		$a = b = 6.2838(1) \text{ \AA}$					
		$c = 11.1485(2) \text{ \AA}$					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{eq} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{eq} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{eq} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{eq} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_0 = 5.0828(4)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_0 = 11.5415(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name		Li3Na(NH2)4_00					
Space Group		I – 4					
Scale		0.000000(1)					
Lattice Parameter		$a = b = a_{00} = 1.0*a_0 + 0.0*a_{10} = 5.08280(4) \text{ \AA}$					
		$c = c_{00} = 1.0*c_0 + 0.0*c_{10} = 11.5415(2) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 1.0*z_{N_0} + 0.0*z_{N_{10}} = 0.0997(2)$					
Occupancy Parameter		$o_{Na00} = 1.0*y_{Na_0} + 0.0*y_{Na_{10}} = 0.938(7)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_00)	0.983(7)	$b_{eq} = 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_00)	0.062(7)	$b_{eq} = 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} = 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	$b_{eq} = 2.2484$

Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _01					
Space Group		I - 4					
Scale		0.000026(1)					
Lattice Parameter		a = b = a ₀₁ = 0.9*a ₀ + 0.1*a ₁₀ = 5.08152(6) Å					
		c = c ₀₁ = 0.9*c ₀ + 0.1*c ₁₀ = 11.5130(3) Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.9* z _{N₀} + 0.1* z _{N₁₀} = 0.0998(3)					
Occupancy Parameter		oNa01 = 0.9* yNa ₀ + 0.1*yNa ₁₀ = 0.923(8)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₁)	0.923(8)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₁)	0.077(8)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _02					
Space Group		I - 4					
Scale		0.000027(2)					
Lattice Parameter		a = b = a ₀₂ = 0.8*a ₁₀ + 0.2*a ₁₀ = 5.08024(7) Å					
		c = c ₀₂ = 0.8*c ₁₀ + 0.2*c ₁₀ = 11.4844(3) Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.8* z _{N₀} + 0.2* z _{N₁₀} = 0.1000(3)					
Occupancy Parameter		oNa02 = 0.8* yNa ₀ + 0.2*yNa ₁₀ = 0.91(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₂)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₂)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I - 4					
Scale		0.000016(1)					
Lattice Parameter		a = b = a ₀₃ = 0.7*a ₁₀ + 0.3*a ₁₀ = 5.07896(9) Å					
		c = c ₀₃ = 0.7*c ₁₀ + 0.3*c ₁₀ = 11.4559(4) Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.7* z _{N₀} + 0.3* z _{N₁₀} = 0.1002(4)					
Occupancy Parameter		oNa03 = 0.7* yNa ₀ + 0.3*yNa ₁₀ = 0.89(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₃)	0.89(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₃)	0.11(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_04					
Space Group		I - 4					
Scale		0.000012(1)					
Lattice Parameter		$a = b = a_{04} = 0.6*a_{10} + 0.4*a_{10} = 5.0777(1)\text{Å}$					
		$c = c_{04} = 0.6*c_{10} + 0.4*c_{10} = 11.4274(5)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.6*z_{N_0} + 0.4*z_{N_{10}} = 0.1003(4)$					
Occupancy Parameter		$oNa_{04} = 0.6*y_{Na_0} + 0.4*y_{Na_{10}} = 0.88(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_04)	0.88(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_04)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_05					
Space Group		I - 4					
Scale		0.000007(1)					
Lattice Parameter		$a = b = a_{05} = 0.5*a_{10} + 0.5*a_{10} = 5.0764(1)\text{Å}$					
		$c = c_{05} = 0.5*c_{10} + 0.5*c_{10} = 11.3989(6)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.5*z_{N_0} + 0.5*z_{N_{10}} = 0.1005(5)$					
Occupancy Parameter		$oNa_{05} = 0.5*y_{Na_0} + 0.5*y_{Na_{10}} = 0.87(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_05)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_05)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_06					
Space Group		I - 4					
Scale		0.000008(1)					
Lattice Parameter		$a = b = a_{06} = 0.4*a_{10} + 0.6*a_{10} = 5.0751(1)\text{Å}$					
		$c = c_{06} = 0.4*c_{10} + 0.6*c_{10} = 11.3703(6)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.4*z_{N_0} + 0.6*z_{N_{10}} = 0.1007(5)$					
Occupancy Parameter		$oNa_{06} = 0.4*y_{Na_0} + 0.6*y_{Na_{10}} = 0.85(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_06)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_06)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_07					
-------------------	--	----------------	--	--	--	--	--

Space Group		I - 4					
Scale		0.000003(1)					
Lattice Parameter		$a = b = a_{07} = 0.3 \cdot a_{10} + 0.7 \cdot a_{10} = 5.0738(2) \text{ \AA}$					
		$c = c_{07} = 0.3 \cdot c_{10} + 0.7 \cdot c_{10} = 11.3418(7) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.3 \cdot z_{N_0} + 0.7 \cdot z_{N_{10}} = 0.1008(6)$					
Occupancy Parameter		$o_{Na07} = 0.3 \cdot y_{Na_0} + 0.7 \cdot y_{Na_{10}} = 0.83(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_07)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_07)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.000005(1)					
Lattice Parameter		$a = b = a_{08} = 0.2 \cdot a_{10} + 0.8 \cdot a_{10} = 5.0726(2) \text{ \AA}$					
		$c = c_{08} = 0.2 \cdot c_{10} + 0.8 \cdot c_{10} = 11.3133(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.2 \cdot z_{N_0} + 0.8 \cdot z_{N_{10}} = 0.1010(6)$					
Occupancy Parameter		$o_{Na08} = 0.2 \cdot y_{Na_0} + 0.8 \cdot y_{Na_{10}} = 0.82(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_08)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_08)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _09					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{09} = 0.1 \cdot a_{10} + 0.9 \cdot a_{10} = 5.0713(2) \text{ \AA}$					
		$c = c_{09} = 0.1 \cdot c_{10} + 0.9 \cdot c_{10} = 11.2847(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.1 \cdot z_{N_0} + 0.9 \cdot z_{N_{10}} = 0.1012(7)$					
Occupancy Parameter		$o_{Na09} = 0.1 \cdot y_{Na_0} + 0.9 \cdot y_{Na_{10}} = 0.81(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _10					
Space Group		I - 4					
Scale		0.000002(1)					

Lattice Parameter		$a = b = a_{10} = 0.0 \cdot a_{10} + 1.0 \cdot a_{10} = 5.0700(2) \text{ \AA}$					
		$c = c_{10} = 0.0 \cdot c_{10} + 1.0 \cdot c_{10} = 11.2562(9) \text{ \AA}$					
Nitrogen Z Coordinate		$z_{\text{N}} = z_{\text{N}_0} = 0.0 \cdot z_{\text{N}_0} + 1.0 \cdot z_{\text{N}_{10}} = 0.1014(7)$					
Occupancy Parameter		$o_{\text{Na}_{10}} = 0.0 \cdot y_{\text{Na}_0} + 1.0 \cdot y_{\text{Na}_{10}} = 0.79(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₁₀)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₁₀)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH ₂					
Space Group		Fddd					
Scale		0.000059663(5)					
Lattice Parameter		$a = 8.95853(2) \text{ \AA}$					
		$b = 10.4344(3) \text{ \AA}$					
		$c = 8.07177(2) \text{ \AA}$					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

x = 0.25

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted Durbin Watson	7.430		
Goodness of fit	3.316		

LiNH₂₀₀ – LiNH₂₁₀ Lattice Parameter	$a_{\text{Li}_0} = 5.03701(3) \text{ \AA}$
LiNH₂₀₀ – LiNH₂₁₀ Lattice Parameter	$a_{\text{Li}_{10}} = 5.04195(6) \text{ \AA}$
LiNH₂₀₀ – LiNH₂₁₀ Lattice Parameter	$c_{\text{Li}_0} = 10.25577(3) \text{ \AA}$
LiNH₂₀₀ – LiNH₂₁₀ Lattice Parameter	$c_{\text{Li}_{10}} = 10.3311(2) \text{ \AA}$
LiNH₂₀₀ – LiNH₂₁₀ Occ. Parameter	$y_{\text{Li}_0} = 0.987(3)$
LiNH₂₀₀ – LiNH₂₁₀ Occ. Parameter	$y_{\text{Li}_{10}} = 0.95(1)$

Phase Name		LiNH ₂ ₀₀					
Space Group		I – 4					
Scale		0.0000010(3)					
Lattice Parameter		$a = b = a_{\text{LiNH}_{200}} = 1.0 \cdot a_{\text{Li}_0} + 0.0 \cdot a_{\text{Li}_{10}} = 5.03701(3) \text{ \AA}$					
		$c = c_{\text{LiNH}_{200}} = 1.0 \cdot c_{\text{Li}_0} + 0.0 \cdot c_{\text{Li}_{10}} = 10.25577(3) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}00} = 1.0 \cdot y_{\text{Li}_0} + 0.0 \cdot y_{\text{Li}_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)

Site	Na 2	0.0	0.5	-0.25	occ (1-oLi00)	0.013(3)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_01					
Space Group		I - 4					
Scale		0.0000010(5)					
Lattice Parameter		$a = b = a_{\text{liam_01}} = 0.9*a_{Li_0} + 0.1*a_{Li_{10}} = 5.03750(2)\text{\AA}$					
		$c = c_{\text{liam_01}} = 0.9*c_{Li_0} + 0.1*c_{Li_{10}} = 10.26342(5)\text{\AA}$					
Occupancy Parameter		$oLi01 = 0.9*y_{Li_0} + 0.1*y_{Li_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi01)	0.017(3)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam_02}} = 0.8*a_{Li_{10}} + 0.2*a_{Li_0} = 5.03800(2)\text{\AA}$					
		$c = c_{\text{liam_02}} = 0.8*c_{Li_0} + 0.2*c_{Li_{10}} = 10.27106(6)\text{\AA}$					
Occupancy Parameter		$oLi02 = 0.8*y_{Li_0} + 0.2*y_{Li_{10}} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi02)	0.021(5)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam_03}} = 0.7*a_{Li_0} + 0.3*a_{Li_{10}} = 5.03849(3)\text{\AA}$					
		$c = c_{\text{liam_03}} = 0.7*c_{Li_0} + 0.3*c_{Li_{10}} = 10.27871(8)\text{\AA}$					
Occupancy Parameter		$oLi03 = 0.7*y_{Li_0} + 0.3*y_{Li_{10}} = 0.975(6)$					

Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_04} = 0.6*aLi_0 + 0.4*aLi_{10} = 5.03899(3)\text{\AA}$					
		$c = c_{liam_04} = 0.6*cLi_0 + 0.4*cLi_{10} = 10.28635(9)\text{\AA}$					
Occupancy Parameter		$oLi04 = 0.6* yLi_0 + 0.4*yLi_{10} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_05} = 0.5*aLi_0 + 0.5*aLi_{10} = 5.03948(4)\text{\AA}$					
		$c = c_{liam_05} = 0.5*cLi_0 + 0.5*cLi_{10} = 10.2940(1)\text{\AA}$					
Occupancy Parameter		$oLi05 = 0.5* yLi_0 + 0.5*yLi_{10} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_06} = 0.4*aLi_0 + 0.6*aLi_{10} = 5.03997(4)\text{\AA}$					

		$c = c_{\text{liam 06}} = 0.4 * c_{\text{Li}_0} + 0.6 * c_{\text{Li}_{10}} = 10.3016(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li06}} = 0.4 * y_{\text{Li}_0} + 0.6 * y_{\text{Li}_{10}} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi06)	0.036(9)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam 07}} = 0.3 * a_{\text{Li}_0} + 0.7 * a_{\text{Li}_{10}} = 5.04047(5) \text{ \AA}$					
		$c = c_{\text{liam 07}} = 0.3 * c_{\text{Li}_0} + 0.7 * c_{\text{Li}_{10}} = 10.3093(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li07}} = 0.3 * y_{\text{Li}_0} + 0.7 * y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi07)	0.040(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam 08}} = 0.2 * a_{\text{Li}_0} + 0.8 * a_{\text{Li}_{10}} = 5.04096(5) \text{ \AA}$					
		$c = c_{\text{liam 08}} = 0.2 * c_{\text{Li}_0} + 0.8 * c_{\text{Li}_{10}} = 10.3169(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li08}} = 0.2 * y_{\text{Li}_0} + 0.8 * y_{\text{Li}_{10}} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi08)	0.04(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_09					
-------------------	--	----------	--	--	--	--	--

Space Group		I – 4					
Scale		0.0000010(5)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.1 \cdot a_{\text{Li}_0} + 0.9 \cdot a_{\text{Li}_{10}} = 5.04146(6) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.1 \cdot c_{\text{Li}_0} + 0.9 \cdot c_{\text{Li}_{10}} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}09} = 0.1 \cdot y_{\text{Li}_0} + 0.9 \cdot y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH ₂ _10					
Space Group		I – 4					
Scale		0.0000010(3)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.0 \cdot a_{\text{Li}_0} + 1.0 \cdot a_{\text{Li}_{10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.0 \cdot c_{\text{Li}_0} + 1.0 \cdot c_{\text{Li}_{10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li}10} = 0.0 \cdot y_{\text{Li}_0} + 1.0 \cdot y_{\text{Li}_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		Li ₂ O					
Space Group		Fm3m					
Scale		0.000151(2)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{\text{eq}} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.8$

Phase Name		LiNa ₂ (NH ₂) ₃					
Space Group		P4 ₂ /m					
Scale		0.0000443(2)					
Lattice Parameter		$a = b = 6.2838(1) \text{ \AA}$					
		$c = 11.1485(2) \text{ \AA}$					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{\text{eq}} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{\text{eq}} = 1.5810$

Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{eq} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$a_0 = 5.0828(4)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_0 = 11.5415(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name	Li ₃ Na(NH ₂) ₄ 00						
Space Group	I – 4						
Scale	0.0000001(3)						
Lattice Parameter	$a = b = a_{00} = 1.0*a_0 + 0.0*a_{10} = 5.08280(4)\text{Å}$						
	$c = c_{00} = 1.0*c_0 + 0.0*c_{10} = 11.5415(2)\text{Å}$						
Nitrogen Z Coordinate	$z_N = z_{N_0} = 1.0*z_{N_0} + 0.0*z_{N_{10}} = 0.0997(2)$						
Occupancy Parameter	$o_{Na00} = 1.0*y_{Na_0} + 0.0*y_{Na_{10}} = 0.938(7)$						
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₀)	0.983(7)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₀)	0.062(7)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name	Li ₃ Na(NH ₂) ₄ 01						
Space Group	I – 4						
Scale	0.0000001(3)						
Lattice Parameter	$a = b = a_{01} = 0.9*a_0 + 0.1*a_{10} = 5.08152(6)\text{Å}$						
	$c = c_{01} = 0.9*c_0 + 0.1*c_{10} = 11.5130(3)\text{Å}$						
Nitrogen Z Coordinate	$z_N = z_{N_0} = 0.9*z_{N_0} + 0.1*z_{N_{10}} = 0.0998(3)$						
Occupancy Parameter	$o_{Na01} = 0.9*y_{Na_0} + 0.1*y_{Na_{10}} = 0.923(8)$						
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₁)	0.923(8)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₁)	0.077(8)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name	Li ₃ Na(NH ₂) ₄ 02						
-------------------	--	--	--	--	--	--	--

Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{02} = 0.8*a_{10} + 0.2*a_{10} = 5.08024(7)\text{Å}$					
		$c = c_{02} = 0.8*c_{10} + 0.2*c_{10} = 11.4844(3)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.8*z_{N_0} + 0.2*z_{N_{10}} = 0.1000(3)$					
Occupancy Parameter		$oNa_{02} = 0.8*y_{Na_0} + 0.2*y_{Na_{10}} = 0.91(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_02)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_02)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{03} = 0.7*a_{10} + 0.3*a_{10} = 5.07896(9)\text{Å}$					
		$c = c_{03} = 0.7*c_{10} + 0.3*c_{10} = 11.4559(4)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.7*z_{N_0} + 0.3*z_{N_{10}} = 0.1002(4)$					
Occupancy Parameter		$oNa_{03} = 0.7*y_{Na_0} + 0.3*y_{Na_{10}} = 0.89(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_03)	0.89(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_03)	0.11(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _04					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{04} = 0.6*a_{10} + 0.4*a_{10} = 5.0777(1)\text{Å}$					
		$c = c_{04} = 0.6*c_{10} + 0.4*c_{10} = 11.4274(5)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.6*z_{N_0} + 0.4*z_{N_{10}} = 0.1003(4)$					
Occupancy Parameter		$oNa_{04} = 0.6*y_{Na_0} + 0.4*y_{Na_{10}} = 0.88(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_04)	0.88(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_04)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _05					
Space Group		I - 4					
Scale		0.0000001(4)					

Lattice Parameter		$a = b = a_{05} = 0.5 \cdot a_{10} + 0.5 \cdot a_{10} = 5.0764(1) \text{ \AA}$					
		$c = c_{05} = 0.5 \cdot c_{10} + 0.5 \cdot c_{10} = 11.3989(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.5 \cdot z_{N_0} + 0.5 \cdot z_{N_{10}} = 0.1005(5)$					
Occupancy Parameter		$o_{Na05} = 0.5 \cdot y_{Na_0} + 0.5 \cdot y_{Na_{10}} = 0.87(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₅)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₅)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _06					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{06} = 0.4 \cdot a_{10} + 0.6 \cdot a_{10} = 5.0751(1) \text{ \AA}$					
		$c = c_{06} = 0.4 \cdot c_{10} + 0.6 \cdot c_{10} = 11.3703(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.4 \cdot z_{N_0} + 0.6 \cdot z_{N_{10}} = 0.1007(5)$					
Occupancy Parameter		$o_{Na06} = 0.4 \cdot y_{Na_0} + 0.6 \cdot y_{Na_{10}} = 0.85(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₆)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₆)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _07					
Space Group		I - 4					
Scale		0.0000001(3)					
Lattice Parameter		$a = b = a_{07} = 0.3 \cdot a_{10} + 0.7 \cdot a_{10} = 5.0738(2) \text{ \AA}$					
		$c = c_{07} = 0.3 \cdot c_{10} + 0.7 \cdot c_{10} = 11.3418(7) \text{ \AA}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.3 \cdot z_{N_0} + 0.7 \cdot z_{N_{10}} = 0.1008(6)$					
Occupancy Parameter		$o_{Na07} = 0.3 \cdot y_{Na_0} + 0.7 \cdot y_{Na_{10}} = 0.83(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₇)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₇)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{08} = 0.2 \cdot a_{10} + 0.8 \cdot a_{10} = 5.0726(2) \text{ \AA}$					
		$c = c_{08} = 0.2 \cdot c_{10} + 0.8 \cdot c_{10} = 11.3133(8) \text{ \AA}$					

Nitrogen Z Coordinate		$z \text{ N} = z \text{ N}_0 = 0.2 * z \text{ N}_0 + 0.8 * z \text{ N}_{10} = 0.1010(6)$					
Occupancy Parameter		$o\text{Na}08 = 0.2 * y\text{Na}_0 + 0.8 * y\text{Na}_{10} = 0.82(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_08)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_08)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_09					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{09} = 0.1 * a_{10} + 0.9 * a_{10} = 5.0713(2) \text{ \AA}$					
		$c = c_{09} = 0.1 * c_{10} + 0.9 * c_{10} = 11.2847(8) \text{ \AA}$					
Nitrogen Z Coordinate		$z \text{ N} = z \text{ N}_0 = 0.1 * z \text{ N}_0 + 0.9 * z \text{ N}_{10} = 0.1012(7)$					
Occupancy Parameter		$o\text{Na}09 = 0.1 * y\text{Na}_0 + 0.9 * y\text{Na}_{10} = 0.81(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_10					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{10} = 0.0 * a_{10} + 1.0 * a_{10} = 5.0700(2) \text{ \AA}$					
		$c = c_{10} = 0.0 * c_{10} + 1.0 * c_{10} = 11.2562(9) \text{ \AA}$					
Nitrogen Z Coordinate		$z \text{ N} = z \text{ N}_0 = 0.0 * z \text{ N}_0 + 1.0 * z \text{ N}_{10} = 0.1014(7)$					
Occupancy Parameter		$o\text{Na}10 = 0.0 * y\text{Na}_0 + 1.0 * y\text{Na}_{10} = 0.79(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_10)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_10)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH2					
Space Group		Fddd					
Scale		0.00002618(9)					
Lattice Parameter		$a = 8.95853(2) \text{ \AA}$					
		$b = 10.4344(3) \text{ \AA}$					
		$c = 8.07177(2) \text{ \AA}$					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283

Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

$$x = 0.167$$

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH2_00 – LiNH2_10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH2_00 – LiNH2_10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH2_00 – LiNH2_10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH2_00 – LiNH2_10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name		LiNH2_00					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a _{liam_00} = 1.0*aLi ₀ + 0.0*aLi ₁₀ = 5.03701(3) Å					
		c = c _{liam_00} = 1.0*cLi ₀ + 0.0*cLi ₁₀ = 10.25577(3) Å					
Occupancy Parameter		oLi00 = 1.0* yLi ₀ + 0.0*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH2_01					
Space Group		I – 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a _{liam_01} = 0.9*aLi ₀ + 0.1*aLi ₁₀ = 5.03750(2) Å					
		c = c _{liam_01} = 0.9*cLi ₀ + 0.1*cLi ₁₀ = 10.26342(5) Å					
Occupancy Parameter		oLi01 = 0.9* yLi ₀ + 0.1*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	b _{eq} = 3.0(1)

Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_02} = 0.8*aLi_{10} + 0.2*aLi_0 = 5.03800(2)\text{Å}$ $c = c_{liam_02} = 0.8*cLi_0 + 0.2*cLi_{10} = 10.27106(6)\text{Å}$					
Occupancy Parameter		$oLi02 = 0.8* yLi_0 + 0.2*yLi_{10} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_03} = 0.7*aLi_{10} + 0.3*aLi_0 = 5.03849(3)\text{Å}$ $c = c_{liam_03} = 0.7*cLi_0 + 0.3*cLi_{10} = 10.27871(8)\text{Å}$					
Occupancy Parameter		$oLi03 = 0.7* yLi_0 + 0.3*yLi_{10} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_04} = 0.6*aLi_{10} + 0.4*aLi_0 = 5.03899(3)\text{Å}$ $c = c_{liam_04} = 0.6*cLi_0 + 0.4*cLi_{10} = 10.28635(9)\text{Å}$					
Occupancy Parameter		$oLi04 = 0.6* yLi_0 + 0.4*yLi_{10} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ	0.972(7)	$b_{eq} = 3.0(1)$

					(oLi04)		
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_05} = 0.5*aLi_0 + 0.5*aLi_{10} = 5.03948(4)\text{\AA}$					
		$c = c_{liam_05} = 0.5*cLi_0 + 0.5*cLi_{10} = 10.2940(1)\text{\AA}$					
Occupancy Parameter		$oLi05 = 0.5* yLi_0 + 0.5*yLi_{10} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi05)	0.032(8)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_06} = 0.4*aLi_0 + 0.6*aLi_{10} = 5.03997(4)\text{\AA}$					
		$c = c_{liam_06} = 0.4*cLi_0 + 0.6*cLi_{10} = 10.3016(1)\text{\AA}$					
Occupancy Parameter		$oLi06 = 0.4* yLi_0 + 0.6*yLi_{10} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi06)	0.036(9)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_07} = 0.3*aLi_0 + 0.7*aLi_{10} = 5.04047(5)\text{\AA}$					
		$c = c_{liam_07} = 0.3*cLi_0 + 0.7*cLi_{10} = 10.3093(1)\text{\AA}$					
Occupancy		$oLi07 = 0.3* yLi_0 + 0.7*yLi_{10} = 0.96(1)$					

Parameter							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_08							
Space Group							
I - 4							
Scale							
0.000001(1)							
Lattice Parameter							
$a = b = a_{liam_08} = 0.2*aLi_0 + 0.8*aLi_{10} = 5.04096(5) \text{ \AA}$							
$c = c_{liam_08} = 0.2*cLi_0 + 0.8*cLi_{10} = 10.3169(2) \text{ \AA}$							
Occupancy Parameter							
$oLi08 = 0.2 * yLi_0 + 0.8 * yLi_{10} = 0.96(1)$							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_09							
Space Group							
I - 4							
Scale							
0.000001(1)							
Lattice Parameter							
$a = b = a_{liam_09} = 0.1*aLi_0 + 0.9*aLi_{10} = 5.04146(6) \text{ \AA}$							
$c = c_{liam_09} = 0.1*cLi_0 + 0.9*cLi_{10} = 10.3246(2) \text{ \AA}$							
Occupancy Parameter							
$oLi09 = 0.1 * yLi_0 + 0.9 * yLi_{10} = 0.95(1)$							
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name							
LiNH2_10							
Space Group							
I - 4							
Scale							
0.000001(1)							

Lattice Parameter		$a = b = a_{\text{Li10}} = 0.0 \cdot a_{\text{Li0}} + 1.0 \cdot a_{\text{Li10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{\text{Li10}} = 0.0 \cdot c_{\text{Li0}} + 1.0 \cdot c_{\text{Li10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li10}} = 0.0 \cdot y_{\text{Li0}} + 1.0 \cdot y_{\text{Li10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		Li2O					
Space Group		Fm3m					
Scale		0.000065(3)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{\text{eq}} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.8$

Phase Name		LiNa2(NH2)3					
Space Group		P42/m					
Scale		0.0000174(2)					
Lattice Parameter		$a = b = 6.2838(1) \text{ \AA}$					
		$c = 11.1485(2) \text{ \AA}$					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{\text{eq}} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{\text{eq}} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{\text{eq}} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{\text{eq}} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{\text{eq}} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{\text{eq}} = 2.0455$

Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_0 = 5.0828(4)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_0 = 11.5415(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{\text{N}_0} = 0.0997(2)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Lattice Parameter	$z_{\text{N}_{10}} = 0.1014(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{\text{Na}_0} = 0.938(7)$
Li3Na(NH2)4_00 – Li3Na(NH2)4_10 Occ. Parameter	$y_{\text{Na}_{10}} = 0.79(2)$

Phase Name	Li3Na(NH2)4_00
Space Group	I – 4

Scale	0.0000001(5)						
Lattice Parameter	a = b = a ₀₀ = 1.0*a ₀ + 0.0*a ₁₀ = 5.08280(4) Å						
	c = c ₀₀ = 1.0*c ₀ + 0.0*c ₁₀ = 11.5415(2) Å						
Nitrogen Z Coordinate	z _N = z _{N0} = 1.0*z _{N0} + 0.0*z _{N10} = 0.0997(2)						
Occupancy Parameter	oNa00 = 1.0* yNa ₀ + 0.0*yNa ₁₀ = 0.938(7)						
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₀)	0.983(7)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₀)	0.062(7)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name	Li ₃ Na(NH ₂) ₄ _01						
Space Group	I - 4						
Scale	0.0000008(7)						
Lattice Parameter	a = b = a ₀₁ = 0.9*a ₀ + 0.1*a ₁₀ = 5.08152(6) Å						
	c = c ₀₁ = 0.9*c ₀ + 0.1*c ₁₀ = 11.5130(3) Å						
Nitrogen Z Coordinate	z _N = z _{N0} = 0.9*z _{N0} + 0.1*z _{N10} = 0.0998(3)						
Occupancy Parameter	oNa01 = 0.9* yNa ₀ + 0.1*yNa ₁₀ = 0.923(8)						
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₁)	0.923(8)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₁)	0.077(8)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name	Li ₃ Na(NH ₂) ₄ _02						
Space Group	I - 4						
Scale	0.0000024(7)						
Lattice Parameter	a = b = a ₀₂ = 0.8*a ₁₀ + 0.2*a ₁₀ = 5.08024(7) Å						
	c = c ₀₂ = 0.8*c ₁₀ + 0.2*c ₁₀ = 11.4844(3) Å						
Nitrogen Z Coordinate	z _N = z _{N0} = 0.8*z _{N0} + 0.2*z _{N10} = 0.1000(3)						
Occupancy Parameter	oNa02 = 0.8* yNa ₀ + 0.2*yNa ₁₀ = 0.91(1)						
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₂)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₂)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name	Li ₃ Na(NH ₂) ₄ _03						
Space Group	I - 4						
Scale	0.0000001(7)						
Lattice Parameter	a = b = a ₀₃ = 0.7*a ₁₀ + 0.3*a ₁₀ = 5.07896(9) Å						

$c = c_{03} = 0.7 \cdot c_{10} + 0.3 \cdot c_{10} = 11.4559(4) \text{ \AA}$							
Nitrogen Z Coordinate		$z_{\text{N}} = z_{\text{N}_0} = 0.7 \cdot z_{\text{N}_0} + 0.3 \cdot z_{\text{N}_{10}} = 0.1002(4)$					
Occupancy Parameter		$o_{\text{Na}03} = 0.7 \cdot y_{\text{Na}_0} + 0.3 \cdot y_{\text{Na}_{10}} = 0.89(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_03)	0.89(1)	$b_{\text{eq}} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_03)	0.11(1)	$b_{\text{eq}} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{\text{eq}} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{\text{eq}} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	$b_{\text{eq}} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{\text{eq}} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{\text{eq}} 2.2484$

Phase Name		Li3Na(NH2)4_04					
Space Group		I - 4					
Scale		0.0000001(7)					
Lattice Parameter		$a = b = a_{04} = 0.6 \cdot a_{10} + 0.4 \cdot a_{10} = 5.0777(1) \text{ \AA}$					
		$c = c_{04} = 0.6 \cdot c_{10} + 0.4 \cdot c_{10} = 11.4274(5) \text{ \AA}$					
Nitrogen Z Coordinate		$z_{\text{N}} = z_{\text{N}_0} = 0.6 \cdot z_{\text{N}_0} + 0.4 \cdot z_{\text{N}_{10}} = 0.1003(4)$					
Occupancy Parameter		$o_{\text{Na}04} = 0.6 \cdot y_{\text{Na}_0} + 0.4 \cdot y_{\text{Na}_{10}} = 0.88(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_04)	0.88(1)	$b_{\text{eq}} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_04)	0.12(1)	$b_{\text{eq}} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{\text{eq}} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{\text{eq}} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	$b_{\text{eq}} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{\text{eq}} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{\text{eq}} 2.2484$

Phase Name		Li3Na(NH2)4_05					
Space Group		I - 4					
Scale		0.0000001(7)					
Lattice Parameter		$a = b = a_{05} = 0.5 \cdot a_{10} + 0.5 \cdot a_{10} = 5.0764(1) \text{ \AA}$					
		$c = c_{05} = 0.5 \cdot c_{10} + 0.5 \cdot c_{10} = 11.3989(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_{\text{N}} = z_{\text{N}_0} = 0.5 \cdot z_{\text{N}_0} + 0.5 \cdot z_{\text{N}_{10}} = 0.1005(5)$					
Occupancy Parameter		$o_{\text{Na}05} = 0.5 \cdot y_{\text{Na}_0} + 0.5 \cdot y_{\text{Na}_{10}} = 0.87(1)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_05)	0.87(1)	$b_{\text{eq}} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_05)	0.13(1)	$b_{\text{eq}} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{\text{eq}} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{\text{eq}} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	$b_{\text{eq}} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{\text{eq}} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{\text{eq}} 2.2484$

Phase Name		Li3Na(NH2)4_06					
Space Group		I - 4					
Scale		0.0000001(7)					
Lattice Parameter		$a = b = a_{06} = 0.4 \cdot a_{10} + 0.6 \cdot a_{10} = 5.0751(1) \text{ \AA}$					
		$c = c_{06} = 0.4 \cdot c_{10} + 0.6 \cdot c_{10} = 11.3703(6) \text{ \AA}$					
Nitrogen Z Coordinate		$z_{\text{N}} = z_{\text{N}_0} = 0.4 \cdot z_{\text{N}_0} + 0.6 \cdot z_{\text{N}_{10}} = 0.1007(5)$					

Occupancy Parameter			$oNa06 = 0.4 * yNa_0 + 0.6 * yNa_{10} = 0.85(1)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_06)	0.85(1)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_06)	0.15(1)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_07				
Space Group			I - 4				
Scale			0.0000001(6)				
Lattice Parameter			$a = b = a_{07} = 0.3 * a_{10} + 0.7 * a_{10} = 5.0738(2) \text{ \AA}$				
			$c = c_{07} = 0.3 * c_{10} + 0.7 * c_{10} = 11.3418(7) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.3 * z_{N_0} + 0.7 * z_{N_{10}} = 0.1008(6)$				
Occupancy Parameter			$oNa07 = 0.3 * yNa_0 + 0.7 * yNa_{10} = 0.83(2)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_07)	0.83(2)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_07)	0.17(2)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_08				
Space Group			I - 4				
Scale			0.0000001(7)				
Lattice Parameter			$a = b = a_{08} = 0.2 * a_{10} + 0.8 * a_{10} = 5.0726(2) \text{ \AA}$				
			$c = c_{08} = 0.2 * c_{10} + 0.8 * c_{10} = 11.3133(8) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.2 * z_{N_0} + 0.8 * z_{N_{10}} = 0.1010(6)$				
Occupancy Parameter			$oNa08 = 0.2 * yNa_0 + 0.8 * yNa_{10} = 0.82(2)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_08)	0.82(2)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_08)	0.18(2)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_09				
Space Group			I - 4				
Scale			0.0000001(7)				
Lattice Parameter			$a = b = a_{09} = 0.1 * a_{10} + 0.9 * a_{10} = 5.0713(2) \text{ \AA}$				
			$c = c_{09} = 0.1 * c_{10} + 0.9 * c_{10} = 11.2847(8) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.1 * z_{N_0} + 0.9 * z_{N_{10}} = 0.1012(7)$				
Occupancy Parameter			$oNa09 = 0.1 * yNa_0 + 0.9 * yNa_{10} = 0.81(2)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b_{eq} 2.2484

Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _10					
Space Group		I - 4					
Scale		0.0000001(6)					
Lattice Parameter		a = b = a ₁₀ = 0.0*a ₁₀ + 1.0*a ₁₀ = 5.0700(2) Å					
		c = c ₁₀ = 0.0*c ₁₀ + 1.0*c ₁₀ = 11.2562(9) Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.0* z _{N₀} + 1.0* z _{N₁₀} = 0.1014(7)					
Occupancy Parameter		oNa ₁₀ = 0.0* yNa ₀ + 1.0*yNa ₁₀ = 0.79(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_10)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_10)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH ₂					
Space Group		Fddd					
Scale		0.0000367(1)					
Lattice Parameter		a = 8.95853(2) Å					
		b = 10.4344(3) Å					
		c = 8.07177(2) Å					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

$$x = 0.083$$

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted Durbin Watson	7.430		
Goodness of fit	3.316		

LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name		LiNH ₂ _00					
Space Group		I - 4					
Scale		0.0000010(3)					
Lattice Parameter		a = b = a _{liam_00} = 1.0*aLi ₀ + 0.0*aLi ₁₀ = 5.03701(3) Å					
		c = c _{liam_00} = 1.0*cLi ₀ + 0.0*cLi ₁₀ = 10.25577(3) Å					
Occupancy Parameter		oLi00 = 1.0* yLi ₀ + 0.0*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH ₂ _01					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a _{liam_01} = 0.9*aLi ₀ + 0.1*aLi ₁₀ = 5.03750(2) Å					
		c = c _{liam_01} = 0.9*cLi ₀ + 0.1*cLi ₁₀ = 10.26342(5) Å					
Occupancy Parameter		oLi01 = 0.9* yLi ₀ + 0.1*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi01)	0.017(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH ₂ _02					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		a = b = a _{liam_02} = 0.8*aLi ₁₀ + 0.2*aLi ₀ = 5.03800(2) Å					
		c = c _{liam_02} = 0.8*cLi ₀ + 0.2*cLi ₁₀ = 10.27106(6) Å					
Occupancy Parameter		oLi02 = 0.8* yLi ₀ + 0.2*yLi ₁₀ = 0.979(5)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi02)	0.021(5)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)

Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_03} = 0.7*aLi_0 + 0.3*aLi_{10} = 5.03849(3) \text{ \AA}$					
		$c = c_{liam_03} = 0.7*cLi_0 + 0.3*cLi_{10} = 10.27871(8) \text{ \AA}$					
Occupancy Parameter		$oLi03 = 0.7* yLi_0 + 0.3*yLi_{10} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.025(6)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_04} = 0.6*aLi_0 + 0.4*aLi_{10} = 5.03899(3) \text{ \AA}$					
		$c = c_{liam_04} = 0.6*cLi_0 + 0.4*cLi_{10} = 10.28635(9) \text{ \AA}$					
Occupancy Parameter		$oLi04 = 0.6* yLi_0 + 0.4*yLi_{10} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_05} = 0.5*aLi_0 + 0.5*aLi_{10} = 5.03948(4) \text{ \AA}$					
		$c = c_{liam_05} = 0.5*cLi_0 + 0.5*cLi_{10} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$oLi05 = 0.5* yLi_0 + 0.5*yLi_{10} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-	0.032(8)	$b_{eq} = 3.0(1)$

					oLi05)		
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_06} = 0.4*aLi_0 + 0.6*aLi_{10} = 5.03997(4)\text{\AA}$					
		$c = c_{liam_06} = 0.4*cLi_0 + 0.6*cLi_{10} = 10.3016(1)\text{\AA}$					
Occupancy Parameter		$oLi06 = 0.4* yLi_0 + 0.6*yLi_{10} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_07} = 0.3*aLi_0 + 0.7*aLi_{10} = 5.04047(5)\text{\AA}$					
		$c = c_{liam_07} = 0.3*cLi_0 + 0.7*cLi_{10} = 10.3093(1)\text{\AA}$					
Occupancy Parameter		$oLi07 = 0.3* yLi_0 + 0.7*yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_08} = 0.2*aLi_0 + 0.8*aLi_{10} = 5.04096(5)\text{\AA}$					
		$c = c_{liam_08} = 0.2*cLi_0 + 0.8*cLi_{10} = 10.3169(2)\text{\AA}$					
Occupancy Parameter		$oLi08 = 0.2* yLi_0 + 0.8*yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$

Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_09} = 0.1 * a_{Li_0} + 0.9 * a_{Li_{10}} = 5.04146(6) \text{ \AA}$					
		$c = c_{liam_09} = 0.1 * c_{Li_0} + 0.9 * c_{Li_{10}} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$oLi09 = 0.1 * y_{Li_0} + 0.9 * y_{Li_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi09)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_10					
Space Group		I - 4					
Scale		0.0000010(3)					
Lattice Parameter		$a = b = a_{liam_10} = 0.0 * a_{Li_0} + 1.0 * a_{Li_{10}} = 5.04195(6) \text{ \AA}$					
		$c = c_{liam_10} = 0.0 * c_{Li_0} + 1.0 * c_{Li_{10}} = 10.3311(2) \text{ \AA}$					
Occupancy Parameter		$oLi10 = 0.0 * y_{Li_0} + 1.0 * y_{Li_{10}} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi10)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		Li2O					
Space Group		Fm3m					
Scale		0.000089(2)					
Lattice Parameter		$a = b = c = 4.61589(5) \text{ \AA}$					
Site	Li	0.25	0.25	0.25	occ	1	$b_{eq} = 0.9148$

Site	O	0.0	0.0	0.0	occ	1	$b_{eq} = 0.8$
------	---	-----	-----	-----	-----	---	----------------

Phase Name		LiNa ₂ (NH ₂) ₃					
Space Group		P4 ₂ /m					
Scale		0.00000113(7)					
Lattice Parameter		a = b = 6.2838(1) Å					
		c = 11.1485(2) Å					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{eq} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{eq} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{eq} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{eq} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$a_0 = 5.0828(4)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$a_{10} = 5.0700(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_0 = 11.5415(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name		Li ₃ Na(NH ₂) ₄ 00					
Space Group		I – 4					
Scale		0.0000001(3)					
Lattice Parameter		a = b = a ₀₀ = 1.0*a ₀ + 0.0*a ₁₀ = 5.08280(4) Å					
		c = c ₀₀ = 1.0*c ₀ + 0.0*c ₁₀ = 11.5415(2) Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 1.0* z _{N₀} + 0.0* z _{N₁₀} = 0.0997(2)					
Occupancy Parameter		o _{Na00} = 1.0* y _{Na₀} + 0.0*y _{Na₁₀} = 0.938(7)					
Site	Na 1	0.0	0.50	0.25	occ (o _{Na₀₀})	0.983(7)	$b_{eq} 2.2484$
Site	Li 1	0.0	0.50	0.25	occ (1-o _{Na₀₀})	0.062(7)	$b_{eq} 2.2484$
Site	Li 2	0.0	0.0	0.0	occ	1	$b_{eq} 2.2484$
Site	Li 3	0.0	0.50	0.0087	occ	1	$b_{eq} 2.2484$
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	$b_{eq} 2.2484$
Site	H 1	0.365	0.290	0.110	occ	1	$b_{eq} 2.2484$
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	$b_{eq} 2.2484$

Phase Name		Li ₃ Na(NH ₂) ₄ 01					
Space Group		I – 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₁ = 0.9*a ₀ + 0.1*a ₁₀ = 5.08152(6) Å					
		c = c ₀₁ = 0.9*c ₀ + 0.1*c ₁₀ = 11.5130(3) Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.9* z _{N₀} + 0.1* z _{N₁₀} = 0.0998(3)					

Occupancy Parameter			$oNa01 = 0.9 * yNa_0 + 0.1 * yNa_{10} = 0.923(8)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_01)	0.923(8)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_01)	0.077(8)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_02				
Space Group			I - 4				
Scale			0.0000001(4)				
Lattice Parameter			$a = b = a_{02} = 0.8 * a_{10} + 0.2 * a_{10} = 5.08024(7) \text{ \AA}$				
			$c = c_{02} = 0.8 * c_{10} + 0.2 * c_{10} = 11.4844(3) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.8 * z_{N_0} + 0.2 * z_{N_{10}} = 0.1000(3)$				
Occupancy Parameter			$oNa02 = 0.8 * yNa_0 + 0.2 * yNa_{10} = 0.91(1)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_02)	0.91(1)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_02)	0.09(1)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_03				
Space Group			I - 4				
Scale			0.0000001(4)				
Lattice Parameter			$a = b = a_{03} = 0.7 * a_{10} + 0.3 * a_{10} = 5.07896(9) \text{ \AA}$				
			$c = c_{03} = 0.7 * c_{10} + 0.3 * c_{10} = 11.4559(4) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.7 * z_{N_0} + 0.3 * z_{N_{10}} = 0.1002(4)$				
Occupancy Parameter			$oNa03 = 0.7 * yNa_0 + 0.3 * yNa_{10} = 0.89(1)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_03)	0.89(1)	b_{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_03)	0.11(1)	b_{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b_{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b_{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b_{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b_{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b_{eq} 2.2484

Phase Name			Li3Na(NH2)4_04				
Space Group			I - 4				
Scale			0.0000001(4)				
Lattice Parameter			$a = b = a_{04} = 0.6 * a_{10} + 0.4 * a_{10} = 5.0777(1) \text{ \AA}$				
			$c = c_{04} = 0.6 * c_{10} + 0.4 * c_{10} = 11.4274(5) \text{ \AA}$				
Nitrogen Z Coordinate			$z_N = z_{N_0} = 0.6 * z_{N_0} + 0.4 * z_{N_{10}} = 0.1003(4)$				
Occupancy Parameter			$oNa04 = 0.6 * yNa_0 + 0.4 * yNa_{10} = 0.88(1)$				
Site	Na 1	0.0	0.50	0.25	occ (oNa_04)	0.88(1)	b_{eq} 2.2484

Site	Li 1	0.0	0.50	0.25	occ (1-oNa_04)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_05					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a_05 = 0.5*a ₁₀ + 0.5*a ₁₀ = 5.0764(1)Å					
		c = c_05 = 0.5*c ₁₀ + 0.5*c ₁₀ = 11.3989(6)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.5* z N ₀ + 0.5* z N ₁₀ = 0.1005(5)					
Occupancy Parameter		oNa05 = 0.5* yNa ₀ + 0.5*yNa ₁₀ = 0.87(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_05)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_05)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_06					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a_06 = 0.4*a ₁₀ + 0.6*a ₁₀ = 5.0751(1)Å					
		c = c_06 = 0.4*c ₁₀ + 0.6*c ₁₀ = 11.3703(6)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.4* z N ₀ + 0.6* z N ₁₀ = 0.1007(5)					
Occupancy Parameter		oNa06 = 0.4* yNa ₀ + 0.6*yNa ₁₀ = 0.85(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_06)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_06)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_07					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a_07 = 0.3*a ₁₀ + 0.7*a ₁₀ = 5.0738(2)Å					
		c = c_07 = 0.3*c ₁₀ + 0.7*c ₁₀ = 11.3418(7)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.3* z N ₀ + 0.7* z N ₁₀ = 0.1008(6)					
Occupancy Parameter		oNa07 = 0.3* yNa ₀ + 0.7*yNa ₁₀ = 0.83(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa_07)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_07)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484

Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₈ = 0.2*a ₁₀ + 0.8*a ₁₀ = 5.0726(2)Å					
		c = c ₀₈ = 0.2*c ₁₀ + 0.8*c ₁₀ = 11.3133(8)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.2* z N ₀ + 0.8* z N ₁₀ = 0.1010(6)					
Occupancy Parameter		oNa08 = 0.2* yNa ₀ + 0.8*yNa ₁₀ = 0.82(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₈)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₈)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _09					
Space Group		I - 4					
Scale		0.0000001(5)					
Lattice Parameter		a = b = a ₀₉ = 0.1*a ₁₀ + 0.9*a ₁₀ = 5.0713(2)Å					
		c = c ₀₉ = 0.1*c ₁₀ + 0.9*c ₁₀ = 11.2847(8)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.1* z N ₀ + 0.9* z N ₁₀ = 0.1012(7)					
Occupancy Parameter		oNa09 = 0.1* yNa ₀ + 0.9*yNa ₁₀ = 0.81(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₉)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₉)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _10					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₁₀ = 0.0*a ₁₀ + 1.0*a ₁₀ = 5.0700(2)Å					
		c = c ₁₀ = 0.0*c ₁₀ + 1.0*c ₁₀ = 11.2562(9)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.0* z N ₀ + 1.0* z N ₁₀ = 0.1014(7)					
Occupancy Parameter		oNa10 = 0.0* yNa ₀ + 1.0*yNa ₁₀ = 0.79(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₁₀)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₁₀)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484

Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH ₂					
Space Group		Fddd					
Scale		0.0000592(1)					
Lattice Parameter		a = 8.95853(2) Å					
		b = 10.4344(3) Å					
		c = 8.07177(2) Å					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556

x = 0.0

R _{expected}	4.521	R _{expected} '	9.452
R _{weighted pattern}	14.989	R _{weighted pattern} '	31.342
R _{Pattern}	9.839	R _{Pattern} '	28.861
Weighted_Durbin_Watson	7.430		
Goodness of fit	3.316		

LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₀ = 5.03701(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	aLi ₁₀ = 5.04195(6) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₀ = 10.25577(3) Å
LiNH₂_00 – LiNH₂_10 Lattice Parameter	cLi ₁₀ = 10.3311(2) Å
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₀ = 0.987(3)
LiNH₂_00 – LiNH₂_10 Occ. Parameter	yLi ₁₀ = 0.95(1)

Phase Name		LiNH ₂ _00					
Space Group		I – 4					
Scale		0.0000010(3)					
Lattice Parameter		a = b = a _{liam_00} = 1.0*aLi ₀ + 0.0*aLi ₁₀ = 5.03701(3) Å					
		c = c _{liam_00} = 1.0*cLi ₀ + 0.0*cLi ₁₀ = 10.25577(3) Å					
Occupancy Parameter		oLi00 = 1.0* yLi ₀ + 0.0*yLi ₁₀ = 0.987(3)					
Site	Li 1	0.0	0.0	0.0	occ	1	b _{eq} = 0.95(1)
Site	Li 2	0.0	0.5	-0.25	occ (oLi00)	0.987(3)	b _{eq} = 3.0(1)
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi00)	0.013(3)	b _{eq} = 3.0(1)
Site	Li 3	0.0	0.5	0.00620	occ	1	b _{eq} = 0.95(1)
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	b _{eq} = 0.95(1)
Site	H 1	-0.226	-0.149	-0.172	occ	1	b _{eq} = 0.95(1)
Site	H 2	-0.308	-0.359	-0.114	occ	1	b _{eq} = 0.95(1)

Phase Name		LiNH ₂ _01					
Space Group		I – 4					

Scale		0.0000010(5)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.9 \cdot a_{\text{Li}_0} + 0.1 \cdot a_{\text{Li}_{10}} = 5.03750(2) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.9 \cdot c_{\text{Li}_0} + 0.1 \cdot c_{\text{Li}_{10}} = 10.26342(5) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li01}} = 0.9 \cdot y_{\text{Li}_0} + 0.1 \cdot y_{\text{Li}_{10}} = 0.987(3)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi01)	0.987(3)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi01)	0.017(3)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_02					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.8 \cdot a_{\text{Li}_0} + 0.2 \cdot a_{\text{Li}_{10}} = 5.03800(2) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.8 \cdot c_{\text{Li}_0} + 0.2 \cdot c_{\text{Li}_{10}} = 10.27106(6) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li02}} = 0.8 \cdot y_{\text{Li}_0} + 0.2 \cdot y_{\text{Li}_{10}} = 0.979(5)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi02)	0.979(5)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi02)	0.021(5)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_03					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{LiNH}_2} = 0.7 \cdot a_{\text{Li}_0} + 0.3 \cdot a_{\text{Li}_{10}} = 5.03849(3) \text{ \AA}$					
		$c = c_{\text{LiNH}_2} = 0.7 \cdot c_{\text{Li}_0} + 0.3 \cdot c_{\text{Li}_{10}} = 10.27871(8) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li03}} = 0.7 \cdot y_{\text{Li}_0} + 0.3 \cdot y_{\text{Li}_{10}} = 0.975(6)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.975(6)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi07)	0.025(6)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_04					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam_04}} = 0.6 * a_{\text{Li}_0} + 0.4 * a_{\text{Li}_{10}} = 5.03899(3) \text{ \AA}$					
		$c = c_{\text{liam_04}} = 0.6 * c_{\text{Li}_0} + 0.4 * c_{\text{Li}_{10}} = 10.28635(9) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li04}} = 0.6 * y_{\text{Li}_0} + 0.4 * y_{\text{Li}_{10}} = 0.972(7)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi04)	0.972(7)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi04)	0.028(7)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_05					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam_05}} = 0.5 * a_{\text{Li}_0} + 0.5 * a_{\text{Li}_{10}} = 5.03948(4) \text{ \AA}$					
		$c = c_{\text{liam_05}} = 0.5 * c_{\text{Li}_0} + 0.5 * c_{\text{Li}_{10}} = 10.2940(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li05}} = 0.5 * y_{\text{Li}_0} + 0.5 * y_{\text{Li}_{10}} = 0.968(8)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi05)	0.968(8)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi05)	0.032(8)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{\text{eq}} = 0.95(1)$

Phase Name		LiNH2_06					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{\text{liam_06}} = 0.4 * a_{\text{Li}_0} + 0.6 * a_{\text{Li}_{10}} = 5.03997(4) \text{ \AA}$					
		$c = c_{\text{liam_06}} = 0.4 * c_{\text{Li}_0} + 0.6 * c_{\text{Li}_{10}} = 10.3016(1) \text{ \AA}$					
Occupancy Parameter		$o_{\text{Li06}} = 0.4 * y_{\text{Li}_0} + 0.6 * y_{\text{Li}_{10}} = 0.964(9)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{\text{eq}} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi06)	0.964(9)	$b_{\text{eq}} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi06)	0.036(9)	$b_{\text{eq}} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{\text{eq}} = 0.95(1)$

Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_07					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_07} = 0.3*aLi_0 + 0.7*aLi_{10} = 5.04047(5) \text{ \AA}$					
		$c = c_{liam_07} = 0.3*cLi_0 + 0.7*cLi_{10} = 10.3093(1) \text{ \AA}$					
Occupancy Parameter		$oLi07 = 0.3* yLi_0 + 0.7*yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi07)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi07)	0.040(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_08					
Space Group		I - 4					
Scale		0.000001(1)					
Lattice Parameter		$a = b = a_{liam_08} = 0.2*aLi_0 + 0.8*aLi_{10} = 5.04096(5) \text{ \AA}$					
		$c = c_{liam_08} = 0.2*cLi_0 + 0.8*cLi_{10} = 10.3169(2) \text{ \AA}$					
Occupancy Parameter		$oLi08 = 0.2* yLi_0 + 0.8*yLi_{10} = 0.96(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi08)	0.96(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1- oLi08)	0.04(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH2_09					
Space Group		I - 4					
Scale		0.0000010(5)					
Lattice Parameter		$a = b = a_{liam_09} = 0.1*aLi_0 + 0.9*aLi_{10} = 5.04146(6) \text{ \AA}$					
		$c = c_{liam_09} = 0.1*cLi_0 + 0.9*cLi_{10} = 10.3246(2) \text{ \AA}$					
Occupancy Parameter		$oLi09 = 0.1* yLi_0 + 0.9*yLi_{10} = 0.95(1)$					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi09)	0.95(1)	$b_{eq} = 3.0(1)$

Site	Na 2	0.0	0.5	-0.25	occ (1-oLi09)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		LiNH ₂ _10					
Space Group		I - 4					
Scale		0.0000010(3)					
Lattice Parameter		a = b = a _{liam_10} = 0.0*aLi ₀ + 1.0*aLi ₁₀ = 5.04195(6)Å					
		c = c _{liam_10} = 0.0*cLi ₀ + 1.0*cLi ₁₀ = 10.3311(2)Å					
Occupancy Parameter		oLi10 = 0.0* yLi ₀ + 1.0*yLi ₁₀ = 0.95(1)					
Site	Li 1	0.0	0.0	0.0	occ	1	$b_{eq} = 0.95(1)$
Site	Li 2	0.0	0.5	-0.25	occ (oLi10)	0.95(1)	$b_{eq} = 3.0(1)$
Site	Na 2	0.0	0.5	-0.25	occ (1-oLi10)	0.05(1)	$b_{eq} = 3.0(1)$
Site	Li 3	0.0	0.5	0.00620	occ	1	$b_{eq} = 0.95(1)$
Site	N	-0.2303(1)	-0.2407(3)	-0.11436(4)	occ	1	$b_{eq} = 0.95(1)$
Site	H 1	-0.226	-0.149	-0.172	occ	1	$b_{eq} = 0.95(1)$
Site	H 2	-0.308	-0.359	-0.114	occ	1	$b_{eq} = 0.95(1)$

Phase Name		Li ₂ O					
Space Group		Fm3m					
Scale		0.000000(1)					
Lattice Parameter		a = b = c = 4.61589(5) Å					
Site	Li	0.25	0.25	0.25	occ	1	$b_{eq} = 0.9148$
Site	O	0.0	0.0	0.0	occ	1	$b_{eq} = 0.8$

Phase Name		LiNa ₂ (NH ₂) ₃					
Space Group		P4 ₂ /m					
Scale		0.00000019(6)					
Lattice Parameter		a = b = 6.2838(1)Å					
		c = 11.1485(2)Å					
Site	N 1	0.66317	0.27595	0.0	occ	1	$b_{eq} = 1.5810$
Site	H 1	0.73697	0.29827	0.056	occ	1	$b_{eq} = 1.5810$
Site	N 2	0.20732	0.27336	0.15765	occ	1	$b_{eq} = 1.5810$
Site	H 2	0.16362	0.18116	0.21186	occ	1	$b_{eq} = 1.5810$
Site	H 3	0.10362	0.32316	0.14126	occ	1	$b_{eq} = 1.5810$
Site	Na 1	0.50	0.0	0.14216	occ	1	$b_{eq} = 2.2740$
Site	Na 2	0.0	0.0	0.0	occ	1	$b_{eq} = 2.2740$
Site	Na 3	0.50	0.50	0.25	occ	1	$b_{eq} = 2.2740$
Site	Li 1	0.35356	0.36094	0.0	occ	1	$b_{eq} = 2.0455$

Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	$a_0 = 5.0828(4)$
Li₃Na(NH₂)₄_00 – Li₃Na(NH₂)₄_10 Lattice Parameter	$a_{10} = 5.0700(2)$

Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_0 = 11.5415(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$c_{10} = 11.2562(9)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$z_{N_0} = 0.0997(2)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Lattice Parameter	$z_{N_{10}} = 0.1014(7)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Occ. Parameter	$y_{Na_0} = 0.938(7)$
Li₃Na(NH₂)₄ 00 – Li₃Na(NH₂)₄ 10 Occ. Parameter	$y_{Na_{10}} = 0.79(2)$

Phase Name	Li ₃ Na(NH ₂) ₄ 00						
Space Group	I – 4						
Scale	0.0000001(3)						
Lattice Parameter	$a = b = a_{00} = 1.0*a_0 + 0.0*a_{10} = 5.08280(4)\text{Å}$						
	$c = c_{00} = 1.0*c_0 + 0.0*c_{10} = 11.5415(2)\text{Å}$						
Nitrogen Z Coordinate	$z_N = z_{N_0} = 1.0*z_{N_0} + 0.0*z_{N_{10}} = 0.0997(2)$						
Occupancy Parameter	$o_{Na00} = 1.0*y_{Na_0} + 0.0*y_{Na_{10}} = 0.938(7)$						
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₀)	0.983(7)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₀)	0.062(7)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0997(2)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name	Li ₃ Na(NH ₂) ₄ 01						
Space Group	I – 4						
Scale	0.0000001(4)						
Lattice Parameter	$a = b = a_{01} = 0.9*a_0 + 0.1*a_{10} = 5.08152(6)\text{Å}$						
	$c = c_{01} = 0.9*c_0 + 0.1*c_{10} = 11.5130(3)\text{Å}$						
Nitrogen Z Coordinate	$z_N = z_{N_0} = 0.9*z_{N_0} + 0.1*z_{N_{10}} = 0.0998(3)$						
Occupancy Parameter	$o_{Na01} = 0.9*y_{Na_0} + 0.1*y_{Na_{10}} = 0.923(8)$						
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₁)	0.923(8)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₁)	0.077(8)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.0998(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name	Li ₃ Na(NH ₂) ₄ 02						
Space Group	I – 4						
Scale	0.0000001(4)						
Lattice Parameter	$a = b = a_{02} = 0.8*a_{10} + 0.2*a_{10} = 5.08024(7)\text{Å}$						
	$c = c_{02} = 0.8*c_{10} + 0.2*c_{10} = 11.4844(3)\text{Å}$						
Nitrogen Z Coordinate	$z_N = z_{N_0} = 0.8*z_{N_0} + 0.2*z_{N_{10}} = 0.1000(3)$						
Occupancy Parameter	$o_{Na02} = 0.8*y_{Na_0} + 0.2*y_{Na_{10}} = 0.91(1)$						
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₂)	0.91(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₂)	0.09(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484

Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1000(3)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _03					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₃ = 0.7*a ₁₀ + 0.3*a ₁₀ = 5.07896(9) Å					
		c = c ₀₃ = 0.7*c ₁₀ + 0.3*c ₁₀ = 11.4559(4) Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.7* z N ₀ + 0.3* z N ₁₀ = 0.1002(4)					
Occupancy Parameter		oNa03 = 0.7* yNa ₀ + 0.3*yNa ₁₀ = 0.89(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₃)	0.89(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₃)	0.11(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1002(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _04					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₄ = 0.6*a ₁₀ + 0.4*a ₁₀ = 5.0777(1)Å					
		c = c ₀₄ = 0.6*c ₁₀ + 0.4*c ₁₀ = 11.4274(5)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.6* z N ₀ + 0.4* z N ₁₀ = 0.1003(4)					
Occupancy Parameter		oNa04 = 0.6* yNa ₀ + 0.4*yNa ₁₀ = 0.88(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₄)	0.88(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₄)	0.12(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1003(4)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _05					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₅ = 0.5*a ₁₀ + 0.5*a ₁₀ = 5.0764(1)Å					
		c = c ₀₅ = 0.5*c ₁₀ + 0.5*c ₁₀ = 11.3989(6)Å					
Nitrogen Z Coordinate		z N = z N ₀ = 0.5* z N ₀ + 0.5* z N ₁₀ = 0.1005(5)					
Occupancy Parameter		oNa05 = 0.5* yNa ₀ + 0.5*yNa ₁₀ = 0.87(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₅)	0.87(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₅)	0.13(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1005(5)	occ	1	b _{eq} 2.2484

Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _06					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₆ = 0.4*a ₁₀ + 0.6*a ₁₀ = 5.0751(1)Å					
		c = c ₀₆ = 0.4*c ₁₀ + 0.6*c ₁₀ = 11.3703(6)Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.4* z _{N₀} + 0.6* z _{N₁₀} = 0.1007(5)					
Occupancy Parameter		oNa06 = 0.4* yNa ₀ + 0.6*yNa ₁₀ = 0.85(1)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₆)	0.85(1)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₆)	0.15(1)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1007(5)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _07					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₇ = 0.3*a ₁₀ + 0.7*a ₁₀ = 5.0738(2)Å					
		c = c ₀₇ = 0.3*c ₁₀ + 0.7*c ₁₀ = 11.3418(7)Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.3* z _{N₀} + 0.7* z _{N₁₀} = 0.1008(6)					
Occupancy Parameter		oNa07 = 0.3* yNa ₀ + 0.7*yNa ₁₀ = 0.83(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₇)	0.83(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₇)	0.17(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1008(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li ₃ Na(NH ₂) ₄ _08					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		a = b = a ₀₈ = 0.2*a ₁₀ + 0.8*a ₁₀ = 5.0726(2)Å					
		c = c ₀₈ = 0.2*c ₁₀ + 0.8*c ₁₀ = 11.3133(8)Å					
Nitrogen Z Coordinate		z _N = z _{N₀} = 0.2* z _{N₀} + 0.8* z _{N₁₀} = 0.1010(6)					
Occupancy Parameter		oNa08 = 0.2* yNa ₀ + 0.8*yNa ₁₀ = 0.82(2)					
Site	Na 1	0.0	0.50	0.25	occ (oNa ₀₈)	0.82(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa ₀₈)	0.18(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1010(6)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_09					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{09} = 0.1*a_{10} + 0.9*a_{10} = 5.0713(2)\text{Å}$					
		$c = c_{09} = 0.1*c_{10} + 0.9*c_{10} = 11.2847(8)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.1*z_{N_0} + 0.9*z_{N_{10}} = 0.1012(7)$					
Occupancy Parameter		$oNa_{09} = 0.1*yNa_0 + 0.9*yNa_{10} = 0.81(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_09)	0.81(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_09)	0.19(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1012(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		Li3Na(NH2)4_10					
Space Group		I - 4					
Scale		0.0000001(4)					
Lattice Parameter		$a = b = a_{10} = 0.0*a_{10} + 1.0*a_{10} = 5.0700(2)\text{Å}$					
		$c = c_{10} = 0.0*c_{10} + 1.0*c_{10} = 11.2562(9)\text{Å}$					
Nitrogen Z Coordinate		$z_N = z_{N_0} = 0.0*z_{N_0} + 1.0*z_{N_{10}} = 0.1014(7)$					
Occupancy Parameter		$oNa_{10} = 0.0*yNa_0 + 1.0*yNa_{10} = 0.79(2)$					
Site	Na 1	0.0	0.50	0.25	occ (oNa_10)	0.79(2)	b _{eq} 2.2484
Site	Li 1	0.0	0.50	0.25	occ (1-oNa_10)	0.21(2)	b _{eq} 2.2484
Site	Li 2	0.0	0.0	0.0	occ	1	b _{eq} 2.2484
Site	Li 3	0.0	0.50	0.0087	occ	1	b _{eq} 2.2484
Site	N	0.2390(7)	0.2390(9)	0.1014(7)	occ	1	b _{eq} 2.2484
Site	H 1	0.365	0.290	0.110	occ	1	b _{eq} 2.2484
Site	H 2	0.233	0.139(6)	0.168(3)	occ	1	b _{eq} 2.2484

Phase Name		NaNH2					
Space Group		Fddd					
Scale		0.0000482(1)					
Lattice Parameter		$a = 8.95853(2)\text{Å}$					
		$b = 10.4344(3)\text{Å}$					
		$c = 8.07177(2)\text{Å}$					
Site	Na 1	0.0	0.14841	0.0	occ	1	b _{eq} 2.6283
Site	N	0.0	0.0	0.23425	occ	1	b _{eq} 3.2183
Site	H 1	0.05938	0.95625	0.29968	occ	1	b _{eq} 2.7556