

Supporting information

Synthesis of Highly Aligned and Ultralong Coordination Polymer Nanowires and Their Calcination to Porous Manganese Oxide Nanostructures

Cheng Chao Li,^{ab} Lin Mei,^a Li Bao Chen,^a Qiu hong Li,^{*a} and Tai Hong Wang^{*a}

^a Key Laboratory for Micro-Nano Optoelectronic Devices of Ministry of Education and State Key Laboratory of Chemo/Biosensing and Chemometrics, Hunan University, Changsha, 410082, P. R. China

E-mail: liqiu hong@hnu.cn; thwang@hnu.cn (T. H. Wang)

^b Department of Chemical and Biomolecular Engineering, National University of Singapore, 10 Kent Ridge Crescent, Singapore, 119260




Figure S1. FESEM images of Mn-based coordination polymer nanostructures synthesized by MnCl_2 at ratio of 1:3 between water and IPA (v/v).

Precursor salts	Mn%	C%	H%	N%	S%	Cl%
Chloride	29.9	25.5	2.7	3.2	0	0.3
Acetate	30.6	23.8	2.9	2.6	0	0
Sulfate	31.8	24.0	2.7	3.4	0.4	0
Nitrate	31.0	23.1	2.6	2.8	0	0

Table S1. Elemental analysis of the coordination polymer nanostructures prepared by different precursor salts.