Non symmetric superparamagnetic clusters in the relaxor manganites $Sr_{2-x}Bi_xMnTiO_6$ (0≤x≤0.75)

Inmaculada Álvarez-Serrano,^{a,*} M. Luisa López, ^a Fausto Rubio,^b Mar García-Hernández,^c Gabriel J. Cuello,^d Carlos Pico^a and M.Luisa Veiga^a

Supporting information

| Table S1 Obtained | parameters from | deconvolution | of Raman | spectra at 98K |
|---------------------|-----------------|---------------|-----------|----------------|
| Table JL. Obtailled | parameters nom | acconvolution | oritanian | |

| 98K | x=0.25 | | | | x=0.50 | | | | Bi75 | | | |
|-------|---------------|-------------|--------------|-----------|---------------|-------------|--------------|-----------|---------------|-------------|--------------|-----------|
| BANDS | Intensity (a. | width (cm-1 | Shift (cm-1) | Norm_Area | Intensity (a. | width (cm-1 | Shift (cm-1) | Norm_Area | Intensity (a. | width (cm-1 | Shift (cm-1) | Norm_Area |
| 1 | 352,67 | 76,31 | 1136,43 | 0,027 | 256,15 | 81,11 | 1125,25 | 0,017 | 522,49 | 70,52 | 1133,89 | 0,027 |
| 2 | 790,33 | 87,48 | 1065,65 | 0,07 | 465,12 | 79,34 | 1061,35 | 0,03 | 1192,26 | 89,27 | 1064,72 | 0,078 |
| 3 | 1331,85 | 79,28 | 971,99 | 0,107 | 812,01 | . 76,81 | 973,02 | 0,051 | 1746,91 | 75,72 | 975,48 | 0,097 |
| 4 | 1660,51 | 65,15 | 913,51 | 0,11 | 1283,02 | 70,42 | 913,38 | 0,074 | 2788,95 | 73,36 | 913,94 | 0,15 |
| 5 | 950,57 | 85,21 | 845,11 | 0,082 | 950,67 | 79,49 | 840,01 | 0,062 | 978,38 | 78,89 | 837,64 | 0,057 |
| 6 | 1728,22 | 70,43 | 774,49 | 0,123 | 2550 | 81,82 | 762,92 | 0,171 | 1043,15 | 92,33 | 778,48 | 0,071 |
| 7 | 630,5 | 63,47 | 700,1 | 0,041 | 1147,1 | 79,4 | 697,45 | 0,074 | 722,39 | 63,27 | 693,05 | 0,034 |
| 8 | 982,88 | 36,88 | 638,8 | 0,037 | 2250, 19 | 49,62 | 630,25 | 0,091 | 890,41 | 60,76 | 633,59 | 0,04 |
| 9 | 1027,7 | 93,66 | 556,48 | 0,098 | 1700,96 | 88,1 | 552,5 | 0,122 | 1418,51 | 91,35 | 548,86 | 0,095 |
| 10 | 1161,13 | 69,44 | 488,87 | 0,082 | 1458,77 | 67,97 | 491,93 | 0,081 | 2011,58 | 73,72 | 488,65 | 0,109 |
| 11 | 975,28 | 40,42 | 443,84 | 0,04 | 2466,52 | 44,77 | 439,39 | 0,09 | 1230,63 | 67,57 | 436,83 | 0,061 |
| 12 | 371,77 | 43,48 | 395,8 | 0,016 | 785,72 | 45,06 | 384,54 | 0,029 | 575,12 | 67,36 | 385,68 | 0,028 |
| 13 | 938,17 | 175,5 | 362,89 | 0,167 | 833,82 | 157,65 | 329,39 | 0,107 | 1306,39 | 158,03 | 334,06 | 0,152 |

Table S2. Raman bands for $Sr_{1.50}Bi_{0.50}MnTiO_6$ at 98 K and previous assignments

| Band | Bi50_98K shift (cm-1) | I (%) | Assignment | |
|------|--------------------------|-------|---|--|
| 1 | 1125,25 | 10,0 | - | |
| 2 | 1061,35 | 18,2 | - | |
| 3 | 973,02 | 31,8 | A_{1a} symmetric breathing (stretching) of MO ₆ octahedra | |
| 4 | 913,38 | 50,3 | | |
| 5 | 840,01 | 37,3 | A _{1g} ordering of B-cations (1:1) | |
| 6 | 762,92 | 100 | A_{1g} symmetric breathing (stretching) of M(IV)O ₆ octahedra | |
| 7 | 697,45 | 45 | | |
| 8 | 630,25 | 88,2 | B _{1g} breathing Mn ³⁺ J-T effect, CO/OO phenomena | |
| 9 | 552,5 | 66,7 | E_{g} asymmetric breathing (antistretching) of MO_6 octahedra | |
| 10 | 491,93 | 57,2 | F_{2g} ordering of B-cations (1:1) ; B_{1g} breathing Mn ³⁺ J-T effect | |
| 11 | 439,39 | 96,7 | F _{2g} bending of octahedra oxygen atoms | |
| 12 | 384,54 | 30,8 | B _{1g} A-cations displacement ; B-sites ordered nanodomains | |
| 13 | 329,39 | 32,7 | F_{2q} , B_{1q} A-cations displacement | |