

Supporting Information

Thermolysis of 2.

The tungsten complex **2** (300mg) was dissolved in trioctylphosphine and heated to 250°C for 18h. After cooling, a solid was precipitated by addition of methanol, collected via centrifugation and redispersed in toluene. The TEM image shows ca. 17nm sized particles.

