Supporting information

Erasable thin-film optical diode based on a photoresponsive liquid crystal polymer

Xinping Zhang,*a Jian Zhang, Yujian Sun, bc Huai Yang,*d and Haifeng Yu*d

The DSC measurements on the LCP is shown in Fig. S1, which shows a glass-transition temperature of about 82 $^{\circ}$ C and a clearing point at about 139 $^{\circ}$ C.




Fig. S1 The DSC measurements on the LCP.

^aInstitute of Information Photonics Technology and College of Applied Sciences, Beijing University of Technology, Beijing 100124, P. R. China

^bAnshan Normal University, Anshan 114005, Liaoning, China

^cSchool of Materials Science and Engineering, University of Science and Technology Beijing, Beijing 10083, China

^dDepartment of Materials Science and Engineering, College of Engineering, Peking University, Beijing 100871, P. R. China

^{*}Emails: zhangxinping@bjut.edu.cn, yanghuai@coe.pku.edu.cn, yuhaifeng@pku.edu.cn