



Fig. S1. The  $J$ - $V$  curves for the DSSCs comprising TiO<sub>2</sub> IO electrode with and without graphene underlayer on the FTO substrate. The addition of graphene arranged under the IO structure decreased the  $J_{SC}$  by half. This may be attributed to an increase of electron recombination and a decrease of the light harvesting by the graphene layer.