



GPC Sample Results

	Retention Time	Mn	Mw	MP	Mz	Poly-dispersity
1	10.092	47920	80161	27464	124675	1.673