

Supporting information

One-step fabrication of 3D hierarchical Ni-incorporated β -Co(OH)₂ assembled by 2D center disk and 1D length-tunable brush

Hongyi Gao^a, Ge Wang^{*a}, Mu Yang^a, Zhan Shi^b, Chunguang Li^b, Xinxin Zhang^c, Xin Cui^c

^aSchool of Materials Science and Engineering, University of Science and Technology Beijing, Beijing 100083, China

E-mail: gewang@mater.ustb.edu.cn

^bState Key Laboratory of Inorganic Synthesis and Preparative Chemistry, College of Chemistry, Jilin University, Changchun 130012, China

^cSchool of Mechanical Engineering, University of Science and Technology Beijing, Beijing 100083, China

Table S1 The mean nanorod length and mean disk diameter of samples with different R.

Samples with different R	Nanorod length (nm)	Disk diameter (nm)
R=3	174	1888
R=2	419	1873
R=1	1130	2137
R=1/2	1481	3274




Fig. S1 SEM photographs of the as-synthesized products with double-faced brush structure prepared for selected R. (a) R=1/3, (b) R=0.