Supporting Information

Benzo[1,2-b:4,5-b']difuran-based sensitizers for dye-sensitized solar cells

Hui Li, Chenyi Yi, Sofiane Moussi, Shi-Xia Liu,* Claude Daul, Michael Grätzel,* and Silvio Decurtins

Experimental

Materials and equipment

The compounds I^1 , $III^{2,3}$ and IV^3 were prepared according to the literature procedures. All other chemicals and solvents were purchased from commercial sources and used without further purification. All ¹H NMR and ¹³C NMR spectra were measured at 300 and 75.5 MHz, respectively. Chemical shifts (δ) were calibrated against residual solvent signals. UV-vis absorption and emission spectra were recorded on a Perkin-Elmer Lambda 900 spectrometer and a Perkin-Elmer Spectrophotometer LS50B. Melting points were performed and not corrected. HRMS data was obtained with ESI (electrospray ionization) mode. Powder X-ray diffraction (PXRD) patterns were recorded on a STOE spellmann generator type DF4 with a Cu anode.

2.2. Synthesis of compound II

A mixture of 4-bromobenzaldehyde (54 mg, 0.29 mmol), $Pd(PPh_3)_2Cl_2$ (10 mg, 0.015 mmol), CuI (3 mg, 0.015 mmol) in Et₃N (20 mL) was purged with Argon for 20 min. To this mixture was dropwise added a solution of compound I (103 mg, 0.15 mmol) in THF (15 mL) under reflux. The resulting solution was refluxed for 3 h. After removing the solvents, the residue was poured into a silica gel column, eluting with gradients of *n*-hexane/CH₂Cl₂ (from 1:1 to 1:8) to obtain II as a red solid (87 mg, 74%): mp 131.5°C-131.6°C; ¹H-NMR (300 MHz, CDCl₃): $\delta = 10.02$ (s, 1 H), 7.86 (m, 4 H), 7.68 (m, 2 H), 7.35 (m, 3 H), 3.65 (t, J = 7.59 Hz, 8H), 1.79 (m, 8H), 1.36 (m, 24H), 0.89 (t, J = 7.02 Hz, 12H); ¹³C-NMR (75.5 MHz, CDCl₃): $\delta = 191.4$, 163.2, 163.1, 145.2, 145.0, 135.5, 131.9, 131.6, 129.6, 129.4, 128.7, 128.4, 123.6, 123.2, 123.0, 116.5, 116.3, 100.3, 98.6, 96.9, 95.0, 84.0, 79.7, 62.6, 62.5, 50.4, 50.3, 31.5, 29.7, 28.6, 26.2, 22.6, 13.9; HRMS (ESI) *m/z*: [M]⁺ calcd for C₅₃H₆₂N₄O₃ 802.4816; found 802.4817.

2.3. Synthesis of Dye-1

A mixture of compound II (80 mg, 0.10 mmol) and cyanoacetic acid (85 mg, 1.0 mmol), ammonium acetate (23 mg, 0.3 mmol), and glacial acetic acid (20 mL) was purged with Argon for 15 min, and then stirred at 135°C for 24 h. After cooling to room temperature, the mixture was poured into ice water and the resulting precipitate was filtered off, washed with water several times and dried under vacuum. A red solid was obtained (57 mg, 66%): mp 248.6°C-248.7 °C; ¹H-NMR (400 MHz, DMSO-*d*₆, 80°C): $\delta = 8.36$ (s, 1 H), 8.11 (d, J = 8.34 Hz, 2 H), 7.67 (d, J = 8.34 Hz, 2 H); 7.59 (m, 2 H), 7.47 (m, 3 H); ¹³C-NMR (100 MHz, DMSO-*d*₆, 80°C): $\delta = 162.6$, 130.9, 130.6, 128.1, 114.8, 61.2, 49.5, 30.4, 27.5, 25.1, 21.5, 13.1; HRMS (ESI) *m/z*: [M]⁺ calcd for C₅₆H₆₃N₅O₄ 869.4875; found 869.4870.

2.4. Synthesis of Dye-2

A mixture of compound IV (100 mg, 0.12 mmol) and cyanoacetic acid (102 mg, 1.2 mmol), ammonium acetate (23 mg, 0.3 mmol), and glacial acetic acid (50 mL) was purged by Ar for 15 mins, and then stirred at 135°C for 24 h. After cooling to room temperature, the mixture was poured into ice water and the resulting precipitate was filtered off, washed with water several times and dried under vacuum, a red solid was obtained (108 mg, 93%). mp 289.1°C-289.2 °C; ¹H-NMR (400 MHz, DMSO- d_6 ,

80°C): δ = 8.32 (s, 2 H), 8.09 (d, J = 8.92 Hz, 4 H), 7.76 (d, J = 8.92 Hz, 4 H), 3.65 (t, J = 8.04 Hz, 8 H), 1.76 (m, 8 H), 1.34 (m, 24 H), 0.86 (t, J = 6.72 Hz, 12 H); HRMS (ESI) m/z: [M]⁺ calcd for C₆₀H₆₄N₆O₆ 964.4882; found 964.4874.

2.5. Cyclic voltammetry

Cyclic voltammetry was conducted on an Autolab PGSTAT 101 electrochemical analyzer. An Ag/AgCl electrode containing 2M LiCl (in ethanol) served as the reference electrode with a glassy carbon electrode as the counter electrode and a Pt disk as the working electrode. Cyclic voltammetric experiments were performed at room temperature under Argon in CHCl₃ with 0.1 M n-Bu₄NPF₆ as a supporting electrolyte.

2.6. Fabrication of DSSCs

Electrodes with 4 μ m transparent layer and 5 μ m scattering layer of TiO₂ were screen-printed on fluorine-doped tin oxide (FTO) as reported in the literature.⁵ After sintering at 500°C for 0.5 h and cooling to room temperature, the electrodes were treated with 33 mM TiCl₄ solution at 70°C for 0.5 h. The films were sintered at 500°C for 0.5 h and cooled to 80°C before dipping into dye solution (0.1 mM dye with or without 0.3 mM chenodeoxycholic acid in a mixture of 1:1 THF and ethanol) for 12 h. After the sensitization, the electrodes were rinsed with acetonitrile and dried in air. The cells were sealed with a Surlyn film and Platinized FTO counter electrode. The composition of electrolyte of this study is 0.2 M [Co(bpy)₃][B(CN)₄]₂, 0.05 M [Co(bpy)₃][B(CN)₄]₃, 0.1 M LiOTf, 0.5 M 4-*tert*-butylpyridine in acetonitrile.

Computational studies: All of the theoretical calculations were carried out within the density functional theory approach by using A.02 revision of Gaussian 09 program package⁶ with the Coulomb Attenuated Methods for Density Functional Theory by means of the hybrid functional B3LYP (CAM-B3LYP)⁷ and the basis set $6-31 + 10^{-10}$

G(d,p).⁸ This method includes long range correction into the non-coulomb part of exchange functional which gives a correct description of electron excitation and charge transfer. To reduce computational costs, the alkyl groups of BDF were substituted by methyl groups. First we optimized the ground-state geometry of **dye-1** and **dye-2** in THF using the PCM model (polarized continuum model)⁹⁻¹² with CAM-B3LYP methods without any symmetry restriction. The obtained structures for **dye-1** and **dye-2** are both planar giving to **dye-2** a C_i symmetry. Once the geometries were optimized, we performed excited state calculations using time-dependent CAM-B3LYP Methods.



Figure S1. Cyclic voltammograms of **Dye-1** (1×10^{-4} M, black line) and **Dye-2** (1×10^{-4} M, red line) in CHCl₃ (0.1 M Bu₄N(PF₆); Pt-disk working electrode; scan rate 100 mVs⁻¹).



Figure S2. Electronic absorption spectra of Dye-1 (top) and Dye-2 (bottom) in THF solution, together with the calculated $S_0 \rightarrow S_n$ transitions at the CAM-B3LYP /6-31G(d,p) level of theory.



Figure S3. Frontier molecular orbitals of the π -conjugated skeletons of **Dye-1**.



Figure S4. Frontier molecular orbitals of the π -conjugated skeletons of **Dye-2**.

State	Excitation energy [cm ⁻¹]	Oscillator strength	Dominant contributions (%)
S_1	22 750	1.32	$\begin{array}{l} H \rightarrow L \ (72), H \rightarrow L + 1 \ (16), H - 1 \rightarrow L \ (5), \\ H - 2 \rightarrow L \ (3) \end{array}$
S_2	27 211	1.38	H-1→L (54), H→L+1 (12), H-2→L (12) H-3→L (6), H-1→L+1 (6), H→L (2)
S_3	30 358	0.38	H→L+1 (42), H-1→L+1 (17), H→L (10), H-1→L (10), H-2→L (10), H-2→L+1 (3)
S_4	32 498	0.10	H-2 \rightarrow L (26), H \rightarrow L+1 (23), H-1 \rightarrow L+1 (19), H \rightarrow L (14), H-3 \rightarrow L (6), H-2 \rightarrow L+1 (4), H-5 \rightarrow L (3)
S_5	35 012	0.05	H-3→L (26), H-2→L+1 (22), H-2→L (18), H-1→L+1 (10), H-5→L (10), H-6→L (2)
S_6	35 485	0.03	H-6→L (82), H-6→L+1(2), H-1→L+3 (2), H-2→L+3 (2)
S_7	37 757	0.48	H→L+5 (23), H→L+2 (13), H-1→L+1 (8)
S_{δ}	38 260	0.22	H-1→L+1 (23), H-1→L (17), H→L+5 (8)

Table S1. The vertical CAM-B3LYP calculated $S_0 \rightarrow S_n$ transitions for **Dye-1**.

Table S2. The vertical CAM-B3LYP calculated $S_0 \rightarrow S_n$ transitions for **Dye-2**.

State	Excitation energy [cm ⁻¹]	Oscillator strength	Dominant contributions (%)
$\overline{S_I}$	21 753	1.71	$H \rightarrow L (77), H \rightarrow L+2 (11), H-1 \rightarrow L (5), H-2 \rightarrow L+1 (2)$
S_2	26 446	1.93	H-1→ L (70), H-3→L+1 (6), H-2→L+1 (5), H-1→L+2 (5), H→L (5), H→L+2 (4)
S_5	33 288	0.08	H→L+2 (65), H→L (10), H-1→L+2 (4)
S_7	34 632	0.69	H-4→ L (25), H-1→L+2 (23), H-3→L+1 (16), H-2→L+1 (12), H→L+2 (9), H→L (6),
S_{9}	35 491	0.08	H-6→ L (48), H-5→L+1 (35), H-1→L+4 (3), H-3→L+3 (2)
S_{11}	38 339	0.41	$H \rightarrow L+6$ (46), $H \rightarrow L+15$ (13), $H-2 \rightarrow L+1$ (5), $H \rightarrow L+11$ (5), $H \rightarrow L+12$ (4), $H \rightarrow L+4$ (4)

Table S3 XYZ coordinates and absolute energies of Dye-1

	X	Y	Z
С	-2.60591900	1.20145800	-0.01160200
C	-1.21322800	1.24896000	-0.01113400
C	-0.34882100	0.15633900	0.00655000
C	-1.00188800	-1.09160800	0.02357000
C	-2 39551400	-1 13776300	0 02278200
C	-3 25961600	-0 04655900	0 00435700
c C	-0 56237500	-2 47275900	0.03565400
C	-1 72583000	-3 2/391500	0.05505400
\sim	-2 82035500	-2 11176800	0.03010000
C	0 77529300	-2 91612400	0.03777500
C N	1 88845200	-3 24836100	-0 01727200
N	-1 96241200	-3.24030100	-0.01727200
	-1.90241200	-4.55004900	-0 12050600
С И	-3.30298000	-1.26267000	-0.12030000
	-4.05554500	-4.50507900	0.17014000
п С	-5.42/0//00	-5.99585900	0.43949600
	-0.05/10500	-5.50511100	0.04209200
H	-1.21892500	-6.4/536800	0.38203200
H Q	-0.044/6000	-5.19/32/00	0.69943100
	-3.04616000	2.38402100	-0.02301700
	-1.88383900	3.354/1500	-0.04444300
	-0./8846/00	2.554/3600	-0.02656900
N	-1.64460200	4.6/011800	-0.10401900
C	-0.30514500	5.19442600	0.14965400
H	-0.1/802/00	6.11014100	-0.42884300
H	0.44854800	4.4/549200	-0.16165900
	-2.74864800	5.61/53000	-0.03312900
H	-3.56110300	5.31043600	-0.68991100
H	-2.385/4000	6.58/41100	-0.3/224400
C	1.06219300	0.30513100	0.00558300
C	2.26/16000	0.41/91400	0.00441600
C	-4.38301700	3.03023700	0.00794400
N	-5.49363700	3.37056500	0.03619300
C	-4.67154200	-0.19831500	0.00158300
C	-5.87540800	-0.32097600	-0.00230600
C	-7.30217100	-0.41162300	-0.00666800
C	-7.94099300	-1.65997000	0.00228800
C	-8.07367000	0.76040100	-0.02008400
C	-9.32840500	-1.73178600	-0.00237000
H	-7.34404300	-2.56560300	0.01287400
C	-9.46066200	0.67742500	-0.02487300
H	-7.57440400	1.72368800	-0.02621600
C	-10.09109900	-0.56538600	-0.01605000
H	-9.81629200	-2.70101000	0.00470500
H	-10.05205500	1.58720500	-0.03531900
H	-11.17462400	-0.62517400	-0.01966200
C	3.69063000	0.49246600	0.00165900
C	4.34719000	1.73163400	-0.00262600
C	4.45067600	-0.68981900	0.00253700
C	5.72937200	1.77930500	-0.00606800
H	3.76790300	2.64782000	-0.00341600

5.83260600	-0.63441300	-0.00076700
3.94066200	-1.64702700	0.00528000
6.50067300	0.60326000	-0.00520100
6.22924600	2.74276100	-0.00955800
6.38757700	-1.56276500	-0.00015500
7.94227900	0.77282600	-0.00939400
8.96382400	-0.11742500	-0.00955900
8.27843400	1.80675500	-0.01314100
8.81514800	-1.53878000	-0.00504300
8.70679100	-2.69176900	-0.00138100
10.34973300	0.42283900	-0.01481100
10.62422800	1.60466900	-0.01905400
11.27535800	-0.54313500	-0.01433500
12.15456100	-0.12904000	-0.01789900
-0.16689100	5.42238000	1.21282500
-3.13006000	5.72037300	0.98891300
-3.44477700	-5.32422200	-1.18888600
-0.47641300	-5.60726300	-0.97935400
	5.83260600 3.94066200 6.50067300 6.22924600 6.38757700 7.94227900 8.96382400 8.27843400 8.27843400 8.81514800 8.70679100 10.34973300 10.62422800 11.27535800 12.15456100 -0.16689100 -3.13006000 -3.44477700 -0.47641300	$\begin{array}{rrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrrr$

E= - 1959.20392514 ua; μ = 5.564 Debye

Table S4 XYZ coordinates and absolute energies of Dye-2

	X	Y	Z
С	-0.66286000	-1.23332400	-0.00380900
C	0.72611900	-1.11728000	-0.01710200
C	1.45593300	0.06888100	-0.01589200
C	0.66286000	1.23332400	0.00380900
C	-0 72611900	1 11728000	0 01710200
C	-1 45593300	-0 06888100	0 01589200
C	0 93907300	2 65616800	0 02164500
C	-0.30640300	3 28675900	0.02977300
0	-1,30045100	2.36428700	0.03734500
C	2 21634400	3 25155300	0 04682900
N	3 28374100	3 71017300	0.06855800
N	-0 69512200	4 56543100	0 00773100
C	-2 08880300	4 92556800	0 25786200
Ч	-2 75136500	4 13173200	-0 07768400
н	-2 31608900	5 83355900	-0.30171200
C	0 29357300	5 63122400	0.10381100
С Н	1 12364900	5 44839000	-0 57723200
C	-0 93907300	-2 65616800	-0 02164500
C	0 30640300	-3 28675900	-0.02977300
0	1 30045100	-2 36428700	-0 03734500
N	0 69512200	-4 56543100	-0 00773100
C	2 08880300	-4 92556800	-0 25786200
н	2 31608900	-5 83355900	0.20171200
н	2 75136500	-4 13173200	0.07768400
C	-0 29357300	-5 63122400	-0.10381100
Ч	-1 12364900	-5 44839000	0.57723200
н	0 18538600	-6 56537800	0.18722300
C	2 87453900	0.08529800	-0 03393600
C	4 08417000	0 11340800	-0.05044600
C	-2 21634400	-3 25155300	-0 04682900
N	-3 28374100	-3 71017300	-0.06855800
C	-2.87453900	-0.08529800	0.03393600
C	-4.08417000	-0.11340800	0.05044600
C	-5,50659100	-0.20645600	0.06887700
C	-6.30278300	0.94966700	0.10739400
C	-6.12383600	-1.46631100	0.04865000
С	-7.68211700	0.85379200	0.12541800
H	-5.82864200	1.92440000	0.12338400
C	-7.50429100	-1.55430600	0.06698700
H	-5.51145800	-2.36088800	0.01868400
С	-8.31160500	-0.40349900	0.10531300
H	-8.26419300	1.76445400	0.15557400
Н	-7.97377800	-2.53283800	0.05118100
С	5.50659100	0.20645600	-0.06887700
С	6.30278300	-0.94966700	-0.10739400
С	6.12383600	1.46631100	-0.04865000
С	7.68211700	-0.85379200	-0.12541800
Н	5.82864200	-1.92440000	-0.12338400
С	7.50429100	1.55430600	-0.06698700
Н	5.51145800	2.36088800	-0.01868400
С	8.31160500	0.40349900	-0.10531300

Н	8.26419300	-1.76445400	-0.15557400
Н	7.97377800	2.53283800	-0.05118100
С	9.74899600	0.61916300	-0.12166000
С	10.79287200	-0.24533400	-0.15285700
Н	10.04001500	1.66481000	-0.10594300
С	10.67380900	-1.67129600	-0.17746100
Ν	10.58813600	-2.82555700	-0.19751000
С	12.19719100	0.23673000	-0.16391800
0	13.15995300	-0.50113900	-0.19045300
0	12.30382200	1.57204800	-0.14176200
Н	13.24794700	1.80018500	-0.15043000
С	-9.74899600	-0.61916300	0.12166000
Н	-10.04001500	-1.66481000	0.10594300
С	-10.79287200	0.24533400	0.15285700
С	-10.67380900	1.67129600	0.17746100
N	-10.58813600	2.82555700	0.19751000
С	-12.19719100	-0.23673000	0.16391800
0	-13.15995300	0.50113900	0.19045300
0	-12.30382200	-1.57204800	0.14176200
Н	-13.24794700	-1.80018500	0.15043000
Н	2.26111600	-5.11094300	-1.32406400
Н	-0.67913500	-5.73462200	-1.12400200
Н	-0.18538600	6.56537800	-0.18722300
Н	0.67913500	5.73462200	1.12400200
Н	-2.26111600	5.11094300	1.32406400

E= -2317.29880004 ua; μ = 0.000 Debye C_i Symmetry



Figure S5. UV-Vis spectra of Dye-1(red) and Dye-2 (black) adsorbed on the TiO₂

film.



Figure S6. PXRD patterns of Dye-1(blue curve) and Dye-2 (red curve).

References:

1 H. Li, J. Ding, S. Chen, C. Beyer, S.-X. Liu, H.-A. Wagenknecht, A. Hauser and S. Decurtins, *Chem. Eur. J.* 2013, **19**, 6459.

2 S. Keller, C. Yi, C. Li, S.-X. Liu, C. Blum, G. Frei, O. Sereda, A. Neels, T. Wandlowski and S. Decurtins, *Org. Biomol. Chem.* 2011, **9**, 6410.

3 C. Yi, C. Blum, M. Lehmann, S. Keller, S.-X. Liu, G. Frei, A. Neels, J. Hauser, S. Schuerch and S. Decurtins, *J. Org. Chem.* 2010, **75**, 3350.

4 H. Li, C. Schubert, P. O. Dral, R. D. Costa, A. La Rosa, J. Thüring, S.-X. Liu, C. Yi,
S. Filippone, N. Martín, S. Decurtins, T. Clark and D. M. Guldi, ChemPhysChem.
2013, DOI:10.1002/cphc.201300378.

5 H. N. Tsao, P. Comte, C. Y. Yi, M. Graetzel, ChemPhysChem 2012, 13, 2976.

6 Gaussian 09, Revision A.02, M. J. Frisch, G. W. Trucks, H. B. Schlegel, G. E.

Scuseria, M. A. Robb, J. R. Cheeseman, G. Scalmani, V. Barone, B. Mennucci, G. A.

Petersson, H. Nakatsuji, M. Caricato, X. Li, H. P. Hratchian, A. F. Izmaylov, J.

Bloino, G. Zheng, J. L. Sonnenberg, M. Hada, M. Ehara, K. Toyota, R. Fukuda, J.

Hasegawa, M. Ishida, T. Nakajima, Y. Honda, O. Kitao, H. Nakai, T. Vreven, J. A.

Montgomery, Jr., J. E. Peralta, F. Ogliaro, M. Bearpark, J. J. Heyd, E. Brothers, K. N.

Kudin, V. N. Staroverov, R. Kobayashi, J. Normand, K. Raghavachari, A. Rendell, J.

C. Burant, S. S. Iyengar, J. Tomasi, M. Cossi, N. Rega, J. M. Millam, M. Klene, J. E.

Knox, J. B. Cross, V. Bakken, C. Adamo, J. Jaramillo, R. Gomperts, R. E. Stratmann,

O. Yazyev, A. J. Austin, R. Cammi, C. Pomelli, J. W. Ochterski, R. L. Martin, K.

Morokuma, V. G. Zakrzewski, G. A. Voth, P. Salvador, J. J. Dannenberg, S. Dapprich,

A. D. Daniels, Ö. Farkas, J. B. Foresman, J. V. Ortiz, J. Cioslowski, and D. J. Fox, Gaussian, Inc., Wallingford CT, 2009.

7 T. Yanai, D. P. Tew and N. C. Handy, Chem. Phys. Lett. 2004, 393, 51.

8 C. Lee, W. Yang and R. G. Parr, *Phys. Rev. B* 1988, **37**, 785.

9 S. Miertus, E. Scrocco and J. Tomasi, Chem. Phys. 1981, 55, 117.

10 R. Cammi and J. Tomasi, J. Comput. Chem. 1995, 16, 1449.

11 B. Mennucci, E. Cancès and J. Tomasi, J. Phys. Chem. B 1997, 101, 10506.

12 E. Cancès, B. Mennucci and J. Tomasi, J. Chem. Phys. 1993, 107, 3032.