

Electrochemical formation of Cu/Ag surfaces and their applicability as heterogeneous catalysts

Ilija Najdovski,^{a,b} PR Selvakannan^{a,b} and Anthony P. O'Mullane^{*a,c}

^a School of Applied Sciences, RMIT University, GPO Box 2476V, Melbourne, Vic 3001, Australia

^b Centre for Advanced Materials and Industrial Chemistry, School of Applied Sciences, RMIT University, GPO Box 2476V, Melbourne, Vic 3001, Australia

^c Present address: School of Chemistry, Physics and Mechanical Engineering, Queensland University of Technology, GPO Box 2434, Brisbane, QLD 4001, Australia
Email: anthony.omullane@qut.edu.au

Supplementary Information




Figure S1: SEM images of porous Cu/Ag (C1-C4) electrodeposited at -3 A cm^{-2} on copper foil from 0.4 M CuSO_4 in 1.5 M H_2SO_4 containing 5 mM (C1), 10 mM (C2), 20 mM (C3) and 50 mM (C4) AgNO_3 and then removed via sonication.