Supporting Information for

An Eco-friendly Way to Fire Retardant Flexible Polyurethane Foam: Layer-by-Layer Assembly of Fully Bio-based Substance

Xin Wang, Ye-Tang Pan, Jin-Tao Wan, De-Yi Wang*

Madrid Institute for Advanced Studies of Materials (IMDEA Materials), C/Eric Kandel, 2, 28906 Getafe, Madrid, Spain

* Tel.: +34 915493422-1055. Fax: +34 915503047. E-mail: deyi.wang@imdea.org.

The flame retardant properties of the treated PUFs are evaluated by horizontal flame tests, as shown in Figure S1. As can be seen, un-coated PUF vigorously and completely burn. After PUF is coated by CS and AL, the sample starts to burn very slowly and extinguish at 105 s and 67 s for PUF-5 BL and PUF-10 BL, respectively. Additionally, the presence of CS-AL coating inhibits the dripping of PUF.



Figure S1. Snapshots showing horizontal burning tests of PUF, PUF-5BL and PUF-10BL