

## Supporting Information:




Fig. S1 XRD patterns of the samples prepared in a) ammonium water solution and b) NaOH solution in the absence of CTAB.

Table S1 Chemical properties of the samples prepared in different alkaline solutions in the absence of CTAB.

Samples	Yield	R. C.	$\text{SiO}_2/\text{Al}_2\text{O}_3$		$\text{Na}_2\text{O}$
	%	%	Framework	Bulk	%
$\text{NH}_3\text{-OCTAB-c}$	96	56	--	8.14	3.77
$\text{NaOH-OCTAB-c}$	75	-- <sup>a</sup>	--	6.33	11.57

<sup>a</sup> : the formation of zeolite P.