

Supporting Information

Surface Immobilized Block Copolymer Micelles with Switchable Accessibility of Hydrophobic Pockets

Julia Gensel,^a Eva Betthausen,^b Christoph Hasenöhl,^a Katja Trenkenschuh,^a Markus Hund,^a Fouzia Boulmedais,^c Pierre Schaaf,^c Axel. H. E. Müller,^b Andreas Fery^{a,}*

^a Physical Chemistry II, University of Bayreuth, Universitätsstr. 30, 95440 Bayreuth, Germany

^b Macromolecular Chemistry II, University of Bayreuth, Universitätsstr. 30, 95440 Bayreuth, Germany

^c Institut Charles Sadron, Université de Strasbourg, Centre National de la recherche scientifique, UPR 22, 23 rue du Loess, 67034 Strasbourg Cedex, France.

* e-mail: Andreas.Fery@uni-bayreuth.de

Table S1. Analysis of the QCM-D data, according to the Voigt-Voinova's model, monitored during the pH changes between pH 10, pH 7 and pH 4 applied on BMAADq micelles (0.45 g/L in pH 10 buffer).

Rinsing steps	Thickness (nm)	Viscosity (kg/ms)	ChiSqr
pH10	55	$3.80 \cdot 10^{-3}$	$1.25 \cdot 10^{-3}$
pH 7	55	$3.80 \cdot 10^{-3}$	$1.25 \cdot 10^{-3}$
pH 4	81	$3.00 \cdot 10^{-3}$	$1.41 \cdot 10^{-2}$
pH 10	54	$3.80 \cdot 10^{-3}$	$1.35 \cdot 10^{-3}$
pH 4	81	$3.00 \cdot 10^{-3}$	$1.35 \cdot 10^{-2}$
pH 10	54	$3.80 \cdot 10^{-3}$	$2.50 \cdot 10^{-4}$
pH 4	80	$3.00 \cdot 10^{-3}$	$1.51 \cdot 10^{-2}$